



Standard Practice for Measuring Colorimetric Characteristics of Retroreflectors Under Nighttime Conditions¹

This standard is issued under the fixed designation E 811; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the instrumental determination of retroreflected chromaticity coordinates of retroreflectors. It includes the techniques used in a photometric range to measure retroreflected (nighttime) chromaticity with either a telecolorimeter or telespectroradiometer.

1.2 This practice covers the general measurement procedures. Additional requirements for specific tests and specifications are described in Section 7.

1.3 The description of the geometry used in the nighttime colorimetry of retroreflectors is described in Practice E 808 and the methods for calculation of chromaticity are contained in Test Method E 308.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 284 Terminology of Appearance²

E 308 Test Method for Computing the Colors of Objects by Using the CIE System²

E 808 Practice for Describing Retroreflection²

E 809 Practice for Measuring Photometric Characteristics of Retroreflectors²

2.2 CIE Documents:

CIE Publication No. 15.2 Colorimetry, 2d ed.³

CIE Standard S 001/ISO IS 10526, Colorimetric Illuminants³

CIE Standard S 002/ISO IS 10527, Colorimetric Observers³

3. Terminology

3.1 The terms and definitions in Terminology E 284 apply to this practice.

3.2 Definitions:

3.2.1 *chromaticity coordinates, n* —the ratios of each of the tristimulus values of a psychophysical color to the sum of the tristimulus values.

3.2.1.1 *Discussion*—Chromaticity coordinates in the CIE 1931 system of color specification are designated by x, y, z and in the CIE 1964 supplementary system by x_{10}, y_{10}, z_{10} .

3.2.2 *CIE 1931 (x, y)-chromaticity diagram*—the chromaticity diagram for the CIE 1931 standard observer, in which the CIE 1931 chromaticity coordinates are plotted with x as the abscissa and y as the ordinate.

3.2.3 *CIE 1931 standard observer, n* —ideal colorimetric observer with color matching functions $\bar{x}(\lambda), \bar{y}(\lambda), \bar{z}(\lambda)$ corresponding to a field of view subtending a 2° angle on the retina; commonly called the “ 2° standard observer.” [CIE]^{B4}

3.2.3.1 *Discussion*—The color matching functions of the CIE 1931 standard observer are tabulated in Test Method E 308, CIE Publication 15.2, and CIE Standard S 002.

3.2.4 *CIE standard illuminant A, n* —colorimetric illuminant, representing the full radiation at 2855.6 K, defined by the CIE in terms of a relative spectral power distribution. [CIE]^B

3.2.4.1 *Discussion*—The relative spectral power distribution of CIE standard illuminant A is tabulated in Test Method E 308, CIE Publication 15.2, and CIE Standard S 001.

3.2.5 *CIE standard source A, n* —a gas-filled tungsten-filament lamp operated at a correlated color temperature of 2855.6 K. [CIE]^B

3.2.6 *entrance angle, β , n* —in retroreflection, angle between the illumination axis and the retroreflector axis.

3.2.6.1 *Discussion*—The entrance angle is usually no larger than 90° , but for completeness its full range is defined as $0^\circ \leq \beta \leq 180^\circ$. To completely specify the orientation, this angle is characterized by two components, β_1 and β_2 .

3.2.7 *goniometer, n* —an instrument for measuring or setting angles.

3.2.8 *illumination axis, n* —in retroreflection, a line from the effective center of the source aperture to the retroreflector center.

3.2.9 *observation angle, n* —angle between the axes of the incident beam and the observed (reflected) beam, (in retroreflection, α , angle between the illumination axis and the observation axis).

⁴ Stephenson, H. F., “The Colorimetric Measurement of Retroreflective Materials. Progress Report on International Exchange Tests.” *Proceedings of the CIE*, 18th Session (London), pp. 595–609, 1975.

¹ This practice is under the jurisdiction of ASTM Committee E-12 on Appearance and is the direct responsibility of Subcommittee E12.10 on Retroreflection.

Current edition approved March 15, 1995. Published May 1995. Originally published as E 811 – 81. Last previous edition E 811 – 94a.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ Available from USNC/CIE Publications Office, % TLA Lighting Consultants, Inc., 7 Pond St., Salem, MA 01970.

3.2.10 *observation axis, n*—in retroreflection, a line from the effective center of the receiver aperture to the retroreflector center.

3.2.11 *retroreflection, n*—reflection in which the reflected rays are preferentially returned in directions close to the opposite of the direction of the incident rays, this property being maintained over wide variations of the direction of the incident rays. [CIE]^B

3.2.12 *retroreflective device, n*—deprecated term; use *retroreflector*.

3.2.13 *retroreflective sheeting, n*—a retroreflective material preassembled as a thin film ready for use.

3.2.14 *retroreflector, n*—a reflecting surface or device from which, when directionally irradiated, the reflected rays are preferentially returned in directions close to the opposite of the direction of the incident rays, this property being maintained over wide variations of the direction of the incident rays. [CIE, 1982]^B

3.2.15 *retroreflector axis, n*—a designated line segment from the retroreflector center that is used to describe the angular position of the retroreflector.

3.2.15.1 *Discussion*—The direction of the retroreflector axis is usually chosen centrally among the intended directions of illumination; for example, the direction of the road on which or with respect to which the retroreflector is intended to be positioned. In testing horizontal road markings the retroreflector axis is usually the normal to the test surface.

3.2.16 *retroreflector center, n*—a point on or near a retroreflector that is designated to be the center of the device for the purpose of specifying its performance.

3.2.17 *rotation angle, ϵ , n*—in retroreflection, angle indicating the orientation of the specimen when it is rotated about the retroreflector axis.

3.2.17.1 *Discussion*—The rotation angle is the dihedral angle from the half-plane originating on the retroreflector axis and containing the positive part of the second axis to the half plane originating on the retroreflector axis and containing the datum mark. Range: $-180^\circ \leq \epsilon \leq 180^\circ$.

3.2.18 *spectroradiometer, n*—an instrument for measuring the spectral distribution of radiant energy or power.

3.2.19 *tristimulus colorimeter, n*—instrument that measures psychophysical color, in terms of tristimulus values, by the use of filters to convert the relative spectral power distribution of the illuminator to that of a standard illuminant, and to convert the relative spectral responsivity of the receiver to the responsivities prescribed for a standard observer.

3.2.19.1 *Discussion*—In some instruments, the filters may be combined into one set placed in the receiver; in such cases, caution should be observed when measuring fluorescent specimens.

3.2.20 *viewing angle, v , n*—in retroreflection, the angle between the retroreflector axis and the observation axis.

3.3 Definitions of Terms Specific to This Standard:

3.3.1 *telecolorimeter, n*—a tristimulus colorimeter equipped with collection optics for viewing a limited area at a distance from the instrument.

3.3.2 *telespectroradiometer, n*—a spectroradiometer equipped with collection optics for viewing a limited area at a distance from the instrument.

4. Summary of Practice

4.1 Two procedures are described in this practice (see also Practice E 809). Procedure A is based on a calibrated light source, colored reference filters, a white reference standard and a telecolorimeter equipped with tristimulus filters. In this procedure, measurements of the incident light on the white standard at the specimen position are made using the colored filters and correction factors developed. Then the retroreflected light is measured under the test geometry and the corrected relative tristimulus values are computed. In Procedure B, spectral measurements are made of the incident light and of the retroreflected light under the test geometry required. From these spectral measurements, the relative tristimulus values are determined. In both procedures, the chromaticity coordinates x , y are based on the CIE 1931 Standard Color Observer.

5. Significance and Use

5.1 This practice describes a procedure for measuring the color appearance of retroreflectors as seen under nighttime conditions of illumination and viewing. CIE Standard Source A has been chosen to represent a tungsten automobile headlamp. Although the geometry must be specified by the user of this practice, it will, in general, correspond to the relationship between the vehicle headlamp, the retroreflector, and the vehicle driver's eyes. Thus, the chromaticity coordinates determined by the procedures in this practice describe numerically the nighttime appearance of the retroreflector.⁵

6. Use of the CIE Chromaticity Diagram for the Specification of Color

6.1 *Tristimulus Values for a Colored Sample*—The spectral nature of the light coming to the eye from a retroreflector depends upon the spectral distribution of the radiation from the source, $S(\lambda)$, and a quantity proportional to the spectral reflectance of the retroreflector, $R(\lambda)$. For nighttime colorimetric measurements of retroreflectors, $S(\lambda)$ is Illuminant A. The spectral tristimulus values, $\bar{x}$, $\bar{y}$, and $\bar{z}$ the illuminant power $S(\lambda)$, and the reflectance quantity $R(\lambda)$ are used together to calculate three numbers, the tristimulus values X , Y , and Z as follows:

$$X = k \int_{380}^{740} S_A(\lambda) R(\lambda) \bar{x}(\lambda) d\lambda$$

$$Y = k \int_{380}^{740} S_A(\lambda) R(\lambda) \bar{y}(\lambda) d\lambda$$

$$Z = k \int_{380}^{740} S_A(\lambda) R(\lambda) \bar{z}(\lambda) d\lambda$$

where:

⁵ Rennilson, J. J., "Chromaticity Measurements of Retroreflective Material Under Nighttime Geometry," *Applied Optics*, Vol 45, April 1980.