



Designation: F655 – 06

An American National Standard

Standard Specification for Test Carpets and Pads for Vacuum Cleaner Testing¹

This standard is issued under the fixed designation F655; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification provides construction details and a replacement procedure for the standard carpet and pad to be used when testing vacuum cleaners.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:²

F608 Test Method for Evaluation of Carpet Embedded Dirt Removal Effectiveness of Household/Commercial Vacuum Cleaners

3. Basis of Selection

3.1 These standard carpets and pads are intended to provide a database and shall meet the following requirements:

3.1.1 Representative of carpets currently in popular use in the United States.

3.1.2 Reasonable anticipation of continued availability.

3.1.3 Compatible with other ASTM Committee F11 methods.

3.1.4 Provide a separation of cleaning effectiveness ratings between products with good reliability and repeatability.

4. Classification

4.1 The carpet types shall be classified according to accepted carpet industry practice, such as shag, multilevel, plush, etc.

¹ This specification is under the jurisdiction of ASTM Committee F11 on Vacuum Cleaners and is the direct responsibility of Subcommittee F11.21 on Cleanability.

Current edition approved April 1, 2006. Published April 2006. Originally approved in 1980. Last previous edition approved in 2003 as F655 – 03. DOI: 10.1520/F0655-06.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Physical Requirements

5.1 *Carpets*³—The following carpet types and construction have been found acceptable for use in vacuum cleaner testing. They shall be made in accordance with the physical requirements given herein.

5.1.1 *Shag Custom Tufted Test Carpet Construction:*

	Construction type	tufted
	Gage	1/8 in.
	Stitches	29 2/3 in.
	Pile height	1 1/8 in. (26.99 mm)
	Pile fiber	1710 denier type 6.6 Nylon, type 896AS yarn
	Yarn ply	2-ply tumbled autoclave heat set
	Face weight	70 oz/yd ² ± 6 % variance in order to maintain the specified stitching and pile height
	Twist	6Z × 6S
	Heat setting	autoclave- "superba" setting with stuffer box
	Shift	no
	Finish	pure—no type of finish shall be applied to the yarn or carpet
Reference Only	Backing material:	
	Primary	woven polypropylene
	Secondary Back coating	woven polypropylene latex, 24 oz/vd ² (814 g/m ²)

5.1.2 *Plush Custom Tufted Test Carpet Construction:*

Construction type	tufted
Gage	3/16 in. (4.8 mm)
Stitches	7.5/in. (2.95/cm)
Pile height	3/16 in. (14.29 mm)
Pile fiber	filament nylon denier 1184/70 7N66 twist 1.5Z × 2.25S autoclave heat set
Yarn ply	4 ply
Face weight	38.9 oz/yd ² (1319 g/m ²) ± 6 % variance in order to maintain the specified stitching and pile height

³ The sole source of supply of the test carpets known to the committee at this time is Textile Innovators Corporation, P.O. Box 8, Windsor, NC 27983. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

Reference Only	Finish	pure—no type of finish shall be applied to the yarn or carpet
	Backing material:	
	Primary	polypropylene, 3½ oz/yd ² (118.7 g/m ²)
	Secondary	jute, 7 oz/yd ² (237.3 g/m ²)
	Back coating	latex, 24 oz/yd ² (814 g/m ²)
	Finished weight	72 oz/yd ² (2442 g/m ²)

5.1.3 Multilevel Custom Tufted Test Carpet Construction:

	Construction type	tufted
	Gage	⅝ in. (3.97 mm)
	Stitches	6.5/in. (2.56/cm)
	Pile height	⅞ in. (14.29 mm)
	Pile fiber	filament nylon Allied Chemical Type 1225 denier, 0.75 turns per inch (37041)
	Yarn ply	2 ply
	Face weight	25.7 oz/yd ² (871 g/m ²) ± 6 % variance in order to maintain the specified stitching and pile height
Reference Only	Finish	pure—no type of finish shall be applied to the yarn or carpet
	Backing material:	
	Primary	polypropylene, 3½ oz/yd ² (118.7 g/m ²)
	Secondary	jute, 7 oz/yd ² (237.3 g/m ²)
	Back coating	latex, 24 oz/yd ² (814 g/m ²)
	Finished weight	60.5 oz/yd ² (1715 g/m ²)

5.1.4 Level Loop Test Carpet Construction:

	Construction type	woven-level loop-woven through back
	Pitch	216
	Wires	8/in. (3.15/cm)
	Pile height	¼ in. (6.35 mm)
	Pile fiber	wool
	Yarn ply	3 ply
	Face weight	43.9 oz/yd ² (1489 g/m ²)
Reference Only	Finish	pure—no type of finish shall be applied to the yarn or carpet
	Backing material:	synthetic and jute, 15.4 oz/yd ² (436.6 g/m ²)
	Back coating	latex, 15.4 oz/yd ² (522.14 g/m ²)
	Finished weight	73.3 oz/yd ² (2078 g/m ²)

5.2 *Padding*⁴—Sponge rubber type of waffle construction with a reinforcing skrim.

5.2.1 Specification:

Color	rose
Oz weight/yd ²	68 ± 3 %
Belt design	Montego
Roll size	54 in. × 40 ft
Density, pcf	11
Thickness, inclusive	0.530
CLD, psi, at 25 %	0.480
DOC FF 1-70 (Pill Test)	pass

6. Carpet and Pad Selection

6.1 A test carpet or pad specified in this specification that does not satisfy the requirements of Section 3 shall be replaced using the procedures described in 6.2-6.6.

⁴ The sole source of supply of the padding (CANNES 2209-68) with the construction described in 5.2 is General Felt Industries, Co., 80 Park Plaza West-One, Saddlebrook, NJ 07662-5864. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

6.2 A three-member task group shall be assigned from Subcommittee F11.21.

6.3 When the task group has tentatively agreed on a replacement carpet, the proposed carpet shall be evaluated. The laboratories of the three task group members shall gather test data. Testing shall be conducted in accordance with Test Method F608.

6.3.1 Testing must be done with at least one agitator-type upright vacuum cleaner, one combination cleaner, and one straight air canister cleaner. The test cleaners selected shall be used for testing in all three task group member laboratories. Additional cleaners may be used at the discretion of the task group members.

6.3.2 The proposed replacement test carpet shall be supplied to each of the participating laboratories.

6.3.3 Each test laboratory shall make certain that the same intralaboratory technician (or technicians, if more than one is required) conducts the required series of runs to establish the test score for a cleaner type. The runs required for a test score for a cleaner type shall be a continuous series of runs within a single working day.

6.4 The carpet being selected shall have a construction similar to that specified in Section 5. The proposed test carpet shall be judged equivalent if the average test score of the participating laboratories for each of the cleaner types falls within the specified limits listed when compared to the carpet it is intended to replace.

Amount of Dirt Picked Up	Specified Limits
30 g or more	3 g
10 to 29 g	10 %
9 g or less	1 g

6.4.1 When the subcommittee deems it necessary to replace a specified carpet with a new or different carpet construction, or both, the task group shall conduct a search for the appropriate carpet. Each of the three members of the task group shall be supplied with samples and gather test data in accordance with Test Method F608. Every effort shall be made to replace the specified carpet with a carpet that meets the limits listed in Section 3. Every effort shall be made to select a carpet that provides pickup performance, cleaner ranking, and ratio of performance between agitator and straight air type vacuum cleaners within 10 % of that measured on the currently specified carpet to be replaced.

6.5 When the task group reaches agreement on the proposed carpet, it will submit its recommendation and test data to Subcommittee F11.21 for approval and subsequent ASTM balloting, including amendments to 5.1.

6.6 If the specified carpet padding becomes obsolete, the procedure specified in Section 6 shall be used to determine an equivalent replacement using all of the standard test carpets listed in 5.1.

7. Keywords

7.1 vacuum cleaners