



Designation: G 101 – 97

## Standard Guide for Estimating the Atmospheric Corrosion Resistance of Low- Alloy Steels<sup>1</sup>

This standard is issued under the fixed designation G 101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This guide presents two methods for estimating the atmospheric corrosive resistance of low-alloy weathering steels, such as those described in Specifications A 242/A 242M, A 588/A 588M, A 606 Type 4, A 709/A 709M grades 50W, 70W, and 100W, A 852, and A 871. One method gives an estimate of the long term thickness loss of a steel at a specific site based on results of short-term tests. The other gives an estimate of relative corrosion resistance based on chemical composition.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 242/A 242M Specification for High-Strength Low-Alloy Structural Steel<sup>2</sup>

A 588/A 588M Specification for High-Strength Low-Alloy Structural Steel with 50 Ksi (345 MPa) Minimum Yield Point to 4 in. (100 mm) Thick<sup>2</sup>

A 606 Specification for Steel, Sheet and Strip, High Strength, Low-Alloy, Hot-Rolled and Cold Rolled, With Improved Atmospheric Corrosion Resistance<sup>3</sup>

A 709/A 709M Specification for Carbon and High-Strength Low-Alloy Structural Steel Shapes, Plates, and Bars and Quenched-and-Tempered Alloy Structural Steel Plates for Bridges

A 852/A 852M Specification for Quenched and Tempered Low-Alloy Structural Steel Plate with 70 ksi (485 MPa) Minimum Yield Strength to 4 in (100 mm) Thick<sup>2</sup>

A 871/A 871M Specification for High Strength Low-Alloy Structural Steel Plate With Atmospheric Corrosion Resistance<sup>2</sup>

G 1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens<sup>4</sup>

G 16 Guide for Applying Statistics to Analysis of Corrosion Data<sup>4</sup>

G 50 Practice for Conducting Atmospheric Corrosion Tests on Metals<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *low-alloy steels*—Iron-carbon alloys containing greater than 1.0 % but less than 5.0 %, by mass, total alloying elements.

NOTE 1—Most “low-alloy weathering steels” contain additions of both chromium and copper, and may also contain additions of silicon, nickel, phosphorus, or other alloying elements which enhance atmospheric corrosion resistance.

### 4. Summary of Guide

4.1 In this guide, two general methods are presented for estimating the atmospheric corrosion resistance of low-alloy weathering steels. These are not alternative methods; each method is intended for a specific purpose, as outlined in 5.2 and 5.3.

4.1.1 The first method utilizes linear regression analysis of short-term atmospheric corrosion data to enable prediction of long-term performance by an extrapolation method.

4.1.2 The second method utilizes predictive equations based on the steel composition to calculate indices of atmospheric corrosion resistance.

### 5. Significance and Use

5.1 In the past, ASTM specifications for low-alloy weathering steels, such as Specifications A 242/A 242M, A 588/A 588M, A 606 Type 4, A 709/A 709M Grade 50W, 70W, and 100W, A 852, and A 871 stated that the atmospheric corrosion resistance of these steels is “approximately two times that of carbon structural steel with copper.” A footnote in the specifications stated that “two times carbon structural steel with copper is equivalent to four times carbon structural steel without copper (Cu 0.02 maximum).” Because such statements relating the corrosion resistance of weathering steels to that of other steels are imprecise and, more importantly, lack significance to the user (**1 and 2**)<sup>5</sup>, the present guide was prepared to describe more meaningful methods of estimating the atmospheric corrosion resistance of weathering steels.

<sup>5</sup> The boldface numbers in parentheses refer to the list of references at the end of this guide.

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee G-1 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.04 on Atmospheric Corrosion.

Current edition approved April 10, 1997. Published July 1997. Originally published as G 101 – 89. Last previous edition G 101 – 94.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 01.04.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.03.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 03.02.

5.2 The first method of this guide is intended for use in estimating the expected long-term atmospheric corrosion losses of specific grades of low-alloy steels in various environments, utilizing existing short-term atmospheric corrosion data for these grades of steel.

5.3 The second method of this guide is intended for use in estimating the relative atmospheric corrosion resistance of a specific heat of low-alloy steel, based on its chemical composition.

5.4 It is important to recognize that the methods presented here are based on calculations made from test data for flat, boldly exposed steel specimens. Atmospheric corrosion rates can be much higher when the weathering steel remains wet for prolonged periods of time, or is heavily contaminated with salt or other corrosive chemicals. Therefore, caution must be exercised in the application of these methods for prediction of long-term performance of actual structures.

## 6. Procedure

6.1 Atmospheric corrosion data for the methods presented here should be collected in accordance with Practice G 50. Specimen preparation, cleaning, and evaluation should conform to Practice G 1.

### 6.2 Linear Regression Extrapolation Method:

6.2.1 This method essentially involves the extrapolation of logarithmic plots of corrosion losses versus time. Such plots of atmospheric corrosion data generally fit well to straight lines, and can be represented by equations in slope-intercept form, (3-5):

$$\log C = \log A + B \log t \quad (1)$$

where:

$C$  = corrosion loss,

$t$  = time, and

$A$  and  $B$  = constants.  $A$  is the corrosion loss at  $t = 1$ , and  $B$  is the slope of a  $\log C$  versus  $\log t$  plot.

$C$  may be expressed as mass loss per unit area, or as a calculated thickness loss or penetration based on mass loss.

6.2.2 The method is best implemented by linear regression analysis, using the method of least squares detailed in Guide G 16. At least three data points are required. Once the constants of the equation are determined by the linear regression analysis, the projected corrosion loss can be calculated for any given time. A sample calculation is shown in Appendix X1.

NOTE 2—Eq 1 can also be written as follows:

$$C = At^B \quad (2)$$

Differentiation of Eq 2 with respect to time gives the corrosion rate ( $R$ ) at any given time:

$$R = ABt^{(B-1)} \quad (3)$$

Also, the time to a given corrosion loss can be calculated as follows:

$$t = (C/A)^{1/B} \quad (4)$$

6.2.3 Examples of projected atmospheric corrosion losses over a period of fifty years for low-alloy weathering steels in various environments are presented in Appendix X1.

NOTE 3—It has been reported (6 and 7) that for some environments, use of log-log linear regression extrapolations may result in predictions which

are somewhat lower or somewhat higher than actual losses. Specifically, in environments of very low corrosivity, the log-log predictions may be higher than actual losses (6), whereas in environments of very high corrosivity the opposite may be true (7). For these cases, use of numerical optimization or composite modeling methods (7 and 8) may provide more accurate predictions. Nevertheless, the simpler log-log linear regression method described above provides adequate estimates for most purposes.

### 6.3 Predictive Method Based on Steel Composition:

6.3.1 Equations for predicting corrosion loss of low-alloy steels after 15.5 years of exposure to various atmospheres, based on the chemical composition of the steel, were published by Legault and Leckie (9). The equations are based on extensive data published by Larrabee and Coburn (10).

6.3.2 For use in this guide, the Legault-Leckie equation for an industrial atmosphere (Kearny, N.J.) was modified to allow calculation of an atmospheric corrosion resistance index based on chemical composition. The modification consisted of deletion of the constant and changing the signs of all the terms in the equation. The modified equation for calculation of the atmospheric corrosion resistance index ( $I$ ) is given below. The higher the index, the more corrosion resistant is the steel.

$$I = 26.01 (\% Cu) + 3.88 (\% Ni) + 1.20 (\% Cr) \\ + 1.49 (\% Si) + 17.28 (\% P) - 7.29 (\% Cu) \\ (\% Ni) - 9.10 (\% Ni) (\% P) - 33.39 (\% Cu)^2$$

NOTE 4—Similar indices can be calculated for the Legault-Leckie equations for marine and semi-rural atmospheres. However, it has been found that the *ranking* of the indices of various steel compositions is the same for all these equations. Therefore, only one equation is required to rank the relative corrosion resistance of different steels.

6.3.3 The predictive equation should be used only for steel compositions within the range of the original test materials in the Larrabee-Coburn data set (7). These limits are as follows:

Cu 0.51 % max  
Ni 1.1 % max  
Cr 1.3 % max  
Si 0.64 % max  
P 0.12 % max

6.3.4 Examples of averages and ranges of atmospheric corrosion resistance indices calculated for 72 heats of each of two weathering steels are shown in Table X2.1.

6.3.5 The minimum acceptable atmospheric corrosion index should be a matter of negotiation between the buyer and the seller.

## 7. Report

7.1 When reporting estimates of atmospheric corrosion resistance, the method of calculation should always be specified. Also, in the Linear Regression Extrapolation Method (6.2) of this guide, the data used should be referenced with respect to type of specimens, condition and location of exposure, and duration of exposure.

## 8. Keywords

8.1 atmospheric corrosion resistance; compositional effects; corrosion indices; high-strength; low-alloy steel; industrial environments; marine environments; rural environments; weathering steels