

ANSI/AWWA **B506-25**
(Revision of ANSI/AWWA B506-18)

AWWA Standard



Zinc Orthophosphate

Effective date: July 1, 2025.

First edition approved by Board of Directors Feb. 12, 2006.

This edition approved Jan. 23, 2025.

Approved by American National Standards Institute Jan. 7, 2025.




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 1180 Avenue of the Americas, 10th Floor, New York, NY 10036; 212.642.4900, or e-mailing info@ansi.org.



ISBN-13, print: 978-1-64717-254-1

ISBN-13, electronic: 978-1-61300-777-8

DOI: <http://dx.doi.org/10.12999/AWWA.B506.25>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2025 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Standards Committee on Scale and Corrosion-Control Chemicals, which reviewed and approved this standard, had the following personnel at the time of approval:

Milton D. Larsen, *Chair*

General Interest Members

M. Aghababaei, Arcadis, San Antonio, Tex.

N.J. Edman (*liaison, nonvoting*), Standards Group Liaison, AWWA, Denver, Colo.

M.D. Larsen, Kennedy Jenks Consultants, Gig Harbor, Wash.

N.E. McTigue, Cornwell Engineering Group, Newport News, Va.

D. Orozco, Consultant, Safety Harbor, Fla.

T. Phelan (*liaison, nonvoting*), Standards Council Liaison, Kelowna, B.C.

R.D. Vaidya, PCL Construction, Tampa, Fla.

Producer Members

H.T. Belcher Jr., Corrtac Systems Corporation, Currituck, N.C.

D. Linville, Aqua Smart Inc., Atlanta, Ga.

C.P. Principi, Carus Corporation, Belmont, N.C.

User Members

D.M. LaFalam, Town of Lincoln, Lincoln, Mass.

R.M. Powell, Pinellas County Utilities, Spring Hill, Fla.

This page intentionally blank.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		2	References 2
I Introduction.....	vii	3	Definitions 2
I.A Background.....	vii	4	Requirements
I.B History.....	x	4.1	Physical Requirements..... 3
I.C Acceptance	x	4.2	Chemical Requirements
II Special Issues	xi	4.3	Impurities..... 4
II.A Storage and Handling Precautions....	xi	5	Verification
III Use of This Standard	xi	5.1	Sampling..... 4
III.A Purchaser Options and		5.2	Test Procedures..... 5
Alternatives	xi	5.3	Notice of Nonconformance
III.B Modification to Standard	xii	6	Delivery
IV Major Revisions.....	xii	6.1	Marking
V Comments	xii	6.2	Packaging and Shipping
		6.3	Affidavit of Compliance or
			Certified Analysis
<i>Standard</i>			
1 General		<i>Table</i>	
1.1 Scope.....	1	1	Sample Size Determination for
1.2 Purpose	1		Orthophosphate Analysis
1.3 Application.....	1		

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA B506.*

I. Introduction

I.A. *Background.* Phosphate chemicals are among the few substances that can be safely and effectively used in potable water for corrosion control and/or inhibition. There are several types of phosphate inhibitors available, including zinc orthophosphate (ZOP), which was originally found to suppress iron corrosion by the Long Beach, Calif., Water Department in the 1940s.[†] Since that time, various formulations of ZOP have been used as corrosion inhibitors in potable water supplies.

ZOP can be an effective chemical inhibitor of electrolytic corrosion in iron, steel, copper, and lead, which occurs in aggressive water (with low to moderate hardness and alkalinity). ZOP was originally used to suppress colored water caused by leaching of tuberculation of iron pipe.[†] This treatment technology can be effective in waters without elevated concentrations of iron and manganese to sequester and where calcium precipitation and scaling are of minimal concern.

ZOP can also reduce asbestos fiber counts and provide protection for asbestos-cement and concrete pipe. It prevents concrete pipe deterioration in aggressive waters because the zinc interacts with cement and forms a protective zinc carbonate barrier on the surface at zinc concentrations as low as 0.2 mg/L.[‡]

ZOP formulations consist of zinc salts (sulfate and chloride) combined with orthophosphate formulated in a wide variety of zinc-to-phosphate ratios, ranging from 15:1 to 1:16.

Typically, as the zinc-to-phosphate ratio and dosage are decreased, it is necessary to increase the phosphate portion and dosage. The reverse also often occurs. The zinc proportion is provided by dissolving zinc in sulfonic, sulfuric, or hydrochloric acid and mixing that solution with sodium orthophosphate or phosphoric acid. Until the mid-1980s, the zinc proportion was more economical than the phosphate, and higher

* American National Standards Institute, 1180 Avenue of the Americas, 10th Floor, New York, NY 10036.

† Murray, W.B. 1970. "A Corrosion Inhibitor Process for Domestic Water." *Journal AWWA*. 62(10):659–662.

‡ Leroy, P. et al. 1996 (2nd ed.). Ch. 7, "Cement Based Materials," p. 354; and Vik, E.A. et al. 1996 (2nd ed.). Ch. 8, "Mitigation of Corrosion Effects," p. 426. In *Internal Corrosion of Water Distribution Systems* (AwwaRF and DVGW-TZW). Denver, Colo.: AwwaRF and AWWA.

zinc-to-phosphate ratios were used. Chemical costs change relatively rapidly, and the cost value of the ratio may change.

ZOP solutions are usually acidic, have a pH of less than 2, and are a hazardous chemical. Double containment of large storage vessels and piping as well as other chemical handling safety measures are appropriate and required.

ZOP in metal-corrosion suppression functions by two direct mechanisms: film formation and electrochemical passivation. In metal-corrosion protection, the orthophosphate provides an anodic inhibitor, and zinc films form at the cathode and provide a cathodic inhibitor. The blockage of both anodic and cathodic corrosion sites provides a double interruption of the electrochemical-corrosion reaction; that can be more effective than a single-acting inhibitor, which is typical for other phosphate or silicate chemicals.

Asbestos-cement pipe, concrete pipe, or cement linings can be protected by zinc carbonate film, which inhibits aggressive water (with a Langelier Index of less than zero) from leaching calcium and deteriorating the cement surface. There is no apparent benefit from the orthophosphate in cement protection, and other zinc formulations, including zinc chloride, can be used. However, ZOP can be a wide-ranging corrosion inhibitor for multiple types of pipe and reservoir materials of water distribution and consumer plumbing systems.

Typically, maximum ZOP dosages are limited to 5–30 mg/L, depending on supplier qualifications in testing to NSF[§]/ANSI/CAN[†] 60, Drinking Water Treatment Chemicals—Health Effects, in the United States. The supplier can provide operators appropriate information on certification and dosage limit of the product for use in potable water. German and other European potable water standards do not allow the use of zinc in chemicals added to potable water, and the possible use of ZOP as a corrosion inhibitor must be evaluated in each country for its intended use.

The zinc concentration is frequently limited to 0.2–2 mg/L to avoid water system secondary-contaminant limits and wastewater and effluent-discharge toxicity limits. However, as is typical for most corrosion inhibitors, it is desirable to use a passivating dose of three to five times the maintenance inhibitor dose for a month or more to reach all portions of the distribution system and initially more rapidly passivate the metal to provide the protective films.

Phosphate concentrations should typically be in the range of 0.5–2 mg/L as phosphorus (P). Sometimes, phosphate may stimulate bacteria and bioslime growths,

[§] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

[†] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.