



**American Water Works
Association**

The Authoritative Resource on Safe WaterSM

ANSI/AWWA C115/A21.15-05
(Revision of ANSI/AWWA C115/A21.15-99)

AWWA Standard

Flanged Ductile-Iron Pipe With Ductile-Iron or Gray-Iron Threaded Flanges



Effective date: March 1, 2006.

First edition approved by AWWA Board of Directors Jan. 26, 1975.

This edition approved June 12, 2005.

Approved by American National Standards Institute Dec. 14, 2005.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
► **Science and Technology**
Sections

AWWA Documents
Document Sharing Hub

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

Science and Technology

AWWA unites the entire water community by developing and distributing authoritative scientific and technological knowledge. Through its members, AWWA develops industry standards for products and processes that advance public health and safety. AWWA also provides quality improvement programs for water and wastewater utilities.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2006 by American Water Works Association
Printed in USA

Committee Personnel

Subcommittee 1, Pipe, which developed this standard, had the following personnel at the time:

Philip A. Selig, *Chair*
Troy F. Stroud, *Vice-Chair*

General Interest Members

M.B. Horsley, Black & Veatch, Kansas City, Mo.	(AW/WA)
P.I. McGrath Jr., Consultant, Birmingham, Ala.	(AW/WA)
E.W. Misichko, Underwriters Laboratories, Northbrook, Ill.	(UL)
J.R. Plattsmier, MWH Americas Inc., Denver, Colo.	(AW/WA)
W.H. Smith, Consultant, Flora, Ill.	(AW/WA)
K.E. Wilson, Post Buckley Schuh & Jernigan, Tampa, Fla.	(AW/WA)
L.C. Yates, McGoodwin Williams & Yates, Fayetteville, Ark.	(AW/WA)

Producer Members

D.R. Charko, McWane Inc., Birmingham, Ala.	(AW/WA)
L.R. Dunn, U.S. Pipe & Foundry Company, Birmingham, Ala.	(DIPRA)
Harold Kennedy Jr., Harold Kennedy & Associates, Cary, N.C.	(AW/WA)
C.W. McCauley Jr., Griffin Pipe Products Company, Lynchburg, Va.	(DIPRA)
T.J. Muntz, Fab Pipe Inc., Rogers, Minn.	(AW/WA)
P.A. Selig, American Cast Iron Pipe Company, Birmingham, Ala.	(DIPRA)
T.F. Stroud, Ductile Iron Pipe Research Association, Birmingham, Ala.	(DIPRA)
T.B. Wright, National Association of Pipe Fabricators, Edmond, Okla.	(DIPRA)

User Members

T.E. Coughran, City of Santa Ana, Santa Ana, Calif.	(AW/WA)
A.J. DeBoy, American Water—Central Region, St. Louis, Mo.	(AW/WA)
G.L. Meyer, City of Sioux Falls, Sioux Falls, S.D.	(AW/WA)
C.R. Schwenker, Fairfax County Water Authority, Fairfax, Va.	(AW/WA)

AWWA Standards Committee A21, Ductile-Iron Pipe and Fittings, which reviewed and approved this standard, had the following personnel at the time of approval:

John R. Plattsmier, *Chair*
Charles W. McCauley Jr., *Vice-Chair*

General Interest Members

K.W. Henderson, Malcolm Pirnie Inc., White Plains, N.Y.	(AWWA)
H.E. Holcomb, Jordan Jones & Goulding Inc., Norcross, Ga.	(AWWA)
M.B. Horsley, Black & Veatch, Kansas City, Mo.	(AWWA)
D.H. Kroon, Corrpro Companies Inc., Houston, Texas	(AWWA)
G.E. Laverick, Underwriters Laboratories, Northbrook, Ill.	(UL)
T.J. McCandless,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
P.I. McGrath Jr., Consultant, Birmingham, Ala.	(AWWA)
J.R. Plattsmier, MWH Americas Inc., Denver, Colo.	(AWWA)
W.H. Smith, Consultant, Flora, Ill.	(AWWA)
L.C. Yates, McGoodwin Williams & Yates, Fayetteville, Ark.	(AWWA)
Ken Zastrow,† Underwriters Laboratories Inc., Northbrook, Ill.	(UL)

Producer Members

John Critchlow, Pacific States Cast Iron Pipe Company, Provo, Utah	(AWWA)
L.R. Dunn, U.S. Pipe & Foundry Company, Birmingham, Ala.	(DIPRA)
Harold Kennedy Jr., Harold Kennedy & Associates, Cary, N.C.	(AWWA)
Michael Lundstrom, Eastland, Texas	(AWWA)
C.W. McCauley Jr., Griffin Pipe Products Company, Lynchburg, Va.	(DIPRA)
T.J. Muntz, Fab Pipe Inc., Rogers, Minn.	(AWWA)
Gene Oliver,† American Cast Iron Pipe Company, Birmingham, Ala.	(DIPRA)
P.A. Selig, American Cast Iron Pipe Company, Birmingham, Ala.	(DIPRA)
J.E. Shea,† McWane Cast Iron Pipe Company, Birmingham, Ala.	(AWWA)
E.J. Shields Jr., Waterworks Supply Corporation, Malden, Mass.	(AWWA)
T.F. Stroud, Ductile Iron Pipe Research Association, Birmingham, Ala.	(DIPRA)
T.B. Wright,† National Association of Pipe Fabricators, Edmond, Okla.	(DIPRA)

* Liaison, nonvoting

† Alternate

User Members

D.T. Bradley, Oak Lodge Water District, Milwaukie, Ore.	(AW/WA)
T.E. Coughran, City of Santa Ana, Santa Ana, Calif.	(AW/WA)
A.J. DeBoy, American Water—Central Region, St. Louis, Mo.	(AW/WA)
R.R. Goold, Kansas City Water Services Department, Kansas City, Mo.	(AW/WA)
G.L. Meyer, City of Sioux Falls, Sioux Falls, S.D.	(AW/WA)
D.D. Montgomery, Independence Water Department, Independence, Mo.	(AW/WA)
T.C. Moreno, Bexar Metro Water District, San Antonio, Texas	(AW/WA)
C.J. Patla, Connecticut Water Company, Clinton, Conn.	(AW/WA)
C.R. Schwenker, Fairfax County Water Authority, Fairfax, Va.	(AW/WA)
R.L. Worden, Guadalupe–Blanco River Authority, Seguin, Texas	(AW/WA)
R.D. Zwygart, Tampa Water Department, Tampa, Fla.	(AW/WA)

This page intentionally blank.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.5	Coatings and Linings 8
I	Introduction..... ix	4.6	Marking..... 9
I.A	Background..... ix	5	Verification
I.B	History..... ix	5.1	Quality Control and Inspection..... 9
I.C	Acceptance x	5.2	Inspection by Purchaser 9
II	Special Issues..... xi	5.3	Affidavit of Compliance..... 10
II.A	Flange Material Properties xi	6	Delivery 10
II.B	Special Service Requirements xii	Appendixes	
II.C	Advisory Information..... xiii	A	Bolts and Nuts, Gaskets, and Installation 11
III	Use of This Standard xiii	B	Typical Pipe and Flange Thread Construction..... 15
III.A	Purchaser Options and Alternatives xiv	C	Wall Pipe 17
III.B	Modification of Standard..... xv	Figures	
IV	Major Revisions xv	F.1	Comparison of Flange Dimensions..... xiii
V	Comments xv	1	Solid Flange Details 5
Standard		2	Hollow-Back Flange Details 7
1	General	B.1	Typical Pipe and Flange Thread Construction..... 15
1.1	Scope 1	C.1	Typical Flanged Wall Pipe Installations..... 19
1.2	Purpose 1	Tables	
1.3	Application 1	F.1	Gray-Iron Flange Minimum Tensile Strength..... xi
2	References 3		
3	Definitions 3		
4	Requirements		
4.1	Materials 4		
4.2	Pipe Barrel 4		
4.3	Flanges 4		
4.4	Fabrication 7		

SEC.	PAGE	SEC.	PAGE
1	Ductile-Iron Pipe for Use	A.1	Flange Gasket Details 12
	With Threaded Flanges..... 2	C.1	Collar Dimensions..... 18
2	Solid Gray- or Ductile-Iron	C.2	Suggested Minimum “Face to
	Flange Dimensions 5		Wall” Dimensions..... 19
3	Hollow-Back Ductile-Iron		
	Flange Dimensions 6		

Foreword

This Foreword is for information only and is not part of ANSI/AWWA C115/A21.15.

I. Introduction.

I.A. *Background.* American National Standards Institute (ANSI) Committee A21 on Cast-Iron Pipe and Fittings was organized in 1926 and sponsored by the American Gas Association (AGA), the American Society for Testing and Materials (ASTM), the American Water Works Association (AWWA), and the New England Water Works Association (NEWWA). Between 1972 and 1984, the co-secretariats were AGA, AWWA, and NEWWA, with AWWA serving as administrative secretariat. In 1984, the committee became an AWWA committee with the name AWWA Standards Committee A21 on Ductile-Iron Pipe and Fittings. In 1988, NEWWA withdrew as a separate secretariat; however, it continues to maintain its representation on the A21 Committee. In 1997, AGA withdrew as co-secretariat.

The present scope of Committee A21 activity is the development of standards and manuals addressing ductile-iron pressure pipe for water and ductile-iron and gray-iron fittings for use with such pipe. These standards and manuals include topics such as design, dimensions, materials, coatings, linings, joints, accessories, methods of inspection and testing, and installation.

The work of Committee A21 is conducted by subcommittees. The scope of Subcommittee 1, Pipe, includes the periodic review of all current Committee A21 standards for pipe, the preparation of revisions and new standards, and other matters pertaining to pipe standards.

I.B. *History.* Flanged fittings, sizes 3 in. through 48 in. (76 mm through 1,219 mm), are described in ANSI/AWWA C110/A21.10, American National Standard for Ductile-Iron and Gray-Iron Fittings for Water. Flanged fittings, sizes 54 in. through 64 in. (1,400 mm through 1,600 mm), are covered in ANSI/AWWA C153/A21.53, American National Standard for Ductile-Iron Compact Fittings for Water Service. The flanged pipe used with these fittings has been purchased for many years in accordance with users', manufacturers', and fabricators' standards. An ANSI standard was needed for flanged pipe. Consequently, Subcommittee 1 submitted a proposed standard for flanged pipe to Committee A21 in 1974. The first edition of the standard was adopted in 1975. Subsequent revisions to ANSI/AWWA C115/A21.15 were approved by the AWWA Board of Directors in 1983, 1988, 1994, and

1999. Subcommittee 1 reviewed the 1999 edition and submitted a proposed revision to Committee A21 in 2003. This sixth edition of ANSI/AWWA C115/A21.15 was approved by the AWWA Board of Directors on June 12, 2005.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF[†]/ANSI[‡] 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[§] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

*Persons outside the United States should contact the appropriate authority having jurisdiction.

†NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.

‡American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

§Both publications available from National Academy of Sciences, 500 Fifth Street, N.W., Washington, DC 20418.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C115/A21.15 does not address additives requirements. Users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by all parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

II.A. *Flange Material Properties.* Because this standard requires the material properties of gray-iron and ductile-iron flanges to comply with ANSI/AWWA C110/A21.10, the following material properties specified in ANSI/AWWA C110/A21.10 are listed for information purposes.

1. Gray-iron flanges, in accordance with ANSI/AWWA C110/A21.10, shall be manufactured of the following minimum tensile-strength iron listed in Table F.1.

Table F.1 Gray-iron flange minimum tensile strength

Nominal Size [*] <i>in.</i> [†]	Minimum Tensile Strength	
	<i>psi</i>	<i>(kPa)</i>
3–12	25,000	(172,000)
14–24	30,000	(207,000)

* Purchasers of gray-iron flanges greater than 24 in. should contact the manufacturer or fabricator for strength requirements.

† To convert inches to millimeters, multiply by 25.4.

2. Ductile-iron flanges made in accordance with ANSI/AWWA C110/A21.10 shall be manufactured of grades of ductile iron with the following minimum physical properties:

70,000 psi (483,000 kPa) tensile strength,
 50,000 psi (345,000 kPa) yield strength, and
 5 percent elongation;