

American Water Works Association

ANSI/AWWA C205-95

(Revision of ANSI/AWWA C205-89)



AWWA STANDARD
FOR
**CEMENT-MORTAR PROTECTIVE
LINING AND COATING FOR
STEEL WATER PIPE—4 IN. (100 mm)
AND LARGER—SHOP APPLIED**



Effective date: Jan. 1, 1997.

First edition approved by AWWA Board of Directors June 26, 1941.

This edition approved June 18, 1995.

Approved by American National Standards Institute Jan. 12, 1996.

Addendum C205a-96 approved by the AWWA Board of Directors June 23, 1996.

Addendum approved by American National Standards Institute Nov. 6, 1996.

Changes specified in the addendum are incorporated into Sec. 4.4.3.1.

AMERICAN WATER WORKS ASSOCIATION

6666 West Quincy Avenue, Denver, Colorado 80235

Copyright (C) 1998 American Water Works Association, All Rights Reserved.

AVA Documents
Document Sharing Hub

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 11 W. 42nd St., New York, NY 10036; (212) 642-4900.

Copyright © 1996 by American Water Works Association
Printed in USA

Committee Personnel

The Task Group on updating AWWA C205, which developed this standard, had the following personnel at the time:

Henry H. Bardakjian, <i>Chair</i>	Jim Davenport
Bruce Britton	Benedict H. Ebner
Robert Card	Bruce Vanderploeg

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

George J. Tupac, *Chair*
 John H. Bambei Jr., *Vice-Chair*
 Dennis A. Dechant, *Secretary*

Consumer Members

G.A. Andersen, New York City Bureau of Water Supply, Corona, N.Y.	(AWWA)
Ergun Bakall, San Diego County Water Authority, San Diego, Calif.	(AWWA)
J.H. Bambei Jr., Denver Water, Denver, Colo.	(AWWA)
J.L. Doane, Portland Bureau of Water Works, Portland, Ore.	(AWWA)
R.V. Frisz, US Bureau of Reclamation, Denver, Colo.	(USBR)
Wesley Kremkau, Washington Suburban Sanitary Commission, Laurel, Md.	(AWWA)
T.A. Larson, Tacoma Water Division, Tacoma, Wash.	(AWWA)
R.T. Menlove, Los Angeles Department of Water and Power, Los Angeles, Calif.	(AWWA)
G.M. Snyder, Metropolitan Water District of Southern California, Los Angeles, Calif.	(AWWA)
M.L. Young, East Bay Municipal Utilities District, Stockton, Calif.	(AWWA)

General Interest Members

G.E. Block, Rizzo Associates Inc., Natick, Mass.	(NEWWA)
W.R. Brunzell, Brunzell & Associates Ltd., Skokie, Ill.	(AWWA)
B.R. Bullert,* Council Liaison, City of St. Paul Water Utility, St. Paul, Minn.	(AWWA)
R.L. Coffey, R.W. Beck and Associates, Seattle, Wash.	(AWWA)
B.R. Elms,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
L.J. Farr, CH2M Hill Inc., Redding, Calif.	(AWWA)
S.N. Foellmi,† Black & Veatch Engineers, Irvine, Calif.	(AWWA)
J.W. Green, Alvord Burdick & Howson, Chicago, Ill.	(AWWA)

*Liaison, nonvoting

†Alternate

Karl Henrichsen, HDR Engineering Inc., Denver, Colo.	(AWWA)
G.K. Hickox, Engineering Consultant, Houston, Texas	(AWS)
M.B. Horsley, Black & Veatch, Kansas City, Kan.	(AWWA)
J.K. Jeyapalan, American Ventures Inc., Bellevue, Wash.	(AWWA)
R.Y. Konyalian, Boyle Engineering Corporation, Newport Beach, Calif.	(AWWA)
E. Smock,* Montgomery Watson, Walnut Creek, Calif.	(AWWA)
R.V. Stokes, Montgomery Watson, Los Angeles, Calif.	(AWWA)
H.R. Stoner, Henry R. Stoner Associates Inc., North Plainfield, N.J.	(AWWA)
Cris Sundberg,* CH2M Hill Inc., Bellevue, Wash.	(AWWA)
G.J. Tupac, G.J. Tupac & Associates, Pittsburgh, Pa.	(AWWA)
L.W. Warren, KCM Inc., Seattle, Wash.	(AWWA)
W.R. Whidden, Post Buckley Schuh & Jernigan, Winter Park, Fla.	(AWWA)
R.E. Young, Robert E. Young Engineers, Sacramento, Calif.	(AWWA)

Producer Members

H.H. Bardakjian, Ameron Concrete & Steel Pipe, Rancho Cucamonga, Calif.	(AWWA)
T.R. Brown, Rockwell International, Pittsburgh, Pa.	(AWWA)
J.H. Burton, Baker Coupling Company Inc., Los Angeles, Calif.	(SPFA)
R.J. Card, Thompson Pipe & Steel Company, Englewood, Colo.	(AWWA)
J.R. Davenport, California Steel Pressure Pipe, Riverside, Calif.	(AWWA)
Dennis Dechant, Northwest Pipe & Casing Company, Portland, Ore.	(AWWA)
George Harris, Tapecoat Company, Evanston, Ill.	(AWWA)
J.R. Pegues, American Cast Iron Pipe Company, Birmingham, Ala.	(MSS)
Bruce Vanderploeg,* Northwest Pipe & Casing Company, Portland, Ore.	(AWWA)
J.A. Wise, Canus Industries Ltd., Vancouver, B.C.	(AWWA)

*Alternate

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		3	Definitions 3
I	Introduction..... vii	4	Requirements
I.A	Background vii	4.1	General..... 4
I.B	History..... vii	4.2	Material..... 4
I.C	Acceptance..... vii	4.3	Surface Preparation 5
II.	Special Issues..... viii	4.4	Cement–Mortar Lining 5
II.A	Soft, Aggressive Waters..... viii	4.5	Cement–Mortar Coating..... 8
II.B	Intermittent Operations..... viii	4.6	Field Joints 11
II.C	Flow Velocity ix		
II.D	Strain Limitations ix	5	Verification
III	Use of This Standard ix	5.1	Sampling and Testing Cement
III.A	Purchaser Options and Alternatives ix		Mortar for Linings 12
III.B	Modification to Standard ix	5.2	Testing Cement Mortar for
IV	Major Revisions x		Coatings 13
V	Comments x	5.3	Inspection and Testing by
			Purchaser 13
Standard		6	Delivery
1	General	6.1	General..... 14
1.1	Scope 1	6.2	Plastic End Caps 14
1.2	Purpose..... 2	6.3	Affidavit of Compliance..... 14
1.3	Application 2		
2	References 2	Tables	
		1	Cement–Mortar Lining Thickness 6

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of AWWA C205.

I. Introduction

I.A. Background. Cement–mortar-lined-and-coated steel pipe was first used in the United States in the late 1800s. Some of the first pipelines were in service for almost a century by the time the first national standard was written. However, it was not until the 1920s that a practical method of plant-applied, cement–mortar lining was developed. The first plant-applied linings were installed by standing the pipe on end, placing a tapered plug with a rope attached to the leading end inside the pipe, placing enough cement mortar on top of the plug to coat the pipe, and then pulling the plug up through the pipe. Improvements in the lining process were developed, and the centrifugal process for plant-applied, cement–mortar lining emerged.

Cement–mortar-lined and cement–mortar-coated steel pipe combines the physical strength of steel with the protective qualities of cement mortar. The lining, applied centrifugally, creates a smooth, dense finish that protects the pipe from tuberculation and provides a measure of corrosion protection. The smooth interior surface will provide a high flow coefficient for the design life of the pipeline under normal operating conditions. In addition, the cement–mortar coating results in a tough, durable, and rugged coating that forms an alkaline environment where oxidation or corrosion of the steel is inhibited.

I.B. History. The first edition of this standard, designated 7A.7-41, Standard Specifications for Cement-Mortar Protective Coating for Steel Water Pipe of Sizes 30 Inches and Over, was approved by the AWWA Board of Directors on June 26, 1941. Before that a tentative draft had been published in the January 1940 *Journal AWWA* for review and comment.

The first edition provided for the field application of cement–mortar lining, which was deleted by action of the Board of Directors effective June 30, 1951. Pending the promulgation of AWWA C602, Cement–Mortar Lining of Water Pipelines—4 In. (100 mm) and Larger—In Place, the ninth, 10th, and 11th printing of 7A.7 (AWWA C205) continued to carry the withdrawn section.

The next edition, published in 1962, was a major revision and provided for pipe sizes of 4 in. (100 mm) and larger. The standard was subsequently revised in 1971, 1980, 1985, and 1989.

I.C. Acceptance. In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for all direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AWWARF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including:

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, ANSI/NSF[†] 60, Drinking Water Treatment Chemicals—Health Effects, and ANSI/NSF 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[§] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with ANSI/NSF 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Appendix A, “Toxicology Review and Evaluation Procedures,” to ANSI/NSF 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Appendix A procedures may not always be identical, depending on the certifier.

AWWA C205-95 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by all parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues

The purchaser of cement–mortar linings is cautioned about the following concerns:

II.A. *Soft, Aggressive Waters.* Soft, aggressive waters, as well as prolonged contact with heavily chlorinated water, may be injurious to cement–mortar linings. When this environment is anticipated, further studies may be necessary to determine the suitability of this type of lining.

II.B. *Intermittent Operations.* Cement–mortar linings are best suited for pipelines that are continuously filled with water. When cement–mortar-lined pipelines

*Persons in Canada, Mexico, and non–North American countries should contact the appropriate authority having jurisdiction.

[†]American National Standards Institute, 11 W. 42nd St., New York, NY 10036.

[‡]NSF International, 3475 Plymouth Rd., Ann Arbor, MI 48106.

[§]Both publications available from National Academy of Sciences, 2102 Constitution Ave. N.W., Washington, DC 20418.

are operated under prolonged empty conditions, special precautions may have to be taken to prevent excessive drying out of the mortar lining.

II.C. Flow Velocity. Cement–mortar linings perform best when flow velocities are in normal ranges. When the flow velocity exceeds approximately 20 ft/s (6.1 m/s), special studies may be required to determine the suitability of this type of lining material.

II.D. Strain Limitations. Consideration should be given to limiting the maximum strains (or stresses) developed in the steel cylinder of cement–mortar-lined and/or coated steel water pipe from internal pressure to ensure the long-term design life of the system.

III. Use of This Standard. AWWA has no responsibility for the suitability or compatibility of the provisions of this standard to any intended application by any user. Accordingly, each user of this standard is responsible for determining that the standard's provisions are suitable for and compatible with that user's intended application.

III.A. Purchaser Options and Alternatives. When purchasing protective cement–mortar lining or coating for steel water pipe under the provisions of this standard, the following items (including specific details where applicable) should be covered in the purchaser's specifications:

1. Standard used—that is, AWWA C205-95, Standard for Cement–Mortar Protective Lining and Coating for Steel Water Pipe—4 In. (100 mm) and Larger—Shop Applied.
2. If interior lining only, exterior coating only, or both lining and coating are required.
3. Footage, inside diameter after lining, lengths of pipe sections, steel-wall thickness, type of joint, and information regarding fittings.
4. If an affidavit of compliance is required (Sec. 6.3).
5. Type of wire-fabric reinforcement required, if limited to a single type (Sec. 4.2.1.2).
6. Type of cement required, if other than type I, type II, or type V (Sec. 4.2.2.1).
7. Lining options or restrictions, if any, such as thickness of lining (Sec. 4.4.2), thickness tolerances (Sec. 4.4.2), and length of lining holdback (Sec. 4.4.2).
8. Coating options or restrictions, if any, such as type of undercoat, if any (Sec. 4.5.1); length of coating holdback (Sec. 4.5.3); thickness of mortar coating (Sec. 4.5.3); minimum thickness (Sec. 4.5.3); type of reinforcement (Sec. 4.5.5); and method of curing (Sec. 4.5.9).
9. If additional testing of cement mortar for linings is required (Sec. 5.1.1).
10. The basis of payment for additional testing specified or ordered by the purchaser (Sec. 5.1.1).

NOTE: Generally accepted practice has been that all tests required by Sec. 5.1.1 are made by and at the expense of the manufacturer; and the costs of any additional testing specified or ordered by the purchaser are at the expense of the purchaser. Retests are at the expense of the manufacturer.

III.B. Modification to Standard. Any modification to the provisions, definitions, or terminology in this standard must be provided in the purchaser's specifications.