

ANSI/AWWA

C218-23

(Revision of ANSI/AWWA C218-16)

AWWA Standard

Liquid Coatings for Aboveground Steel Water Pipe and Fittings

Effective date: June 1, 2023.

First edition approved by Board of Directors Nov. 1, 1991.

This edition approved Jan. 12, 2023.

Approved by American National Standards Institute Jan. 26, 2023.



American Water Works
Association



Documents

STANDARD

Document Sharing Hub


AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900, or e-mailing info@ansi.org.



ISBN-13, print: 978-1-64717-128-5

ISBN-13, electronic: 978-1-61300-659-7

DOI: <http://dx.doi.org/10.12999/AWWA.C218.23>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2023 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group on updating ANSI/AWWA C218 had the following personnel at the time:

Dan Libby, *Chair*

L. McKinney, *Vice-Chair*

M. Buratto, Seal For Life, Pflugerville, Tex.

A. Cain, Chemline, St. Louis, Mo.

G. Davidenko, Northwest Pipe Company, Saginaw, Tex.

B. Keil, Northwest Pipe Company, Draper, Utah

D. Libby, Chase Corporation, Westwood, Mass.

L. McKinney, Womble Company Inc., Houston, Tex.

R. Mielke, Northwest Pipe, Raleigh, N.C.

V. O'Dea, Tnemec Company Inc., North Kansas City, Mo.

B. Simpson, American SpiralWeld, Birmingham, Ala.

G. Sincovich, Sherwin-Williams Company, Oakville, Ontario

S. Thomas, Liberty Coating Company, Pelham, N.H.

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*

Bob J. Card, *Vice-Chair*

John L. Luka, *Secretary*

General Interest Members

S.A. Arnaout (*alternate*), Stantec, Dallas, Tex.

J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.

R.J. Card, Lockwood, Andrews & Newnam Inc., Houston, Tex.

R.L. Coffey, HDR Engineering Inc., Omaha, Neb.

M. Garcia (*liaison, nonvoting*), Standards Council Liaison, AECOM, Denver, Colo.

R.L. Gibson, Freese and Nichols Inc., Fort Worth, Tex.

M.D. Gossett (*alternate*), HDR, Denver, Colo.

M.B. Horsley (*alternate*), Horsley Engineering LLC, Overland Park, Kans.

R. Issa, AECOM, McKinney, Tex.

C.H. Kirby (*alternate*), Lockwood, Andrews & Newnam Inc., Houston, Tex.
R.A. Kufaas, Norske Corrosion & Inspection Services Ltd., Surrey, B.C.
A. Murdock, CH2M, Salt Lake City, Utah
R. Ortega, Lockwood, Andrews & Newnam, Houston, Tex.
E.S. Ralph (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
A.E. Romer (*alternate*), AECOM, Orange, Calif.
J.R. Snow, Stantec, Denver, Colo.
A.M. Stanton, Black & Veatch, Los Angeles, Calif.
W.R. Whidden, Woolpert, Winter Park, Fla.

Producer Members

H.H. Bardakjian, Consultant, Glendale, Calif.
D. Dechant, Dechant Infrastructure Service, Aurora, Colo.
D.W. Dunker, Thompson Pipe Group, Grand Prairie, Tex.
W.B. Geyer, Steel Plate Fabricators Assoc., Lake Zurich, Ill.
B.D. Keil, Northwest Pipe Company, Draper, Utah
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.
R. Mielke (*alternate*), Northwest Pipe, Raleigh, N.C.
G.F. Ruchti (*alternate*), Consultant, Punta Gorda, Fla.
B.P. Simpson (*alternate*), American Cast Iron Pipe Company, Birmingham, Ala.
C.C. Sundberg, Victaulic, Issaquah, Wash.
R. Wu (*alternate*), Thompson Pipe Group, Grand Prairie, Tex.

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo.
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.
B. Cheng, Metro Vancouver, Burnaby, B.C.
F. Fountain, San Diego County Water Authority, San Diego, Calif.
J. Garcia (*alternate*), Metropolitan Water District of Southern California, Los Angeles, Calif.
S. Hattan, Tarrant Regional Water District, Fort Worth, Tex.
M. Lobik, Springfield Water & Sewer Commission, Springfield, Mass.
T. Peng, Metropolitan Water District of Southern California, Los Angeles, Calif.
M. Turney (*alternate*), Denver Water, Denver, Colo.
V. Scutelnicu, Los Angeles Department of Water and Power, Los Angeles, Calif.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		4.5	Coating Application 11
I	Introduction..... vii	4.6	Coating Fittings and Appurtenances 12
I.A	Background..... vii	4.7	Coating Repair 12
I.B	History..... vii	4.8	Field Joints—Welded 13
I.C	Acceptance vii	4.9	Field Procedures 13
II	Special Issues vii	5	Verification
II.A	Advisory Information on Product Use..... vii	5.1	Coating Materials Prequalification 13
III	Use of This Standard ix	5.2	Requirements of Coating System..... 14
III.A	Purchaser Options and Alternatives ix	5.3	Quality Assurance and Records 14
III.B	Modification to Standard x	5.4	Inspection and Testing by the Purchaser..... 14
IV	Major Revisions..... x	5.5	Quality Control Requirements of Applied Coating System 14
V	Comments xi	5.6	Rejection 15
<i>Standard</i>		6	Delivery
1	General	6.1	Marking 16
1.1	Scope..... 1	6.2	Packaging and Shipping 16
1.2	Purpose 1	6.3	Affidavit of Compliance 16
1.3	Application..... 2		
2	References 2	<i>Appendix</i>	
3	Definitions 4	A	Selection and Use of Coating Systems 17
4	Requirements	A.1	General 17
4.1	Equipment 4	A.2	Coating Systems..... 18
4.2	Materials and Workmanship..... 4		
4.3	Coating Systems..... 5	<i>Table</i>	
4.4	Surface Preparation..... 9	1	Coating Systems Summary 5

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI /AWWA C218.*

I. Introduction.

I.A. *Background.* Preventing the corrosion of aboveground steel water pipe subjected to atmospheric weathering has become an increasing concern over the years. The increasing incidence of atmospheric corrosive conditions, such as acid rain, has prompted water suppliers to evaluate the paint and coating systems used to protect aboveground steel water pipe.

Although not all aboveground steel water pipe is subjected to the same atmospheric corrosive conditions, a review of the paint and coating systems currently available to the industry has become necessary. The purchasers must have the option of selecting a system that best suits their needs. These needs may be based on current surface preparation; the types of volatile organic compound (VOC) allowances permitted by regulatory agencies; and regulatory requirements for lead abatement. The paint and coating systems in this standard are designed to assist the user in producing specifications to meet these needs.

I.B. *History.* In November 1986, the AWWA Standards Council authorized AWWA's Steel Pipe Committee to develop a new standard for coatings to be used on aboveground steel water pipe exposed to the atmosphere. The first edition of this standard was published as [ANSI/AWWA C218-91](#), Standard for Coating the Exterior of Aboveground Steel Water Pipelines and Fittings, with an effective date of Nov. 1, 1991. Subsequent editions of this standard were approved by the AWWA Board of Directors on June 17, 1995; Jan. 24, 1999; June 16, 2002; Jan. 27, 2008; and June 19, 2016. This edition of C218 was approved on Jan. 12, 2023.

I.C. *Acceptance.* This standard has no applicable information for this section.

II. Special Issues.

II.A. *Advisory Information on Product Use.* This standard defines the performance and quality of external pipe coatings and coating systems designed to protect from and prevent atmospheric corrosion. This standard applies to the exterior coating of aboveground steel water pipelines and the associated fittings installed aboveground, outdoors, or inside an associated pump station, a valve chamber, or other water facilities. The coating systems cited in this standard are not all-inclusive but are

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

those most commonly used with an accepted performance record. Before selecting and specifying any of these coating systems, the purchaser should determine their suitability for the intended service.

II.A.1. General. This standard presents several alternative coating systems currently in use in the water industry, often serving dual functions of corrosion protection and aesthetics. Another function of coating systems may be to color code the pipe to identify the type of service.

Most coating manufacturers are reformulating their coatings to comply with current federal, state or provincial, and local environmental regulations. Some of the coatings discussed in this standard have been used successfully as solvent-based coatings for the last 20–30 years but are now available as water-based coatings. Others have been reformulated to reduce the amount of solvents, resulting in coatings with much lower VOCs. In some cases, high-solids coatings have been developed in which the solids content exceeds 80 percent and may reach 100 percent. Primers have been reformulated to remove heavy metals and toxic inhibitors.

In many instances, these changes have altered the application, curing, adhesion, and inhibiting characteristics of coating systems. The manufacturer should be consulted for the technical data and material safety data sheets, which provide the prospective user with the information necessary to select the coating system that best satisfies the purchaser's requirements.

II.A.2. Materials. *Code of Federal Regulations* 29,[†] Labor—Part 1910, Occupational Safety and Health Administration (OSHA) regulations establish restrictive limits on the constructor regarding inhaling or absorbing lead- and chromate-bearing pigments and solvents through the skin. This regulation refers to shop applications, and it can significantly increase the cost of shop-coating applications.

Whenever coating materials are referenced to federal, military, or other standards, the reference identifies a generic type of coating material or system.

II.A.3. Selecting coating systems. Several generic coating systems (see Table 1 in Sec. 4) are included in this standard because no single coating or coating system is appropriate for all service applications. Often it is impractical for an occasional coatings user to make sufficient laboratory tests to verify and compare the relative performance characteristics of various coating systems to a given set of performance criteria. Consequently, it is necessary for the purchaser to consider the atmospheric and environmental conditions of service to which the coating or coating system will be

[†] Available from the US Government Printing Office, Superintendent of Documents, Washington, DC 20402.

exposed. For information on establishing exposure conditions, the purchaser may refer to ISO 12944-2 “Paints and varnishes—Corrosion protection of steel structures by protective paint systems—Part 2: Classification of environments.” For information on the selection of coating systems based on exposure conditions, the purchaser may refer to ISO 12944-5 “Paints and varnishes—Corrosion protection of steel structures by protective paint systems—Part 5: Protective paint systems.” Other industry-recognized resources are available, and the purchaser should consult a coatings professional to assist with coating system selection based on site-specific exposure conditions.

The coatings listed in this standard have been used extensively and have provided excellent corrosion protection and weathering endurance. In recent years, the development of new polymers, pigments, and solvents has contributed to the rapid advancement of materials technology for painting and coating of steel structures. These advancements, coupled with regulatory agency concerns about air pollution by VOCs, have led to the development of many new paint formulations. Although not listed in this standard, many of these new products provide performance equal to or better than the systems presented in this standard.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. Purchaser Options and Alternatives. The following information should be provided by the purchaser.

1. Standard used, that is, ANSI/AWWA C218, Liquid Coatings for Aboveground Steel Water Pipe and Fittings, of latest revision.
2. Any exceptions to the standard that may be required.
3. Diameter, length, and location of the pipeline.
4. Coating system to be supplied (Sec. 4.3).
5. Color, if special color is specified (Sec. 4.3.1).
6. Optional four-coat system (Sec. 4.3.2).
7. Optional two-coat system (Sec. 4.3.5 and Sec. 4.3.6).
8. Surface preparation for overcoating (Sec. 4.4.6).
9. Previously coated pipe (Sec. 4.4.6.1 and Sec. 4.4.6.2).
10. Coating of special pipe fittings and appurtenances (Sec. 4.6).
11. Abrasive blasting of bolts (Sec. 4.6.2).
12. Coating requirements for threaded connections (Sec. 4.6.4).
13. Inspection (Sec. 5.4).
14. Whether adhesion testing is required (Sec. 5.5.4).

15. Adhesion test procedure (Sec. 5.5.4.1).
16. Affidavit of compliance, if required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Added Sec. 1.1.2 to discuss other substrates. The change has been made to other applicable standards.
2. Sec. 4.1 Equipment and 4.2 Materials and Workmanship were added. These sections are standard language and included in all other similar AWWA coating standards.
3. Removed the color designations from the coating systems (i.e., -B, -W, -C for black, white, and other color) in Sec. 4.3.3 through Sec. 4.3.7. This change also allowed the tables in these sections to be simplified by removing the “System” column.
4. Added a new Sec. 4.3.8 Coating System No. 7 (two-coat system consisting of a prime/base coat of two-component, 100% solids aromatic polyurethane followed by a finish coat of an aliphatic polyurethane). Updated references throughout the document.
5. Sec. 4.3 Coating Material Information Requirements was removed. Product labeling and shelf life are now listed in Section 6, which is consistent with other AWWA coating standards. The other listed product information is available in the product technical data sheet.
6. Updated Sec. 4.4 Surface Preparation to be consistent with the language used in all other similar AWWA coating standards. The level of surface protection has not been changed.
7. Removed Sec. 4.5.2. The material preparation varies greatly between the different system types in this document. Manufacturer recommendations should always be followed.
8. Sec. 4.6 was removed and replaced with Sec. 4.2.3 to be consistent with other AWWA coating documents.
9. Renumbered and reformatted Sec. 4.3 through Sec. 4.9 to better match other AWWA coating standards.
10. In Sec. 5.5.3, NACE SP0274 was added as an option for electrical continuity testing.