

American Water Works Association

ANSI/AWWA C602-95

(Revision of ANSI/AWWA C602-89)



AWWA STANDARD
FOR
CEMENT-MORTAR LINING
OF WATER PIPELINES IN PLACE—
4 IN. (100 mm) AND LARGER



All changes specified in erratum to C602-95 are incorporated into this standard.

Effective date: June 1, 1996.

First edition approved by AWWA Board of Directors June 17, 1955.

This edition approved June 17, 1995.

Approved by American National Standards Institute Jan. 12, 1996.

AMERICAN WATER WORKS ASSOCIATION

6666 West Quincy Avenue, Denver, Colorado 80235

Copyright (C) 1998 American Water Works Association, All Rights Reserved.

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 11 W. 42nd St., New York, NY 10036; (212) 642-4900.

Copyright © 1996 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

George J. Tupac, *Chair*
John H. Bambei Jr., *Vice-Chair*
Dennis Dechant, *Secretary*

Consumer Members

G.A. Anderson, NYC Bureau of Water Supply, Corona, N.Y.	(AWWA)
E. Bakall, San Diego County Water Authority, San Diego, Calif.	(AWWA)
J.H. Bambei Jr., Denver Water, Denver, Colo.	(AWWA)
B.R. Bullert,* City of St. Paul Water Authority, St. Paul, Minn.	(AWWA)
J.L. Doane, Portland Bureau of Water Works, Portland, Ore.	(AWWA)
R.V. Frisz, US Bureau of Reclamation, Denver, Colo.	(USBR)
Wesley Kremkau, Washington Suburban Sanitary Commission, Laurel, Md.	(AWWA)
T.A. Larson, Tacoma Water Division, Tacoma, Wash.	(AWWA)
R.T. Menlove, Los Angeles Department of Water & Power, Los Angeles, Calif.	(AWWA)
G.M. Snyder, Metropolitan Water District of Southern California, Los Angeles, Calif.	(AWWA)
M.L. Young, East Bay Municipal Utilities District, Stockton, Calif.	(AWWA)

General Interest Members

G.E. Block Jr., Rizzo Associates Inc., Natick, Mass.	(NEWWA)
W.R. Brunzell, Brunzell Associates Ltd., Skokie, Ill.	(AWWA)
R.L. Coffey, R.W. Beck & Associates, Seattle, Wash.	(AWWA)
B.R. Elms,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
L.J. Farr, CH2M Hill Inc., Redding, Calif.	(AWWA)
S.N. Foellmi,† Black & Veatch Engineers, Irvine, Calif.	(AWWA)
J.W. Green, Alvord Burdick & Howson, Chicago, Ill.	(AWWA)
K.D. Henrichsen, HDR Engineering Inc., Denver, Colo.	(AWWA)
G.K. Hickox, Engineering Consultant, Houston, Texas	(AWS)
M.B. Horsley, Black & Veatch Engineers, Kansas City, Mo.	(AWWA)
J.K. Jeyapalan, American Ventures Inc., Bellevue, Wash.	(AWWA)
R.Y. Konyalian, Consultant, Irvine, Calif.	(AWWA)
E. Smock,† J.M. Montgomery Construction Engineers, Walnut Creek, Calif.	(AWWA)
R.V. Stokes, Montgomery Watson, San Diego, Calif.	(AWWA)

*Liaison, nonvoting

†Alternate

H.R. Stoner, Henry R. Stoner Associates Inc., North Plainfield, N.J.	(AWWA)
Chris Sundberg,* CH2M Hill Inc., Bellevue, Wash.	(AWWA)
G.J. Tupac, G.J. Tupac & Associates, Pittsburgh, Pa.	(AWWA)
L.W. Warren, KCM Inc., Seattle, Wash.	(AWWA)
W.R. Whidden, Post Buckley Schuh & Jernigan, Winter Park, Fla.	(AWWA)
R.E. Young, Robert E. Young Engineers, Sacramento, Calif.	(AWWA)

Producer Members

H.H. Bardakjian, American Concrete & Steel Pipe, Rancho Cucamongo, Calif.	(AWWA)
T.R. Brown, Smith-Blair Inc., Uniontown, Pa.	(AWWA)
J.H. Burton, Baker Coupling Company Inc., Los Angeles, Calif.	(SPFA)
R.J. Card, Thompson Pipe & Steel Company, Englewood, Colo.	(AWWA)
J.R. Davenport, California Steel Pressure Pipe, Riverside, Calif.	(AWWA)
Dennis Dechant, Northwest Pipe & Casing Company, Portland, Ore.	(AWWA)
George Harris, Harris Corrosion Specialists, Longboat Key, Fla.	(AWWA)
J.R. Pegues, American Cast Iron Pipe Company, Birmingham, Ala.	(MSS)
B. Vanderploeg,* Northwest Pipe & Casing Company, Portland, Ore.	(AWWA)
J.A. Wise, Canus Industries Ltd., Burnaby, B.C.	(AWWA)

*Alternate

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.6	Temporary Bypass to Customers 8
I	Introduction..... vi	4.7	Contingent Work 9
I.A	Background vi	4.8	Methods for Lining of New Steel Pipe 9
I.B	History..... vi		
I.C	Acceptance..... vii	5	Verification
II	Special Issues..... vii	5.1	Inspection..... 11
III	Use of This Standard viii	5.2	Inspection of Rehabilitated Pipelines..... 12
III.A	Purchaser Options and Alternatives viii	5.3	Inspection of New Steel Pipe..... 13
III.B	Modification to Standard ix		
IV	Major Revisions ix	6	Delivery
V	Comments ix	6.1	Marking..... 14
		6.2	Shipping 14
		6.3	Affidavit of Compliance..... 15
Standard			
1	General	Figures	
1.1	Scope 1	1	Nominal Slumps of Cement–Mortar Mixes for Application of Pipe Linings Using Pump Feed..... 4
1.2	Purpose..... 1	2	Slump Limits of Cement–Mortar Mixes for Application of Pipe Linings Using Mechanical Feed..... 5
1.3	Application 1		
2	References 2	Tables	
3	Definitions 2	1	Recommended Thickness of Cement–Mortar Lining for Pipelines In Place..... 5
4	Requirements	2	Acceptable Performance for Smooth-Bore Pipe..... 13
4.1	Workmanship 2		
4.2	Equipment..... 2		
4.3	Materials for Construction..... 3		
4.4	General Cement–Mortar Lining Design..... 3		
4.5	Methods for Construction of Rehabilitated Pipelines 5		

Foreword

This foreword is for information only and is not part of AWWA C602.

I. Introduction

I.A. Background. Cement–mortar lining provides the interior of a ferrous-metal pipe with a smooth finish that protects it from corrosion and tuberculation. The lining can significantly retard the recurrence of these problems in previously used pipe if the pipe has been properly cleaned and repaired before application of the lining. Furthermore, the lining can increase the pipeline's carrying capacity because of the reduction in friction resulting from streamlining surface irregularities.

The use of cement mortar as a protective lining for water mains was reported by the French Academy of Science in 1836. Fourteen years later, cement-lined, coated, sheet-metal pipe was introduced in the United States. Some of the early pipelines were in use for the better part of a century, but it was not until the 1930s that a practical method was developed for lining pipe in place.

The first field trial of in-place cement–mortar lining (of pipe that had been in service) was conducted in Jersey City, N.J., in 1933. The pipe was a short section 72 in. (1,830 mm) in diameter. The favorable outcome of the trial led to the cleaning and lining of more than 27,000 ft (8,230 m) of aged, 48-in. (1,220-mm), riveted-steel pipe supplying Newark, N.J. The lining stopped all leakage and, as a result of streamlining the surface over large rivets, also increased the Hazen–Williams flow coefficient by 14 points (estimated by the engineer).

For many years, the smallest-diameter pipe that could be reconditioned by the centrifugal process was 24 in. (600 mm), since a man was required to ride the lining machine through the pipe. In 1950, a remote-control centrifugal-lining machine was introduced that made in-place lining of progressively smaller-diameter pipe possible. Presently, pipelines ranging from 4 in. (100 mm) to 21 ft (64 m) in diameter can be cleaned and cement–mortar lined in place.

I.B. History. The first AWWA standard for cement–mortar lining of pipe in place was published in 1939 as part of AWWA C205-41 (formerly 7A-7-41), Standard for Cement–Mortar Protective Lining and Coating for Steel Water Pipe. That standard was primarily concerned with in-plant lining and coating, a completely different process from in-place lining. Therefore, in 1951, the in-place lining portion was withdrawn and expanded into a separate standard under the direction of the late H.A. Price, who authored most of the new document. That standard, AWWA C602, Standard for Cement–Mortar Lining of Water Pipelines in Place—Sizes 16 In. and Larger, was approved as tentative in 1954 and made standard in 1955.

In 1962, Price suggested to the AWWA Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) that AWWA C602-55 should be revised in view of the extended competence of the centrifugal-lining process, which at that time included pipe as small as 4 in. (100 mm) in diameter. The assignment was given to SWPMTAC Subcommittee 8 and resulted in the revision of the standard adopted and published in 1967.

In 1972, the standard was again considered for revision to reflect the state of the art of in-place cement–mortar lining. The more frequent use of in-place cement–mortar lining in new, large-diameter steel pipelines prompted the committee to note some of the standard procedures used in this application. This edition was approved on Jan. 25, 1976. The standard was revised in 1983 and 1988.

I.C. Acceptance. In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for all direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AWWARF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including:

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF: ANSI[†]/NSF[‡] 60, Drinking Water Treatment Chemicals—Health Effects, and ANSI/NSF 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[§] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with ANSI/NSF 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Appendix A, “Toxicology Review and Evaluation Procedures,” to ANSI/NSF 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Appendix A procedures may not always be identical, depending on the certifier.

AWWA C602-95 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to:

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by all parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. This standard has no applicable information for this section.

*Persons in Canada, Mexico, and non-North American countries should contact the appropriate authority having jurisdiction.

[†]American National Standards Institute, 11 W. 42nd St., New York, NY 10036.

[‡]NSF International, 3475 Plymouth Rd., Ann Arbor, MI 48106.

[§]Both publications available from National Academy of Sciences, 2102 Constitution Ave. N.W., Washington, DC 20418.

III. Use of This Standard. AWWA has no responsibility for the suitability or compatibility of the provisions of this standard to any intended application by any user. Accordingly, each user of this standard is responsible for determining that the standard's provisions are suitable for and compatible with that user's application.

III.A. *Purchaser Options and Alternatives.* The following information should be included in the purchaser's specifications:

1. Project. Diameter, length, and location of pipeline, including plan and profile drawings when available; limits of pipeline shutdowns, if service requirements make such limits necessary; location of access manholes; location, type, and size of valves; location of interconnecting pipelines, hydrant branches, and service pipes; location of fittings and restrictions that could interfere with cleaning and lining operations; location, diameter, and connections of temporary bypass, if required; and all other details of the pipe within the scope of the contract between the purchaser and the constructor.

2. Thickness of cement–mortar lining. Nominal thickness of cement–mortar lining required (Sec. 4.4.5).

3. Services furnished by purchaser. Description of all services or field operations to be performed by the purchaser, such as locating the main to be cleaned and lined, removal and replacement of line valves, operation of valves, tagging all valves that separate the main to be cleaned and lined from the water system to prevent accidental opening, shutting off all inflow of water from connecting pipelines, locating and operating blowoffs, connecting and disconnecting temporary bypasses to customer services, obtaining all permits required for the work, handling all customer contacts, disinfection, and conducting flow tests.

4. Additional work to be performed by constructor. Description of work, including repairs to deteriorated pipe; extra thickness of lining over the rivet heads and lockbar seams; excavation, backfill, and resurfacing work at access excavations; method of opening and closing access openings in the pipeline; furnishing, laying, and removing temporary bypass pipe; and operation of main-line or blowoff valves.

NOTE: When it is necessary to repair deteriorated pipe before lining, the pipe will be repaired by the purchaser or under provisions of the contract between the purchaser and the constructor.

5. Water for cleaning and lining operations. Location of water sources, method of furnishing, quantity available, and pressure information.

6. Disposal of cleaning water and debris. Requirements for the disposal of cleaning water, old lining, and other debris; instructions regarding permits from the responsible authorities.

7. Permissible cement–mortar materials. Preference for, or any restrictions on, type of portland cement and inclusion of pozzolanic materials or admixtures to be used in lining mortar.

8. Purchaser options. Options that may be included in the purchaser's specifications after reviewing the following items in the sections noted:

- a. Affidavit of compliance (Sec. 6.3).
- b. Portland cement (Sec. 4.3.1).
- c. Use of admixtures (Sec. 4.3.3, Sec. 4.4.1, and Sec. 4.4.2).
- d. Use of pozzolanic material (Sec. 4.4.1 and Sec. 4.4.2).
- e. Mortar lining thickness (Sec. 4.4.5).
- f. Access openings (Sec. 4.5.1).
- g. Traffic control (Sec. 4.5.1).
- h. Surface finish (Sec. 4.5.4).

- i. Cleaning of valves; new bolts and gaskets (Sec. 4.5.6.1 and Sec. 4.5.6.2).
- j. Curing by purchaser (Sec. 4.5.7.3).
- k. Temporary bypass to customers (Sec. 4.6).
- l. Disinfection of temporary bypass (Sec. 4.6.2).
- m. Leaking valves (Sec. 4.7.2).
- n. Access openings for lining for new pipe (Sec. 4.8.1).
- o. Surface finish for new pipe (Sec. 4.8.4).
- p. Curing by purchaser for new pipe (Sec. 4.8.7.3).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided in the purchaser's specifications.

IV. Major Revisions. The major changes made to the standard in this edition include the following:

- 1. The format has been changed to AWWA standard style.
- 2. The title of the standard was revised.
- 3. Definitions (Sec. 3) have been revised.
- 4. Sec. 5.2.1 (old Sec. 5.1) and Sec. 5.3.1 (old Sec. 9.1) have been revised.
- 5. Table 1 on recommended thicknesses of cement-mortar linings has been revised.

V. Comments. If you have any comments or questions about this standard, please call the AWWA Standards and Materials Development Department, (303) 794-7711 ext. 6283, FAX (303) 795-1440, or write to the department at 6666 W. Quincy Ave., Denver, CO 80235.