

ANSI/AWWA **D104-23**
(Revision of ANSI/AWWA D104-17)

AWWA Standard

Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks

Effective date: Dec. 1, 2023.

First edition approved by the Board of Directors Jan. 27, 1991.

This edition approved June 9, 2023.

Approved by American National Standards Institute June 9, 2023.




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



ISBN-13, print: 978-1-64717-159-9

ISBN-13, electronic: 978-1-61300-688-7

DOI: <http://dx.doi.org/10.12999/AWWA.D104.23>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher.

Copyright © 2023 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Cathodic Protection Task Force, which developed this standard, had the following personnel at the time:

Miles Steele, *Chair*

Shannon C. Vidika, *Vice-Chair*

D.H. Kroon, Aegion Corporation, Houston, Tex.

B. Misenhelter, Tank Connection, Parsons, Kans.

M.P. Parker, Statewide Aquastore Inc., East Syracuse, N.Y.

L.D. Scott, Tank Industry Consultants, Atascadero, Calif.

M. Steele, Corrpro Companies Inc., Conyers, Ga.

G.R. Stein, Tank Industry Consultants, Indianapolis, Ind.

S.C. Vidika, Dixon Engineering Inc., Medina, Ohio

C. Xiao, City of Phoenix Water Services Department, Phoenix, Ariz.

The Standards Committee on Steel and Composite Water Storage Tanks, which reviewed and approved this standard, had the following personnel at the time of approval:

Gregory R. Stein, *Chair*

Leslie D. Scott, *Vice Chair*

User Members

J. Camarena, East Bay Municipal Utility District, Oakland, Calif.

T.M. Dawson Jr., Emerald Coast Utilities Authority, Pensacola, Fla.

M.F. Gaffey, Naval Facilities Expeditionary Warfare Center, Washington Navy Yard, D.C.

N.J. Meder, Connecticut Water Company, Clinton, Conn.

R.B. Potts, Louisville Water Company, Louisville, Ky.

B. Reilley (*liaison, nonvoting*), Standards Council Liaison, Massachusetts Water Resources Authority, Boston, Mass.

G. Terrell, Birmingham Water Works Board, Birmingham, Ala.

C. Xiao, City of Phoenix Water Services Department, Phoenix, Ariz.

General Interest Members

D.M. Algranti, Albert A. Webb Associates, Riverside, Calif.
J.W. Birkhoff, Birkhoff, Hendricks & Carter LLP, Dallas, Tex.
J.D. Brock, Poggemeyer Design Group, Bowling Green, Ohio
E. Darrimon, Bay Area Coating Consultants Inc., Denair, Calif.
W.J. Dixon (*alternate*), Dixon Engineering Inc., Lake Odessa, Mich.
M.L. Hickey, Murraysmith, Portland, Ore.
F.S. Kurtz (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
R. Perez, Greeley and Hansen, Indianapolis, Ind.
J. Rowley, Dixon Engineering Inc., Lake Odessa, Mich.
L.D. Scott (*alternate*), Tank Industry Consultants, Atascadero, Calif.
G.R. Stein, Tank Industry Consultants, Indianapolis, Ind.
J.I. Strand, CBS Squared Inc., Chippewa Falls, Wis.
T.A. Tovey, Jacobs Engineering, Portland, Ore.

Producer Members

C. Brown (*alternate*), Tnemec Company Inc., Kansas City, Mo.
G.A. Burke, Caldwell Tanks Inc., Louisville, Ky.
W.J. Czaska, McDermott, Plainfield, Ill.
J.W. Davis, Tesla NanoCoatings Inc., Massillon, Ohio
K.T. Fuller, Phoenix Fabricators and Erectors LLC, Avon, Ind.
J. Grendzinski (*alternate*), Landmark Structures, Wheaton, Ill.
B.E. Kromer, Tank Builders Inc., Euless, Tex.
K.E. Kromer (*alternate*), Tank Builders Inc., Euless, Tex.
K. McGuire, CST Industries, Parsons, Kans.
R.L. Moore, Tnemec Company Inc., Kansas City, Mo.
R. Pawski, Landmark Structures, Wheaton, Ill.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		2	References 2
I Introduction.....	vii	3	Definitions 2
I.A Background.....	vii	4	Requirements
I.B History.....	vii	4.1 Design.....	5
I.C Acceptance	vii	4.2 System Components.....	7
II Special Issues	viii	4.3 Installation	9
II.A Protective Coatings.....	viii	5	Verification
II.B Cathodic Protection	ix	5.1 Inspection and Handling.....	11
III Use of This Standard	xi	5.2 Testing	11
III.A Purchaser, Designer, and Installer		5.3 Operation and Maintenance	
Responsibilities	xii	Manual.....	11
III.B Modification to Standard	xiv		
IV Major Revisions.....	xiv	<i>Appendixes</i>	
V Comments	xiv	A Commentary and Additional	
		Information.....	13
<i>Standard</i>		B Operation Guidelines for Cathodic	
1 General		Protection Systems	21
1.1 Scope.....	1	C Service and Maintenance of Impressed-	
1.2 Purpose	1	Current Cathodic Protection	
1.3 Application.....	2	Systems	23

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA D104.

I. Introduction.

I.A. *Background.* This standard describes automatically controlled, impressed-current cathodic protection systems for the interior submerged surfaces of steel water storage tanks. This standard does not cover sacrificial (galvanic) anode-type cathodic protection systems (see ANSI/AWWA D106) or manually controlled rectifiers.

I.B. *History.* Before the development of ANSI/AWWA D104, cathodic protection equipment was covered in ANSI/AWWA D102, Painting and Repainting Steel Tanks, Standpipes, Reservoirs, and Elevated Tanks for Water Storage. ANSI/AWWA D102-64 addressed cathodic protection equipment in Section 4. In the 1978 edition of that standard, however, the provisions for cathodic protection equipment were removed, and the development of a new AWWA standard on cathodic protection was needed. This standard became ANSI/AWWA D104, Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks. The first edition of ANSI/AWWA D104 was approved by the AWWA Board of Directors on Jan. 27, 1991. Subsequent editions were approved on Feb. 2, 1997; June 17, 2001; June 13, 2004; Jan. 23, 2011; and June 11, 2017. This edition of the standard was approved on June 9, 2023.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). AWWA and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[†] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

[†] Persons outside the United States should contact the appropriate authority having jurisdiction.

2. Four standards developed under the direction of NSF:[‡] NSF/ANSI/CAN[§] 60, Drinking Water Treatment Chemicals—Health Effects; NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects; NSF/ANSI 372, Drinking Water System Components—Lead Content; and NSF/ANSI/CAN 600, Health Effects Evaluation and Criteria for Chemicals in Drinking Water.

3. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[¶] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI/CAN 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA D104 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

II.A. *Protective Coatings.* Protective coatings are commonly used in steel water storage tanks. They are an effective method of corrosion control except where holidays exist in the coating caused by poor surface preparation, improper application, defective materials, unanticipated conditions, deterioration over time, or damage. When properly designed and maintained, cathodic protection systems will mitigate corrosion at the submerged locations where there are coating holidays or other coating

[‡] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

[§] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

[¶] Both publications available from the National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20001.

defects. A properly applied coating reduces the surface area of bare steel in contact with the drinking water that requires cathodic protection and reduces the amount of current required to cathodically protect the tank's interior submerged surface. Use and maintenance of protective coatings extend the life of the cathodic protection system and reduce operating costs. For submerged areas of a tank, cathodic protection can also reduce the frequency of coating maintenance. Cathodic protection or coatings can independently reduce corrosion on the interior submerged surfaces; however, the combination of coatings and cathodic protection may be more economical and effective than using coatings or cathodic protection alone.

II.B. *Cathodic Protection.* The two major components of an automatically controlled, impressed-current cathodic protection system are the direct current (DC) power supply controller (rectifier) and the anode system. The range of output current capacity required for an automatically controlled rectifier in a specific application is determined by assuming the area of submerged bare steel to be protected when the interior tank coating is new and when the interior coating has deteriorated to the point at which recoating is necessary. In potable water, current density requirements can range from 0.5 to 5.0 mA/ft² (5.4 to 53.8 mA/m²) of bare steel surface. Applications involving turbulence, high temperature, or a combination of these may require higher current densities. For newly coated tanks, the total current requirement may be as little as 1 percent of the current required to protect an uncoated surface. As a rule, rectifiers for newly coated tanks should have sufficient current capacity to protect the anticipated bare submerged surface area before coating repair or replacement. The required operating voltage of a rectifier for a specific tank depends on the current required to provide adequate protection and the total circuit resistance of the system.

Automatically controlled rectifier systems should be used for cathodic protection of water storage tanks when alternating current (AC) power is available to the tank site. Automatically controlled systems use one or more long-life reference electrodes to monitor the protection levels maintained on the submerged surfaces. The rectifier controller continuously monitors the potential difference between the reference electrode and the tank's submerged surface, referred to as the *tank-to-water potential*, which will be free of IR (current × resistance, or voltage) drop error. IR drop must be eliminated or minimized to accurately determine if the voltage difference between the submerged surface of the tank and the reference electrode meets the criteria for cathodic protection. The controller instantaneously interrupts the flow of cathodic protection current, providing an IR drop-free measurement, which closely approximates the polarized potential. The controller compares the measured tank-to-water potential to

a preset value and automatically adjusts the voltage output of the rectifier to either increase or decrease current accordingly. Automatic units include a tank-to-water potential monitoring meter, which can be easily checked by the purchaser.

NOTE: Manually controlled rectifiers are not recommended for use in water storage tanks and are not covered by this standard. The reason for this is that they require frequent monitoring, testing, and manual adjustment of the rectifier current output whenever the current requirements change because of changes in water level, coating condition, temperature, water chemistry, water turbulence, or accumulation of polarization films. Failure to adjust the current output for manual rectifiers can result in corrosion caused by underprotection or coating damage caused by overprotection.

The second major component of an automatically controlled system is the anode system. The anode system includes the anode material and the method of suspending the anode within the tank. The type of anode material and suspension system used is typically based on the tank's susceptibility to icing conditions.

For tanks subject to icing conditions, a seasonal or a long-life anode system may be used. A seasonal (or temporary) arrangement consists of vertically suspended anodes. This type of suspension system is susceptible to ice damage. Ice will adhere to some portion of the anode string and tear the anodes loose, causing the system to fail. Because it is anticipated that the anodes will be damaged annually, low-cost aluminum rod anodes are used. While the anode system is intact, the system will operate properly during the more corrosive summer season. In locations subject to freezing temperatures, there is usually a 2- to 5-month period during the winter when the system may not operate properly because of ice damage. This type of anode system will usually require annual replacement of the anodes and vertical anode suspension system. Anode remnants should be removed from the tank whenever the interior is accessible.

A long-life anode system includes suspension systems that are designed to be more resistant to ice damage and permit the use of long-life anode materials that have a design life of at least 10 years. The potential for ice damage is reduced by attaching the anode material to a buoyant or horizontally submerged radial rope system that is attached to the walls of the tank and prevents the anode system from coming in contact with ice formations. Another type of system compensates for ice damage by attaching the anode material to an extendable element suspended from the tank roof. The extendable element stretches with the movement of ice and allows the anode to eventually return to its original position.

For tanks not subject to icing conditions, anodes may be suspended from the tank roof without an extendable element or may be horizontally supported from a submerged radial rope system.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

Contractual responsibilities for items such as design, material, fabrication, construction, inspection, testing, and operation have been removed from the standard and must be addressed in the contract documents.

Many tanks using automatically controlled, impressed-current cathodic protection systems for interior submerged surfaces** have been in service for more than 30 years. Proper design and maintenance of impressed-current cathodic protection systems can significantly extend the service life of steel water storage tanks.

This standard does not cover systems where the purchaser specifies criteria for protection other than those listed in this standard. This standard does not cover systems to be installed in areas subject to regulations or requirements that are more stringent than the requirements contained herein. Where local, municipal, county, or state government requirements apply to the installation of the impressed-current cathodic protection system, such requirements govern, and this standard should be interpreted to supplement them. It is the purchaser's responsibility to supplement or modify this standard for compliance with these local requirements.

At a minimum, it is important that all of the requirements in this standard be met. An impressed-current cathodic protection system cannot be represented as an ANSI/AWWA D104-compliant system if it does not meet the minimum requirements of this standard.

Annual inspection and maintenance of the system are important to ensuring maximum tank life.

AWWA Manual M27, *External Corrosion Control for Infrastructure Sustainability*, addresses corrosion and corrosion protection for water tanks; and AWWA Manual M42, *Steel Water-Storage Tanks*, provides guidance on inspection and maintenance of welded steel tanks for water storage.

** The word "system" and the phrase "cathodic protection system" are used herein broadly in place of the lengthy phrase "automatically controlled, impressed-current cathodic protection system for interior submerged surfaces of steel water storage tanks."

This standard does not cover tank disinfection procedures or cleaning and painting. ANSI/AWWA C652, Disinfection of Water-Storage Facilities, should be consulted for recommended procedures for disinfection of water storage facilities.

III.A. *Purchaser, Designer, and Installer Responsibilities.* Proper use of this standard requires that the purchaser, purchaser's representative, or the designer specify certain requirements. It may be desirable to modify, delete, or amplify sections of this standard to suit special conditions.

III.A.1 Information Specified by Purchaser. The following information should be provided by the purchaser or designated representative when specifying an impressed-current cathodic protection system for the interior submerged surfaces of a steel water storage tank:

1. Compliance with the latest revision of ANSI/AWWA D104, Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks.
2. Compliance requirement for NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects (see Sec. 4.1.2).
3. Location of site.
4. Gross capacity of the tank, the tank diameter, and type of roof.
5. For elevated tanks, the style and shape of tank, bottom capacity level (BCL), head range, and the diameter and type of riser (wet or dry).
6. For ground-supported flat-bottom tanks, the maximum water level (MWL).
7. Chemical analysis of the water to be stored, including total dissolved solids (TDS), conductivity, pH, chloride ion concentration, and sulfate ion concentration.
8. Whether water turbulence caused by filling and/or mixing may exist.
9. Operating temperature range (ambient or modified) and typical flow rate (gallons per day).
10. Type and age of protective coatings.
11. Maximum anticipated coating deterioration expressed as a percentage of the total interior submerged coated surface area that is allowed to become bare before the coating is repaired or replaced (for cathodic protection design purposes).
12. Presence of submerged surface area of stainless steel, copper, brass, and metals other than carbon steel in the submerged portion of the reservoir.
13. Source of AC power.
14. Required design life of the anode system.
15. Location of the site.
16. Required time for system installation.