



BSI Standards Publication

AEROSPACE SERIES

Specification for nickel-chromium-titanium-aluminium heat-resisting alloy billets, bars, forgings and parts (Nickel base, Cr 19.5, Ti 2.2, Al 1.4)

Publishing and copyright information

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2016
Published by BSI Standards Limited 2016

ISBN 978 0 580 93962 4

ICS 49.025.99

The following BSI references relate to the work on this standard:

Committee reference ACE/61

Draft for comment 09/30199922 DC; 16/30340198 DC

Publication history

First published 1970

Second edition, February 1973

Third (present) edition, January 2010

Amendments issued since publication

Date	Text affected
------	---------------

July 2016	A1. See foreword
-----------	------------------

Contents

Foreword *ii*

1 Scope 1

2 Normative references 1

3 Technical requirements 1

Bibliography 10

List of tables

Table 1 – Technical requirements for nickel-chromium-titanium-aluminium heat-resisting alloy bars and extruded sections for machining 2

Table 2 – Technical requirements for nickel-chromium-titanium-aluminium heat-resisting alloy extruded sections for subsequent forming 4

Table 3 – Technical requirements for nickel-chromium-titanium-aluminium heat-resisting alloy billets and bars for forging 6

Table 4 – Technical requirements for nickel-chromium-titanium-aluminium heat-resisting alloy forgings 8

Summary of pages

This document comprises a front cover, an inside front cover, pages i to ii, pages 1 to 10, an inside back cover and a back cover.

Foreword

Publishing information

This British Standard is published by BSI Standards Limited, under licence from the British Standards Institution, and came into effect on 31 January 2010. It was prepared by Panel ACE/61/-/48, *Heat resisting alloys*, under the authority of Technical Committee ACE/61, *Metallic materials for aerospace purposes*. A list of organizations represented on this committee can be obtained on request to its secretary.

Supersession

This standard supersedes BS 3HR 1:2010, which is withdrawn.

Information about this document

Text introduced or altered by Amendment(s) No. 1 is indicated in the text by tags $\boxed{A_1}$ $\langle A_1 \rangle$. Minor editorial changes are not tagged.

This is a full revision of BS HR 1. The principal change from the previous edition is that the requirements are stated in tabular format in accordance with EN 4500-1 and EN 4500-3.

Hazard warnings

WARNING. This British Standard calls for the use of substances and/or procedures that can be injurious to health if adequate precautions are not taken. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

Use of this document

It has been assumed in the preparation of this British Standard that the execution of its provisions will be entrusted to appropriately qualified and experienced people, for whose use it has been produced.

Presentational conventions

The provisions of this standard are presented in roman (i.e. upright) type. Its requirements are expressed in sentences in which the principal auxiliary verb is “shall”.

Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.

Contractual and legal considerations

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

1 Scope

This British Standard specifies requirements for nickel-chromium-titanium-aluminium heat-resisting alloy supplied in the following forms, and as parts.

- a) Bars and extruded sections for machining: solution treated, designation HR 1A.
- b) Extruded sections for subsequent forming: softened, designation HR 1B.
- c) Billets and bars for forging: hot or cold worked and subsequently machined or ground, designation HR 1C.
- d) Forgings: solution treated, designation HR 1D.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

BS HR 100, *Procedure for inspection, testing and acceptance of wrought heat-resisting alloys*

3 Technical requirements

3.1 Material to this standard shall conform to Table 1, Table 2, Table 3 and Table 4.

NOTE The format and symbols used in Table 1, Table 2, Table 3 and Table 4 are derived from EN 4500-1 and EN 4500-3.

3.2 Parts finally heat-treated after machining shall conform to Section 1 and Section 8 of BS HR 100.

3.3 Parts shall be supplied in the solution treated and precipitation treated condition.

3.4 If required by the purchaser and stated on the drawing or order, finished parts shall be precipitation treated at a temperature of $(750 \pm 10)^\circ\text{C}$ for 4 h, followed by cooling in air.