

Tyres and wheels —

Part 1: Tyres —

Section 2: Commercial vehicle tyres —

Subsection 2.3 Method of measuring rolling resistance

UDC [629.114.3/.5].012.55:531.45.083

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

BSI
Documents

AVA

Document Sharing Hub

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Automobile Standards Policy Committee (AUE/-) to Technical Committee AUE/4, upon which the following bodies were represented:

- Agricultural Engineers' Association
- Automobile Association
- British Industrial Truck Association
- British Pressure Gauge Manufacturers' Association
- British Rubber Manufacturers' Association
- Bus and Coach Council
- Department of Transport
- Freight Transport Association
- Institute of Road Transport Engineers (Inc)
- Motor Cycle Industry's Association of Great Britain Ltd.
- Motor Industry Research Association
- National Tyre Distributors' Association
- Retread Manufacturers' Association
- Road Haulage Association Ltd.
- Society of Motor Manufacturers and Traders Ltd.

This British Standard, having been prepared under the direction of the Automobile Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 15 May 1993

© BSI 12-1999

The following BSI references relate to the work on this standard:
Committee reference AUE/4
Draft for comment 91/71575 DC

ISBN 0 580 21747 7

Amendments issued since publication

Amd. No.	Date	Comments

Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
1 Scope	1
2 Definitions	1
3 Test methods	1
4 Test equipment	1
5 Test conditions	2
6 Test procedure	2
7 Data interpretation	3
8 Data analysis	4
Annex A (normative) Test equipment tolerances	6
Annex B (informative) Optional test conditions	7
Annex C (informative) Measurement methods of moment of inertia for drum and tyre assembly — Deceleration method	7
Figure 1 — Free-body diagram of tyre/drum system, assuming no bearing and windage losses	3
Figure C.1 — Arrangement	8
Figure C.2 — Spring method	9
Figure C.3 — Bifilar pendulum (rope) method	9
Table B.1	7

National foreword

This Subsection of this Part of BS AU 50 has been prepared under the direction of the Automobile Standards Policy Committee. It is identical with ISO 9948:1992 *Truck and bus tyres — Methods of measuring rolling resistance*, published by the International Organization for Standardization (ISO). Other Parts of this standard are as follows:

- *Part 2: Wheels and rims;*
- *Part 3: Valves;*
- *Part 4: Rim profiles and dimensions.*

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 9 and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope

This International Standard specifies methods for measuring rolling resistance, under controlled laboratory conditions, for new pneumatic tyres designed primarily for use on trucks and buses. The relationship between values obtained and the fuel economy of the vehicle is undetermined, and such values are not intended to be used to indicate levels of performance or quality.

This International Standard applies to all truck and bus tyres.

It enables comparisons to be made between the rolling resistance of new tyres when they are free-rolling straight ahead, in a position perpendicular to the drum outer surface, and in steady-state conditions.

In measuring tyre rolling resistance, it is necessary to measure small forces in the presence of much larger forces. It is, therefore, essential that equipment and instrumentation of appropriate accuracy be used.

2 Definitions

For the purposes of this International Standard, the following definitions apply.

2.1

rolling resistance, F_r

loss of energy (or energy consumed) per unit of distance

NOTE 1 The SI unit conventionally used for the rolling resistance is the newton metre per metre (N m/m). This is equivalent to the drag force in newtons (N).

2.2

rolling resistance coefficient, C_r

ratio of the rolling resistance, in newtons, to the load on the tyre, in newtons. This quantity is dimensionless and is derived as follows:

$$C_r = \frac{\text{rolling resistance}}{\text{test load}}$$

2.3

capped inflation

process of inflating the tyre and allowing the inflation pressure to build up, as the tyre is warmed up while running

2.4

regulated inflation

process of inflating the tyre to the required pressure independent of its temperature, and maintaining this inflation pressure while the tyre runs under load. This is most commonly done by using a regulated pressure source attached to the tyre through a rotating union. (See Annex B.)

2.5

parasitic loss

loss of energy (or energy consumed) per unit distance excluding tyre losses, and attributable to aerodynamic loss, bearing friction and other sources of systematic loss which may be inherent in the measurement

2.6

skim reading

type of parasitic loss measurement, in which the tyre is kept rolling, without slippage, while reducing the tyre load to a level at which energy loss within the tyre itself is virtually zero

2.7

machine reading

type of parasitic loss measurement, involving losses of the test machine, exclusive of losses in the rotating spindle which carries the tyre and rim

2.8

moment of inertia

(see Annex C)

3 Test methods

The following alternative measurement methods are given in this International Standard. The choice of an individual method is left to the tester. For each method, the test measurements shall be converted to a rolling resistance force acting at the tyre/drum interface.

- a) Force method: the reaction force at the tyre spindle.
- b) Torque method: the torque input to the test drum.
- c) Power method: the power input to the test drum.
- d) Deceleration method: the deceleration of the test drum and tyre assembly.

4 Test equipment

4.1 Drum specifications

4.1.1 Diameter

The test dynamometer shall have a cylindrical flywheel (drum) with a diameter of between 1,7 m and 3 m inclusive. It should be noted that the results are different; see 8.3 for drum diameter correction for comparisons, if necessary.

4.1.2 Surface

The surface of the drum shall be smooth steel or textured, and shall be kept clean. For the textured drum surface, see B.4.