

Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties

The European Standard EN 10273:2000 has the status of a
British Standard

ICS 77.140.30; 77.140.60

National foreword

This British Standard is the official English language version of EN 10273:2000. It partially supersedes BS 1502:1982 which will be withdrawn on the publication of BS EN 10272.

The UK participation in its preparation was entrusted by Technical Committee ISE/73, Steels for pressure purposes, to Subcommittee ISE/73/2, Steel plates and bars for pressure purposes, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 28, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Engineering Sector Committee, was published under the authority of the Standards Committee and comes into effect on 15 May 2000

© BSI 10-2000

ISBN 0 580 35676 0

Amendments issued since publication

Amd. No.	Date	Comments
11021 Corrigendum No. 1	October 2000	Correction to National foreword supersession details

English version

**Hot rolled weldable steel bars for pressure purposes
with specified elevated temperature properties**

Barres laminées à chaud en aciers soudables pour
appareils à pression, avec des caractéristiques spécifiées
aux températures élevées

Warmgewalzte Schweißgeeignete Stäbe für Druckbehälter
mit festgelegten Eigenschaften bei erhöhten Temperaturen

This European Standard was approved by CEN on 29 October 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword	4
1 Scope	5
2 Normative References	5
3 Definitions	6
4 Dimensions and tolerances on dimensions	6
5 Calculation of mass	6
6 Classification and designation	7
6.1 Classification	7
6.2 Designation	7
7 Information to be supplied by the purchaser	7
7.1 Mandatory information	7
7.2 Options	7
8 Requirements	8
8.1 Steelmaking process	8
8.2 Delivery condition	8
8.3 Chemical composition	8
8.4 Mechanical properties	9
8.5 Surface condition	9
8.6 Internal soundness	9
8.7 Weldability	9
9 Inspection	10
9.1 General	10
9.2 Types of inspection and inspection documents	10
9.3 Tests to be carried out	11
9.4 Re-tests	11
10 Sampling	11
10.1 Frequency of testing	11
10.2 Selection and preparation of samples and test pieces	11
11 Test methods	12
11.1 Chemical analysis	12
11.2 Tensile test at room temperature	12
11.3 Tensile test at elevated temperature	12
11.4 Impact test	12
11.5 Other testing	13
12 Marking	13
Annex A (informative) Reference data of strength values for 1% (plastic) creep strain and creep rupture	23

Annex B (informative) Guidance for heat treatment	25
Annex C (informative) Bibliography	26
Annex D (informative) National A-deviations	27
Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives	28

Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 22, Steels for pressure purposes - Qualities, the Secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2000, and conflicting national standards shall be withdrawn at the latest by July 2000.

Annex D contains national A-deviations specifying the restrictions for the application of this European Standard in Sweden.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

NOTE: The clauses marked with a point (●) contain information relating to agreements which are to be made at the time of ordering. The clauses marked with two points (●●) contain information relating to agreements which may be made at the time of enquiry and order.

1 Scope

This European Standard specifies the technical delivery conditions for hot rolled weldable steel bars for the construction of pressure equipments for use at elevated temperatures.

The general technical delivery conditions in EN 10021 also apply to products supplied in accordance with this European Standard.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

CR 10260	Designation systems for steel - Additional symbols for steel names
prEN 1011-2	Welding - Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels
EN 10002-1	Metallic materials - Tensile testing - Part 1: Method of test (at ambient temperature) (including Corrigendum AC1:1990)
EN 10002-5	Metallic materials - Tensile testing - Part 5: Method of test at elevated temperatures
EN 10020	Definition and classification of grades of steel
EN 10021	General technical delivery requirements for steel and iron products
EN 10027-1	Designation systems for steel - Part 1: Steel names, principal symbols
EN 10027-2	Designation systems for steel - Part 2: Numerical system
EN 10045-1	Metallic materials - Charpy impact test - Part 1: Test method
EN 10052	Vocabulary of heat treatment terms for ferrous products
EN 10079	Definition of steel products
EN 10168 ¹⁾	Iron and steel products - Inspection and delivery documents contents - List of information and description
EN 10204	Metallic products - Types of inspection documents (including amendment A1:1995)
EN 10221	Surface quality classes for hot-rolled bars and rods - Technical delivery conditions

¹⁾ In preparation; until this document is published as European Standard a corresponding national standard should be agreed at the time of enquiry and order.

EN ISO 377	Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377:1997)
ISO 14284	Steel and iron - Sampling and preparation of samples for the determination of chemical composition

3 Definitions

For the purposes of this standard the definitions of standards:

- EN 10020 for classification of steels;
- EN 10052 for the types of heat treatment; and
- EN 10079 for the various product forms.

apply.

Deviating from (see 3.1) or additional to (see 3.2) EN 10052, are the following defined.

3.1 Normalizing rolling is a rolling process in which the final deformation process is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing. The symbol for this delivery condition is N.

3.2 Additionally to the definitions for quenching and tempering the following should be noted:

NOTE: Quenching and tempering (symbol QT) also includes direct hardening plus tempering.

3.3 Purchaser: The person or organization that orders products in accordance with this standard. The purchaser is not necessarily, but may be, a manufacturer of pressure equipment in accordance with the EU Directive listed in Annex ZA. Where a purchaser has responsibilities under this EU Directive, this standard will provide a presumption of conformity with the essential requirements of the Directive so identified in Annex ZA.

4 • Dimensions and tolerances on dimensions

The nominal dimensions and tolerances on dimensions for the products shall be agreed at the time of enquiry and order with reference to one of the dimensional standards listed below for:

- rectangular section to EURONORM 58;
- square section to EURONORM 59;
- round section to EURONORM 60;
- hexagonal section to EURONORM 61.

5 Calculation of mass

A density of 7,85 kg/dm³ shall be used as the basis for the calculation of the nominal mass from the nominal dimensions of all steels.

6 Classification and designation

6.1 Classification

This European Standard covers the steel grades given in table 1.

According to EN 10020 the steels P235GH, P250GH, P265GH, P295GH, P355GH, P275NH and P355NH are non-alloy quality steels. All other steel grades covered by this European Standard are alloy special steels.

6.2 Designation

The steel grades specified in this European Standard are designated with steel names and steel numbers in accordance with EN 10027-1 and CR 10260. The corresponding steel numbers have been established in accordance with EN 10027-2.

7 Information to be supplied by the purchaser

7.1 Mandatory information

The complete order of a product as specified in this European Standard shall include the following information:

- a) the quantity required;
- b) the shape of bars;
- c) the tolerances on dimensions, shape and mass (see clause 4);
- d) the nominal dimensions of the product;
- e) the number of this European Standard;
- f) the steel name or number;
- g) the delivery condition (see 8.2);
- h) type of inspection document (see 9.2.1).

7.2 Options

A number of options are specified in this European Standard and these are listed below. If the purchaser does not indicate his wish to implement any of these options the products shall be supplied in accordance with the basic specification (see 7.1).

- 1) Specification of the steelmaking process (see 8.1).
- 2) Deviating delivery condition (see 8.2.1 and 8.2.3).
- 3) Specification of a lower maximum copper content and a maximum tin content (see table 1, footnote 2).
- 4) Specification of a higher minimum chromium content (see table 1, footnote 9).
- 5) Specification of a maximum carbon equivalent value (see 8.3.3 and table 3).
- 6) Mechanical properties for diameters or thicknesses > 150 mm (see table 4, footnote 2).
- 7) Special surface condition (see 8.5).
- 8) Requirements for and verification of internal soundness (see 8.6).

- 9) Specific tests for verification of general delivery requirements (see 8.6 and 9.1).
- 10) Delivery of data on suitable welding conditions (see 8.7.2).
- 11) Product analysis (see 9.3.2, 10.1.1 and 11.1).
- 12) Verification of 0,2 % proof strength at elevated temperature (see 9.3.2 and 11.3).
- 13) Special marking requirements (see 12.2).

8 Requirements

8.1 ●● Steelmaking process

Unless a special steelmaking process is agreed at the time of enquiry and order, the steelmaking process for steels in accordance with this European Standard shall be at the discretion of the manufacturer.

8.2 ● Delivery condition

8.2.1 ●● Unless otherwise agreed at the time of enquiry and order, the products covered by this European Standard shall be supplied in the conditions given in table 4.

8.2.2 Normalizing may be replaced by normalizing rolling for steel grades P235GH, P250GH, P265GH, P295GH, P355GH, P275NH, P355NH and P460NH. This means that the requirements have to be met again even after subsequent normalizing.

In the case of the grade P460NH delayed cooling or additional tempering may be necessary for small sections and in special cases.

8.2.3 ●● Products made of steel grades P235GH, P250GH, P265GH, P295GH, P355GH, P275NH, P355NH, P460NH and 16Mo3 may also be delivered in the untreated condition if so agreed (Annex B contains for the grades P...GH as well as for 16Mo3, 13CrMo4-5, 10CrMo9-10 and 11CrMo9-10 heat treatment information for the purchaser).

In these cases, the test pieces shall be tested in the delivery condition as indicated in table 4.

NOTE: The testing of the test pieces in a simulated heat treated condition does not discharge the processor who carries out the heat treatment from the obligation of providing proof of the specified properties in the finished product.

8.3 Chemical composition

8.3.1 The requirements of table 1 shall apply for the chemical composition determined from the cast analysis.

8.3.2 The product analysis shall not deviate from the specified values for the cast analysis as specified in table 1 by more than the values given in table 2.

8.3.3 ●● A maximum value for the carbon equivalent may be agreed upon at the time of enquiry and order for steel grades P235GH, P265GH, P295GH, P355GH, P275NH and P355NH. In this case, for the grades P275NH and P355NH the values given in table 3 shall apply.