

Metallic materials — Uniaxial creep testing in tension — Methods of test

The European Standard EN 10291:2000 has the status of a
British Standard

ICS 77.040.10

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

BSI
Documents

AVA

Document Sharing Hub

National foreword

This British Standard is the official English language version of EN 10291:2000. It supersedes BS 3500-1:1969, BS 3500-3:1969 and BS 3500-5:1969 which are withdrawn.

The UK participation in its preparation was entrusted by Technical Committee ISE/NFE/4, Mechanical testing of metals, to Subcommittee ISE/NFE/4/1, Uniaxial testing of metals, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 31 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Engineering Sector Committee, was published under the authority of the Standards Committee and comes into effect on 15 December 2000

© BSI 12-2000

ISBN 0 580 36703 7

Amendments issued since publication

Amd. No.	Date	Comments

English version

Metallic materials — Uniaxial creep testing in tension — Method of test

Matériaux métalliques — Essai de fluage uniaxial en traction — Méthode d'essai

Metallische Werkstoffe — Einachsiger Zeitstandversuch unter Zugbeanspruchung — Prüfverfahren

This European Standard was approved by CEN on 4 September 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Symbols and designations	7
5 Principle	9
6 Apparatus	9
6.1 Testing machine	9
6.2 Elongation measuring device	9
6.3 Heating device	10
7 Test pieces	12
7.1 Shape and dimensions	12
7.2 Preparation	13
7.3 Determination of the original cross-sectional area	14
7.4 Marking of the original gauge length (L_0)	14
8 Test procedure	14
8.1 Heating of the test piece	14
8.2 Application of the test force	14
8.3 Test interruptions	14
8.4 Recording of temperature and elongation	15
9 Determination of results	15
10 Test validity	16
11 Accuracy of the results	16
11.1 Expression of the results	16
11.2 Final uncertainty	16
12 Test report	16
Annex A (informative) Information concerning different types of thermocouples	23
Annex B (informative) Information concerning methods of calibration of thermocouples	24
Annex C (informative) Method of estimating the uncertainty of the measurement in accordance with the ISO "Guide to the expression of uncertainty in measurement"	25
Bibliography	30

Foreword

This European Standard has been prepared by Technical Committee ECISS/TC 1 Steel — Mechanical testing, the Secretariat of which is held by AFNOR.

It is based on ISO 204 with addition of the provisions concerning the interrupted creep test.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2001, and conflicting national standards shall be withdrawn at the latest by April 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the method for the uninterrupted and interrupted creep tests and defines the properties of metallic materials which can be determined from these tests, in particular the creep elongation and the time of creep rupture, at a specified temperature.

NOTE The stress rupture test is also covered by this standard.

2 Normative references

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 7500-2, *Metallic materials — Verification of static uniaxial testing machines — Part 2: Tensile creep testing machines — Verification of the force applied (ISO 7500-2:1996)*.

EN 10002-4, *Metallic materials — Tensile test — Part 4: Verification of extensometers used in uniaxial testing*.

EN 10002-5, *Metallic materials — Tensile test — Part 5: Method of testing at elevated temperature*.

EN 20286-2, *ISO system of limits and fits — Part 2: Table of standard tolerances grades and limit deviations for holes and shafts (ISO 286-2:1998)*.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply:

3.1

reference length (L_r)

base length used for the calculation of elongation

NOTE In some cases, the reference length needs to be calculated. An example of a procedure is given in Figure 2.

Distinction is made between:

3.1.1

original reference length (L_{ro})

reference length determined at ambient temperature before the test

3.1.2

final reference length (L_{ru})

reference length determined at ambient temperature after rupture, with the pieces carefully fitted back together with their axes in a straight line

3.2

original gauge length (L_o)

length between gauge length marks on the test piece measured at ambient temperature before the test

3.3

final gauge length after rupture (L_u)

length between gauge length marks on the test piece measured after rupture, at ambient temperature, with the pieces carefully fitted back together with their axes in a straight line

3.4

parallel length (L_c)

length of the parallel reduced section of the test piece

3.5

extensometer gauge length (L_e)

distance between the measuring points of the extensometer

NOTE In some cases, $L_e = L_o$.

3.6

original cross-sectional area (S_o)

cross-sectional area of the parallel length as determined at ambient temperature prior to testing

3.7

minimum cross-sectional area after rupture (S_u)

minimum cross-sectional area of the parallel length as determined at ambient temperature after rupture, with the pieces carefully fitted back together with their axes in a straight line

3.8

initial stress (σ_o)

applied force divided by the original cross-sectional area (S_o) of the test piece

3.9

elongation (ΔL_r)

increase of the reference length (L_r), see 6.2

3.10

percentage elongation (A)

elongation expressed as a percentage of the original reference length L_{ro} , see Figure 1

NOTE In the case of the terms for elongation in 3.10 (except A_u , in 3.10.6), the symbol “ ε ” may replace “ A ”. However, when “ ε ” is used, the following convention should apply:

- ε % = percentage strain/elongation;
- ε = absolute strain.

3.10.1

percentage initial plastic elongation (A_i)

non-proportional increase of the original reference length L_{ro} due to the application of the test force

3.10.2

percentage creep elongation (A_f)

increase in reference length at time t (ΔL_{rt}) at a specified temperature expressed as a percentage of the original reference length (L_{ro}):

$$A_f = \frac{\Delta L_{rt}}{L_{ro}} \times 100$$

NOTE 1 A_f may have the specified temperature (T) in Celsius degrees as superscript and the initial stress (σ_o) in megapascals¹⁾ and time t (in hours) as subscript.

NOTE 2 By convention the beginning of creep elongation measurement is the time at which the initial stress (σ_o) is applied to the test piece (see Figure 1).

¹⁾ 1 MPa = 1 N/mm²

3.10.3

percentage plastic elongation (A_p)

non-proportional increase of the original reference length (L_{ro}) at time t :

$$A_p = A_i + A_f$$

3.10.4

percentage anelastic elongation (A_k)

non-proportional decrease of the original reference length (L_{ro}) at time t due to unloading

3.10.5

percentage permanent elongation (A_{per})

total increase of the original reference length (L_{ro}) at time t determined after unloading:

$$A_{per} = A_p - A_k$$

3.10.6

percentage elongation after creep rupture (A_u)

permanent increase of the original reference length (L_{ro}) after rupture ($L_{ru} - L_{ro}$) expressed as a percentage of the original reference length (L_{ro}):

$$A_u = \frac{L_{ru} - L_{ro}}{L_{ro}} \times 100$$

NOTE A_u may have the specified temperature (T) in Celsius degrees as superscript and the initial stress (σ_0) in megapascals²⁾ as subscript.

3.11

percentage reduction of area after creep rupture (Z_u)

maximum change in cross-sectional area measured after rupture ($S_0 - S_u$) expressed as a percentage of the original cross-sectional area (S_0):

$$Z_u = \frac{S_0 - S_u}{S_0} \times 100$$

NOTE Z_u may have the specified temperature (T) in Celsius degrees as superscript and the initial stress (σ_0) in megapascals²⁾ as subscript.

3.12

creep elongation time (t_{fx})

time required for a strained test piece to obtain at the specified values of temperature (T) and initial stress (σ_0) a specified percentage creep elongation (x)

EXAMPLE $t_{f0,2}$

3.13

plastic elongation time (t_{px})

time required to obtain at the specified values of temperature (T) and initial stress (σ_0) a specified percentage plastic elongation (x)

3.14

creep rupture time (t_u)

time required for the test piece maintained at the specified temperature (T) and strained by the specified tensile force to rupture

²⁾ 1 MPa = 1 N/mm²

NOTE The symbol t_u may have as superscript the specified temperature (T) in Celsius degrees and as subscript the initial stress (σ_o) in megapascals²⁾.

3.15

simple machine

a testing machine that permits straining of a single test piece

3.16

multiple machine

a testing machine that permits straining of more than one test piece simultaneously at the same temperature

4 Symbols and designations

The symbols and corresponding designations are given in Table 1.

Table 1 — Symbols and designations

Reference number ^{a)}	Symbol ^{b)}	Unit	Designation
1	d	mm	Diameter of the cross-section of the parallel length of a cylindrical test piece
2	b	mm	Width of the cross-section of the parallel length of a test piece of square or rectangular cross-section
3	L_r	mm	Reference length
4	a	mm	Thickness of a test piece of square or rectangular cross-section
-	L_{ro}	mm	Original reference length
-	L_{ru}	mm	Final reference length
-	ΔL_r	mm	Elongation
-	ΔL_{rt}	mm	Increase in reference length at time t
5	L_o	mm	Original gauge length
-	L_u	mm	Final gauge length after rupture
6	L_c	mm	Parallel length
7	L_e	mm	Extensometer gauge length
8	r	mm	Transition radius
9	S_o	mm ²	Original cross-sectional area of the parallel length
-	S_u	mm ²	Minimum cross-sectional area after rupture
10	σ_o	MPa	Initial stress
11	$A_e^{c)}$	%	Percentage elastic elongation
12	$A_i^{c)}$	%	Percentage initial plastic elongation
13	$A_k^{c)}$	%	Percentage anelastic elongation
14	$A_p^{c)}$	%	Percentage plastic elongation
15	$A_{per}^{c)}$	%	Percentage permanent elongation

continued

Table 1 — Symbols and designations (*continued*)

Reference number ^{a)}	Symbol ^{b)}	Unit	Designation
16	$A_f^{c)}$	%	Percentage creep elongation: $A_f = \frac{\Delta L_{rt}}{L_{ro}} \times 100$ NOTE As an example, the symbol may be completed as follows: $A_{f50/5000}^{375}$: percentage creep elongation with an initial stress of 50 MPa after 5 000 h at the specified temperature of 375 °C.
23	$A_u^{c)}$	%	Percentage elongation after creep rupture: $A_u = \frac{L_{ru} - L_{ro}}{L_{ro}} \times 100$ NOTE As an example, the symbol may be completed as follows: A_{u50}^{375} : percentage elongation after creep rupture with an initial stress of 50 MPa at the specified temperature of 375 °C.
-	Z_u	%	Percentage reduction of area after creep rupture: $Z_u = \frac{S_o - S_u}{S_o} \times 100$ NOTE As an example, the symbol may be completed as follows: Z_{u50}^{375} : percentage reduction of area after creep rupture with an initial stress of 50 MPa at the specified temperature of 375 °C.
-	t_{fx}	H	Creep elongation time
-	t_{px}	H	Plastic elongation time
24	t_u	H	Creep rupture time NOTE As an example, the symbol may be completed as follows: t_{u50}^{375} : creep rupture time with an initial stress of 50 MPa at the specified temperature of 375 °C.
-	t_{uc}	H	Creep rupture time of a notched test piece
-	T	°C	Specified temperature

continued

Table 1 — Symbols and designations (*concluded*)

Reference number ^{a)}	Symbol ^{b)}	Unit	Designation
-	T_i	°C	Indicated temperature
-	x	%	Specified percentage creep or plastic elongation
-	n	-	Creep exponent
^{a)} See Figures 1 and 2. ^{b)} The main subscripts (r , o and u) of the symbols are used as follows: r corresponds to reference; o corresponds to original; u corresponds to ultimate (after rupture). ^{c)} See note in 3.10.			

5 Principle

The test consists of heating a test piece to the specified temperature and of straining the test piece by means of a constant tensile force or constant tensile stress (see note) applied along its longitudinal axis for a period of time to obtain either:

- a specified creep elongation or to rupture the test piece (uninterrupted test); or
- values of permanent elongation at suitable intervals throughout the test or to rupture the test piece (interrupted test).

NOTE “Constant stress” means that the ratio of the force to the instantaneous cross-section remains constant throughout the test. The results obtained with constant stress are generally different from those with constant force.

6 Apparatus

6.1 Testing machine

The testing machine shall apply a force along the axis of the test piece while keeping inadvertent bending or torsion of the test piece to a minimum.

NOTE 1 The force should be applied to the test piece without shock.

NOTE 2 It is recommended that the machine be isolated from external vibration and shock. The machine should be equipped with a device which minimizes shock when the test piece ruptures.

The machine shall be verified and shall meet the requirements of at least Class 1 in EN ISO 7500-2.

6.2 Elongation measuring device

In uninterrupted tests, the elongation shall be measured using an extensometer, which meets the performance requirements of Class 1 or better of EN 10002-4, or by other means which ensure the same accuracy without interruption of the test.

The extensometer shall be calibrated at intervals not exceeding 3 years. If the predicted test time exceeds the date of the expiry of the calibration certificate then the extensometer shall be recalibrated prior to commencement of the creep test.