

Phosphate conversion coatings of metals — Method of specifying requirements

The European Standard EN 12476:2000 has the status of a
British Standard

ICS 25.220.20

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

BSI
Documents

AVA

Document Sharing Hub

National foreword

This British Standard is the official English language version of EN 12476:2000. It supersedes BS 3189:1991 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/38, Chemical conversion coatings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 15 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 October 2000

© BSI 10-2000

ISBN 0 580 34680 3

Amendments issued since publication

Amd. No.	Date	Comments

English version

Phosphate conversion coatings of metals - Method of specifying requirements

Couches de conversion phosphatées des métaux -
Méthode de spécifications des exigences

Phosphatierüberzüge auf Metallen - Verfahren für die
Festlegung von Anforderungen

This European Standard was approved by CEN on 1 March 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Information to be supplied by the purchaser	4
4 Coating types and designation	4
4.1 Coating types	4
4.2 Conversion coating designation	5
5 Sampling	6
6 Coating requirements	6
6.1 Appearance	6
6.2 Coating mass per unit area	6
6.3 Corrosion resistance	6
Annex A (informative) Guidance	7
Annex B (informative) Recommendations	9
Annex C (normative) After-treatments	12
Annex D (normative) Determination of corrosion resistance	13
Bibliography	15

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 262, Metallic and other inorganic coatings, the Secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2000, and conflicting national standards shall be withdrawn at the latest by October 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a method of specifying requirements for phosphate conversion coatings, intended primarily for application to ferrous metals, aluminium, zinc, cadmium and their alloys (see annex A).

2 Normative references

This European Standard incorporates by dated and undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 3892, *Conversion coatings on metallic materials — Determination of coating mass per unit area — Gravimetric methods (ISO 3892:1980)*.

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*.

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*.

3 Information to be supplied by the purchaser

The following information shall be supplied by the purchaser:

- a) the coating designation (see clause 4);
- b) any necessary heat treatment for parts that might be subject to failure from the effects of hydrogen induced during the preparation or phosphating processes (see notes 1 and 2);
- c) sampling methods, acceptance levels or any other inspection requirements, if different from those given in ISO 4519 (see clause 5);
- d) the surface preparation prior to phosphate conversion coating (see A.2);
- e) the surface appearance (see 6.1);
- f) corrosion resistance (see 6.3);
- g) the nature, condition and finish of the basis metal, if any of these could affect the serviceability and/or the appearance of the coating.

NOTE 1 Heat treatment procedures and classes are specified in ISO 9587 for stress relieving before processing and in ISO 9588 for embrittlement relief after processing, but other conditions may be specified by the purchaser provided that they can be shown to be effective.

NOTE 2 Heat treatment in accordance with the recommended conditions can never guarantee complete freedom from hydrogen embrittlement and tests should be specified whenever possible. Freedom from failure of test samples will enable a degree of confidence in the procedure to be demonstrated depending on the size of the sample tested.

4 Coating types and designation

4.1 Coating types

The conversion coating shall be described in accordance with Table 1.

NOTE Annex B provides guidance on coating type, purpose, end use and mass per unit area.