

BS EN 13252:2014+A1:2015



BSI Standards Publication

Geotextiles and geotextile-related products — Characteristics required for use in drainage systems

bsi.

...making excellence a habit.
AVA Documents™
Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN 13252:2014+A1:2015. It supersedes BS EN 13252:2014 which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to CEN text carry the number of the CEN amendment. For example, text altered by CEN amendment A1 is indicated by A1 A1.

The UK participation in its preparation was entrusted to Technical Committee B/553, Geotextiles and geomembranes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 86221 2

ICS 59.080.70

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

Amendments/corrigenda issued since publication

Date	Text affected
28 February 2015	Implementation of CEN amendment A1:2015

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13252:2014+A1

February 2015

ICS 59.080.70

Supersedes EN 13252:2014

English Version

Geotextiles and geotextile-related products - Characteristics required for use in drainage systems

Géotextiles et produits apparentés - Caractéristiques
requises pour l'utilisation dans les systèmes de drainage

Geotextilien und geotextilverwandte Produkte - Geforderte
Eigenschaften für die Anwendung in Dränanlagen

This European Standard was approved by CEN on 9 November 2013 and includes Amendment 1 approved by CEN on 13 December 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2015 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN 13252:2014+A1:2015 E

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms, definitions and abbreviations	7
3.1 Terms and definitions	7
3.2 Abbreviations	8
4 Required characteristics and corresponding methods of test	8
4.1 General.....	8
4.2 Selection of the appropriate standard in a specific application	9
4.3 Characteristics relevant to specific conditions of use (S-coded characteristics)	12
4.3.1 Tensile strength of seams and joints	12
4.3.2 Strength of structural junctions - geocomposites	12
4.3.3 Static puncture.....	12
4.3.4 Friction characteristics	12
4.3.5 Compression strength under load	12
4.3.6 Water flow capacity	12
4.4 Release of dangerous substances.....	12
5 Assessment and verification of constancy of performance (AVCP)	12
5.1 General.....	12
5.2 Presentation of characteristics	13
5.3 Product type determination (PTD)	13
5.4 Factory production control (FPC)	14
5.5 Verification of values	14
5.6 Initial inspection of factory and of FPC	14
5.7 Continuous surveillance of FPC	15
6 Marking	15
Annex A (normative) Factory production control	16
A.1 Factory production control scheme	16
A.1.1 General.....	16
A.1.2 Product design.....	16
A.1.3 Production	16
A.1.4 Finished products	16
A.1.5 Provisions applicable to A.1.2, A.1.3 and A.1.4 (to be used where appropriate)	17
A.2 Assessment of a factory production control (FPC) system	18
A.2.1 General.....	18
A.2.2 Checklist	18
A.2.3 Test frequency	21
Annex B (normative)  Durability aspects 	23
B.1 General.....	23

B.1.1	Service life	23
B.1.2	Initial and repeat testing of durability	23
B.1.3	Use of rework material	24
B.2	Weathering (all products)	24
B.3	Products used in non-reinforcing applications and with service lives up to 5 years	24
B.4	Other applications and service lives up to 25 years, 50 years and 100 years	25
B.4.1	General	25
B.4.2	Tests for specific materials	25
Annex C	(informative) Guidelines for the selection of the appropriate standard in a specific application	29
Annex D	(informative) Significant technical changes to the superseded standard	31
Annex ZA	(informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation	32
ZA.1	Scope and relevant characteristics	32
ZA.2	Procedure for AVCP of Geotextiles and geotextiles-related products for the use in the construction of roads and other trafficked areas	37
ZA.2.1	Systems of AVCP	37
ZA.2.2	Declaration of performance (DoP)	39
ZA.3	CE marking and labelling	42
Bibliography		45

Foreword

This document (EN 13252:2014+A1:2015) has been prepared by Technical Committee CEN/TC 189 “Geosynthetics”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2015, and conflicting national standards shall be withdrawn at the latest by November 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes  EN 13252:2014 .

This document includes Amendment 1 approved by CEN on 2014-12-13.

The start and finish of text introduced or altered by amendment is indicated in the text by tags  .

Annex D provides details of significant technical changes between this European Standard and the previous edition.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) Nr. 305/2011.

For relationship with Regulation (EU) Nr. 305/2011, see informative Annex ZA, which is an integral part of this document.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard allows manufacturers to describe geotextiles and geotextile-related products on the basis of declared values for characteristics relevant to the intended use and if tested to the specified method. It also includes procedures for the assessment and verification of constancy of performance and factory production control.

This European Standard may also be used by designers, end-users and other interested parties to define which functions and conditions of use are relevant.

The term “product” used in this European Standard refers to a geotextile or geotextile-related product.

This European Standard is part of a series of standards, addressing the requirements for geotextiles and geotextile-related products when used in a specific application. Annex C provides guidance on how to select the appropriate standard.

1 Scope

This European Standard specifies the relevant characteristics of geotextiles and geotextile-related products used in drainage systems and the appropriate test methods to determine these characteristics.

The intended use of these geotextiles or geotextile-related products is to fulfil one or more of the following functions: filtration, separation and drainage. The separation function is always used in conjunction with filtration or drainage. Accordingly, separation will never be specified alone.

This European Standard is not applicable to geosynthetic barriers, as defined in EN ISO 10318.

This European Standard provides for the assessment and verification of constancy of performance of the product to this European Standard and for factory production control procedures.

This European Standard defines requirements to be met by manufacturers and distributors with regard to the presentation of product properties.

NOTE Particular application cases may contain requirements regarding additional properties and – preferably standardised – test methods, if they are technically relevant.

This European Standard may be used to derive design values by taking into account factors within the context of the definitions given in EN 1997-1 (Eurocode 7), e.g. factors of safety. The design life of the product should be determined, since its function may be temporary, as a construction expediency, or permanent, for the lifetime of the structure.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12224, *Geotextiles and geotextile-related products — Determination of the resistance to weathering*

EN 12226, *Geosynthetics - General tests for evaluation following durability testing*

EN 12447, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to hydrolysis in water*

EN ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics (ISO 1043-1)*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)* ^{A1}

EN ISO 9862, *Geosynthetics — Sampling and preparation of test specimens (ISO 9862)*

EN ISO 10318, *Geosynthetics — Terms and definitions (ISO 10318)*

EN ISO 10319, *Geosynthetics — Wide-width tensile test (ISO 10319)*

EN ISO 10320, *Geotextiles and geotextile-related products — Identification on site (ISO 10320)*

EN ISO 10321, *Geosynthetics — Tensile test for joints/seams by wide-width strip method (ISO 10321)*

EN ISO 10722, *Geosynthetics — Index test procedure for the evaluation of mechanical damage under repeated loading — Damage caused by granular material (ISO 10722)*

EN ISO 11058, *Geotextiles and geotextile-related products — Determination of water permeability characteristics normal to the plane, without load (ISO 11058)*

EN ISO 12236, *Geosynthetics — Static puncture test (CBR test) (ISO 12236)*

EN ISO 12956, *Geotextiles and geotextile-related products — Determination of the characteristic opening size (ISO 12956)*

EN ISO 12957-1, *Geosynthetics — Determination of friction characteristics — Part 1: Direct shear test (ISO 12957-1)*

EN ISO 12957-2, *Geosynthetics — Determination of friction characteristics — Part 2: Inclined plane test (ISO 12957-2)*

EN ISO 12958, *Geotextiles and geotextile-related products — Determination of water flow capacity in their plane (ISO 12958)*

EN ISO 13426-1, *Geotextiles and geotextile-related products — Strength of internal structural junctions — Part 1: Geocells (ISO 13426-1)*

EN ISO 13426-2, *Geotextiles and geotextile-related products — Strength of internal structural junctions — Part 2: Geocomposites (ISO 13426-2)*

EN ISO 13433, *Geosynthetics — Dynamic perforation test (cone drop test) (ISO 13433)*

EN ISO 13438, *Geotextiles and geotextile-related products — Screening test method for determining the resistance to oxidation (ISO 13438)*

EN ISO 25619-1, *Geosynthetics — Determination of compression behaviour — Part 1: Compressive creep properties (ISO 25619-1)*

EN ISO 25619-2, *Geosynthetics — Determination of compression behaviour — Part 2: Determination of short-term compression behaviour (ISO 25619-2)*

ISO 10390:2005, *Soil quality — Determination of pH*

ASTM D7409 — 07e1, *Standard Test Method for Carboxyl End Group Content of Polyethylene Terephthalate (PET) Yarns*

ASTM D4603 — 03(2011)e1, *Standard Test Method for Determining Inherent Viscosity of Poly(Ethylene Terephthalate) (PET) by Glass Capillary Viscometer*

3 Terms, definitions and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions of EN ISO 10318 and the following apply:

3.1.1

product

geotextile or geotextile-related product

3.1.2

specification

any document in which the work, functions and specific conditions of use of the product are described

3.1.3

drainage system

any system used in geotechnical or civil engineering applications, which includes a geotextile or geotextile-related product in contact at least on one side with soil and/or another material and/or a geosynthetic, for the intake and transportation of a fluid

3.1.4

rework material (RWM)

material that is generated in a process and capable of being reclaimed within the same process that generated it

3.1.5

post-consumer material (PCM)

material generated by households or by commercial, industrial and institutional facilities in their role as end-users of the product which can no longer be used for its intended purpose. This includes returns of material from the distribution chain

3.1.6

post-industrial material (PIM)

material diverted from the waste stream during a manufacturing process

3.2 Abbreviations

For the purposes of this document, the abbreviations given in EN ISO 1043-1 and EN ISO 10318 and the following apply.

- AR: aramid
- GCO-D: geocomposite drainage

4 Required characteristics and corresponding methods of test

4.1 General

The main functions of geotextiles and geotextile-related products used in drainage systems are filtration, separation and drainage. If an erosion control system is integrated in the construction, the requirements of the appropriate standard shall also be fulfilled. As the separation function is always used in conjunction with another function, the separation function shall never be specified alone.

The specification shall define which functions and conditions of use are relevant (see Table 1). The producer of the product shall provide the necessary data based on the requirements and test methods described in this European Standard.

The characteristics, their relevance to the conditions of use, and the test methods to be used, are given in Table 1. The list of characteristics in Table 1 includes those needed for regulatory purposes (H), those relevant to all conditions of use (A), and those relevant to specific conditions of use (S). The indication “—” means that the characteristic is not relevant for that function.

Where, for the same property, data for more than one function shall be provided, the following ranking order shall be observed: H overrules A, A overrules S, and S overrules “—”.

The functions and conditions of use, corresponding with the characteristics, marked with “S” in Table 1, are specified in 4.3.

When static puncture resistance, dynamic perforation resistance, characteristic opening size and/or permeability normal to the plane are required for composite products, these requirements shall only apply to the filter layers and each filter layer shall be tested separately if they are different.

The producer of the geotextile or geotextile-related product shall provide the data based on the results of tests specified in this European Standard, as described in 5.1.

NOTE If filtration properties cannot be measured on a geocomposite, the filtration-related performance of the product is expressed as the performance of the single layer for the following characteristics:

- dynamic perforation;
- opening size;
- water permeability.

Durability shall be assessed in accordance with the requirements of Annex B.

4.2 Selection of the appropriate standard in a specific application

Guidelines for the selection of the appropriate standard in a specific application are given in Annex C.

Table 1 — Geotextiles and geotextile-related products used in the construction of drainage systems— Functions, function-related characteristics and test methods to be used

Characteristic	Test method	Functions		
		Filtration	Separation	Drainage
(1) Tensile strength ^{b)}	EN ISO 10319	H	H	H
(2) Elongation at maximum load	EN ISO 10319	H	H	H
(3) Compression strength under load	EN ISO 25619-2	—	—	S
(4) Tensile strength of seams and joints ^{c) d)}	EN ISO 10321	S	S	S
(5) Tensile strength of internal junction (of GCO)	EN ISO 13426-2	—	—	S
(6) Static puncture resistance (CBR test) ^{a) b)}	EN ISO 12236	S	H	--
(7) Dynamic perforation resistance (cone drop test) ^{a)}	EN ISO 13433	H	A	--
(8) Friction characteristics	EN ISO 12957-1; EN ISO 12957-2	S	S	S
(9) Compressive creep characteristics	EN ISO 25619-1	—	—	A
(10) Damage during installation resistance	EN ISO 10722	A	A	A
(11) Characteristic opening size	EN ISO 12956	H	H	--
(12) Water permeability normal to the plane	EN ISO 11058	H	H	--
(13) Water flow capacity in the plane (soft/soft)	EN ISO 12958	--	--	H
(14) Water flow capacity in the plane (soft/rigid or rigid/rigid)	EN ISO 12958	—	—	S
(15) Durability characteristics	According to Annex B	H	H	H

Relevance:

H: required for regulatory purposes

A: relevant to all conditions of use

S: relevant to specific conditions of use

“_”: indicates that the characteristic is not relevant for that function.

^a Static or dynamic puncture resistance may not be relevant for some types of products, e.g. GCO-D.

^b If the mechanical properties (tensile strength and static puncture) are coded “H” in this Table, the producer shall provide data for both. The use of only one, either tensile strength or static puncture resistance, is sufficient in a tender specification.

^c The strength of internal structural junctions of geocells shall be tested in accordance with EN ISO 13426-1.

^d The strength of internal structural junctions of geocomposites shall be tested in accordance with EN ISO 13426-2.

4.3 Characteristics relevant to specific conditions of use (S-coded characteristics)

4.3.1 Tensile strength of seams and joints

Data on tensile strength of seams and joints are necessary for all functions if the product is to be mechanically jointed and if load is transferred across the seams and joints.

4.3.2 Strength of structural junctions - geocomposites

Data on junction strength are necessary when geocomposites are subjected to shear loads.

4.3.3 Static puncture

Data on static puncture or - as an alternative - on tensile strength, are necessary for the filtration function if required by the specification, i.e. when the site loading conditions are such that there is a potential risk of static puncture of the filter layer.

4.3.4 Friction characteristics

Data on friction characteristics are necessary for the functions separation and filtration when the product is used in a situation where a differential movement can take place between the product and adjacent material that may endanger the stability of the works. The friction characteristics can be measured, using site specific materials, by a direct shear test according to EN ISO 12957-1 or, in the case of loads up to 5 kPa, by an inclined plane test according to EN ISO 12957-2.

Friction behaviour with the adjacent construction materials, e.g. the soil or the polymeric geosynthetic barrier, should also be considered.

4.3.5 Compression strength under load

Data on compression strength under load are necessary when required by the tender specification.

4.3.6 Water flow capacity

Data on water flow capacity with bedding rigid/soft (or rigid/rigid) are necessary when required by the tender specification.

4.4 Release of dangerous substances

National regulations on dangerous substances may require verification and declaration on release, and sometimes content, when construction products covered by this European Standard are placed on those markets.

In the absence of European harmonized test methods, verification and declaration on release/content should be done taking into account national provisions in the place of use.

NOTE An informative database covering European and national provisions on dangerous substances is available at the Construction website on EUROPA accessed through: <http://ec.europa.eu/enterprise/construction/cpd-ds/>.

5 Assessment and verification of constancy of performance (AVCP)

5.1 General

The compliance of geotextiles and geotextile-related products with the requirements of this European Standard and with the declared values shall be demonstrated by:

- Product type determination (PTD)
- Factory production control (FPC) by the manufacturer, including product assessment

The manufacturer shall always retain the overall control and shall have the necessary means to take responsibility for the product.

5.2 Presentation of characteristics

The characteristics specified in Table 2, except for durability, shall be expressed as mean values and tolerance value(s) corresponding to the 95 % confidence level. The values expressed may be verified using the procedure referred to in 5.5.

NOTE The 95 % confidence level corresponds to the mean value minus (and/or plus) 1,0 tolerance value(s).

Information on durability shall be expressed in accordance with Annex B.

5.3 Product type determination (PTD)

PTD tests shall be carried out by the manufacturer to define the values of the properties to be declared for the product to satisfy the requirements of this European Standard.

PTD tests shall also be carried out on existing products when a change in the basic materials or manufacturing procedures affects the declared properties or the use of a product. In these cases, the PTD tests are those for the properties which are affected or shall be confirmed and new properties introduced by a change of use.

The tests to be conducted shall be reference tests as specified in this European Standard and shall be selected from the characteristics specified in Table 2, consistent with the product's intended use:

Table 2 — Characteristics required for PTD and AVCP

Characteristic	Functions
Tensile strength	Filtration, separation, drainage
Elongation at maximum load	Filtration, separation, drainage
Static puncture resistance (CBR test)	Separation
Dynamic perforation resistance (cone drop test)	Filtration
Characteristic opening size	Filtration, separation
Water permeability normal to the plane	Filtration, separation
Water flow capacity in the plane	Drainage
Durability ^a	Filtration, separation, drainage
^a For the durability aspects, see Table 1 and Annex B.	

The results of PTD tests shall be recorded and be available for inspection.

The sample for the PTD tests shall be drawn according to EN ISO 9862 from a normal production run using the same materials and forming processes as used for the full production process. The size of the sample shall be big enough to allow the determination of the characteristics specified in Table 2. Handmade samples, short trial batches and other development prototypes may be tested by the same methods, but shall not be used for establishing characteristic values in PTD tests.