

BS EN 14227-5:2013



BSI Standards Publication

Hydraulically bound mixtures — Specifications

Part 5: Hydraulic road binder bound
granular mixtures

bsi.

...making excellence a habit.
AVA Documents™
Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN 14227-5:2013. It supersedes BS EN 14227-5:2004 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/510/4, Cementitious bound materials, unbound granular materials, waste materials and marginal materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 74216 3

ICS 93.080.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2013.

Amendments issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14227-5

May 2013

ICS 93.080.20

Supersedes EN 14227-5:2004

English Version

**Hydraulically bound mixtures - Specifications - Part 5: Hydraulic
road binder bound granular mixtures**

Mélanges traités aux liants hydrauliques - Spécifications -
Partie 5: Mélanges granulaires traités aux liants
hydrauliques routiers

Hydraulisch gebundene Gemische - Anforderungen - Teil 5:
Tragschichtbindergebundene Gemische

This European Standard was approved by CEN on 1 March 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2013 CEN All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members.

Ref. No. EN 14227-5:2013: E

Contents

Page

Foreword.....	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Symbols and abbreviated terms	7
5 Constituents	8
5.1 Aggregates	8
5.2 Hydraulic road binder.....	8
5.3 Water	8
5.4 Retarders	8
6 Hydraulic road binder bound granular mixture	8
6.1 Types.....	8
6.1.1 Hydraulic road binder bound granular mixture 1	8
6.1.2 Hydraulic road binder bound granular mixture 2	8
6.1.3 Hydraulic road binder bound granular mixture 3	9
6.1.4 Hydraulic road binder bound granular mixture 4	9
6.2 Water content of mixtures	9
6.3 Proportioning of the constituents, grading and dry density	9
6.4 Other requirements for the fresh mixture	10
6.4.1 Compacity.....	10
6.4.2 Immediate bearing index of the mixture.....	10
6.4.3 Workability period.....	10
7 Laboratory mechanical performance classification.....	10
7.1 General.....	10
7.2 Classification by compressive strength.....	11
7.3 Classification by R_t , E	12
7.3.1 General.....	12
7.3.2 Method by direct tensile testing.....	12
7.3.3 Method by indirect tensile testing.....	12
7.3.4 Method by indirect tensile and compression testing.....	12
8 Other requirements for the mixture	13
8.1 Strength after immersion in water	13
8.2 Other characteristics	13
9 Production control	13
10 Designation and description	13
10.1 Designation	13
10.2 Description	14
11 Marking and labelling	14
12 Figures	15
Annex A (normative) Compacity of a hydraulic road binder bound granular mixture 2	20
Annex B (informative) Production control for hydraulic road binder bound granular mixtures	21
B.1 General.....	21
B.2 Quality manual	21
B.3 Organisation.....	21
B.3.1 Responsibility and authority	21
B.3.2 Management representative	21

B.3.3	Internal audits	21
B.3.4	Management review	22
B.3.5	Sub-contract services	22
B.3.6	Records	22
B.3.7	Training.....	22
B.4	Control procedures	22
B.4.1	Production management	22
B.4.2	Composition of the mixture.....	23
B.4.3	Constituents.....	23
B.4.4	Process control	23
B.4.5	Inspection, calibration and control of process equipment.....	23
B.4.6	Handling and delivery	24
B.5	Inspection and testing of constituents and mixtures during production.....	24
B.5.1	General	24
B.5.2	Characteristics that require control during production	24
B.5.3	Frequency of sampling the mixture.....	24
B.6	Inspection and testing equipment	25
B.6.1	General	25
B.6.2	Measuring and testing equipment	25
B.6.3	Measuring and testing equipment in the process	25
B.6.4	Measuring and testing equipment in laboratory	25
B.7	Non-conformity.....	26
B.7.1	General	26
B.7.2	Non-conformity of constituents	26
B.7.3	Non-conformity of the mixture.....	26
	Bibliography.....	27

Foreword

This document (EN 14227-5:2013) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2013, and conflicting national standards shall be withdrawn at the latest by November 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14227-5:2004.

Compared with EN 14227-5:2004, the following changes have been made:

- Changing of the title;
- Revision of Clause 1 "Scope";
- Revision of Clause 2 "Terms and definitions";
- Revision of Clause 4 "Symbols and abbreviated terms";
- Revision of Clause 5 "Constituents";
- Revision of Clause 6 "Cement bound granular mixture";
- Revision of Clause 7 "Laboratory mechanical performance classification";
- Inclusion of Clause 8 "Other requirements for the mixtures";
- Revision of Clause 10 "Designation and description";
- Inclusion of Annex A (normative) "Compacity of a cement bound granular mixture 2".

This standard is one of a series of parts for EN 14227, *Hydraulically bound mixtures — Specifications*:

- *Part 1: Cement bound granular mixtures*
- *Part 2: Slag bound granular mixtures*
- *Part 3: Fly ash bound granular mixtures*
- *Part 4: Fly ash for hydraulically bound mixtures*
- *Part 5: Hydraulic road binder bound granular mixtures*
- *Part 10: Soil treated by cement*
- *Part 11: Soil treated by lime*
- *Part 12: Soil treated by slag*

— *Part 13: Soil treated by hydraulic road binder*

— *Part 14: Soil treated by fly ash*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies hydraulic road binder bound granular mixtures for road construction, airfields and other trafficked areas and specifies the requirements for their constituents, composition and laboratory performance classification.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 1097-6:2000, *Tests for mechanical and physical properties of aggregates — Part 6: Determination of particle density and water absorption*

EN 1097-7, *Tests for mechanical and physical properties of aggregates — Part 7: Determination of the particle density of filler — Pyknometer method*

EN 13242, *Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction*

EN 13282-1, *Hydraulic road binders — Part 1: Rapid hardening hydraulic road binders — Composition, specifications and conformity criteria*

EN 13286-1, *Unbound and hydraulically bound mixtures — Part 1: Test methods for laboratory reference density and water content — Introduction, general requirements and sampling*

EN 13286-2, *Unbound and hydraulically bound mixtures — Part 2: Test methods for laboratory reference density and water content — Proctor compaction*

EN 13286-3, *Unbound and hydraulically bound mixtures — Part 3: Test methods for laboratory reference density and water content — Vibrocompression with controlled parameters*

EN 13286-4, *Unbound and hydraulically bound mixtures — Part 4: Test methods for laboratory reference density and water content — Vibrating hammer*

EN 13286-5, *Unbound and hydraulically bound mixtures — Part 5: Test methods for laboratory reference density and water content — Vibrating table*

EN 13286-40, *Unbound and hydraulically bound mixtures — Part 40: Test method for the determination of the direct tensile strength of hydraulically bound mixtures*

EN 13286-41, *Unbound and hydraulically bound mixtures — Part 41: Test method for the determination of the compressive strength of hydraulically bound mixtures*

EN 13286-42, *Unbound and hydraulically bound mixtures — Part 42: Test method for the determination of the indirect tensile strength of hydraulically bound mixtures*

EN 13286-43, *Unbound and hydraulically bound mixtures — Part 43: Test method for the determination of the modulus of elasticity of hydraulically bound mixtures*

EN 13286-45, *Unbound and hydraulically bound mixtures — Part 45: Test method for the determination of the workability period of hydraulically bound mixtures*

EN 13286-47, *Unbound and hydraulically bound mixtures — Part 47: Test method for the determination of California bearing ratio, immediate bearing index and linear swelling*

EN 13286-50, *Unbound and hydraulically bound mixtures — Part 50: Method for the manufacture of test specimens of hydraulically bound mixtures using Proctor equipment or vibrating table compaction*

EN 13286-51, *Unbound and hydraulically bound mixtures — Part 51: Method for the manufacture of test specimens of hydraulically bound mixtures using vibrating hammer compaction*

EN 13286-52, *Unbound and hydraulically bound mixtures — Part 52: Method for the manufacture of test specimens of hydraulically bound mixtures using vibrocompression*

EN 13286-53, *Unbound and hydraulically bound mixtures — Part 53: Methods for the manufacture of test specimens of hydraulically bound mixtures using axial compression*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

hydraulically bound mixture

mixture which sets and hardens by hydraulic reaction

3.2

hydraulic road binder bound granular mixture

granular hydraulically bound mixture where hydraulic road binder is the binder

3.3

slenderness ratio

height to diameter ratio of the specimen

3.4

compacity

ratio of the absolute volume of the solid to the apparent volume of the mixture (see Annex A)

4 Symbols and abbreviated terms

For the purpose of this document, the following symbols and abbreviated terms apply.

R_c is the compressive strength, expressed in megapascals (MPa);

R_i is the compressive strength after immersion, expressed in megapascals (MPa);

R_t is the direct tensile strength, expressed in megapascals (MPa);

R_{it} is the indirect tensile strength, expressed in megapascals (MPa);

E is the modulus of elasticity, expressed in megapascals (MPa);

E_c is the E determined by compression, expressed in megapascals (MPa);

E_t is the E determined in direct tension, expressed in megapascals (MPa);

E_{it} is the E determined in indirect tension, expressed in megapascals (MPa).

5 Constituents

5.1 Aggregates

Aggregates shall be selected from EN 13242.

The properties and the appropriate categories of the aggregates shall be specified depending on the position of the hydraulic road binder bound granular mixture in the pavement structure and the traffic to be carried.

Aggregates shall be volumetrically stable. When this is not the case, the use of the mixture shall be permitted provided there is a satisfactory performance record or a thorough laboratory evaluation of the mixture has been carried out in accordance with provisions valid at the place of use.

5.2 Hydraulic road binder

Hydraulic road binder shall comply with EN 13282-1 or with a European Technical Approval.

5.3 Water

Water shall not contain components which adversely affect the hardening and performance of the hydraulic road binder bound granular mixtures.

5.4 Retarders

Retarders shall comply with provisions valid in the place of use.

NOTE Generally, retarders are not necessary.

6 Hydraulic road binder bound granular mixture

6.1 Types

Hydraulic road binder bound granular mixture shall be made from the constituents specified in Clause 5.

The mixture shall be selected from the 4 types described in 6.1.1 to 6.1.4 and shall conform to the specified requirements for the selected mixture.

6.1.1 Hydraulic road binder bound granular mixture 1

Hydraulic road binder bound granular mixture 1 shall be a 0/31,5 mm mixture with a grading, determined in accordance with EN 933-1, complying with the requirements in Figure 1.

6.1.2 Hydraulic road binder bound granular mixture 2

6.1.2.1 Description

Hydraulic road binder bound granular mixture 2 shall be a granular mixture with compacity requirement. There are 3 sub-types depending on the aggregate size.

6.1.2.2 Grading of the mixture

The grading of the selected sub-type, determined in accordance with EN 933-1, shall comply with Table 1. According to the use of the mixture, either category G1 or category G2 of the grading envelopes in Figures 2 to 4 shall be specified.