

Vitreous and porcelain enamels — Determination of resistance to chemical corrosion —

Part 3: Determination of resistance to chemical corrosion by alkaline liquids using a hexagonal vessel

The European Standard EN 14483-3:2004 has the status of a
British Standard

ICS 25.220.50

National foreword

This British Standard is the official English language version of EN 14483-3:2004. It supersedes BS 1344-5:1984 and BS EN ISO 4535:2000 which are withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/36, Vitreous enamel coatings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 7 December 2004

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 15 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 7 December 2004

ISBN 0 580 44979 3

English version

Vitreous and porcelain enamels - Determination of resistance to
chemical corrosion - Part 3: Determination of resistance to
chemical corrosion by alkaline liquids using a hexagonal vessel

Emaux vitrifiés - Détermination de la résistance à la
corrosion chimique - Partie 3: Détermination de la
résistance à la corrosion chimique par des liquides alcalins
dans un récipient hexagonal

Emails und Emailierungen - Bestimmung der Beständigkeit
gegen chemische Korrosion - Teil 3: Bestimmung der
Beständigkeit gegen chemische Korrosion durch alkalische
Flüssigkeiten unter Verwendung eines Gerätes mit
hexagonalem Gefäß

This European Standard was approved by CEN on 1 April 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword.....	3
Introduction	4
1 Scope	6
2 Normative references	6
3 Principle	6
4 Reagents	6
5 Apparatus and materials	7
5.1 Test apparatus	7
5.1.1 General description	7
5.2 Hot air oven, capable of being maintained at $(120 \pm 5) ^\circ\text{C}$	12
5.3 Desiccator, for example with an internal diameter of 200 mm.....	12
5.4 Balance, accurate to 0,2 mg.	12
5.5 Cotton wool	12
6 Test specimens	12
7 Procedure	12
8 Expression of results	12
9 Standard detergent solution test	13
9.1 General.....	13
9.2 Test solution.....	13
9.3 Test temperature.....	13
9.4 Duration of the test.....	13
9.5 Test report	14
10 Other test solutions and/or conditions	14
10.1 General.....	14
10.2 Test solution.....	14
10.3 Test temperature.....	14
10.4 Duration of the test.....	14
10.5 Test report	15

Foreword

This document (EN 14483-3:2004) has been prepared by Technical Committee CEN/TC 262 “Metallic and other inorganic coatings”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2004, and conflicting national standards shall be withdrawn at the latest by December 2004.

This European Standard is divided into the following five parts, in accordance with the different apparatus and the different physical test conditions (temperature, pressure, stirring) that are used:

EN 14483 *Vitreous and porcelain enamels — Determination of resistance to chemical corrosion*

Part 1: *Determination of resistance to chemical corrosion by acids at room temperature*

Part 2: *Determination of resistance to chemical corrosion by boiling acids, neutral liquids and/or their vapours*

Part 3: *Determination of resistance to chemical corrosion by alkaline liquids using a hexagonal vessel*

Part 4: *Determination of resistance to chemical corrosion by alkaline liquids using a cylindrical vessel*

Part 5: *Determination of resistance to chemical corrosion in closed systems*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Corrosion of vitreous and porcelain enamel by aqueous solutions is a dissolution process. The main component of the vitreous and porcelain enamel, SiO_2 , forms a three-dimensional silica network. After hydrolysis it decomposes and forms silicic acid or silicates, respectively. These are released into the attacking medium. Other components, mainly metal oxides, are hydrolyzed as well and form the corresponding hydrated metal ions or hydroxides, respectively. All corrosion products are more or less soluble in the attacking medium. The whole process results in a loss in mass per unit area.

For some aqueous solutions, the attack of the vitreous and porcelain enamel proceeds linearly during the corrosion time, for other aqueous solutions, the attack of the vitreous and porcelain enamel proceeds in a logarithmic manner during the corrosion time. Only for the first series of solutions, a scientific exact rate of loss in mass per unit area ($\text{g/m}^2\cdot\text{h}$) can be calculated as well as a corrosion rate (mm/a).

The most important parameters influencing aqueous corrosion of vitreous and porcelain enamel are vitreous and porcelain enamel quality, temperature and pH-value. Besides, inhibition effects resulting from limited solubility of silica can contribute. The following list describes different types of enamel attack for different corrosion conditions.

- a) In aqueous alkali solutions like 0,1 mol/l NaOH (see clause 9 of EN 14483-4:2004) the silica network of the vitreous and porcelain enamel is considerably attacked at 80 °C. Silicates and most of the other hydrolyzed components are soluble in the alkali. Attack proceeds linearly during regular testing times. Therefore test results are expressed in terms of a rate of loss in mass per unit area (weight loss per unit area and time) and a corrosion rate (millimetres per year).
- b) At room temperature, in weak aqueous acids like citric acid (see clause 9 of EN 14483-1:2004) or also in stronger acids like sulfuric acid (see clause 10 of EN 14483-1:2004), there is only minor attack on the silica network of the vitreous and porcelain enamel. Other constituents are leached to some extent from the surface. High resistant vitreous and porcelain enamels will show no visual change after exposure. On less resistant vitreous and porcelain enamels some staining or surface roughening will occur.
- c) In boiling aqueous acids (see EN 14483-2) the silica network of the vitreous and porcelain enamel is being attacked, and silica as well as the other vitreous and porcelain enamel components are released into solution. However, solubility of silica in acids is low. Soon the attacking solutions will become saturated with dissolved silica and will then only leach the surface. The acid attack is inhibited, corrosion markedly drops.

NOTE The test equipment made of glass also releases silica by acid attack and contributes to the inhibition.

Inhibition is effectively prevented in vapour phase tests. The condensate formed on the test specimen is free of any dissolved vitreous and porcelain enamel constituents.

Examples for enamel corrosion proceeding in a logarithmic manner c.1) and linearly c.2) are:

- **c.1) Boiling citric acid (see clause 10 of EN 14483-2:2004) and boiling 30 % sulfuric acid (see clause 11 of EN 14483-2:2004):**

Since only minute amounts of these acids are found in their vapours the test is restricted to the liquid phase. The attack is influenced by inhibition effects and corrosion depends on time of exposure. Therefore test results are expressed in terms of loss in mass per unit area, no rate of loss in mass per unit area is calculated.

- **c.2) Boiling 20 % hydrochloric acid (see clause 12 of EN 14483-2:2004):**

Since this is an azeotropic boiling acid, acid concentration in liquid and vapour phase are identical and liquid phase testing need not be performed. Vigorous boiling supplies an uninhibited condensate and the attack proceeds linearly with time of exposure. Therefore test results are only expressed in terms of rate