BS EN 14771:2023

BSI Standards Publication

Bitumen and bituminous binders — Determination of the flexural creep stiffness — Bending Beam Rheometer (BBR)

Documents
Document Sharing Hub

Full document details: BS EN 14771:2023

National foreword

This British Standard is the UK implementation of EN 14771:2023. It supersedes BS EN 14771:2012, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/13, Petroleum Testing and Terminology.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2023
Published by BSI Standards Limited 2023

ISBN 978 0 539 18397 9

ICS 75.140; 91.100.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2023.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS EN 14771:2023

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN 14771

July 2023

ICS 75.140; 91.100.50

Supersedes EN 14771:2012

English Version

Bitumen and bituminous binders - Determination of the flexural creep stiffness - Bending Beam Rheometer (BBR)

Bitumes et liants bitumineux - Détermination du module de rigidité en flexion - Rhéomètre à flexion de barreau (BBR)

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Biegekriechsteifigkeit - Biegebalkenrheometer (BBR)

This European Standard was approved by CEN on 28 May 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2023 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 14771:2023 E

Documents
Document Sharing Hub

Full document details: BS EN 14771:2023

Contents

Page

European foreword 3
1 Scope 5
2 Normative references 5
3 Terms and definitions 5
4 Principle 6
5 Apparatus 6
6 Preparation of test samples 7
6.1 General 7
6.2 Preparation of moulds 7
6.3 Preparation of test specimen 8
7 Procedure 8
7.1 Measurement 8
7.2 Deflection in a valid determination 9
8 Calculation 9
8.1 General 9
8.2 Measured stiffness 10
8.3 Calculated stiffness 10
8.4 m-value 10
8.5 Validity of the results 11
9 Expression of results 11
10 Precision 11
10.1 Repeatability, *r* 11
10.2 Reproducibility, *R* 11
11 Test report 11
Annex A (informative) Calculation of *T* (m = 0,300), *T* (S = 300 MPa) and respective m-value at *T* (S = 300 MPa) 15
Annex B (informative) Calculation of ΔT_c 18
Bibliography 19

Documents
Document Sharing Hub
Full document details: BS EN 14771:2023

European foreword

This document (EN 14771:2023) has been prepared by Technical Committee CEN/TC 336 “Bituminous binders”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2024, and conflicting national standards shall be withdrawn at the latest by January 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14771:2012.

In comparison with the previous edition, the main technical changes are:

a) Scope aligned with other test standards;

b) reference to EN 14023 moved from normative references to bibliography;

c) Notes in 3.3 and 3.4 updated with reference to SI unit;

d) wording of test specimen and sample applied consistently;

e) 5.1.1.1 reworded to provide more clarity;

f) 5.1.3 Note updated;

g) former 5.2.1, now 5.3, reworded to provide more clarity;

h) numbering in Clause 5 aligned with CEN-CENELEC Internal regulations: former 5.2.1, now 5.3;

i) 6.1 Sample preparation aligned with EN 12594 and reference to scope added in note;

j) 6.2: reference to plastic films added in Note 2;

k) 6.2: Note 3 turned into standard text and moved before notes;

l) 6.3 clarified with regards to pouring, and inconsistencies in the description of storage removed; Note 1 deleted as in conflict with standard text;

m) text on heated moulds moved from 6.3 to 6.2;

n) description reworded to provide more clarity; timing of trimming adjusted;

o) information to discard damaged or distorted test specimen added in 6.3, in c) wording aligned with 5.1.1.1;

p) information added in 7.1 to place test specimen 5 minutes apart into testing bath, wording aligned;

q) description of flexural creep stiffness worded more precisely in keys to formulae in 8.2 and 8.3;

r) writing of decimal logarithm aligned with ISO 80000-2:2019 [6] in 8.3, 8.4 and Annex A;

AVA Documents
Document Sharing Hub

Full document details: BS EN 14771:2023

t) Keys in Figures 1 to 4 updated and formatted;

u) Figure 5: load in legend and in figure renamed as P, also consistent with Formula (1);

v) Annex A added;

w) Annex B added;

x) Bibliography updated with EN 1427.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom

Documents
Document Sharing Hub

Full document details: BS EN 14771:2023

1 Scope

This document specifies a method for the determination of the flexural creep stiffness of bitumen and bituminous binders in the range of 30 MPa to 1 GPa by means of the bending beam rheometer.

The method can be applied to a variety of bitumens, including unmodified as well as modified binders, as fresh (unused) binders, as well as binders after laboratory ageing conditioning (e.g. EN 12607-1, EN 14769), and also binders that have been recovered from asphalt mixtures.

WARNING — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1
flexural creep stiffness
S(t)
ratio obtained by dividing the bending stress by the bending strain, given in MPa

Note 1 to entry: The strain will increase with the loading time and therefore the flexural creep stiffness will also be a function of time.

3.2
m-value
absolute value of the slope of the curve of the logarithm of the stiffness versus the logarithm of time

3.3
contact load
P_c
load required to maintain positive contact between the test specimen, supports and the loading shaft

Note 1 to entry: The SI unit for the load is N, however for practical reasons loads are given in mN for this test. The contact load of 25 mN to 45 mN is used in this method.

Documents
Document Sharing Hub
Full document details: BS EN 14771:2023