BS EN 17534:2022

BSI Standards Publication

Textiles — Physiological effects — Measurement of liquid sweat transport and buffering

Documents
Document Sharing Hub

Full document details: BS EN 17534:2022

National foreword

This British Standard is the UK implementation of EN 17534:2022.

The UK participation in its preparation was entrusted to Technical Committee TCI/100, Co-ordination of activities in textiles and clothing.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 539 06723 1

ICS 59.080.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2022.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS EN 17534:2022

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN 17534

November 2022

ICS 59.080.30

English Version

Textiles - Physiological effects - Measurement of liquid sweat transport and buffering

Textiles - Effets physiologiques - Mesurage du transfert de sueur liquide et de l'effet tampon vis-à-vis de la sueur liquide

Textilien - Physiologische Wirkungen - Messung des flüssigen Schweißtransports und der flüssigen Schweißpufferung

This European Standard was approved by CEN on 26 September 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2022 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 17534:2022 E

Documents
Document Sharing Hub

Full document details: BS EN 17534:2022

Contents

Page

European foreword 3
Introduction 4
1 Scope 5
2 Normative references 5
3 Terms and definitions 5
4 Reagents 6
5 Test accessories 6
5.1 Thin foil 6
5.2 Polyester woven fabric 6
5.3 Frame (for method B) 6
5.4 Specimen carrier 6
6 Measurement and test methods 7
6.1 General 7
6.2 Method A 8
6.2.1 Principle 8
6.2.2 Test specimens 9
6.2.3 Test procedure 9
6.2.4 Evaluation of test results 10
6.2.5 Physiological assessment of the textile material 11
6.2.6 Calibration of test apparatus 11
6.2.7 Precision of results 11
6.2.8 Test report 12
6.3 Method B (Modification of Method A) 12
6.3.1 Principle of test 12
6.3.2 Test procedure 13
6.3.3 Evaluation of test results 13
Annex A (informative) Specimen carrier 14
Bibliography 19

Documents
Document Sharing Hub
Full document details: BS EN 17534:2022

European foreword

This document (EN 17534:2022) has been prepared by Technical Committee CEN/TC 248 “Textiles and textile products”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2023, and conflicting national standards shall be withdrawn at the latest by May 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

AVA Documents
Document Sharing Hub

Full document details: BS EN 17534:2022

Introduction

For the assessment of the physiological properties of textiles worn next to the skin, not only their thermophysiological properties in stationary conditions (thermal and water vapour resistance) are important, which can be measured according to EN ISO 11092 with the sweating guarded-hotplate (Skin Model), but also their capacity to buffer in stationary sweat pulses and to transport liquid sweat, occurring in the practical use of textiles and clothing.

With liquid sweat appearing on the wearer's skin, the textiles take it up and transport it into the next textile layers or into the environmental air. This so-called buffering capacity and transport of liquid water (sweat) of a textile is measured quantitatively with the sweating guarded-hotplate, slightly modified from the design and procedures described in the above standard. A textile is judged to perform better, the more efficient the transport of sweat from the skin is, and the less liquid sweat remains on the skin.

Documents
Document Sharing Hub

Full document details: BS EN 17534:2022

1 Scope

This document specifies a test method for measuring liquid sweat management properties of knitted, woven and nonwoven textile fabrics, namely buffering index, sweat transport and sweat uptake.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

EN ISO 11092, *Textiles — Physiological effects — Measurement of thermal and water-vapour resistance under steady-state conditions (sweating guarded-hotplate test) (ISO 11092)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at https://www.electropedia.org/

— ISO Online browsing platform: available at https://www.iso.org/obp

3.1
uptake
buffering
effect measured by the quantity of liquid water remaining in the textile material in grams during and after a period of time in contact with water

3.2
sweat transport
F
amount of liquid water (sweat) in grams taken up by 1 m² of the textile material and within 1 h transported into ambient air with specific temperature and relative humidity

3.3
liquid sweat management
combining of the uptake or buffering of the sweat from the skin, on one hand, and of the transport of the sweat from the skin to the ambience, on the other hand

3.4
moisture permeability
F_1
effect measured by the amount of liquid water in grams taken up by 1 m² of the textile material and within 1 h transported into ambient air with a water vapour pressure gradient of 1 hPa between the two sides of the textile material

3.5
sweat uptake
G_2
effect measured by the portion of liquid water remaining in the textile material in grams after 15 min of contact with water

Documents
Document Sharing Hub
Full document details: BS EN 17534:2022