

Electrical insulating materials — Thermal endurance properties —

Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method

The European Standard EN 60216-6:2004 has the status of a British Standard

ICS 17.220.99; 29.035.01

National foreword

This British Standard is the official English language version of EN 60216-6:2004. It is identical with IEC 60216-6:2003.

The UK participation in its preparation was entrusted by Technical Committee GEL/15, Insulating material, to Subcommittee GEL/15/5, Methods of test, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 42, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 20 October 2004

© BSI 20 October 2004

ISBN 0 580 44613 1

**Electrical insulating materials -
Thermal endurance properties
Part 6: Determination of thermal endurance indices (TI and RTE)
of an insulating material using the fixed time frame method
(IEC 60216-6:2003)**

Matériaux isolants électriques -
Propriétés d'endurance thermique
Partie 6: Détermination des indices
d'endurance thermique (TI et RTE)
d'un matériau isolant en utilisant
la méthode de trame de durées fixes
(CEI 60216-6:2003)

Elektroisolierstoffe -
Eigenschaften hinsichtlich
des thermischen Langzeitverhaltens
Teil 6: Bestimmung der thermischen
Langzeitkennwerte (TI und RTE)
eines Isolierstoffes unter Anwendung
des Festzeitrahmenverfahrens
(IEC 60216-6:2003)

This European Standard was approved by CENELEC on 2004-03-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 15E/221/FDIS, future edition 1 of IEC 60216-6, prepared by SC 15E, Methods of test, of IEC TC 15, Insulating materials, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 60216-6 on 2004-03-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2004-12-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2007-03-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 60216-6:2003 was approved by CENELEC as a European Standard without any modification.

CONTENTS

1	Scope.....	5
2	Normative references	5
3	Terms, definitions, symbols and abbreviated terms.....	6
3.1	Terms, abbreviations and definitions	6
3.2	Symbols and abbreviated terms.....	9
4	FTFM protocol – Principles and objectives	10
4.1	Principles of FTFM protocol.....	10
4.2	Objectives of FTFM protocol.....	10
5	TI determination	11
5.1	Ageing procedures	11
5.2	Ageing times and temperatures	11
5.3	Test specimens	12
5.4	Diagnostic tests.....	13
5.5	Selection of end-points.....	13
5.6	Establishment of initial property value	13
5.7	Ageing conditions.....	14
5.8	Procedure for ageing.....	14
6	Calculation procedures	15
6.1	General principles	15
6.2	Precision of calculations.....	16
6.3	Derivation of temperatures equivalent to property values.....	16
6.4	Regression analysis (temperature on time).....	19
6.5	Statistical tests.....	21
6.6	Thermal endurance graph	23
7	Calculation and requirements for results.....	24
7.1	Calculation of thermal endurance characteristics.....	24
7.2	Reporting of results.....	24
8	Report	25
9	RTE Determination – Objectives	25
10	Additional symbols	26
11	Experimental procedures	26
12	Calculation procedures	27
12.1	General principles	27
12.2	Input data.....	27
12.3	RTE.....	28
12.4	Confidence limits.....	28
12.5	Extrapolation	30
13	Results and report.....	30
13.1	Results of statistical and numerical tests	30
13.2	Result	30
13.3	Report.....	30

Annex A (normative) Decision flow chart.....	31
Annex B (normative) Decision table	32
Annex C (informative) Statistical tables.....	33
Annex D (informative) Suggested ageing times and temperatures.....	36
Annex E (informative) Figures.....	38
Annex F (normative) Statistical significance of the difference between two regression estimates	41
Figure E.1 – Property–temperature graph with regression line	38
Figure E.2 – Thermal endurance graph	38
Figure E.3 – Ageing times and temperatures in relation to thermal endurance graph	39
Figure E.4 – Ageing times and temperatures in relation to thermal endurance graph	39
Figure E.5 – Ageing times and temperatures in relation to thermal endurance graph	40
Table B.1 – Decision table	32
Table C.1 – χ^2 -function	33
Table C.2 – t -function.....	33
Table C.3 – F -function, $P = 0,05$	34
Table C.4 – F -function, $P = 0,005$	35
Table D.1 – Ageing temperatures and ageing periods	36

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method

1 Scope

This part of IEC 60216 specifies the experimental and calculation procedures for deriving the thermal endurance characteristics, temperature index (TI) and relative thermal endurance index (RTE) of a material using the “fixed time frame method (FTFM)”.

In this protocol, the ageing takes place for a small number of fixed times, using the appropriate number of ageing temperatures throughout each time, the properties of the specimens being measured at the end of the relevant time interval. This differs from the procedure of IEC 60216-1, where ageing is conducted at a small number of fixed temperatures, property measurement taking place after ageing times dependent on the progress of ageing.

Both the TI and the RTE determined according to the FTFM protocol are derived from experimental data obtained in accordance with the instructions of IEC 60216-1 and IEC 60216-2, as modified in this standard. The calculation procedures and statistical tests are modified in relation to IEC 60216-3 and IEC 60216-5.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60212:1971, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

IEC 60216-1:2001, *Electrical insulating materials – Properties of thermal endurance – Part 1: Ageing procedures and evaluation of test results*

IEC 60216-2:1990, *Guide for the determination of thermal endurance properties of electrical insulating materials – Part 2: Choice of test criteria*

IEC 60216-3:2002, *Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics*

IEC 60216-4-1:1990, *Guide for the determination of thermal endurance properties of electrical insulating materials – Part 4: Ageing ovens – Section 1: Single-chamber ovens*

IEC 60216-4-2:2000, *Electrical insulating materials – Thermal endurance properties – Part 4-2: Ageing ovens – Precision ovens for use up to 300 °C*

IEC 60216-4-3:2000, *Electrical insulating materials – Thermal endurance properties – Part 4-3: Ageing ovens – Multi-chamber ovens*

IEC 60216-5:2003, *Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative thermal endurance index (RTE) of an insulating material*

IEC 60493-1:1974, *Guide for the statistical analysis of ageing test data – Part 1: Methods based on mean values of normally distributed test results*

3 Terms, definitions, symbols and abbreviated terms

For the purposes of this document, the following terms, definitions, symbols and abbreviations apply.

3.1 Terms, abbreviations and definitions

3.1.1

assessed thermal endurance index

ATE

numerical value of the temperature in degrees Celsius, up to which the control material possesses known, satisfactory service performance in the specified application

NOTE 1 The ATE of a specific material may vary between different applications of the material.

NOTE 2 ATE is sometimes referred to as “absolute” thermal endurance index.

3.1.2

ageing temperature

temperature in degrees Celsius at which a group of specimens is thermally aged

3.1.3

end-point temperature

temperature in degrees Celsius at which a specimen is considered to have reached its end-point after ageing for the specified time

3.1.4

candidate material

material for which an estimate of the thermal endurance is required to be determined

NOTE The determination is made by simultaneous thermal ageing of the material and a control material.

3.1.5

central second moment of a data group

sum of the squares of the differences between the data values and the value of the group mean divided by the number of data in the group

3.1.6

95 % confidence limit

statistical parameter, calculated from test data, which with 95 % confidence constitutes an upper or lower limit for the true value of a quantity estimated by statistical analysis

NOTE 1 This implies that there is only 5 % probability that the true value of the quantity estimated is actually larger (or smaller) than the upper (or lower) confidence limit.

NOTE 2 In other connections, confidence values other than 95 % may sometimes be used, e.g. in the linearity test for destructive test data.

3.1.7

control material

material with known assessed thermal endurance index (ATE), preferably derived from service experience, used as a reference for comparative tests with the candidate material

3.1.8

correlation coefficient

number expressing the completeness of the relation between members of two data sets, equal to the covariance divided by the square root of the product of the variances of the sets

NOTE 1 The value of its square is between 0 (no correlation) and 1 (complete correlation).

NOTE 2 In this standard, the two data sets are the values of the independent variable and the means of the dependent variable groups.

3.1.9

correlation time of RTE

estimated time to end-point of the control material at a temperature equal to its ATE in degrees Celsius

3.1.10

correlation time of TI

hypothetical time to end-point used to calculate TI

NOTE Its usual value is 20 000 h.

3.1.11

covariance of data sets

for two sets of data with equal numbers of elements where each element in one set corresponds to one in the other, the sum of the products of the deviations of the corresponding members from their set means, divided by the number of degrees of freedom

3.1.12

degrees of freedom

number of data values minus the number of parameter values

3.1.13

destructive test

diagnostic property test, where the test specimen is irreversibly changed by the property measurement, in a way which precludes a repeated measurement on the same specimen

3.1.14

end-point line

line parallel to the temperature axis intercepting the property axis at the end-point value

3.1.15

halving interval

HIC

numerical value of the temperature interval in kelvin which expresses the halving of the time to end-point taken at a time equal to TI

3.1.16

regression analysis

process of deducing the best fit line expressing the relation of corresponding members of two data groups by minimizing the sum of squares of deviations of members of one of the groups from the line

3.1.17**regression coefficients**

coefficients of the equation derived by regression analysis

3.1.18**relative thermal endurance index****RTE**

estimate of the thermal endurance of a candidate material, made by thermal ageing simultaneously with the control material, as described in this standard

NOTE The value of RTE is the value of the temperature in degrees Celsius at which the estimated time to end-point of the candidate material is the same as the estimated time to end-point of the control material at a temperature equal to its ATE.

3.1.19**significance**

probability of a value of a statistical function greater than a specified value

NOTE The value is equal to $(1 - p)$ where p is the cumulative distribution function value. Significance is conventionally printed in upper case (P).

3.1.20**standard deviation**

square root of the variance of a data group or sub-group

3.1.21**standard error of an estimate of the true value of a data group property**

value of the standard deviation of the hypothetical sampling population of which the group property may be considered to be a member

NOTE For an estimate of the group mean, the standard error is equal to the group standard deviation divided by the square root of the number of data in the group, and indicates the uncertainty in the estimate of the true value of the mean. This standard is concerned only with means and the difference between two means.

3.1.22**temperature index****TI**

numerical value of the temperature in degrees Celsius derived from the thermal endurance relationship at a time of 20 000 h (or other specified time)

3.1.23**temperature group (of specimens)**

number of specimens being exposed together to thermal ageing at the same temperature in the same oven

NOTE Where there is no risk of ambiguity, either temperature groups or test groups may be referred to simply as "groups".

3.1.24**test group (of specimens)**

number of specimens removed together from a temperature group for destructive testing

NOTE Where there is no risk of ambiguity, either temperature groups or test groups may be referred to simply as "groups".

3.1.25**thermal endurance graph**

graph in which the logarithm of the time to reach a specified end-point in a thermal endurance test is plotted against the reciprocal thermodynamic (absolute) test temperature

3.1.26

thermal endurance graph paper

graph paper having a logarithmic time scale as the ordinate and values proportional to the reciprocal of the thermodynamic (absolute) temperature as the abscissa

NOTE The ordinate is in powers of ten (from 10 h to 100 000 h is often a convenient range). The abscissa is usually graduated in a non-linear (Celsius) temperature scale oriented with temperature increasing from left to right.

3.1.27

time group (of specimens)

all test groups removed for testing at the same time

3.1.28

variance of a data group

sum of the squares of the deviations of the data from a reference level defined by one or more parameters divided by the number of degrees of freedom

NOTE The reference level may, for example be a mean value (1 parameter) or a line (2 parameters, in this case intercept on the axis of the independent variable and slope).

3.2 Symbols and abbreviated terms

The following symbols are used in the calculations of Clauses 6, 7 and 12.

Symbol	Description	Clause
a	Regression coefficient: intercept of regression line with x -axis	6.4.3
b	Regression coefficient: slope of regression line relative to y -axis	6.4.3
b_r	Parameter derived from b for calculation of $\hat{Y}_c$	6.5.3
c	Parameter in calculation of χ^2	6.5.1
F	F -distributed variance ratio for linearity test	6.3.3, 6.5.2
g, h, i, j	Indexing parameters for regression calculations	6.3, 6.4
HIC	Halving interval	7.1
k	Number of ageing times	6.1.1
N	Total number of x_{ij} values	6.4.2
n_i	Number of x_{ij} values in time group i	6.1.1
P	Significance of the value of a statistical test function	Annexes A, B, and C
p_e	End-point property value	6.3
p_{gh}	Property value h in temperature group g (time group i implied)	6.3
$\bar{p}_g$	Mean property value in temperature group g (time group i implied)	6.3
q	Base of logarithms in calculation of χ^2	6.5.1
r	Number of temperature groups selected in time group i	6.3.2
r^2	Square of correlation coefficient	6.4.3
s^2	Total (non-regression) variance of x -values	6.5.2

Symbol	Description	Clause
s_{1g}^2	Variance of property values in temperature group g (time group i implied)	6.3.2
s_a^2	Value of s^2 adjusted to allow for acceptable non-linearity.	6.5.2
s_r^2	Parameter derived from s^2 for calculation of $\hat{Y}_c$	6.5.3
t	Student's t -distributed stochastic variable	6.5.3
TC, TC _a	Lower confidence limit of TI or TI _a (see s_a^2 above)	6.5.3
t_p, N	Value of t with probability p and N degrees of freedom	6.5.3
x_{ij}	Value of x , index number j , in time group i	6.3.4
$\bar{x}$	General mean of x -values	6.4.2
$\hat{X}, \hat{X}_c$	Estimate of x , and its confidence limit	6.5.3
y_i	Value of y for time group i	6.1.1
$\bar{y}$	General mean of y -values	6.4.2
$\hat{Y}, \hat{Y}_c$	Estimate of y , and its confidence limit	6.5.3
z_{ij}	Reciprocal kelvin temperature for g_{ij}	6.1.1
$\mu_2(y)$	Central 2 nd moment of y values	6.4.2
v	Total number of property values in time group (i implied)	6.3.2
χ^2	χ^2 distributed variable for variance equality (Bartlett's) test	6.5.1
g_{ij}	Ageing temperature for specimen group j in time group i	6.1.1
Θ_0	273,15 = kelvin value of 0 °C	6.1.1
τ_i	Ageing time for time group i	6.1.1

4 FTFM protocol – Principles and objectives

4.1 Principles of FTFM protocol

The FTFM (fixed time frame method) protocol is based upon the principle that thermal ageing for determination of thermal endurance characteristics is carried out over a small number of fixed times, with a sufficient range of ageing temperatures at each time to ensure that the end-point is reached in a satisfactory manner.

In this it differs from the conventional procedure (fixed temperature frame), where a small number of ageing temperatures is employed, with ageing being carried out with testing at intervals, until the end-point has been reached.

4.2 Objectives of FTFM protocol

The objective of the protocol is to achieve the following advantages:

The determination of thermal endurance characteristics is completed in a fixed, pre-determined time.

This enables much more efficient planning of the determination, and will often have substantial commercial advantage. A simple TI determination will be completed in 5 kh, whereas by the conventional protocol, it may be necessary for ageing to be considerably prolonged past this time to achieve the end-point at the lowest chosen ageing temperature.

Each temperature to end-point (i.e. time-group mean) in the thermal endurance regression is based on a number of temperatures which may be any number between three (3) and the number of temperature groups in a time group.

Since the largest source of systematic error in the conventional (fixed temperature frame) protocol is temperature error (actual indication error or temperature distribution error), systematic errors can be considerably reduced. Errors from this source can lead to results which are either inaccurate or invalid through incorrect assessment of linearity.

5 TI determination

5.1 Ageing procedures

Each test procedure should specify the shape, dimensions and number of the test specimens, the times of exposure, the property to which TI is related, the methods of its determination, the end-point, and the derivation of the thermal endurance characteristics from the experimental data.

The chosen property should, if possible, reflect in a significant fashion a function of the material in practical use. A choice of properties is given in IEC 60216-2.

To provide uniform conditions, the conditioning of specimens after removal from the oven and before measurement may need to be specified.

5.2 Ageing times and temperatures

In the majority of cases, the required thermal endurance characteristics are for a projected duration of 20 000 h. However, there is often a need for such information related to other, longer or shorter times. In cases of longer times, the times given as requirements or recommendations in this standard (e.g. 5 000 h for the minimum value of the longest ageing time) shall be increased in the ratio of the actual specification time to 20 000 h.

In cases of shorter specification times, the related times may be decreased in the same ratio, if necessary.

Particular care will be needed for very short specification times, since the higher ageing temperatures may lead into temperature regions which include transition points, e.g. glass transition temperature or partial melting, with consequent non-linearity. Very long specification times may also lead to non-linearity.

Recommendations for ageing times and temperatures are given in Annex D.

5.3 Test specimens

5.3.1 Preparation

The specimens used for the ageing test should constitute a random sample from the population investigated and shall be treated uniformly.

Since processing conditions may significantly affect the ageing characteristics of some materials, it shall be ensured that, for example, sampling, cutting sheet from the supply roll, cutting of anisotropic material in a given direction, moulding, curing, preconditioning, are performed in the same manner for all specimens.

The material specifications or the standards for the diagnostic test methods will contain all necessary instructions for the preparation of specimens.

The thickness of specimens is, in some cases, specified in the list of property measurements for the determination of thermal endurance. See IEC 60216-2. If not, the thickness shall be reported. Some physical properties are sensitive even to minor variations of specimen thickness. In such cases, the thickness after each ageing period may need to be determined and reported if required in the relevant specification.

The thickness is also important because the rate of ageing may vary with thickness. Ageing data of materials with different thicknesses are not always comparable. Consequently, a material may be assigned more than one thermal endurance characteristic derived from the measurement of properties at different thicknesses.

The tolerances of specimen dimensions should be the same as those normally used for general testing. Where specimen dimensions need smaller tolerances than those normally used, these special tolerances should be given.

Screening measurements ensure that specimens are of uniform quality and typical of the material to be tested.

5.3.2 Number of specimens

The accuracy of endurance test results depends largely on the number of specimens aged at each temperature.

The total number of specimens (N) is derived as follows:

$$N = a \times b \times c + d$$

where

- a is the number of specimens in a test group undergoing identical treatment at one temperature and discarded after determination of the property (usually five);
- b is the number of treatments, i.e. total number of exposure temperatures, at one time;
- c is the number of ageing time levels;
- d is the number of specimens in the group used to establish the initial value of the property. Normal practice is to select $d = 2a$ when the diagnostic criterion is a percentage change of the property from its initial level. When the criterion is an absolute property level, d is usually given the value of zero, unless reporting of the initial value is required.