



BSI Standards Publication

Aerospace series — Rivet-collar-system, aluminium alloy, shear type, inch series — Technical Specification

National foreword

This British Standard is the UK implementation of EN 6052:2022.

The UK participation in its preparation was entrusted to Technical Committee ACE/12, Aerospace fasteners and fastening systems.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 539 02996 3

ICS 49.030.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2022.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Aerospace series - Rivet-collar-system, aluminium alloy, shear type, inch series - Technical Specification

Série aérospatiale - Système rivet-collier, alliage
d'aluminium, type cisaillement, série en inches -
Spécification technique

Luft- und Raumfahrt - Passniet-Schließring-System aus
Aluminiumlegierung für Scherbeanspruchung, Zöllige
Reihe - Technische Lieferbedingungen

This European Standard was approved by CEN on 6 October 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 General requirements.....	5
5 Requirements for pins in aluminium alloy 7050-T73.....	5
6 Requirements for collars in aluminium alloy 3003 and 6061.....	8
7 Certification and quality assurance	10
7.1 Qualification tests.....	10
7.2 Quality conformance inspection	10
7.3 Quality control records.....	10
7.4 Lot.....	10
8 Delivery	20
8.1 Unit type containers.....	20
8.2 Unit packages	20
9 Quality management system.....	20
Annex A (informative) Record of revisions	21
Bibliography.....	22

European foreword

This document (EN 6052:2022) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this document has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2023, and conflicting national standards shall be withdrawn at the latest by April 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

1 Scope

This document defines the requirements for qualification, acceptance, delivery and inspection of 100° countersunk head, 100° countersunk reduced head and protruding head close tolerance pins, shear type in aluminium alloy 7050-T73 and collars of aluminium alloy 3003 and of aluminium alloy 6061-T7 for use as permanent fasteners in aerospace applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3115, *Aerospace series — Aluminium alloy 7050-T73 — Wire for solid rivets — $D \leq 10$ mm*

ANSI/ASQ Z 1.4, *Sampling Procedures and Tables for Inspection by Attributes*¹

ANSI/ASME B 46.1, *Surface Texture, Surface Roughness, Waviness and Lay*¹

ASTM-B193, *Standard Test Method for Resistivity of Electrical Conductor Materials*²

ASTM E 1417/E 1417M, *Standard Practice for Liquid Penetrant Testing*²

ASTM E 8/E 8Ma, *Standard Test Methods for Tension Testing of Metallic Materials*²

ASTM-E92, *Standard Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials*²

ASTM-G-110, *Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution*²

NASM1312, *Fastener Test Methods*³

FED-SPEC QQ-A-430, *Aluminium Alloy Rod and Wire, for Rivets and Cold Heading*⁴

SAE AMS2644, *Inspection Material, Penetrant*⁵

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

1 Published by: Department of Defense (DoD), the Pentagon, Washington, D.C., 20307, USA.

2 Published by: American Society for Testing and Materials, 100 Barr Harbor Dr., West Conshohocken, P.A., 19428, USA.

3 Published by: Aerospace Industries Association of America Inc. (AIA), 1250 Eye Street, N.W., Washington, D.C., 20005-3924, USA.

4 Published by: Superintendent of documents, US Government Printing House, Washington, D.C., 20402, USA.

5 Published by: Engineering Society for Advancing Mobility Land, Sea, Air and Space International (SAE), 400 Commonwealth Drive, Warrendale, P.A., 15096-0001, USA.

4 General requirements

The close tolerance pins and collars covered by this specification shall be of the types, sizes, configurations and materials designated by the part numbers specified on the applicable standards which refer to this specification.

5 Requirements for pins in aluminium alloy 7050-T73

The requirements for 7050-T73 aluminium alloy pins, shear type are given in Table 1. These requirements complement the requirements of all other standards or specifications referenced in the document of the pins and may be overridden only when specially instructed in the definition document.

Inspection tests given in Table 1 and Table 2 are mandatory (except as noted) on each lot as defined in 7.2 for the fastener manufacturer. Tests which are not mandatory for the fastener manufacturer may be applied by the receiving contractor.

Table 1 — Requirements for pins in aluminium alloy 7050-T73

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.1	General dimensions	The dimensions and any deviations in form and position, measured at ambient temperature, shall be within the limits specified in the standard part drawings and this procurement specification	Conventional measuring methods	According to Table 3	According to Table 5
5.2	Shank diameter	Underfill permissible, shall be within the specified shank diameter range	Standard micrometer 6,35 mm (¼”) diameter		
5.3	Shank straightness	Refer to Table 8	Conventional measuring methods		
5.4	Sealant escape groove	Refer to Figure 3 and Table 10			
5.5	Head protrusion (100° heads)	According to standard part drawings	In accordance with EN pin standards		
5.6	Surface texture		Visual examination according to ANSI/ASME B 46.1		
5.7	Lubricants		According to applicable specification and visual examination		
5.8	Finish				
5.9	Product identification		Visual examination		
5.10	Delivery	Refer to Clause 8		N/A	
5.11	Shear strength	Table 7 double shear values are applicable for pins having a grip of 2 × nominal diameter or greater for protruding head type and grip of 2,5 × nominal diameter or greater for flush head type. If the pin is too short to perform the shear test, a piece of wire of the same raw material lot heat treated with the fasteners shall be tested. The test wire shall have the	Test no 13 of NASM1312	According to Table 3	According to Table 6

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
		same coating as for pins. Minimum shear strength test of fasteners is to be performed on pins or wire without cetyl alcohol lubrication applied.			
5.12	Tensile strength	Table 7 values are applicable for pins having a grip of $1,5 \times$ nominal diameter or greater. Qualification and acceptance testing shall be performed with a 7° sloped surface (collar side) in minimum and maximum grip with collar according to collar standard.	Test no 8 of NASM1312		
5.13	Head dishing	After installation in a clearance fit of 0,025 mm, head dishing of flush head pins shall not exceed 0,076 mm (see Figure 6). Testing shall be performed with a 7° sloped surface (collar side) in minimum and maximum grip.	Test no. 8 of NASM1312		
5.14	Pin break load	Table 7 values are applicable. Tensile load shall be applied axially at a rate, which breaks the pin at a minimum of 4 s of load application. Test plate countersink for countersunk pins shall have 2° angular misalignment from the hole centerline. Test plate for protruding head pins shall have a 2° slope under the pin head. After evaluation of the pin break loads, head dishing of flush head pins shall not exceed 0,076 mm (see Figure 6). Cracks shall not be allowed in any location of the pin. The presence of cracks shall be determined by fluorescent penetrant inspection according to ASTM E 1417/E 1417M, method B or D, sensitivity level 2 or higher. The penetrant materials used shall be according to SAE AMS2644. Examine all surfaces at $10 \times$ to $30 \times$ magnification.	Test no. 8 of NASM1312 ASTM E 1417/E 1417M		