

BS EN 61249-2-35:2009



BSI Standards Publication

Materials for printed boards and other interconnecting structures —

Part 2-35: Reinforced base materials, clad and unclad — Modified epoxide woven E-glass laminate sheets of defined flammability (vertical burning test), copper-clad for lead-free assembly

bsi.

...making excellence a habit.
AVA Documents™
Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN 61249-2-35:2009. It is identical to IEC 61249-2-35:2008.

The UK participation in its preparation was entrusted to Technical Committee EPL/501, Electronic assembly technology.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

©BSI 2009

ISBN 978 0 580 57383 5

ICS 31.180

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2009

Amendments issued since publication

Amd. No.	Date	Text affected
----------	------	---------------

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 61249-2-35

March 2009

ICS 31.180

English version

**Materials for printed boards and other interconnecting structures -
Part 2-35: Reinforced base materials, clad and unclad -
Modified epoxide woven E-glass laminate sheets of defined flammability
(vertical burning test), copper-clad for lead-free assembly
(IEC 61249-2-35:2008)**

Matériaux pour circuits imprimés
et autres structures d'interconnexion -
Partie 2-35: Matériaux de base renforcés,
plaqués et non plaqués -
Feuilles stratifiées en tissu de verre
de type E époxyde modifié,
plaquées cuivre, d'inflammabilité définie
(essai de combustion verticale)
pour les assemblages sans plomb
(CEI 61249-2-35:2008)

Materialien für Leiterplatten
und andere Verbindungsstrukturen -
Teil 2-35: Kaschierte und unkaschierte
verstärkte Basismaterialien -
Kupferkaschierte mit E-Glasgewebe
verstärkte Laminattafeln auf der Basis
von modifiziertem Epoxidharz
mit definierter Brennbarkeit
(Brennprüfung mit vertikaler Prüflingslage)
für bleifreie Bestückungstechnik
(IEC 61249-2-35:2008)

This European Standard was approved by CENELEC on 2009-02-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: avenue Marnix 17, B - 1000 Brussels

© 2009 CENELEC - All rights of exploitation in any form and by any means reserved worldwide for CENELEC members.

Ref. No. EN 61249-2-35:2009 E

 **Documents**
Document Sharing Hub

Foreword

The text of document 91/810/FDIS, future edition 1 of IEC 61249-2-35, prepared by IEC TC 91, Electronics assembly technology, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 61249-2-35 on 2009-02-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2009-11-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2012-02-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 61249-2-35:2008 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following note has to be added for the standard indicated:

IEC 60194 NOTE Harmonized as EN 60194:2006 (not modified).

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 61189-2	2006	Test methods for electrical materials, printed boards and other interconnection structures and assemblies - Part 2: Test methods for materials for interconnection structures	EN 61189-2	2006
IEC 61249-5-1	1995	Materials for interconnection structures - Part 5: Sectional specification set for conductive foils and films with and without coatings - Section 1: Copper foils (for the manufacture of copper-clad base materials)	EN 61249-5-1	1996
ISO 9000	- ¹⁾	Quality management systems - Fundamentals and vocabulary	EN ISO 9000	2005 ²⁾
ISO 11014-1	- ¹⁾	Safety data sheet for chemical products - Part 1: Content and order of sections	-	-
ISO 14001	- ¹⁾	Environmental management systems - Requirements with guidance for use	EN ISO 14001	2004 ²⁾

¹⁾ Undated reference.

²⁾ Valid edition at date of issue.

CONTENTS

1	Scope	6
2	Normative references.....	6
3	Materials and construction	6
3.1	Resin system	6
3.2	Metal foil	7
3.3	Reinforcement	7
4	Internal marking.....	7
5	Electrical properties	7
6	Non-electrical properties of the copper-clad laminate	7
6.1	Appearance of the copper-clad sheet	7
6.1.1	Indentations (pits and dents)	8
6.1.2	Wrinkles	8
6.1.3	Scratches	8
6.1.4	Raised areas	8
6.1.5	Surface waviness.....	9
6.2	Appearance of the unclad face.....	9
6.3	Laminate thickness.....	9
6.4	Bow and twist	9
6.5	Properties related to the copper foil bond	10
6.6	Punching and machining	11
6.7	Dimensional stability.....	11
6.8	Sheet sizes.....	11
6.8.1	Typical sheet sizes	11
6.8.2	Tolerances for sheet sizes	12
6.9	Cut panels	12
6.9.1	Cut panel sizes	12
6.9.2	Size tolerances for cut panels	12
6.9.3	Rectangularity of cut panels	12
7	Non-electrical properties of the base material after complete removal of the copper foil	12
7.1	Appearance of the dielectric base material	12
7.2	Flexural strength.....	13
7.3	Flammability	13
7.4	Water absorption	14
7.5	Measling.....	14
7.6	Glass transition temperature and cure factor	15
7.7	Decomposition temperature	15
7.8	Thermal resistance	15
7.9	Z-axis expansion	15
8	Quality assurance	16
8.1	Quality system	16
8.2	Responsibility for inspection.....	16
8.3	Qualification inspection	16
8.4	Quality conformance inspection	16
8.5	Certificate of conformance	16

8.6 Safety data sheet.....	17
9 Packaging and marking.....	17
10 Ordering information	17
Annex A (informative) Engineering information	18
Annex B (informative) Common laminate constructions.....	20
Annex C (informative) Guideline for qualification and conformance inspection.....	22
Bibliography	23
Table 1 – Electrical properties	7
Table 2 – Nominal thickness and tolerance of metal-clad laminate	9
Table 3 – Bow and twist	10
Table 4 – Pull-off and peel strength	10
Table 5 – Dimensional stability	11
Table 6 – Size tolerances for cut panels	12
Table 7 – Rectangularity of cut panels	12
Table 8 – Flexural strength.....	13
Table 9 – Flammability	14
Table 10 – Water absorption	14
Table 11 – Measling	15
Table 12 – Glass transition temperature and cure factor	15
Table 13 – Decomposition temperature	15
Table 14 – Thermal resistance	15
Table 15 – Z-axis expansion.....	16

MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

Part 2-35: Reinforced base materials, clad and unclad – Modified epoxide woven E-glass laminate sheets of defined flammability (vertical burning test), copper-clad for lead-free assembly

1 Scope

This part of IEC 61249 gives requirements for properties of modified brominated epoxide woven E-glass laminate sheet 0,05 mm up to 3,2 mm, of defined flammability (vertical burning test), copper-clad. The glass transition temperature is defined to be 150 °C to 200 °C.

Its flame resistance is defined in terms of the flammability requirements of 7.3.

Some property requirements may have several classes of performance. The class desired should be specified on the purchase order; otherwise, the default class of material will be supplied.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2:2006, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 2: Test method for interconnection structures*

IEC 61249-5-1:1995, *Materials for interconnection structures – Part 5: Sectional specification set for conductive foils and films with and without coatings – Section 1: Copper foils (for the manufacture of copper-clad base materials)*

ISO 9000, *Quality management systems – Fundamentals and vocabulary*

ISO 11014-1, *Safety data sheet for chemical products – Part 1: Content and order of sections*

ISO 14001, *Environmental management systems – Requirements with guidance for use*

3 Materials and construction

The sheet consists of an insulating base with metal-foil bonded to one side or both.

3.1 Resin system

Majority di-functional epoxide, modified epoxide, woven E-glass laminate with a glass transition temperature of 150 °C to 200 °C. The flammability rating is achieved through the use of bromine reacted into the polymer. Inorganic fillers may be used. Contrast agents may be added to enhance processing such as automated optical inspection (AOI).

Its flame resistance is defined in terms of the flammability requirements of 7.3.

3.2 Metal foil

Copper as specified in IEC 61249-5-1, copper foil (for the manufacture of copper-clad materials). The preferred foils are electro-deposited of defined ductility.

3.3 Reinforcement

Woven E-glass as specified in the future IEC 61249-6-3, woven E-glass fabric (for the manufacture of prepreg and copper clad materials).

4 Internal marking

Not specified.

5 Electrical properties

The electrical property requirements are shown in Table 1.

Table 1 – Electrical properties

Property	Test method (IEC 61189-2)	Requirements
Resistance of foil	2E12	As specified in IEC 61249-5-1
Surface resistance after damp heat while in the humidity chamber (optional)	2E03	$\geq 10\,000\text{ M}\Omega$
Surface resistance after damp heat and recovery	2E03	$\geq 50\,000\text{ M}\Omega$
Volume resistivity after damp heat while in the humidity chamber (optional)	2E04	$\geq 5\,000\text{ M}\Omega\text{m}$
Volume resistivity after damp heat and recovery	2E04	$\geq 10\,000\text{ M}\Omega\text{m}$
Relative permittivity after damp heat and recovery (1 MHz)	2E10	$\leq 5,4$
Dissipation factor after damp heat and recovery (1 MHz)	2E10	$\leq 0,035$
Electric strength (only for material thickness less than 0,5 mm)	2E11	$\geq 30\text{ kV/mm}$
Arc resistance	2E14	$\geq 60\text{ s}$
Dielectric breakdown (only for material thicknesses $\geq 0,5\text{ mm}$)	2E15	$\geq 40\text{ kV}$
Surface resistance at 125 °C	2E07	$\geq 1\,000\text{ M}\Omega$
Volume resistivity at 125 °C	2E07	$\geq 1\,000\text{ M}\Omega\text{m}$

6 Non-electrical properties of the copper-clad laminate

6.1 Appearance of the copper-clad sheet

The copper-clad face shall be substantially free from defects that may have an impact on the material's fitness for use for the intended purpose.

For the following specific defects, the requirements given shall apply when inspection is made in accordance with IEC 61189-2, method 2M18.