

Mechanical safety of cathode ray tubes

The European Standard EN 61965:2001 has the status of a
British Standard

ICS 31.100

National foreword

This British Standard is the official English language version of EN 61965:2001. It is identical with IEC 61965:2000.

The UK participation in its preparation was entrusted to Technical Committee EPL/39, Electronic tubes, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 12 May 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 50, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 12 May 2003

ISBN 0 580 41810 3

Mechanical safety of cathode ray tubes
(IEC 61965:2000)

Sécurité mécanique des
tubes cathodiques
(CEI 61965:2000)

Mechanische Sicherheit
von Kathodenstrahlröhren
(IEC 61965:2000)

This European Standard was approved by CENELEC on 2001-12-04. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 39/252/FDIS, future edition 1 of IEC 61965, prepared by IEC TC 39, Electronic tubes, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 61965 on 2001-12-04.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2002-09-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2004-12-01

Annexes designated "normative" are part of the body of the standard.

Annexes designated "informative" are given for information only.

In this standard, annex ZA normative and annexes A and B are informative.

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 61965:2000 was approved by CENELEC as a European Standard without any modification.

CONTENTS

	Page
INTRODUCTION.....	6
Clause	
1 Scope	7
2 Normative references	7
3 Definitions.....	8
4 General requirements	9
4.1 Corrosion protection	9
4.2 Mechanical damage	9
4.3 Handling.....	9
5 Environmental conditioning	9
5.1 Standard atmospheric conditions for testing	9
5.2 Preconditioning	10
5.3 Thermal conditioning	10
6 Sampling.....	10
6.1 Sampling plans.....	10
6.2 Sample numbers	10
6.3 Compliance	10
7 Test preparation and set-up	10
7.1 Scratch patterns	10
7.2 Barriers	10
7.3 Mounting	11
7.4 Mounting position	11
8 Testing of large CRTs	11
8.1 Mechanical strength (ball impact test)	11
8.2 Implosion test (missile).....	12
8.3 Implosion test (thermal shock).....	13
8.4 High-energy impact test.....	13
9 Testing of small CRTs.....	14
9.1 Mechanical strength (ball impact test)	14
9.2 Implosion test (high ball)	15
9.3 Implosion test (thermal shock).....	15
9.4 High-energy impact test.....	15
10 Marking.....	16
11 Normative requirements for the use of tables 1 and 2 (prestressed banded CRTs).....	16
11.1 Sampling plan I: New construction.....	17
11.2 Sampling plan II: New construction with known resin or tape	18
11.3 Sampling plan III: Tension band and alternative tension band	18
11.4 Sampling plan IV: Alternative construction.....	19
12 Normative requirements for the use of tables 3 and 4 (bonded frame CRTs)	19
12.1 Sampling plan I: New construction.....	19
12.2 Sampling plan II: Alternative construction	20

Clause	Page
13 Normative requirements for the use of tables 5 and 6 (laminated CRTs)	21
13.1 Sampling plan I: New construction.....	21
13.2 Sampling plan II: Alternative construction	21
Annex A (informative) Background to the development of this standard	37
A.1 Mechanical strength test	38
A.2 Implosion test	38
A.3 Small CRTs (76 mm to 160 mm diagonal)	38
A.4 Evaluation time	38
Annex B (informative) Velocity and potential force of glass particles expelled from a CRT subjected to a ball impact – Ballistic and statistical calculations	39
B.1 Introduction.....	39
B.2 Analysis without friction	39
B.3 Analysis with friction	45
B.4 Potential threat	48
B.5 Conclusions	48
Annex ZA (normative) Normative references to international publications with their corresponding European publications	50
Figure 1 – Example of a test cabinet.....	27
Figure 2 – Example of a ball impact test	28
Figure 3 – Example of a 2,3 kg steel missile	29
Figure 4 – Missile impact area on a typical CRT	30
Figure 5 – Example of a missile impact test	31
Figure 6 – Options for scratch patterns for implosions by the thermal shock method	32
Figure 7 – Example of high-energy impact test set-up.....	33
Figure 8a – Example of steel pin for CRTs exceeding 160 mm face diagonal used in high-energy impact test	34
Figure 8b – Example of steel pin for CRTs from 76 mm to 160 mm diagonal used in high-energy impact test	34
Figure 9a – Example of 4,5 kg weight used in high-energy impact test on CRTs exceeding 160 mm diagonal	35
Figure 9b – Example of 0,45 kg weight used in high-energy impact test on CRTs from 76 mm to 160 mm face diagonal	35
Figure 10 – Example of 1,4 kg steel missile	36
Figure B.1 – Height of the barriers and distances from the CRT face	39
Figure B.2 – Example of the parabolic trajectory of a glass particle and the definition of the distances	40
Figure B.3 – Definition of the initial angle and initial velocity and the forces acting on a particle.....	41
Figure B.4 – Initial velocity required to pass over barriers at $x = l_1$ (solid line) or $x = l_2$ (dashed line) as a function of the initial angle β	43

	Page
Figure B.5 – Trajectories for a glass particle for different initial angles and an initial velocity of 4 m/s	43
Figure B.6 – Definition of the forces acting on a particle	45
Figure B.7 – Measurements of a typical glass particle.....	46
Figure B.8 – Trajectory of a glass particle with an initial velocity of 2 m/s and an initial angle of 45° without friction (dashed line) and with friction (solid line).....	47
Figure B.9 – Trajectories of a glass particle with an initial velocity of 2 m/s and an initial angle of 45° for different values of the cross-sectional area	48
 Table 1 – Sampling and test programme for prestressed banded CRTs exceeding 160 mm diagonal	 22
Table 2 – Sampling and test programme for prestressed banded CRTs from 76 mm to 160 mm diagonal	23
Table 3 – Sampling and test programme for bonded frame CRTs exceeding 160 mm diagonal	24
Table 4 – Sampling and test programme for bonded frame CRTs from 76 mm to 160 mm diagonal	24
Table 5 – Sampling and test programme for laminated CRTs exceeding 160 mm diagonal....	25
Table 6 – Sampling and test programme for laminated CRTs from 76 mm to 160 mm diagonal	25
Table 7 – CRT size and deflection angle ranges	26
 Table B.1 – Values of the distances	 40
Table B.2 – Upper and lower boundary values of the initial angle.....	42

INTRODUCTION

This International Standard sets forth test methods and limits for cathode ray tubes (CRTs). Hitherto, the only IEC standard for the mechanical safety of CRTs has been contained within clause 18 of the equipment standard IEC 60065. Whereas that standard has been accepted and used by many countries, many others have not been able to implement its requirements because of differing local needs. This new standard aims to provide the basis for wider acceptance and use, and reflects the current IEC policy of producing separate component standards to which equipment standards can refer.

Many years of experience had been built up in the use of both the IEC 60065 test and the other commonly used national alternatives. During the development of this new standard, extensive test programmes and ballistic and statistical calculations were carried out to verify that the requirements of the standard give protection for users of CRTs when the tubes are mounted in the equipment for which they are intended. This was also done to ensure that the new standard maintains the stringent requirements of both IEC 60065 and the alternative tests in common use. These tests and calculations also confirmed

- a) the acceptability of one standard ball for the mechanical strength test, and
- b) the need for the implosion test where it is not always possible to induce rapid devacuation using the ball impact test.

As the impact tests in this standard are overstress tests, only the effect of rapid devacuation is evaluated and not subsequent relaxation of mechanical stresses in the CRT from the implosion protection system.

MECHANICAL SAFETY OF CATHODE RAY TUBES

1 Scope

This International Standard is applicable to cathode ray tubes and cathode ray tube assemblies (hereinafter referred to as CRTs) which are intended for use as components in apparatus and which have integral protection with respect to the effects of implosion.

These requirements apply to CRTs intended for use in apparatus including electrical and electronic measuring and testing equipment, information technology equipment, medical equipment, telephone equipment, television equipment and other similar electronic apparatus.

This standard is intended to apply only to those CRTs in which the face of the CRT forms part of the enclosure for the apparatus. The test methods do not apply to CRTs which are protected by separate safety screens.

A CRT covered by this standard is intended to be installed in an enclosure designed both to protect the rear of the CRT against mechanical or other damage under normal conditions of operation and to protect the user against particles expelled in a backwards direction from the CRT face in the event of implosion.

This standard contains requirements for CRTs of 76 mm diagonal and larger that incorporate implosion protection systems providing protection against the hazards of particles expelled forwards beyond the face. There is no intended protection against particles expelled in other directions.

Compliance is tested by subjecting CRTs to the test procedures and criteria which are given in clauses 8 (large CRTs) and 9 (small CRTs) of this standard. The definitions of large and small CRTs are given in clause 3.

NOTE This set of requirements replaces the current requirements for the mechanical safety of cathode ray tubes (CRTs) as described in IEC 60065 (clause 18), which will be modified accordingly.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of IEC and ISO maintain registers of currently valid International Standards.

IEC 60065:1998, *Audio, video and similar electronic apparatus – Safety requirements*

IEC 60068-1:1988, *Environmental testing – Part 1: General and guidance*
Amendment 1 (1992)

IEC 60216-1, *Guide for the determination of thermal endurance properties of electrical insulating materials. Part 1: General guidelines for ageing procedures and evaluation of test results*

3 Definitions

For the purposes of this document the following definitions apply.

3.1

bonded frame

system employing a preformed metal frame that covers the periphery of the CRT rim area. The space or void between the CRT rim and the metal frame is filled with resin or equivalent

3.2

CRT diagonal

nominal diagonal of the glass envelope at its maximum dimension (for example, mould-match line) excluding any hardware

3.3

CRT envelope

structure consisting of a face or faceplate, funnel and neck assembly

3.4

devacuation

equalization of the pressure in a CRT relative to the ambient pressure

3.5

fracture

one or more cracks in the faceplate or funnel causing a rapid or slow devacuation of the CRT envelope

3.6

glass particle

piece of glass that exceeds 0,025 g in weight

3.7

implosion

devacuation due to the rapid and sudden inward collapse of a CRT envelope, usually accompanied by a loud report

3.8

laminated CRT

system that provides a separate external safety panel bonded to the face of the CRT

3.9

prestressed banded CRT

system that employs a metal tension band (located over the CRT rim area) that is tightened by thermal shrinking, or other means, to a tensile load. The system may also include a metal rim band located between the tension band and the CRT rim. The tension band or the rim band or both may have an interlayer of tape, resin or the equivalent placed between the mating parts

3.10

shaling

condition where the glassware splits into thin layers

3.11

test cabinet

enclosure which is used to accommodate the CRT during tests

3.12

useful phosphor screen

- a) colour CRT: the visible phosphored area of the CRT as viewed from the front
- b) monochrome CRT: specified maximum useful phosphored area of the CRT

3.13

large CRT

CRT with diagonal dimension exceeding 160 mm

3.14

small CRT

rectangular CRT with a minor face dimension of at least 50 mm, a minimum diagonal dimension of 76 mm and a maximum diagonal dimension of 160 mm; a round CRT of a minimum diameter of 76 mm and a maximum diameter of 160 mm

3.15

common quality management system

quality management system described in documentation which is identical with systems used in two or more plants and under one central control and management

4 General requirements

4.1 Corrosion protection

If corrosion of a metal part will contribute to a failure to meet the requirements of this standard, then the part shall be adequately protected against corrosion.

4.2 Mechanical damage

To improve repeatability and reproducibility of test results, it should be verified that samples submitted for test have no external visible scratching on the surface of the face plates.

4.3 Handling

Safety precautions should be addressed when handling test samples prior to, and after testing.

5 Environmental conditioning

5.1 Standard atmospheric conditions for testing

Unless otherwise specified, all tests and measurements shall be made under standard atmospheric conditions for testing as given in 5.3 of IEC 60068-1:

- temperature: 15 °C to 35 °C;
- relative humidity: 25 % to 75 %;
- air pressure: 86 kPa to 106 kPa

5.2 Preconditioning

Before CRTs are subjected to thermal conditioning or to testing they will be allowed to stabilize at standard atmospheric conditions for testing (see 5.1) for a minimum period of 16 h.

5.3 Thermal conditioning

Details of thermal conditioning are given in tables 1 to 6. After thermal conditioning has been completed, the CRTs will be allowed to stabilize at standard atmospheric conditions for testing (see 5.1) for a minimum period of 24 h.

6 Sampling

6.1 Sampling plans

Details are given in tables 1 to 6.

6.2 Sample numbers

The numbers of CRTs and the test programmes for prestressed banded CRTs are given in tables 1 and 2, for bonded frame CRTs in tables 3 and 4 and for laminated CRTs in tables 5 and 6.

NOTE In addition to the quantities specified in the tables, additional samples shall be made available for use in case of retest to satisfy the intent of the requirement.

6.3 Compliance

All CRTs in a test group shall comply with the test requirements for that group, except that, if only one CRT from all the test groups does not comply with the requirements, acceptability may be determined by subjecting a second test group to the set of tests during which unacceptable results occurred. The construction is acceptable if all CRTs in the second test group comply with the requirements.

7 Test preparation and set-up

7.1 Scratch patterns

As the form and depth of the scratch patterns may affect the force which is needed to obtain implosion or devacuation of the CRT, it is recommended that the scratches be made using a diamond- or carbide-tipped stylus, a glass cutter with a wheel of hardened steel or other similar tools.

7.2 Barriers

Barriers as specified in the test procedures, each made of 10 mm to 20 mm thick material, 250^{+0}_{-3} mm high and $(2,00 \pm 0,01)$ m long, shall be placed on the floor in front of the test cabinet at the specified locations, measured horizontally from the vertical plane of the centre of the front surface of the CRT to the near surface of the barrier closest to the tube face. The tolerance on the position of the barrier shall be ± 10 mm, unless otherwise stated. The barriers may be less than 2 m long provided that they extend to the walls of the test room (see figures 2 and 5). A non-skid surface such as a blanket or rug may be placed on the floor.

NOTE A particle travelling past the plane of the front surface of the barrier shall be considered to have passed the barrier.

7.3 Mounting

The CRT shall be mounted in a test cabinet of rigid construction and of suitable dimensions that does not permit a gap or opening wider than 6 mm around the CRT (see figure 1). The mounting of the CRT in front of, or behind, the front panel of the test cabinet shall be in accordance with the CRT manufacturer's specifications or intended application. When mounting specifications are not available, the preferred mounting method shall be behind the front panel unless design features do not allow this condition.

A hole of suitable area shall be provided at the top of the cabinet to allow access to the funnel. This hole shall be covered during the impact test.

An opening having an area of not less than one-quarter of the area of the face of the CRT or 0,02 m², whichever is the smaller, shall also be provided in the bottom or rear of the cabinet for air intake in the event of an implosion.

The cabinet shall be firmly supported so as to prevent movement during the test.

7.4 Mounting position

The centre of the CRT shall be $(1,00 \pm 0,05)$ m above the floor.

8 Testing of large CRTs

8.1 Mechanical strength (ball impact test)

8.1.1 Test procedure

A solid smooth steel ball of (40 ± 1) mm diameter and mass of (260 ± 15) g, including the hook, and a minimum C scale Rockwell hardness of 60, shall be suspended by suitable means such as a fine wire or chain with a mass not exceeding 10 % of the mass of the ball and the hook. It shall be allowed to fall freely as a pendulum from a calculated height and strike the face of the CRT with an energy of $(5,5 \pm 0,1)$ J. The CRT shall be placed so that the face is vertical and in the same vertical plane as the point of support of the pendulum. A single impact shall be applied to any point on the CRT face at a distance of 40 mm or greater from the edge of the useful phosphor screen.

NOTE The test laboratory should consider all their test set-up uncertainties to ensure this 40 mm minimum position of the point of impact.

The barrier shall be placed 1,5 m from the plane of the centre of the face of the CRT (see figure 2).

8.1.2 Glass throw criteria

A CRT is in compliance if the expulsion of glass within 5 s of the initial impact meets the following requirements:

- a) there shall be no glass particle (a single piece of glass having a mass greater than 0,025 g) past the 1,5 m barrier;
- b) the total mass of all pieces of glass past the 1,5 m barrier shall not exceed 0,1 g.

8.2 Implosion test (missile)

8.2.1 Test procedure

The face of the CRT at the top and bottom shall be scratched (3 ± 1) mm from the screen or phosphor edge into the viewing area. The scratches shall be horizontal lines (100 ± 5) mm long.

The impact object shall be a steel missile (see example in figure 3) with a mass of ($2,3 \pm 0,1$) kg, a minimum C scale Rockwell hardness of 60 and having one end rounded on a radius of ($25 \pm 0,5$) mm.

The CRT shall be subjected to a single impact, intending to cause rapid devacuation using the minimum energy within the range. The impact object shall be swung through an arc of a pendulum to obtain an impact of not less than 7,0 J and not more than 14,0 J to cause rapid devacuation of the samples in the test group.

The impact area shall be the area bounded by two concentric circles where the radius of one circle is one-sixth of the height of the useful phosphor screen and the second circle radius is one-half of the height of the useful phosphor screen less 50 mm (see figure 4). In figure 4, if R_2 is less than R_1 then the impact shall be applied to the circle specified in R_1 .

NOTE Previous testing experience on a particular CRT design (obtained from the CRT manufacturer or the test laboratory) should be considered when selecting the energy level within the range and the impact location.

The impact object travel shall be restricted so that the rounded end of the missile penetrates the CRT face equal to, or less than 25 mm (see figure 5).

Barriers shall be placed 1,0 m and 1,5 m from the vertical plane of the centre of the face of the CRT (see figure 5).

If no CRTs devacuate as a result of this test then the alternative implosion test (missile) described in 8.2.3 shall be carried out.

8.2.2 Glass throw criteria

A CRT is in compliance if the expulsion of glass within 5 s of the initial impact meets the following requirements:

- a) there shall be no single piece of glass having a mass greater than 15 g between the 1,0 m and 1,5 m barriers;
- b) the total mass of all pieces of glass between the 1,0 m and 1,5 m barriers shall not exceed 45 g;
- c) there shall be no single piece of glass having a mass greater than 1,5 g beyond the 1,5 m barrier.

8.2.3 Alternative implosion test (missile)

This alternative test shall be used as an additional test when the test in 8.2.1 has devacuated no CRTs, or may be used as an alternative to the test in 8.2.1 when it can be shown that the 8.2.1 test is unlikely to devacuate at least one CRT of the sample group.

8.2.3.1 Test procedure

As in 8.2.1, except that the impact object will be a steel missile (see example in figure 10) with a mass of ($1,4 \pm 0,1$) kg, a minimum C scale Rockwell hardness of 60 and one end rounded on a radius of ($15 \pm 0,5$) mm.

8.2.3.2 Glass throw criteria

As in 8.2.2. If no CRTs devacuate as a result of the test in 8.2.3.1, then the glass throw requirements of 8.2.2 are deemed to have been satisfied.

8.3 Implosion test (thermal shock)

8.3.1 Test procedure

The CRT shall be mounted in the test cabinet which is described in 7.3 and 7.4. The barrier shall be placed at (150 ± 2) mm from the vertical plane of the centre of the face of the CRT. An area shall be scratched on the faceplate sidewall or face of the CRT using one of the patterns illustrated in figure 6.

A thermal shock shall be applied using one of the following methods.

a) Liquid nitrogen

The scratched area shall be cooled using liquid nitrogen until a fracture occurs. A dam of modelling clay or equivalent may be used to contain the liquid nitrogen.

b) Hot rod

The end of an ordinary flint glass rod, of suitable diameter (for example, 10 mm) shall be heated until it is red hot and nearly fluid. The heated end of the rod shall be pressed firmly on the scratched area of the CRT. If devacuation of the CRT does not occur within 10 s then the rod shall be withdrawn and cold water poured slowly on the scratched area. If a devacuation cannot be induced by repeated applications of the hot rod then the test shall be carried out using liquid nitrogen (see 8.3.1a)).

8.3.2 Glass throw criteria

A CRT is in compliance if, within 5 s of the initial fracture, no glass particle is expelled through the plane of the face beyond the 150 mm barrier.

8.4 High-energy impact test

CRTs which have a laminated implosion protection system shall be subjected to the following high-energy impact test.

8.4.1 Test procedure

A (25 ± 1) mm diameter steel pin (see figure 8) shall be inserted through the hole at the top of the test cabinet and placed on the CRT envelope (3 ± 1) mm behind the seal of the faceplate and funnel. If the hardware extends back from the seal more than 3 mm so as to interfere with the placement of the pin, then the pin shall be placed as close as possible to the hardware without touching it. A weight (see figure 9a), having a mass of $(4,5 \pm 0,1)$ kg, shall be caused to fall from a height so as to impact the pin at the end of its fall.

The height of the test mass shall be adjusted to limit the amount of energy to the minimum required to produce fracturing of the glassware, but not less than 7 J.

If fracturing of the glass does not occur, the impact energy shall be increased in 7 J increments to a maximum of 63 J using a new test sample each time until all the CRTs in the test group have suffered rapid devacuation.

The impact energy shall not be so large as to cause the pin to punch a hole with little or no cracking or shaling of the glassware. If this condition does occur then a lower impact energy shall be selected so as to result in fracturing (7 J steps not necessary).

NOTE Previous testing experience on a particular CRT design (obtained from the CRT manufacturer or the test laboratory) should be considered when selecting the energy level within the range.

The implosion pin shall be restricted so that its travel on impact shall be a maximum of 6 mm. The pin travel restriction assembly shall be positioned so that its impact energy shall not be transferred to the test cabinet. Figures 7, 8 and 9 give examples of equipment that may be used.

Barriers shall be placed 1,0 m and 1,5 m from the plane of the centre of the face of the CRT.

8.4.2 Glass throw criteria

A CRT is in compliance if the expulsion of glass within 5 s of the initial impact meets the following requirements:

- a) there shall be no single piece of glass having a mass greater than 15 g between the 1,0 m and 1,5 m barriers;
- b) the total mass of all pieces of glass between the 1,0 m and 1,5 m barriers shall not exceed 45 g;
- c) there shall be no single piece of glass having a mass greater than 1,5 g beyond the 1,5 m barrier.

9 Testing of small CRTs

9.1 Mechanical strength (ball impact test)

9.1.1 Test procedure

A solid smooth steel ball of (40 ± 1) mm diameter and mass of (260 ± 15) g, including the hook, and a minimum C scale Rockwell hardness of 60, shall be suspended by suitable means such as a fine wire or chain with a mass not exceeding 10 % of the mass of the ball and hook. It shall be allowed to fall freely as a pendulum from a calculated height and strike the face of the CRT with an energy of $(2,0 \pm 0,1)$ J. The CRT shall be placed so that the face is vertical and in the same vertical plane as the point of support of the pendulum. A single impact shall be applied to any point on the CRT face at a distance of 25 mm or greater from the edge of the useful screen.

NOTE The test laboratory should consider all their test set-up uncertainties to ensure this 25 mm minimum position of the point of impact.

The barrier shall be placed 0,6 m from the plane of the centre of the face of the CRT (see figure 2).

9.1.2 Glass throw criteria

A CRT is in compliance if the expulsion of glass within 5 s of the initial impact meets the following requirements:

- a) there shall be no glass particle (a single piece of glass having a mass greater than 0,025 g) past the 0,6 m barrier;
- b) the total mass of all pieces of glass past the 0,6 m barrier shall not exceed 0,1 g.

9.2 Implosion test (high ball)

If implosion or rapid devacuation does not occur when the CRT is tested as specified in 9.1 then a CRT having other than a laminated implosion protection system shall be subjected to the following test.

9.2.1 Test procedure

The face of the CRT shall be scratched at the top and bottom edges (3 ± 1) mm from the screen phosphor edge into the viewing area. The length of the scratches shall be 45 % to 55 % of the longest dimension/width of the face of the CRT.

Using a (40 ± 1) mm diameter steel ball having a mass of (260 ± 15) g and a minimum C scale Rockwell hardness of 60, a CRT having other than a laminated implosion screen shall be subject to additional impact tests during which the impact energy shall be increased in 0,7 J increments until fracturing occurs. A new sample shall be used for each test until all CRTs in the test group have been tested, with implosion or rapid devacuation occurring.

Barriers shall be placed 0,6 m and 1,2 m from the plane of the centre of the face of the CRT (see figure 2).

9.2.2 Glass throw criteria

A CRT is in compliance if the expulsion of glass within 5 s of the initial impact meets the following requirements:

- a) there shall be no single piece of glass having a mass greater than 15 g between the 0,6 m and 1,2 m barriers;
- b) the total mass of all pieces of glass between the 0,6 m and 1,2 m barriers shall not exceed 45 g;
- c) there shall be no single piece of glass having a mass greater than 1,5 g beyond the 1,2 m barrier.

9.3 Implosion test (thermal shock)

9.3.1 Test procedure

As 8.3.1.

9.3.2 Glass throw criteria

As 8.3.2.

9.4 High-energy impact test

CRTs which have a laminated implosion protection system shall be subjected to the following high-energy impact test.

9.4.1 Test procedure

A ($9,5 \pm 0,5$) mm diameter steel pin shall be inserted through the hole in the top of the test cabinet and placed directly on the envelope seal line. A weight (see figure 9b) having a mass of ($0,45 \pm 0,02$) kg, shall be caused to fall freely from a height so as to impact the pin at the end of its fall.