

Composite station post insulators for substations with a.c. voltages greater than 1 000 V up to 245 kV — Definitions, test methods and acceptance criteria

The European Standard EN 62231:2006 has the status of a
British Standard

ICS 29.080.10

National foreword

This British Standard was published by BSI. It is the UK implementation of EN 62231:2006. It is identical with IEC 62231:2006.

The UK participation in its preparation was entrusted to Technical Committee PEL/36, Insulators for power systems.

A list of organizations represented on this committee can be obtained on request to its secretary.

The attention of users is drawn to the flammability test clause 8.4 in BS EN 62231:2007, which references BS EN 62217:2006 and is used as an indicator of power arc ignition and extinction performance. The UK Committee is of the opinion that work carried out before and after BS EN 62217:2005 was published shows that the flammability test is not suitable for assessing the power arc performance of insulators. The correlation between performance in different flammability tests, laboratory power arc tests and behaviour in service is currently under investigation by CIGRE SC D1. When applying this standard, users are recommended to consult the power arc tests in ANSI C29.18 or IEC 99-4 surge arrester specifications in addition to the test in BS EN 62217:2006. The ANSI test also usefully includes an end fitting seal test after power arc damage.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2007

© BSI 2007

ISBN 978 0 580 50841 7

Amendments issued since publication

Amd. No.	Date	Comments

**Composite station post insulators for substations
with a.c. voltages greater than 1 000 V up to 245 kV -
Definitions, test methods and acceptance criteria
(IEC 62231:2006)**

Isolateurs supports composites rigides
à socle destinés aux postes à courant
alternatif de tensions supérieures
à 1 000 V jusqu'à 245 kV -
Définitions, méthodes d'essai
et critères d'acceptation
(CEI 62231:2006)

Verbundstützisolatoren für Unterwerke
für Wechselspannung größer
1 kV bis 245 kV -
Definitionen, Prüfmethode
und Annahmekriterien
(IEC 62231:2006)

This European Standard was approved by CENELEC on 2006-09-12. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 36C/159/FDIS, future edition 1 of IEC 62231, prepared by SC 36C, Insulators for substations, of IEC TC 36, Insulators, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 62231 on 2006-09-12.

This standard is to be used in conjunction with EN 62217:2006, *Polymeric insulators for indoor and outdoor use with a nominal voltage > 1 000 V - General definitions, test methods and acceptance criteria*.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2007-07-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2009-10-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 62231:2006 was approved by CENELEC as a European Standard without any modification.

CONTENTS

INTRODUCTION.....	5
1 Scope and object.....	7
2 Normative references	7
3 Terms and definitions	8
4 Identification.....	11
5 Environmental conditions	12
6 Information on transport, storage and installation	12
7 Classification of tests.....	12
7.1 Design tests	12
7.2 Type tests	14
7.3 Sample tests	14
7.4 Routine tests	14
8 Design tests	14
8.1 General.....	14
8.2 Tests on interfaces and connections of end fittings.....	15
8.3 Assembled core load tests	15
8.4 Tests on shed and housing material	18
8.5 Tests on the core material	18
9 Type tests	18
9.1 Verification of dimensions	18
9.2 Electrical tests.....	18
9.3 Mechanical tests.....	20
10 Sample tests	22
10.1 General rules.....	22
10.2 Verification of dimensions (E1 + E2)	22
10.3 Galvanizing test (E1 + E2)	22
10.4 Verification of the specified mechanical loads (E1)	23
10.5 Re-testing procedure	23
11 Routine tests	24
11.1 Identification of the station post insulator	24
11.2 Visual examination	24
11.3 Tensile load test.....	24
Annex A (informative) Notes on the mechanical loads and tests.....	26
Annex B (informative) Determination of the equivalent bending moment caused by combined cantilever and compression (tension) loads.....	28
Annex C (informative) Example of torsion load test arrangement.....	30
Annex D (normative) Tolerances of form and position	31
Annex E (informative) Notes on the compression and buckling test.....	34
Annex ZA (normative) Normative references to international publications with their corresponding European publications	36
Bibliography	35

Figure 1 – Thermal-mechanical pre-stressing test – Typical cycles	25
Figure B.1 – Combined loads applied to station post insulators	29
Figure D.1 – Parallelism, coaxiality and concentricity	31
Figure D.2 – Angular deviation of fixing holes: Example 1	32
Figure D.3 – Angular deviation of fixing holes: Example 2	32
Figure D.4 – Tolerances according to standard drawing practice	33
Table 1 – Tests to be carried out after design changes	13
Table 2 – Number of samples for sample tests	22

INTRODUCTION

Composite station post insulators consist of a cylindrical solid insulating core made of resin impregnated fibres, bearing the mechanical load, protected by an elastomer housing, the loads being transmitted to the core by metal fittings. Despite these common features, the materials used and the construction details employed by different manufacturers may be different.

Some tests have been grouped together as "design tests" to be performed only once for insulators of the same design. The design tests are performed in order to eliminate insulator designs, materials and manufacturing technologies not suitable for high-voltage applications. The influence of time on the electrical and mechanical properties of the complete composite station post insulator and its components (core material, housing material, interfaces, etc.) has been considered in specifying the design tests in order to ensure a satisfactory lifetime under normal service conditions.

The approach for mechanical testing under bending loads used in this Standard is based on IEC 61952. This approach uses the concept of a damage limit that is the maximum stress that can be developed in the insulator before damage begins to occur. Work is underway to validate the acoustic emission technique to determine the inception of damage.

In some cases, station post insulators can be subjected to a combination of loads. In order to give some guidance, Annex B explains how to calculate the equivalent bending moment in the insulators resulting from the combination of bending, tensile and compression loads.

Pollution tests, as specified in IEC 60507 and IEC 61245, are not included in this document, their applicability to composite station post insulators having not been proven. Such pollution tests performed on composite insulators do not correlate with experience obtained from service. Specific pollution tests for composite insulators are under consideration.

It has not been considered useful to specify a power arc test as a mandatory test. The test parameters are manifold and can have very different values depending on the configurations of the network and the supports and on the design of arc-protection devices. The heating effect of power arcs should be considered in the design of metal fittings. Critical damage to the metal fittings, resulting from the magnitude and duration of the short-circuit current can be avoided by properly designed arc-protection devices. This standard, however, does not exclude the possibility of a power arc test by agreement between the user and the manufacturer. IEC 61467 gives details of a.c. power arc testing of insulator sets.

Impulse (mechanical) loads in substation are typically caused by short-circuits. Post insulators are affected by forces due to the interaction of the currents circulating in conductors/busbars supported by insulators.

The impulse load or peak load may be evaluated using guidance found in the IEC 60865 series.

Work is in progress in CIGRE ESCC (Effects of Short-Circuit Currents) task force to review impulse loads caused by short-circuit currents in substations. The aim of this work is to introduce a new concept: the ESL factor (Equivalent Static Load factor) which is frequency dependent. The actual peak load may be replaced, in a first approximation, by the peak load times the ESL factor. This new value may be used as the MDCL in this document for the determination of the cantilever strength.

Radio interference and corona tests are not specified in this standard since the radio interference and corona performances are not characteristics of the insulator alone.

Composite hollow core station post insulators are currently not dealt with in this standard. IEC 61462 gives details of tests on hollow core composite insulators, many of which can be applied to such station post insulators.

COMPOSITE STATION POST INSULATORS FOR SUBSTATIONS WITH AC VOLTAGES GREATER THAN 1 000 V UP TO 245 kV – DEFINITIONS, TEST METHODS AND ACCEPTANCE CRITERIA

1 Scope and object

This International Standard applies to composite station post insulators consisting of a load bearing cylindrical insulating solid core made of resin impregnated fibres, a housing (outside the insulating solid core) made of elastomer material (e.g. silicone or ethylene-propylene) and end fittings attached to the insulating core. Composite station post insulators covered by this standard are subjected to cantilever, torsion, tension and compression loads. They are intended for substations with a.c. voltages greater than 1 000 V up to 245 kV.

The object of this standard is

- to define the terms used,
- to prescribe test methods,
- to prescribe acceptance or failure criteria.

This standard does not include requirements dealing with the choice of insulators for specific operating conditions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-471, *International Electrotechnical Vocabulary (IEV) – Chapter 471: Insulators*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements*

IEC 60168:1994, *Tests on indoor and outdoor post insulators of ceramic material or glass for systems with nominal voltages greater than 1 000 V*

IEC 62217, *Polymeric insulators for indoor and outdoor use with a nominal voltage greater than 1000 V – General definitions, test methods and acceptance criteria*

ISO 1101, *Technical drawings – Geometrical tolerancing – Tolerancing of form, orientation, location and run-out – Generalities, definitions, symbols, indications on drawings*

ISO 3452, *Non-destructive testing – Penetrant inspection – General principles*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

composite station post insulator

post insulator consisting of a solid load bearing cylindrical insulating core, a housing and end fittings attached to the insulating core

3.2

core (of an insulator)

central insulating part of an insulator which provides the mechanical characteristics

NOTE The housing and sheds are not part of the core.

[IEV 471-01-03]

3.3

housing

external insulating part of composite insulator providing necessary creepage distance and protecting core from environment

NOTE An intermediate sheath made of insulating material may be part of the housing.

[IEV 471-01-09]

3.4

housing profile

shape and dimensions of the housing of the composite station post insulator which include the following:

- shed overhang(s)
- shed thickness at the base and at the tip
- shed spacing
- shed repetition
- shed inclination(s)

3.5

shed (of an insulator)

insulating part, projecting from the insulator trunk, intended to increase the creepage distance. The shed can be with or without ribs

[IEV 471-01-15]

3.6

insulator trunk

central insulating part of an insulator from which the sheds project

NOTE Also known as shank on smaller insulators.

[IEV 471-01-11]

3.7

creepage distance

shortest distance or the sum of the shortest distances along the surface on an insulator between two conductive parts which normally have the operating voltage between them

NOTE 1 The surface of cement or of any other non-insulating jointing material is not considered as forming part of the creepage distance.

NOTE 2 If a high resistance coating is applied to parts of the insulating part of an insulator, such parts are considered to be effective insulating surfaces and the distance over them is included in the creepage distance.

[IEV 471-01-04]

3.8 arcing distance

shortest distance in air external to the insulator between the metallic parts which normally have the operating voltage between them

[IEV 471-01-01]

NOTE The term “dry arcing distance” is also used.

3.9 interfaces surface between the different materials

NOTE Various interfaces occur in most composite insulators, e.g.

- between housing and fixing devices,
- between various parts of the housing, e.g. between sheds, or between sheath and sheds,
- between core and housing.

[IEC 62217]

3.10 end fitting

integral component or formed part of an insulator intended to connect it to a supporting structure, or to a conductor, or to an item of equipment, or to another insulator

NOTE Where the end fitting is metallic, the term “metal fitting” is normally used.

[IEV 471-01-06, modified]

3.11 connection zone

zone where the mechanical load is transmitted between the insulating body and the end fitting

[IEC 62217]

3.12 coupling

part of the fixing device which transmits load to the hardware external to the insulator

[IEC 62217]

3.13 tracking

process which forms irreversible degradation by formation of conductive paths (tracks) starting and developing on the surface of an insulating material

NOTE These paths are conductive even under dry conditions.

[IEC 62217]

3.14**erosion**

irreversible and non-conducting degradation of the surface of the insulator that occurs by loss of material which can be uniform, localized or tree-shaped

NOTE Light surface traces, commonly tree-shaped, can occur on composite insulators as on ceramic insulators, after partial flashover. These traces are not considered to be objectionable as long as they are non-conductive. When they are conductive they are classified as tracking.

[IEC 62217]

3.15**delamination** (of the core)

loss of bonding between fibres and matrix

3.16**crack**

any internal fracture or surface fissure of depth greater than 0,1 mm

[IEC 62217]

3.17**specified cantilever load****SCL**

cantilever load which can be withstood by the insulator when tested under the prescribed conditions

3.18**maximum design cantilever load****MDCL**

cantilever load level above which damage to the insulator begins to occur and that should not be exceeded in service

3.19**specified torsion load****SToL**

torsion load level which can be withstood by the insulator when tested under the prescribed conditions

3.20**maximum design torsion load****MDToL**

torsion load level above which damage to the insulator begins to occur and that should not be exceeded in service

3.21**specified tension load****STL**

tension load which can be withstood by the insulator when tested under the prescribed conditions

3.22**maximum design tension load****MDTL**

tension load level above which damage to the insulator begins to occur and that should not be exceeded in service