

Methods of test for dense shaped refractory products

Part 9. Determination of creep in compression

The European Standard EN 993-9 : 1997 has the status of a
British Standard

ICS 81.080

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

BSI
Documents



Document Sharing Hub

National foreword

This British Standard is the English language version of EN 993-9 : 1997. It supersedes BS 1902 : Section 4.10 : 1990, which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee RPI/1, Refractory products and materials, to Subcommittee RPI/1/1, Sampling and physical testing of refractory materials, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled 'International Standards Correspondence Index', or using the 'Find' facility of the BSI Standards Electronic Catalogue.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 10, an inside back cover and a back cover.

Amendments issued since publication

Amd. No.	Date	Text affected

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 September 1997

© BSI 1997

ISBN 0 580 28318 6

ICS 81.080

Descriptors: Refractory materials, shaped refractories, dense shaped refractory products, shaped insulated refractory products, mechanical tests, compression tests, creep tests

English version

Methods of test for dense shaped refractory products — Part 9: Determination of creep in compression

Méthodes d'essai pour produits réfractaires
façonnés denses —
Partie 9: Détermination du fluage à la compression

Prüfverfahren für dichte geformte feuerfeste
Erzeugnisse —
Teil 9: Bestimmung des Druckflußverhaltens

This European Standard was approved by CEN on 1997-04-21. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

© 1997 CEN — All rights of exploitation in any form and by any means reserved worldwide for CEN national Members

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 187, Refractory products and materials, the secretariat of which is held by BSI. This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997. Reproducibility and repeatability data are not available at present but may be included in a subsequent edition. EN 993 *Methods of test for dense shaped refractory products* consists of 18 Parts:

- Part 1 : *Determination of bulk density, apparent porosity and true porosity*
- Part 2 : *Determination of true density*
- Part 3 : *Test methods for carbon-containing refractories*
- Part 4 : *Determination of permeability to gases*
- Part 5 : *Determination of cold crushing strength*
- Part 6 : *Determination of modulus of rupture at ambient temperature*
- Part 7 : *Determination of modulus of rupture at elevated temperatures*
- Part 8 : *Determination of refractoriness-under-load*
- Part 9 : *Determination of creep in compression*
- Part 10 : *Determination of permanent change in dimensions on heating*
- Part 11 : *Determination of resistance to thermal shock (ENV)*
- Part 12 : *Determination of pyrometric cone equivalent*
- Part 13 : *Specification for pyrometric cones*
- Part 14 : *Determination of thermal conductivity (hot wire, cross-array)*
- Part 15 : *Determination of thermal conductivity (hot wire, parallel)*
- Part 16 : *Determination of resistance to acids*
- Part 17 : *Determination of bulk density of granular material (mercury method)*
- Part 18 : *Determination of bulk density of granular material (water method)*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Contents

	Page
Foreword	2
1 Scope	3
2 Normative references	3
3 Definitions	3
4 Principle	3
5 Apparatus	3
6 Test pieces	4
7 Procedure	4
8 Calculation of results	5
9 Test report	5
Annex A (informative) Measuring device below or above the furnace	10

1 Scope

This European Standard specifies a method for determining creep in compression of dense and insulating shaped refractory products, creep being the deformation of a refractory product subjected to a constant load under isothermal conditions.

NOTE. The apparatus is the same as that used in the determination of refractoriness-under-load (see EN 993-8).

2 Normative references

This European Standard incorporates by dated or undated references, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 993-8 :	<i>Methods of test for dense shaped refractory products: Part 8: Determination of refractoriness-under-load</i>
EN 60584-1 :	<i>Thermocouples — Part 1: References tables</i>
EN 6058-2 :	<i>Thermocouples — Part 2 : Tolerances</i>
ISO 3599 :	<i>Vernier calipers reading to 0,1 mm and 0,05 mm.</i>

3 Definitions

For the purposes of this European Standard, the following definition applies.

creep in compression

Isothermal deformation of a compressive stressed product as a function of time.

4 Principle

A test piece is submitted to a constant load and then heated under specified conditions to a given temperature. The deformation of the test piece is recorded and the percentage change evaluated as a function of time.

5 Apparatus

5.1 Loading device

5.1.1 General

The loading device shall be capable of applying a load centred on the common axis of the loading column, the test piece and the supporting column, and directed vertically along this axis at all stages of the test. The loading device consists of the items given in 5.1.2 to 5.1.5.

A constant compressive load is applied axially to the test piece in a downward direction from above the test piece resting directly or indirectly on a fixed base. The deformation of the test piece is measured by a device that passes either through the applied load or through an intermediate base.

The text and figures 1 and 2 show the measuring device passing through the base but, by interchanging the bored column and refractory plate with the unbored column and plate, the measuring device may pass through the load, as in figure 3.

NOTE. Although both arrangements are within the scope of this standard, it is preferable that the measuring device should be positioned below the assembly, as shown in the figures. The reasons for this are outlined in annex A.

5.1.2 Fixed column, at least 45 mm in overall diameter and with an axial bore (see 5.1.5).

5.1.3 Moving column, at least 45 mm in overall diameter.

NOTE. Arrangements can be made for the upper moving column to be fixed to the furnace, and the combination of furnace and column then forms the moveable loading device.

5.1.4 Two discs, 5 mm to 10 mm thick, at least 50,5 mm in diameter and not less than the actual diameter of the test pieces, which shall be of an appropriate refractory material compatible with the material under test.

NOTE. For example, high fired mullite or alumina for aluminosilicate products, and magnesia or spinel for basic products.

These discs are placed between the test piece and the fixed and moving columns. The disc placed between the test piece and the fixed column shall have a central bore (see 5.1.5). The ends of the fixed and moving columns shall be plane and perpendicular on their axes; the face of each disc shall be plane and parallel.

If chemical reaction is expected between discs and test piece, a platinum or platinum/rhodium foil (0,2 mm thickness) shall be placed between them.

5.1.5 The arrangement of the two columns, the two discs, the platinum sheet if used, and the test piece is shown in figure 2, which also shows typical diameters of the bores in the fixed column and the disc between them.

5.1.6 The columns and the discs shall be capable of withstanding the applied load up to the final test temperature without significant deformation. There should be no reaction between the discs and the loading system.

NOTE. The material from which the discs are made should be a T_1 value greater than or equal to the temperature of which the test material has a T_5 value (see clause 8), these values being measured in accordance with EN 993-8.