



BSI Standards Publication

## Superconductivity

---

Part 23: Residual resistance ratio measurement — Residual resistance ratio of cavity-grade Nb superconductors

# National foreword

This British Standard is the UK implementation of EN IEC 61788-23:2024. It is identical to IEC 61788-23:2024. It supersedes BS EN IEC 61788-23:2021, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee W/-, Consumer Products and Services Sector Policy and Strategy Committee.

A list of organizations represented on this committee can be obtained on request to its committee manager.

## Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2024  
Published by BSI Standards Limited 2024

ISBN 978 0 539 26878 2

ICS 17.220; 29.050

## Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2024.

## Amendments/corrigenda issued since publication

| Date | Text affected |
|------|---------------|
|------|---------------|

English Version

Superconductivity - Part 23: Residual resistance ratio  
measurement - Residual resistance ratio of cavity-grade Nb  
superconductors  
(IEC 61788-23:2024)

Supraconductivité - Partie 23: Mesurage du rapport de  
résistance résiduelle - Rapport de résistance résiduelle des  
supraconducteurs de Nb à cavités  
(IEC 61788-23:2024)

Supraleitfähigkeit - Teil 23: Messung des  
Restwiderstandsverhältnisses - Restwiderstandsverhältnis  
von hochreinen Nb-Supraleitern für Kavitäten  
(IEC 61788-23:2024)

This European Standard was approved by CENELEC on 2024-06-26. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

The text of document 90/515/FDIS, future edition 3 of IEC 61788-23, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 61788-23:2024.

The following dates are fixed:

- latest date by which the document has to be implemented at national (dop) 2025-03-26 level by publication of an identical national standard or by endorsement
- latest date by which the national standards conflicting with the (dow) 2027-06-26 document have to be withdrawn

This document supersedes EN IEC 61788-23:2021 and all of its amendments and corrigenda (if any).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national committee. A complete listing of these bodies can be found on the CENELEC website.

## Endorsement notice

The text of the International Standard IEC 61788-23:2024 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standard indicated:

|              |      |                            |
|--------------|------|----------------------------|
| IEC 61788-4  | NOTE | Approved as EN IEC 61788-4 |
| IEC 61788-10 | NOTE | Approved as EN 61788-10    |

## Annex ZA

(normative)

### Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cencenelec.eu](http://www.cencenelec.eu).

| <u>Publication</u> | <u>Year</u> | <u>Title</u>                                                               | <u>EN/HD</u> | <u>Year</u> |
|--------------------|-------------|----------------------------------------------------------------------------|--------------|-------------|
| IEC 60050-815      | -           | International Electrotechnical Vocabulary -<br>Part 815: Superconductivity | -            | -           |

## CONTENTS

|                                                                                                                      |    |
|----------------------------------------------------------------------------------------------------------------------|----|
| FOREWORD.....                                                                                                        | 4  |
| INTRODUCTION.....                                                                                                    | 6  |
| 1 Scope.....                                                                                                         | 7  |
| 2 Normative references .....                                                                                         | 7  |
| 3 Terms and definitions .....                                                                                        | 7  |
| 4 Principle .....                                                                                                    | 8  |
| 5 Measurement apparatus .....                                                                                        | 9  |
| 5.1 Mandrel or base plate .....                                                                                      | 9  |
| 5.2 Cryostat and support of mandrel or base plate .....                                                              | 9  |
| 6 Specimen preparation.....                                                                                          | 10 |
| 7 Data acquisition and analysis .....                                                                                | 11 |
| 7.1 Data acquisition hardware.....                                                                                   | 11 |
| 7.2 Resistance ( $R_1$ ) at room temperature .....                                                                   | 11 |
| 7.3 Residual resistance ( $R_2$ ) just above the superconducting transition.....                                     | 12 |
| 7.4 Validation of the residual resistance measurement.....                                                           | 13 |
| 7.5 Residual resistance ratio.....                                                                                   | 13 |
| 8 Uncertainty of the test method .....                                                                               | 13 |
| 9 Test report.....                                                                                                   | 14 |
| 9.1 General.....                                                                                                     | 14 |
| 9.2 Test information.....                                                                                            | 14 |
| 9.3 Specimen information .....                                                                                       | 14 |
| 9.4 Test conditions .....                                                                                            | 14 |
| 9.5 RRR value .....                                                                                                  | 14 |
| Annex A (informative) Additional information relating to the measurement of RRR .....                                | 15 |
| A.1 Considerations for specimens and apparatus.....                                                                  | 15 |
| A.2 Considerations for specimen mounting orientation .....                                                           | 16 |
| A.3 Alternative methods for increasing temperature of specimen above<br>superconducting transition temperature ..... | 16 |
| A.3.1 General .....                                                                                                  | 16 |
| A.3.2 Heater method.....                                                                                             | 16 |
| A.3.3 Controlled methods.....                                                                                        | 16 |
| A.4 Other test methods .....                                                                                         | 16 |
| A.4.1 General .....                                                                                                  | 16 |
| A.4.2 Measurement of resistance versus time .....                                                                    | 17 |
| A.4.3 Comparison of ice point and room temperature.....                                                              | 17 |
| A.4.4 Extrapolation of the resistance to 4,2 K .....                                                                 | 17 |
| A.4.5 Use of magnetic field to suppress superconductivity at 4,2 K .....                                             | 18 |
| A.4.6 AC techniques .....                                                                                            | 18 |
| Annex B (informative) Uncertainty considerations .....                                                               | 19 |
| B.1 Overview.....                                                                                                    | 19 |
| B.2 Definitions.....                                                                                                 | 19 |
| B.3 Consideration of the uncertainty concept .....                                                                   | 20 |
| B.4 Uncertainty evaluation example for IEC TC 90 standards.....                                                      | 22 |
| Annex C (informative) Uncertainty evaluation for resistance ratio measurement of Nb<br>superconductors .....         | 24 |

|       |                                                                                                               |    |
|-------|---------------------------------------------------------------------------------------------------------------|----|
| C.1   | Evaluation of uncertainty.....                                                                                | 24 |
| C.1.1 | Room temperature measurement uncertainty.....                                                                 | 24 |
| C.1.2 | Cryogenic measurement uncertainty.....                                                                        | 25 |
| C.1.3 | Estimation of uncertainty for typical experimental conditions.....                                            | 27 |
| C.2   | Inter-laboratory comparison summary.....                                                                      | 28 |
|       | Bibliography.....                                                                                             | 29 |
|       |                                                                                                               |    |
|       | Figure 1 – Relationship between temperature and resistance near the superconducting transition.....           | 8  |
|       | Figure A.1 – Determination of the value of $R_2$ from a resistance versus time plot.....                      | 17 |
|       | Figure C.1 – Graphical description of the uncertainty of regression related to the measurement of $R_2$ ..... | 27 |
|       |                                                                                                               |    |
|       | Table B.1 – Output signals from two nominally identical extensometers.....                                    | 20 |
|       | Table B.2 – Mean values of two output signals.....                                                            | 20 |
|       | Table B.3 – Experimental standard deviations of two output signals.....                                       | 21 |
|       | Table B.4 – Standard uncertainties of two output signals.....                                                 | 21 |
|       | Table B.5 – Coefficients of variation of two output signals.....                                              | 21 |
|       | Table C.1 – Uncertainty of measured parameters.....                                                           | 27 |
|       | Table C.2 – RRR values obtained by inter-laboratory comparison using liquid helium.....                       | 28 |

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## SUPERCONDUCTIVITY –

**Part 23: Residual resistance ratio measurement –  
Residual resistance ratio of cavity-grade Nb superconductors**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 61788-23 has been prepared by IEC technical committee 90: Superconductivity. It is an International Standard.

This third edition cancels and replaces the second edition published in 2021. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) The principle is changed to represent the present test method.

The text of this International Standard is based on the following documents:

| Draft       | Report on voting |
|-------------|------------------|
| 90/515/FDIS | 90/519/RVD       |

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at [www.iec.ch/members\\_experts/refdocs](http://www.iec.ch/members_experts/refdocs). The main document types developed by IEC are described in greater detail at [www.iec.ch/publications](http://www.iec.ch/publications).

A list of all parts in the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under [webstore.iec.ch](http://webstore.iec.ch) in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

**IMPORTANT – The 'color inside' logo on the cover page of this publication indicates that it contains colors which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a color printer.**

## INTRODUCTION

High-purity niobium is the chief material used to make superconducting radio-frequency cavities. Similar grades of niobium can be used in the manufacture of superconducting wire. Procurement of raw materials and quality assurance of delivered products often use the residual resistance ratio (RRR) to specify or assess the purity of a metal. RRR is defined for non-superconducting metals as the ratio of electrical resistance measured at room temperature (293 K) to the resistance measured for the same specimen at low temperature ( $\sim 4,2$  K). The low-temperature value is often called the residual resistance. Higher purity is associated with higher values of RRR.

Niobium presents special problems due to its transformation to a superconducting state at  $\sim 9$  K, so DC electrical resistance is effectively zero below this temperature. The definition above would then yield an infinite value for RRR. This document describes a test method to determine the residual resistance value by using a plot of the resistance to temperature as the test specimen is gradually warmed through the superconducting transition in the absence of an applied magnetic field. This results in a determination of the residual resistance at just above superconducting transition,  $\sim 10$  K, from which RRR is subsequently determined.

International Standards also exist to determine the RRR of superconducting wires. In contrast to superconducting wires, which are usually a composite of a superconducting material and a non-superconducting material and the RRR value is representative of only the non-superconducting component, here the entire specimen is composed of superconducting niobium. Frequently, niobium is procured as a sheet, bar or rod, and not as a wire. For such forms, test specimens will likely be a few millimetres in the dimensions transverse to electric current flow. This difference is significant when making electrical resistance measurements, since niobium samples will likely be much longer than that for the same length-to-diameter ratio as a wire, and higher electrical current can be required to produce sufficient voltage signals. Guidance for sample dimensions and electrical connections is provided in Annex A. Test apparatus should also take into consideration aspects such as the orientation of a test specimen relative to the liquid helium surface, accessibility through ports on common liquid helium dewars, design of current contacts, and minimization of thermal gradients over long specimen lengths. These aspects distinguish this document from similar wire standards.

Other test methods have been used to determine RRR. Some methods use a measurement at a temperature other than 293 K for the high resistance value. Some methods use extrapolations at 4,2 K in the absence of an applied magnetic field for the low resistance value. Other methods use an applied magnetic field to suppress superconductivity at 4,2 K. A comparison between this document and some other test methods is presented in Annex A. Note that systematic differences of up to 10 % are produced by these other methods, which is larger than the target uncertainty of this document. It is therefore important to apply this document or the appropriate corrections listed in Annex A according to the test method used.

Whenever possible, this test method should be transferred to vendors and collaborators who also perform RRR measurements. To promote consistency, the results of inter-laboratory comparisons are described in Clause C.2.

## SUPERCONDUCTIVITY –

### Part 23: Residual resistance ratio measurement – Residual resistance ratio of cavity-grade Nb superconductors

#### 1 Scope

This part of IEC 61788 addresses a test method for the determination of the residual resistance ratio (RRR),  $r_{RRR}$ , of cavity-grade niobium. This method is intended for high-purity niobium grades with  $150 < r_{RRR} < 600$ . The test method is valid for specimens with rectangular or round cross-section, cross-sectional area greater than 1 mm<sup>2</sup> but less than 20 mm<sup>2</sup>, and a length not less than 10 nor more than 25 times the width or diameter.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary – Part 815: Superconductivity* (available at: <https://www.electropedia.org/>)

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-815 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

##### 3.1

##### **residual resistance ratio RRR**

$r_{RRR}$

ratio of resistance at room temperature to the resistance just above the superconducting transition

$$r_{RRR} = R_1 / R_2 \quad (1)$$

where

$R_1$  is the resistance at room temperature, 293 K;

$R_2$  is the resistance just above the superconducting transition, at ~10 K.