

Plastics piping systems for industrial applications — Poly(vinylidene fluoride) (PVDF) — Specifications for components and the system

ICS 23.040.01

National foreword

This British Standard is the UK implementation of EN ISO 10931:2005+A1:2015. It is identical to ISO 10931:2005, incorporating amendment 1:2015. It supersedes BS EN ISO 10931:2005, which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee PRI/88, Plastics piping systems, to Subcommittee PRI/88/2, Plastics piping for pressure applications.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2008

© The British Standards Institution 2015.
Published by BSI Standards Limited 2015

ISBN 978 0 580 83383 0

Amendments/corrigenda issued since publication

Date	Comments
31 August 2015	Implementation of ISO amendment 1:2015 with CEN endorsement A1:2015. Table A.3 updated

English Version

Plastics piping systems for industrial applications -
Poly(vinylidene fluoride) (PVDF) - Specifications for components
and the system (ISO 10931:2005)

Systèmes de canalisations en matières plastiques pour les
applications industrielles - Poly(fluorure de vinylidène)
(PVDF) - Spécifications pour les composants et le système
(ISO 10931:2005)

Kunststoff-Rohrleitungssysteme für industrielle
Anwendungen - Polyvinyliden Fluorid - Anforderungen an
Rohrleitungsteile und das Rohrleitungssystem (ISO
10931:2005)

This European Standard was approved by CEN on 28 November 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 10931:2005) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2006, and conflicting national standards shall be withdrawn at the latest by June 2006.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 10931:2005 has been approved by CEN as EN ISO 10931:2005 without any modifications.

European foreword to amendment A1

This document (EN ISO 10931:2005/A1:2015) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems" the secretariat of which is held by NEN.

This Amendment to the European Standard EN ISO 10931:2005 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 10931:2005/Amd 1:2015 has been approved by CEN as EN ISO 10931:2005/A1:2015 without any modification.

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	2
3 Terms and definitions.....	3
4 Symbols and abbreviated terms	6
5 Material	7
6 General characteristics — Appearance.....	9
7 Geometrical characteristics.....	9
8 Mechanical characteristics	10
9 Physical characteristics	11
10 Chemical characteristics	11
11 Electrical characteristics	11
12 Performance requirements	11
13 Classification of components.....	12
14 Design of a thermoplastics piping system for industrial applications	12
15 Installation of piping systems	13
16 Declaration of compliance with this International Standard.....	13
17 Marking	13
18 Manufacture.....	15
Annex A (informative) Specific characteristics and requirements for industrial piping systems made from poly(vinylidene fluoride) (PVDF).....	16
Annex ZA (informative) Relationship between this International Standard and the Essential Requirements of EU Directive 97/23/EC (PED).....	35
Bibliography	34

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10931 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 3, *Plastics pipes and fittings for industrial applications*.

This first edition of ISO 10931 cancels and replaces ISO 10931-1:1997, ISO 10931-2:1997, ISO 10931-3:1996, ISO 10931-4:1997 and ISO 10931-5:1998, of which it constitutes a technical revision.

Introduction

This International Standard specifies the characteristics and requirements for a piping system and its components made from poly(vinylidene fluoride) (PVDF) intended to be used for industrial applications, above-ground, by authorities, design engineers, certification bodies, inspection bodies, testing laboratories, manufacturers and users.

At the date of publication of this International Standard, International Standards for piping systems of other plastics used for industrial applications were ISO 15493, for acrylonitrile-butadiene-styrene (ABS), unplasticized poly(vinyl chloride) (PVC-U), chlorinated poly(vinyl chloride) (PVC-C) and ISO 15494, for polybutene (PB), polyethylene (PE), polypropylene (PP).

Plastics piping systems for industrial applications — Poly(vinylidene fluoride) (PVDF) — Specifications for components and the system

IMPORTANT — Requirements for industrial valves are given in this International Standard and/or in other International Standards. Valves may be used with components conforming to this International Standard provided they conform additionally to its relevant requirements. Where existent, national regulations for specific applications (e.g. water treatment) apply. Other application areas are permitted if the requirements of this International Standard and/or applicable national requirements are fulfilled. Relevant regulations in respect of fire behaviour and explosion risk are applicable if applications are envisaged for inflammable media. Components conforming to any of the product standards listed in the Bibliography or to national standards, as applicable, may be used with components conforming to this International Standard, provided they conform to the requirements for joint dimensions and the relevant requirements of this International Standard.

1 Scope

This International Standard specifies the characteristics and requirements for components such as pipes, fittings and valves made from poly (vinylidene fluoride) (PVDF), intended to be used for thermoplastics piping systems in the field of industrial applications above-ground.

It is applicable to PVDF pipes, fittings, valves and ancillary equipment, their joints and to joints with components of other plastics and non-plastics materials, depending on their suitability, intended to be used for the conveyance of liquid and gaseous fluids as well as of solid matters in fluids for industrial applications including

- chemical plants,
- industrial sewerage engineering,
- power engineering (cooling and general purpose water),
- electroplating and pickling plants,
- semiconductor industry,
- agricultural production plants, and
- water treatment.

This International Standard is applicable to PVDF piping systems for use at temperatures up to 150 °C. However, for applications above 120 °C, which depend upon the crystalline melting point of the PVDF material, it is advisable to seek the advice of the manufacturer of the component (the components have to withstand the mechanical, thermal and chemical demands to be expected and to be resistant to the fluids to be conveyed).

Characteristics and requirements which are applicable for PVDF in general are covered by the relevant clauses of this International Standard. Those characteristics and requirements which depend on the material used are given in Annex A.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7-1, *Pipe threads where pressure-tight joints are made on the threads — Part 1: Dimensions, tolerances and designation*

ISO 228-1, *Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation*

ISO 265-1, *Pipes and fittings of plastics materials — Fittings for domestic and industrial waste pipes — Basic dimensions: Metric series — Part 1: Unplasticized poly(vinyl chloride) (PVC-U)*

ISO 472, *Plastics — Vocabulary*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1167:1996, *Thermoplastics pipes for the conveyance of fluids — Resistance to internal pressure — Test method*. Incorporating ISO 1167:1996/Cor 1:1997

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 2505-1:1994, *Thermoplastics pipes — Longitudinal reversion — Part 1: Determination methods*

ISO 2505-2:1994, *Thermoplastics pipes — Longitudinal reversion — Part 2: Determination parameters*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 4065, *Thermoplastics pipes — Universal wall thickness table*

ISO 9080:2003, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO/TR 10358, *Plastics pipes and fittings — Combined chemical-resistance classification table*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11922-1:1997, *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances — Part 1: Metric series*

ISO 12092:2000, *Fittings, valves and other piping system components made of unplasticized poly(vinyl chloride) (PVC-U), chlorinated poly(vinyl chloride) (PVC-C), acrylonitrile-butadiene-styrene (ABS) and acrylonitrile-styrene-acrylester (ASA) for pipes under pressure — Resistance to internal pressure — Test method*

ISO 15853:1999, *Thermoplastic materials — Preparation of tubular test pieces for the determination of the hydrostatic strength of materials used for injection moulding*

ISO 12162:1995, *Thermoplastics materials for pipes and fittings for pressure applications — Classification and designation — Overall service (design) coefficient*

ISO 16135, *Industrial valves — Ball valves of thermoplastics materials* ¹⁾

ISO 16136, *Industrial valves — Butterfly valves of thermoplastics materials* ¹⁾

ISO 16137, *Industrial valves — Check valves of thermoplastics materials* ¹⁾

ISO 16138, *Industrial valves — Diaphragm valves of thermoplastics materials* ¹⁾

ISO 16139, *Industrial valves — Gate valves of thermoplastics materials* ¹⁾

ISO 21787, *Industrial valves — Globe valves of thermoplastics materials*

IEC 60364-1, *Electrical installations of buildings — Part 1: Scope, object and fundamental principles*

IEC 60449, *Voltage bands for electrical installations of buildings*

IEC 60529, *Degrees of protection provided by enclosures (IP-code)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 1043-1, and the following apply.

3.1 Geometrical definitions

NOTE The symbols d_e and e correspond to d_{ey} and e_y given in other International Standards such as ISO 11922-1.

3.1.1

nominal outside diameter

d_n

specified outside diameter of a component which is identical to the minimum mean outside diameter, $d_{em,min}$, in millimetres

NOTE The nominal inside diameter of a socket is equal to the nominal outside diameter of the corresponding pipe.

3.1.2

outside diameter at any point

d_e

measured outside diameter through the cross-section at any point of a pipe or the spigot end of a fitting, rounded up to the next 0,1 mm

3.1.3

mean outside diameter

d_{em}

measured length of the outer circumference of a pipe or the spigot end of a fitting divided by π ($\approx 3,142$), rounded up to the next 0,1 mm

3.1.4

mean inside diameter of a socket

arithmetical mean of two measured inside diameters perpendicular to each other

1) To be published.

3.1.5

nominal size of flange

DN

numerical designation of the size of a flange, used for reference purposes and related to the manufacturing dimension in millimetres

3.1.6

out-of-roundness

⟨pipe/spigot end of fitting⟩ difference between the measured maximum outside diameter and the measured minimum outside diameter in the same cross section of a pipe or the spigot end of a fitting

3.1.7

out-of-roundness

⟨socket⟩ difference between the measured maximum inside diameter and the measured minimum inside diameter in the same cross section of a socket

3.1.8

nominal wall thickness

e_n
wall thickness, in millimetres, corresponding to the minimum wall thickness, $e_{\min}$

3.1.9

wall thickness at any point

e
measured wall thickness at any point around the circumference of a component, rounded up to the next 0,1 mm

3.1.10

pipe series S

S

dimensionless number related to the nominal outside diameter, d_n , and the nominal wall thickness, e_n

NOTE 1 The pipe series S is related to a given pipe geometry as shown in Equation (1):

$$S = \frac{d_n - e_n}{2e_n} \quad (1)$$

NOTE 2 Flanges are designated on the basis of PN.

3.1.11

standard dimension ratio

SDR

ratio of the nominal outside diameter, d_n , of a pipe to its nominal wall thickness, e_n

NOTE According to ISO 4065, the standard dimension ratio, SDR, and the pipe series S are related as shown in Equation (2):

$$SDR = 2S + 1 \quad (2)$$

3.2 Material definitions

3.2.1

virgin material

material in a form such as granules or powder that has not been subjected to use or processing other than that required for its manufacture and to which no reprocessable or recyclable materials have been added

3.2.2

own reprocessable material

material prepared from rejected unused pipes, fittings and valves, including trimmings from the production of pipes, fittings and valves, that will be reprocessed in a manufacturer's plant after having been previously processed by the same manufacturer by a process such as moulding or extrusion and for which the complete formulation or material specification is known

NOTE Only those thermoplastics parts of valves made from material conforming to this International Standard are used.

3.3 Definitions related to material characteristics

3.3.1

lower confidence limit

σ_{LCL}

quantity, expressed in megapascals, which can be considered as a material property, representing the 97,5 % lower confidence limit of the predicted long-term hydrostatic strength for water at a given temperature, T , and time, t

3.3.2

minimum required strength

MRS

value of σ_{LCL} for water at 20 °C for 50 years, rounded to the next lower value of the R10 series when σ_{LCL} is less than 10 MPa, or to the next lower value of the R20 series when σ_{LCL} is ≥ 10 MPa

NOTE The R10 and R20 series are given in ISO 3 and ISO 497.

3.3.3

design stress

σ_s

allowable stress, in megapascals, for a given application or service condition

NOTE It is derived by dividing the MRS by the coefficient C , as given in Equation (3), then rounding to the next lower value of the R10 series or R 20 series, as applicable:

$$\sigma_s = \frac{MRS}{C} \quad (3)$$

3.3.4

overall service coefficient design coefficient

C

overall coefficient with a value greater than one which takes into consideration service conditions as well as the properties of the components of a piping system other than those represented in the lower confidence limit, σ_{LCL}

3.4 Definitions related to service conditions

3.4.1

nominal pressure

PN

numerical designation used for reference purposes related to the mechanical characteristics of the components of a piping system

NOTE 1 A pressure, in bar, with the numerical value of PN is identical to the pressure, p_s , as defined by EU Directive 97/23/ECC (PED), if both pressures are taken at 20 °C.

NOTE 2 For plastics piping systems conveying water, it corresponds to the maximum continuous operating pressure, in bar, which can be sustained for water at 20 °C for 50 years, based on the minimum overall service/design coefficient and calculated using Equation (4):

$$PN = \frac{10\sigma_s}{S} = \frac{20\sigma_s}{SDR - 1} \quad (4)$$

where

σ_s is the design stress, expressed in newtons per square millimetre;

PN is expressed in bar ²⁾.

3.4.2 **hydrostatic stress**

σ
stress induced in the wall of a pipe when an internal hydrostatic pressure is applied

NOTE The hydrostatic stress, in megapascals, is related to the applied internal hydrostatic pressure, p , the wall thickness, e , at any point and the mean outside diameter, d_{em} , of a pipe and calculated using Equation (5):

$$\sigma = p \frac{d_{em} - e}{2e} \quad (5)$$

NOTE Equation (5) is applicable for pipes only.

3.4.3 **long-term hydrostatic stress**

constant hydrostatic stress that is maintained in a component during a sustained period of time

4 Symbols and abbreviated terms

4.1 Symbols

C	overall service (design) coefficient (design factor)
d	nominal outside diameter of the test piece
d_e	outside diameter (at any point)
d_{em}	mean outside diameter
d_n	nominal outside diameter
DN	nominal size of flange
e	wall thickness (at any point)
e_n	nominal wall thickness
l_0	free length
p	internal hydrostatic pressure
p_s	maximum allowable pressure

2) 1 bar = 0,1 MPa = 0,1 N/mm² = 10⁵ N/m².