

BS EN ISO 11114-1:2012+A1:2017



BSI Standards Publication

Gas cylinders — Compatibility of cylinder and valve materials with gas contents

Part 1: Metallic materials
(ISO 11114-1:2012)

bsi.

AVA Documents
Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN ISO 11114-1:2012+A1:2017. It supersedes BS EN ISO 11114-1:2012 which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to ISO text carry the number of the ISO amendment. For example, text altered by ISO amendment 1 is indicated by A1 A1.

The UK participation in its preparation was entrusted to Technical Committee PVE/3, Gas containers.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017.
Published by BSI Standards Limited 2017

ISBN 978 0 580 83956 6

ICS 23.020.35; 23.060.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2012.

Amendments/corrigenda issued since publication

Date

30 April 2017	Implementation of ISO amendment 1:2017 with CEN endorsement A1:2017
---------------	---

English Version

Gas cylinders - Compatibility of cylinder and valve materials with gas contents - Part 1: Metallic materials (ISO 11114-1:2012)

Bouteilles à gaz - Compatibilité des matériaux des bouteilles et des robinets avec les contenus gazeux - Partie 1: Matériaux métalliques (ISO 11114-1:2012)

Gasflaschen - Verträglichkeit von Werkstoffen für Gasflaschen und Ventile mit den in Berührung kommenden Gasen - Teil 1: Metallische Werkstoffe (ISO 11114-1:2012)

This European Standard was approved by CEN on 18 February 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 11114-1:2012) has been prepared by Technical Committee ISO/TC 58 "Gas cylinders" in collaboration with Technical Committee CEN/TC 23 "Transportable gas cylinders" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2012, and conflicting national standards shall be withdrawn at the latest by September 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11114-1:1997.

This European Standard has been submitted for reference into the RID and/or the technical annexes of the ADR.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 11114-1:2012 has been approved by CEN as a EN ISO 11114-1:2012 without any modification.

Foreword to amendment A1:2017

This document (EN ISO 11114-1:2012/A1:2017) has been prepared by Technical Committee ISO/TC 58 "Gas cylinders" in collaboration with Technical Committee CEN/TC 23 "Transportable gas cylinders" the secretariat of which is held by BSI.

This Amendment to the European Standard EN ISO 11114-1:2012 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2017, and conflicting national standards shall be withdrawn at the latest by August 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 11114-1:2012/Amd 1:2017 has been approved by CEN as EN ISO 11114-1:2012/A1:2017 without any modification.

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Materials	2
4.1 General	2
4.2 Cylinder materials	3
4.3 Valve materials	3
5 Compatibility criteria.....	3
5.1 General	3
5.2 Corrosion	4
5.3 Hydrogen embrittlement phenomenon	5
5.4 Generation of dangerous products	5
5.5 Violent reactions (e.g. ignition).....	5
5.6 Stress corrosion cracking	5
6 Material compatibility.....	5
6.1 Table of compatibility for single gases (see Table 1).....	5
6.2 Compatibility for gas mixtures.....	5
6.3 Using Table 1	6
Annex A (informative) Gas/materials NQSAB compatibility code	33
Bibliography.....	47

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11114-1 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 23, *Transportable gas cylinders*, in collaboration with ISO Technical Committee ISO/TC 58, *Gas cylinders*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 11114-1:1997), which has been technically revised. The main changes resulting from the revision of this part of ISO 11114 are

- the term “not recommended” has been replaced by “not acceptable”,
- the text has been clarified,
- a requirement for gas mixtures has been introduced.

ISO 11114 consists of the following parts, under the general title *Gas cylinders — Compatibility of cylinder and valve materials with gas contents*:

- *Part 1: Metallic materials*
- *Part 2: Non-metallic materials*
- *Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*
- *Part 4: Test methods for selecting metallic materials resistant to hydrogen embrittlement*

Introduction

Industrial, medical and special gases (e.g. high-purity gases, calibration gases) can be transported or stored in gas cylinders. An essential requirement of the material from which such gas cylinders and their valves are manufactured is compatibility with the gas content.

Compatibility of cylinder materials with gas content has been established over many years by practical application and experience. Existing national and international regulations and standards do not fully cover this aspect.

This part of ISO 11114 is based on current international experience and knowledge.

Where there is any conflict between this International Standard and any applicable regulation, the regulation always takes precedence.

This part of ISO 11114 has been written to be in conformity with the UN Recommendations on the Transport of Dangerous Goods: Model Regulations. When published it will be submitted to the UN Sub Committee of Experts on the Transport of Dangerous Goods with a request that it be included in the Model Regulations.

Gas cylinders — Compatibility of cylinder and valve materials with gas contents —

Part 1: Metallic materials

1 Scope

This part of ISO 11114 provides requirements for the selection of safe combinations of metallic cylinder and valve materials and cylinder gas content.

The compatibility data given is related to single gases and to gas mixtures.

Seamless metallic, welded metallic and composite gas cylinders and their valves, used to contain compressed, liquefied and dissolved gases, are considered.

NOTE In this part of ISO 11114 the term “cylinder” refers to transportable pressure receptacles, which also include tubes and pressure drums.

Aspects such as the quality of delivered gas product are not considered.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9809-1, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 1: Quenched and tempered steel cylinders with tensile strength less than 1 100 MPa*

ISO 10156, *Gases and gas mixtures — Determination of fire potential and oxidizing ability for the selection of cylinder valve outlets*

ISO 10297, *Transportable gas cylinders — Cylinder valves — Specification and type testing*

ISO 11114-2, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 2: Non-metallic materials*

ISO 11114-3, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*

ISO 11120, *Gas cylinders — Refillable seamless steel tubes for compressed gas transport of water capacity between 150 l and 3 000 l — Design, construction and testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
competent person
person who has the necessary technical knowledge, experience and authority to assess and approve materials for use with gases and to define any special conditions of use that are necessary

3.2
acceptable
A
material/gas combination that is safe under normal conditions of use, provided that any indicated non-compatibility risks are taken into account

NOTE Low levels of impurities can affect the acceptability of some single gases or gas mixtures.

3.3
not acceptable
N
material/single gas combination that is not safe under all normal conditions of use

NOTE For gas mixtures special conditions may apply (see 6.2 and Table 1).

3.4
dry
state in which there is no free water in a cylinder under any service conditions, including at the highest expected operating pressure and at the lowest expected operating temperature

NOTE For compressed gases at, for example, 200 bar and –20 °C, the maximum moisture content is not to exceed 5 ppmV, to avoid condensation of free water. For other temperatures and pressures, the maximum moisture content needed to avoid condensation of water will be different.

3.5
wet
state in which the conditions as defined for **dry** (3.4) are not met

3.6
gas mixture
combination of different single gases deliberately mixed in specified proportions

3.7
single gas
gas which does not contain deliberately added content of another gas or gases

4 Materials

4.1 General

The compatibility of most materials used to manufacture gas cylinders and valves is identified in this part of ISO 11114.

Other materials whose compatibility is not identified in this part of ISO 11114 may be used if all compatibility aspects have been considered and validated by a competent person.

4.2 Cylinder materials

The most commonly used metallic materials for cylinders are (among others) carbon manganese steel, chromium molybdenum steel, chromium molybdenum nickel steel, stainless steel and aluminium alloys, as specified in the following International Standards:

- aluminium, ISO 7866 and ISO 11118;
- steel, ISO 4706, ISO 9328-5, ISO 9809-1, ISO 9809-2, ISO 9809-3, ISO 9809-4, ISO 11118 and ISO 11120;
- aluminium alloys and stainless steel, ISO 6361-2 and ISO 15510.

4.3 Valve materials

4.3.1 General

The most commonly used metallic materials for valve bodies and internal gas wetted parts are brass and other similar copper-based alloys, carbon steel, stainless steel, nickel and nickel alloys, Cu–Be (2 %) and aluminium alloys.

4.3.2 Particular considerations

4.3.2.1 In special cases, non-compatible materials may be used for non-oxidizing gases if suitably plated, protected or coated. This may only be done if all compatibility aspects have been considered and validated by a competent person for the entire life of the valve.

4.3.2.2 Special precautions, in accordance with ISO 11114-3 (which addresses testing, not precautions per se), shall be taken for oxidizing gases as specified in ISO 10156. In this case, non-compatible materials are *not acceptable* (see 3.3) for use in valves, even if plated, protected or coated.

4.3.2.3 For cylinder valves, compatibility in wet conditions shall be considered because of the high risk of contamination by atmospheric moisture and an airborne contaminant.

NOTE Reference is made in this document to stainless steels by their commonly used AISI identification numbers, i.e. 304. For example, the equivalent grades according to EN 10088–1 are as follows:

304	1.4301	316Ti	1.4571
304L	1.4306 and 1.4307	321	1.4541
316	1.4401	904L	1.4539
316L	1.4404 		

5 Compatibility criteria

5.1 General

Compatibility between a gas and the cylinder/valve material is affected by chemical reactions and physical influences, which can be classified into five categories:

- corrosion;
- stress corrosion cracking;
- hydrogen embrittlement;

- generation of dangerous products through chemical reaction;
- violent reactions, such as ignition.

Non-metallic components (valve sealing, gland packing, O-ring, etc.) shall be in accordance with ISO 11114-2.

Sealing or lubricating materials (when used) at the valve stem shall be compatible with the gas content.

NOTE Annex A gives the gas/materials NQSAB compatibility codes, for information.

5.2 Corrosion

Many types of corrosion mechanisms can occur due to the presence of the gas, as outlined in 5.2.1 to 5.2.3.

5.2.1 Corrosion in dry conditions

This corrosion is affected by chemical attack by a dry gas on the cylinder material. The result is a reduction of the cylinder wall thickness. This type of corrosion is not very common, because the rate of dry corrosion is very low at ambient temperature.

5.2.2 Corrosion in wet conditions

This corrosion is the most common type of corrosion, which only occurs in a gas cylinder due to the presence of free water or aqueous solutions. However with some hygroscopic gases (e.g. HCl, Cl₂) corrosion would occur even if the water content were less than the saturation value. Therefore, some gas/material combinations are not recommended, even if inert in the theoretical dry conditions. It is thus very important to prevent any water ingress into gas cylinders. The most common sources of or reasons for water ingress are

- a) the customer, by retro-diffusion/backfilling or when the cylinder is empty, by air entry, if the valve is not closed,
- b) ineffective drying following hydraulic testing, and
- c) during filling.

In some cases it is very difficult to completely prevent water ingress — particularly when the gas is hygroscopic (e.g. HCl, Cl₂). In cases where the filler cannot guarantee the dryness of gas and cylinder, a cylinder material which is compatible with the wet gas shall be used, even if the dry gas is not corrosive.

There are several different types of “wet corrosion” in alloys:

- a) general corrosion leading to the reduction of the wall thickness, e.g. by acid gases (CO₂, SO₂) or oxidizing gases (O₂, Cl₂);
- b) localized corrosion, e.g. pitting corrosion or grain boundary attack.

Additionally, some gases, even inert ones, when hydrolysed could lead to the production of corrosive products.

5.2.3 Corrosion by impurities

Gases which themselves are inert (non-corrosive) can cause corrosion due to the presence of impurities. Pollution of gases can occur, during filling, during use or if the initial product is not properly purified.

The most common pollutants are

- a) atmospheric air, in which case the harmful impurities can be moisture (see also 5.2.2) and oxygen (e.g. in liquefied ammonia);

- b) aggressive products contained in some gases, e.g. H_2S in natural gas;
- c) aggressive traces (acid, mercury, etc.) remaining from the manufacturing process of some gases.

The materials compatible with the impurities shall be used if the presence of these impurities cannot be prevented and if the corresponding corrosion rate is unacceptable for the intended application.

5.3 Hydrogen embrittlement phenomenon

Embrittlement caused by hydrogen can occur at ambient temperature in the case of certain gases and under service conditions which stress the cylinder or valve material.

This type of stress cracking phenomenon can, under certain conditions, lead to the failure of gas cylinders and/or valve components containing hydrogen, mixtures of hydrogen and other gases.

5.4 Generation of dangerous products

In some cases reactions of a gas with a metallic material can lead to the generation of dangerous products. Examples are the possible reactions of C_2H_2 with copper alloys containing more than 65 % copper and of CH_3Cl in aluminium alloy cylinders.

5.5 Violent reactions (e.g. ignition)

In principle, violent reactions of gas/metallic material are not very common at ambient temperatures, because high activation energies are necessary to initiate such reactions. In the case where a combination of non-metallic and metallic materials is used, e.g. for valves, this type of reaction can occur with some gases (e.g. O_2 , Cl_2).

5.6 Stress corrosion cracking

Stress corrosion cracking can occur in many metallic materials subjected to stress, moisture and a contaminant at the same time. Stress corrosion cracking can, under certain conditions, lead to the failure of the gas cylinder or valve and/or its components (e.g. ammonia in contact with copper alloy valves or carbon monoxide/carbon dioxide mixtures in steel cylinders).

6 Material compatibility

6.1 Table of compatibility for single gases (see Table 1)

Before any gas/cylinder/valve combination is chosen a careful study of all the *key compatibility characteristics* given in Table 1 shall be made. Particular attention shall be paid to any restrictions, which shall be applied to acceptable materials.

NOTE The gases are generally listed in the table in English alphabetical order.

6.2 Compatibility for gas mixtures

Any gas mixtures containing single gases that are all compatible with a given material shall be considered as being compatible with this material.

For gas mixtures containing gases causing embrittlement (see 5.3, and Table A.3, groups 2 and 11) the risk of hydrogen embrittlement only occurs if the partial pressure of the gas is greater than 5 MPa (50 bar) and the stress level of the cylinder material is high enough. Some International Standards, such as ISO 11114-4, specify test methods for selecting appropriate steels with a maximum UTS (ultimate tensile strength) greater than 950 MPa.

 NOTE In a gas mixture, the partial pressure for hydrogen sulphide and methyl mercaptan is reduced to 0,25 MPa (2,5 bar) at a maximum UTS of 950 MPa.

For the halogenated gases non compatible with aluminium alloys cylinder, the maximum acceptable concentration in a gas mixtures shall be limited to 0,1 % as indicated in Table 1 unless higher concentrations have been validated after conducting specific tests (example of such tests are given in EIGA document 161/16 Gas compatibility with Aluminium alloy cylinder). The moisture content in these mixtures shall be limited to a maximum of 10 ppmV. 

For non-compatibility of some halogenated gases with aluminium alloys, the maximum acceptable content is given in Table 1. The level of moisture can affect the acceptability of such mixtures.

6.3 Using Table 1

6.3.1 Conventions and numbers

In Table 1, **bold face** type indicates that the material is commonly used under normal service conditions:

- A = acceptable (see 3.2);
- N = not acceptable (see 3.3).

If there is no UN number listed for a gas (or liquid), the gas has no official UN number but may be shipped using a generic NOS (not otherwise specified) number.

EXAMPLE Compressed gas, flammable, NOS, UN 1954.

6.3.2 Abbreviations for materials

CS	Carbon steels used for the manufacture of cylinder valve bodies
NS	Carbon steels heat treated by normalization that are used for the manufacture of seamless and welded cylinders
QTS	Alloy steels that are treated by quenching and tempering and that are used for the manufacture of seamless steel cylinders
SS	Austenitic type stainless steels used for the manufacture of seamless and welded cylinders and some valve bodies and valve components
AA	Aluminium alloys specified in ISO 7866 when used for the manufacture of seamless cylinders. For aluminium valve bodies, alloys not specified in ISO 7866 may also be used
B	Brass and other copper alloys used for the manufacture of cylinder valves
Ni	Nickel alloys used for the manufacture of cylinders, valves and valve components
Cu	Copper
ASB	Aluminium silicon bronze

Table 1 — Gas/material compatibility

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
1	(UN 1001) (UN 3374)	ACETYLENE	C_2H_2	Ability to form explosive acetylides with certain metals, including copper and copper alloys. Use <65 % Cu and copper alloy. This also applies to mixtures of more than 1 % C_2H_2 . The acceptable limit of the silver content of alloys should preferably be 43 % (by mass) but in no case exceeding 50 %.	NS		B	B (Cu >65 %)
					QTS		CS	
					AA		AA	Cu-Be (2 %)
					SS		SS	
					Ni		Ni	
2	(UN 1005)	AMMONIA	NH_3	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric contaminant. This applies to all gases and mixtures containing even traces of NH_3 .	NS		CS	
					QTS		SS	
					AA		AA	B
					SS		Ni	
					Ni			
3	(UN 1006)	ARGON	Ar	No reaction with any common materials in dry or wet conditions.	NS		B	
					QTS		CS	
					AA		SS	
					SS		AA	
4	(UN 2188)	ARSINE	AsH_3	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.	NS		B	
					QTS		CS	
					AA		SS	
					SS		AA	
							Ni	

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
5	(UN 1741)	BORON TRICHLORIDE	BCl_3	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	AA B
6	(UN 1008)	BORON TRIFLUORIDE	BF_3	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures containing less than 0,1 % BF_3 may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni	AA B
7	(UN 1974)	BROMOCHLORODIF- LUORO-METHANE	CBrClF_2 (R12B1)	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS QTS AA SS		B CS SS AA	
8	(UN 1009)	BROMOTRIFLUOROMETHANE	CBrF_3 (R13B1)	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS QTS AA SS		B CS SS AA	
9	(UN 2419)	BROMOTRIFLUOROETHYLENE	C_2BrF_3	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS		B	
10	(UN 1010)	BUTADIENE-1,3	$\text{H}_2\text{C}=\text{CHCH}=\text{CH}_2$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	

A1

A1

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material				
					Cylinder		Valve (body and components)		
					A	N	A	N	
11	(UN 1010)	BUTADIENE-1,2	$\text{H}_2\text{C}=\text{C}(\text{CH}_3)_2$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA		
12	(UN 1011)	BUTANE	C_4H_{10}	No reaction with common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA		
13	(UN 1012)	BUTENE-1	$\text{CH}_3\text{CH}_2\text{CH}=\text{CH}_2$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA		
14	(UN 1012)	BUTENE-2 (CIS)	$\text{CH}_3\text{CHCHCH}_3$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA		
15	(UN 1012)	BUTENE-2 (TRANS)	$\text{CH}_3\text{CHCHCH}_3$	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA		
16	(UN 1013)	CARBON DIOXIDE	CO_2	No reaction with common materials when dry. Forms acidic carbonic in the presence of water; corrosive for NS, QTS and CS. Risk (for NS and QTS) of stress corrosion cracking in presence of CO (see carbon monoxide) and water.	NS QTS AA SS		B CS SS AA		

A1

A1

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
17	(UN 1016)	CARBON MONOXIDE	CO	Risk of formation of toxic metal carbonyls. Highly sensitive to any traces of moisture [>5 ppmV at 20 MPa (200 bar)], in the presence of CO_2 (>5 ppmV). Industrial grades of carbon monoxide normally contain traces of CO_2 . This can result in risk of stress corrosion cracking, in the case of QTS, CS and NS cylinders if used at the normal service stress levels. Experience shows that this risk is eliminated if the fill pressure at 15°C is less than 50 % of the cylinder working pressure. For details, see [9] in the Bibliography. For QTS, CS, and NS steels this risk of stress corrosion cracking shall be considered for mixtures containing down to 0,1 % CO. NOTE AA and SS are not affected by this stress corrosion cracking phenomenon.	NS QTS AA SS		B CS SS AA	
18	(UN 1982)	TETRAFLUOROMETHANE (CARBON TETRAFLUORIDE)	CF_4 (R14)	No reaction with any common materials when dry but in the presence of water, corrosion may occur.	NS QTS AA SS		B CS SS AA	
19	(UN 2204)	CARBONYL SULPHIDE	COS	Risk of formation of toxic metal carbonyls at temperature $> 100^\circ\text{C}$. Highly sensitive to any traces of moisture (>5 ppmV), in the presence of CO_2 (>5 ppmV); industrial grades of carbonyl sulphide normally contain traces of CO_2 . This results in a risk of stress corrosion cracking, in the case of QTS, NS and CS. See also CO (No.17).	NS QTS AA SS		B CS SS AA	
20	(UN 1017)	CHLORINE	Cl_2	Hydrolyses to hypochlorous acid and to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. The service life of brass valves strongly depends on the operating service conditions. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA	CS B ^a SS Ni ASB	AA

^a Brass is only acceptable as valve body but not as general valve component material. ⁽⁴⁾