



BSI Standards Publication

Hygrothermal performance of building materials and products — Determination of water vapour transmission properties — Cup method

National foreword

This British Standard is the UK implementation of EN ISO 12572:2016+A1:2024. It is identical to ISO 12572:2016, incorporating amendment 1:2024. It supersedes BS EN ISO 12572:2016, which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to ISO text carry the number of the ISO amendment. For example, text altered by ISO amendment 1 is indicated by A1 A1.

The UK participation in its preparation was entrusted to Technical Committee B/540/8, Mirror committee for ISO/TC 163 - Thermal Performance and Energy use in the built Environment.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2024
Published by BSI Standards Limited 2024

ISBN 978 0 539 28838 4

ICS 91.100.01; 91.120.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2016.

Amendments/corrigenda issued since publication

Date	Text affected
31 October 2024	Implementation of ISO amendment 1:2024 with CEN endorsement A1:2024

English Version

Hygrothermal performance of building materials and
products - Determination of water vapour transmission
properties - Cup method (ISO 12572:2016)

Performance hygrothermique des matériaux et
produits pour le bâtiment - Détermination des
propriétés de transmission de la vapeur d'eau -
Méthode de la coupelle (ISO 12572:2016)

Wärme- und feuchtetechnisches Verhalten von
Baustoffen und Bauprodukten - Bestimmung der
Wasserdampfdurchlässigkeit - Verfahren mit einem
Prüfgefäß (ISO 12572:2016)

This European Standard was approved by CEN on 16 July 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 12572:2016) has been prepared by Technical Committee CEN/TC 89 “Thermal performance of buildings and building components” the secretariat of which is held by SIS, in collaboration with Technical Committee ISO/TC 163 “Thermal performance and energy use in the built environment”.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2017, and conflicting national standards shall be withdrawn at the latest by February 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 12572:2001.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 12572:2016 has been approved by CEN as EN ISO 12572:2016 without any modification.

European foreword to amendment A1

This document (EN ISO 12572:2016/A1:2024) has been prepared by Technical Committee ISO/TC 163 “Thermal performance and energy use in the built environment” in collaboration with Technical Committee CEN/TC 89 “Thermal performance of buildings and building components” the secretariat of which is held by SIS.

This Amendment to the European Standard EN ISO 12572:2016 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2025, and conflicting national standards shall be withdrawn at the latest by April 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users’ national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 12572:2016/Amd 1:2024 has been approved by CEN as EN ISO 12572:2016/A1:2024 without any modification.

Contents

Page

Foreword	v
1 Scope	1
2 Normative references	1
3 Terms, definitions, symbols, units and subscripts	1
3.1 Terms and definitions	1
3.2 Symbols and units	2
3.3 Subscripts	3
4 Principle	3
5 Apparatus	3
6 Test specimens	4
6.1 General principles for preparation of test specimens	4
6.2 Dimensions of test specimens	4
6.2.1 Shape and fit	4
6.2.2 Exposed area	4
6.2.3 Thickness of test specimens	4
6.3 Number of test specimens	5
6.4 Conditioning of test specimens	5
6.5 Testing low resistance specimens	5
7 Procedure	5
7.1 Test conditions	5
7.2 Preparation of specimen and test assembly	7
7.3 Test procedure	7
8 Calculation and expression of results	8
8.1 Mass change rate	8
8.2 Density of water vapour flow rate	9
8.3 Water vapour permeance	9
8.4 Water vapour resistance	10
8.5 Water vapour permeability	10
8.6 Water vapour resistance factor	10
8.7 Water vapour diffusion-equivalent air layer thickness	11
9 Accuracy of measurement	11
9.1 General	11
9.2 Specimen area	11
9.3 Specimen thickness	11
9.4 Sealants	12
9.5 Weighing precision	12
9.6 Control of environmental conditions	12
9.7 Variations in barometric pressure during test	12
10 Test report	12
Annex A (normative) Methods suitable for self-supporting materials	14
Annex B (normative) Methods suitable for loose fills	16
Annex C (normative) Methods suitable for membranes and foils	18
Annex D (normative) Methods suitable for mastics and sealants	19
Annex E (normative) Methods suitable for paint, varnishes, etc.	21
Annex F (normative) Correction for the effect of a masked edge of a specimen	22
Annex G (normative) Correction for resistance of air layers	24

Annex H (normative) Method for calculating the water vapour resistance of the air layer in the cup25

Annex I (informative) Weighing repeatability, weighing interval and specimen size needed to achieve desired accuracy26

Annex J (informative) Conversion table for water vapour transmission units.....27

Bibliography28

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

ISO 12572 was prepared by the European Committee Standardization (CEN) Technical Committee CEN/TC 89, *Thermal performance of buildings and building components*, in collaboration with ISO Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 1, *Test and measurement methods*, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12572:2001), which has been technically revised with the following changes:

- addition of insulation materials in the Scope;
- addition of e) humidity chamber in [Clause 5](#);
- addition of requirements regarding thickness of test specimen to measure the permeability of core materials in [6.2.3](#);
- change of specimen area size in [6.3](#);
- addition of requirements for storage time and relative humidity for condition D in [6.4](#);
- new clause with requirements in [6.5](#);
- change of requirements for temperature and relative humidity for test conditions in [7.1](#);
- change of the calculation of mass change rate in [8.1](#);
- removal of 9.8.

Hygrothermal performance of building materials and products — Determination of water vapour transmission properties — Cup method

1 Scope

This document specifies a method based on cup tests for determining the water vapour permeance of building products and the water vapour permeability of building materials under isothermal conditions. Different sets of test conditions are specified.

The general principles are applicable to all hygroscopic and non-hygroscopic building materials and products, including insulation materials and including those with facings and integral skins. Annexes give details of test methods suitable for different material types.

The results obtained by this method are suitable for design purposes, production control and for inclusion in product specifications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

There are no normative references in this document.

3 Terms, definitions, symbols, units and subscripts

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9346 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1.1

density of water vapour flow rate

mass of water vapour transferred through the specimen per area and per time

3.1.2

homogeneous material

material with properties likely to affect the transmission of water vapour which do not vary on a macroscopic scale

3.1.3

impermeable material

material with a measured *water vapour diffusion-equivalent air layer thickness* (3.1.8) greater than 1 500 m

3.1.4

water vapour permeance

density of water vapour flow rate (3.1.1) divided by the water vapour pressure difference between the two specimen faces

3.1.5**water vapour resistance**reciprocal of *water vapour permeance* (3.1.4)**3.1.6****water vapour permeability**product of the *water vapour permeance* (3.1.4) and the thickness of a homogeneous specimen

Note 1 to entry: Water vapour permeability can only be calculated for specimens of a *homogeneous material* (3.1.2).

3.1.7**water vapour resistance factor***water vapour permeability* (3.1.6) of air divided by that of the material concerned

Note 1 to entry: The water vapour resistance factor indicates how much greater the resistance of the material is compared to an equally thick layer of stationary air at the same temperature.

3.1.8**water vapour diffusion-equivalent air layer thickness**thickness of a motionless air layer which has the same *water vapour resistance* (3.1.5) as the specimen**3.2 Symbols and units**

Symbol	Quantity	Unit
A	area of specimen	m ²
G	water vapour flow rate through specimen	kg/s
R_v	gas constant for water vapour = 462	N·m/(kg·K)
S	hydraulic diameter of specimen	m
T	thermodynamic temperature	K
W_p	water vapour permeance with respect to partial vapour pressure	kg/(m ² ·s·Pa)
Z_p	water vapour resistance with respect to partial vapour pressure	m ² ·s·Pa/kg
d	mean thickness of specimen	m
g	density of water vapour flow rate	kg/(m ² ·s)
l	diameter of circle or side of square specimen	m
m	mass of specimen and cup assembly	kg
p	barometric pressure	hPa
p_0	standard barometric pressure = 1 013,25	hPa
S_d	water vapour diffusion-equivalent air layer thickness	m
t	time	s
Δp_v	water vapour pressure difference across specimen	Pa
δ_p	water vapour permeability	kg/(m·s·Pa)
δ_a	water vapour permeability of air	kg/(m·s·Pa)
μ	water vapour resistance factor	—
θ	celsius temperature	°C
φ	relative humidity	—

NOTE The above units comply with ISO 9346; a conversion table to other units commonly used in permeability measurements is given in [Annex J](#).

3.3 Subscripts

Subscript	Denoting
I	interval
r	repeatability
a	air
c	corrected for air layer
f	film
j	joint
m	membrane
me	masked edge
s	specimen
t	total

4 Principle

The test specimen is sealed to the open side of a test cup containing either a desiccant (dry cup) or an aqueous saturated solution (wet cup). The assembly is then placed in a temperature and humidity controlled test chamber. Because of the different partial vapour pressure between the test cup and the chamber, a vapour flow occurs through permeable specimens. Periodic weighings of the assembly are made to determine the rate of water vapour transmission in the steady-state.

5 Apparatus

- a) Test cups resistant to corrosion from the desiccant or salt solutions they contain; typically cups are made of glass or metal.

The design of cups suitable for testing various different types of materials is described in [Annexes A](#) to [E](#).

NOTE Circular cups can be easier to seal and transparent cups allow better control of salt solutions.

- b) For certain cups and sealing methods (see [Annex A](#)), a template, with shape and size corresponding to that of the test cup, is used when applying the sealant to give a sharply defined, reproducible test area. The template shall have an area of at least 90 % of the specimen to limit nonlinear vapour flow.
- c) Measuring instruments capable of determining specimen thickness with accuracy required in [7.2](#).
- d) Analytical balance, capable of weighing the test assembly with the repeatability needed for the required accuracy. Wherever possible, a balance of 0,001 g resolution shall be used. For heavy test assemblies, a balance resolution of 0,01 g may be sufficient (see [Annex I](#) for information linking the balance resolution to the duration of test).

NOTE The factors that affect the necessary accuracy of measurement are discussed in [Annex I](#).

- e) Constant temperature, constant humidity chamber, capable of being maintained within ± 5 % relative humidity around the set point relative humidity and $\pm 1,0$ K around the set point temperature. In order to ensure uniform conditions throughout the chamber, the air shall be stirred so as to obtain velocities between 0,02 m/s and 0,3 m/s. If highly permeable materials are being tested, means should be provided to measure the air speed directly over the upper surface of the specimen (see [Annex G](#)).
- f) Suitable sensors and a logging system to continuously record the temperature, relative humidity and, if necessary, the barometric pressure within the test chamber. The sensors shall be calibrated at regular intervals.

- g) Sealant, which is impermeable to water vapour, does not undergo physical or chemical changes during the test and does not cause physical or chemical changes to the specimen.

NOTE Examples of sealants suitable for specific materials, if necessary, are listed in the appropriate Annex.

6 Test specimens

6.1 General principles for preparation of test specimens

The test specimens shall be representative of the product. If the product has natural skins or integral facings, these may be included in the test specimen, but they shall be removed if it is intended to measure the permeability of the core material. If the skins or facings are different on the two sides, specimens shall be tested with vapour flow in the direction of the intended use. If the direction of flow is not known, duplicate specimens shall be prepared and tests carried out for each direction of flow. Unless the product to be tested is isotropic, the test specimens shall be cut so that the parallel faces are normal to the direction of vapour flow of the product in use.

Specimen preparation shall not involve methods which damage the surface in ways which affect the flow of water vapour.

6.2 Dimensions of test specimens

6.2.1 Shape and fit

Test specimens shall be cut to correspond with the dimensions of the chosen test assembly (see [Annexes A to E](#)).

6.2.2 Exposed area

The diameter of a circular specimen or the side of a square specimen shall be at least twice the specimen thickness. The exposed area (the arithmetic mean of the upper and lower free surface areas) shall be at least 0,005 m². The upper and lower free surface areas shall not differ by more than 3 % of the mean in the case of homogeneous materials and by no more than 10 % in the case of other materials.

6.2.3 Thickness of test specimens

Whenever possible, the thickness of the specimen shall be that of the product in use. In the case of homogeneous materials, if the thickness exceeds 100 mm, this may be reduced by cutting. In the case of non-homogeneous materials, such as concrete containing aggregates, the thickness should be at least three times (and preferably five times) the largest particle size.

If a material contains macroscopic formed voids, the solid material should be tested and the resistance of the whole material calculated from the proportions of solid to air space assuming one dimensional vapour flow.

If it is necessary to test a product so thick that the available test cups do not have an area large enough to comply with [6.2.2](#), the product may, only as a last resort, be sliced. In this case, all slices shall be tested and the results reported.

If it is intended to measure the permeability of the core material, all skins and facings shall be removed and the test specimens shall have a thickness of at least 20 mm.

NOTE There is a risk that this procedure leads to significant inaccuracies, especially when wet cup tests are carried out on hygroscopic materials.