BS EN ISO 12736-1:2023

BSI Standards Publication

Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment

Part 1: Validation of materials and insulation systems

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

National foreword

This British Standard is the UK implementation of EN ISO 12736-1:2023. It is identical to ISO 12736-1:2023. Together with BS EN ISO 12736-2:2023 and BS EN ISO 12736-3:2023, it supersedes BS EN ISO 12736:2014, which will be withdrawn upon publication of the rest of the series.

The UK participation in its preparation was entrusted to Technical Committee PSE/17/2, Transmission pipelines.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2023
Published by BSI Standards Limited 2023

ISBN 978 0 539 19691 7

ICS 75.180.10; 25.220.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2023.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 12736-1

October 2023

ICS 25.220.20; 75.180.10

Supersedes EN ISO 12736:2014

English Version

Oil and gas industries including lower carbon energy - Wet thermal insulation systems for pipelines and subsea equipment - Part 1: Validation of materials and insulation systems (ISO 12736-1:2023)

Industries du pétrole et du gaz, y compris les énergies à faible teneur en carbone - Systèmes d'isolation thermique en milieu humide pour conduites et équipements sous-marins - Partie 1: Validation des matériaux et des systèmes d'isolation (ISO 12736-1:2023)

Erdöl- und Erdgasindustrie - Wärmedämmschicht für Rohrleitungen und Unterwasseranlagen - Teil 1: Validierung von Materialien und Isoliersystemen (ISO 12736-1:2023)

This European Standard was approved by CEN on 1 October 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2023 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 12736-1:2023 E

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

European foreword

This document (EN ISO 12736-1:2023) has been prepared by Technical Committee ISO/TC 67 "Oil and gas industries including lower carbon energy" in collaboration with Technical Committee CEN/TC 12 “Oil and gas industries including lower carbon energy” the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2024, and conflicting national standards shall be withdrawn at the latest by April 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 12736:2014.

Any feedback and questions on this document should be directed to the users’ national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 12736-1 has been approved by CEN as EN ISO 12736-1:2023 without any modification.

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

Contents

Page

Foreword ..... **iv**

1 Scope **1**

2 Normative references **1**

3 Terms and definitions **2**

4 Symbols and abbreviated terms **7**
4.1 Symbols 7
4.2 Abbreviated terms 8

5 Conformance **9**
5.1 Rounding 9
5.2 Conformity to requirement 9

6 Material classes **9**

7 Materials and system validation testing **9**
7.1 General 9
7.2 Material validation testing 10
7.2.1 General 10
7.2.2 Small-scale exposure testing for materials 11
7.3 System validation testing 14
7.3.1 General 14
7.3.2 System test requirements 14
7.3.3 Full scale test program for systems 15
7.3.4 Small-scale full-system exposure test 17
7.4 System repairs 17
7.5 Validation of long-term performance 18
7.6 Technical validation dossier 18
7.6.1 General 18
7.6.2 Content of the validation dossier 19
7.7 Anti-corrosion coating documentation 20

Annex A (informative) **Guidelines for using this document** **21**

Annex B (normative) **Thermal conductivity testing** **26**

Annex C (normative) **Hydrostatic compressive behaviour/Tri-axial test procedures** **38**

Annex D (normative) **Simulated bend test** **45**

Annex E (normative) **System shear resistance test** **48**

Annex F (normative) **Impact test** **50**

Annex G (normative) **Simulated service test for pipelines** **53**

Annex H (normative) **Simulated service test for subsea equipment** **55**

Annex I (normative) **Small-scale full-system exposure test** **58**

Bibliography **60**

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Oil and gas industries including lower carbon energy*, Subcommittee SC 2, *Pipeline transportation systems,* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Oil and gas industries including lower carbon energy,* in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 12736-1, together with ISO 12736-2 and ISO 12736-3, cancels and replaces ISO 12736:2014.

The main changes are as follows:

— clearer delineation between validation and projects;

— introduction of material classes;

— modification of material property testing requirements, including detailed thermal conductivity testing requirements;

— introduction of additional long-term testing requirements;

— introduction of additional system testing requirements, including system interfaces;

— removal of project specific testing requirements;

— addition of requirement for risk-based analysis of the system long-term performance;

— modifications of the format and content requirements of the final validation dossier;

— addition of Annex A with guidance for using this document.

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

A list of all parts in the ISO 12736 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

Documents
Document Sharing Hub

Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment —

Part 1: Validation of materials and insulation systems

1 Scope

This document specifies requirements for the validation of wet thermal insulation systems applied to pipelines and subsea equipment in the oil and gas industry.

This document is applicable to wet thermal insulation systems submerged in seawater.

This document is not applicable to:

— maintenance works on existing installed wet thermal insulation systems;

— qualification for anti-corrosion coating;

— thermal insulation in the annulus of a steel pipe-in-pipe system.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 34-2, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 2: Small (Delft) test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 527 (all parts), *Plastics — Determination of tensile properties*

ISO 604, *Plastics — Determination of compressive properties*

ISO 844, *Rigid cellular plastics — Determination of compression properties*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 6721-1, *Plastics — Determination of dynamic mechanical properties — Part 1: General principles*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 11357-4, *Plastics — Differential scanning calorimetry (DSC) — Part 4: Determination of specific heat capacity*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 12736-2, *Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment — Part 2: Qualification processes for production and application procedures*

ISO 12736-3, *Oil and gas industries including lower carbon energy — Wet thermal insulation systems for pipelines and subsea equipment — Part 3: Interfaces between systems, field joint systems, field repairs, and pre-fabricated insulation*

ISO 15711, *Paints and varnishes — Determination of resistance to cathodic disbonding of coatings exposed to sea water*

ISO 80000-1, *Quantities and units — Part 1: General*

ASTM D575, *Standard Test Methods for Rubber Properties in Compression*

ISO 80000-1, *Quantities and units — Part 1: General*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1
agreed
specified in the purchase order

Note 1 to entry: To be discussed by the *system provider* (3.37) and *system purchaser* (3.38) with input from end user as required.

3.2
application procedure specification
APS
quality specification document, or group of specifications, describing procedures, method, equipment, tools, etc. used for *system* (3.35) application

3.3
batch
quantity of *material* (3.18) produced in a continuous manufacturing operation using raw materials of the same source or grade

3.4
blown foam
insulation *material* (3.18) formed by incorporating a gas phase into a polymer matrix

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

3.5
certificate of analysis
document provided by the manufacturer that indicates results of specific tests or analysis, including test methodology, performed on a specified lot of the manufacturer's product and corresponding conformity ranges

3.6
construction joint
interface (3.13) where both *systems* (3.35) are identical

3.7
cutback
length of item left uncoated at each end for joining purposes

Note 1 to entry: Welding is an example of joining purposes.

3.8
field joint
uncoated area that results when two pipe sections, or a pipe section and a *fitting* (3.9), with *cutbacks* (3.7) are assembled by welding or other methods

3.9
fitting
receptacle on a piece of *subsea equipment* (3.33), which interfaces to a *pipeline* (3.22)

3.10
high molecular weight precursor thermoset
material (3.18), which is a polymeric compound that remains malleable until application of sufficient heat to cause network formation and then does not flow upon reheating

EXAMPLE Butyl rubber.

3.11
inorganic syntactic foam
insulation *material* (3.18) formed by dispersing inorganic hollow particles within a polymer matrix

3.12
inspection and test plan
ITP
document providing an overview of the sequence of inspections and tests, including appropriate resources and procedures

3.13
interface
location where two *systems* (3.35) meet and affect each other

Note 1 to entry: A *field joint* (3.8) *system* (3.35) has two interfaces.

Note 2 to entry: In the case of multilayer *systems* (3.35), interfaces can be made up of multiple sub-interfaces.

3.14
jumper
short section of *pipeline* (3.22) that transfers fluid between two pieces of *subsea equipment* (3.33)

3.15
liquid precursor elastomeric thermoset
material (3.18), which is a polymeric compound with its glass transition below ambient temperature, that is produced via the combination of one or more components that can be pumped and flow as liquids and that react to create a crosslinked polymer that does not flow upon reheating

EXAMPLE Liquid precursor silicone rubber.

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

3.16
liquid precursor non-elastomeric thermoset
material (3.18), which is a polymeric compound with its glass transition above ambient temperature, that is produced via the combination of one or more components that can be pumped and flow as liquids and that react to create a crosslinked polymer that does not flow upon reheating

EXAMPLE Liquid epoxy.

3.17
mainline
portion of a *pipeline* (3.22) that is not a *field joint* (3.8)

3.18
material
polymeric compound applied to the *substrate* (3.34) protected or insulated in units of discrete thickness (layers) to build up a *system* (3.35)

3.19
material manufacturer
entity responsible for the manufacture of one or more *materials* (3.18) utilized in a *system* (3.35)

3.20
material maximum and minimum rated temperature
maximum and minimum temperature to which a particular *material* (3.18) can be continuously exposed, as per *system provider* (3.37) recommendation, during storage or in service as part of a *system* (3.35)

Note 1 to entry: For multi-layer systems, the material maximum rated temperature can be less than the *system maximum rated temperature* (3.36).

3.21
maximum rated pressure
maximum hydrostatic pressure to which the *system* (3.35) can be exposed, according to the *system provider* (3.37)

3.22
pipeline
flowline
tubular piping used to convey fluids

Note 1 to entry: Pipeline includes *jumpers* (3.14), *risers* (3.28) and *field joints* (3.8).

3.23
pre-fabricated insulation
section of stand-alone insulation, which is factory manufactured into its final form and then installed in the field by mechanically fastening or bonding to a corrosion protected structure

3.24
pre-production trial
PPT
series of tests performed immediately before the start of production, designed to demonstrate that the requirements of the *validated* (3.43) *system* (3.35), the *procedure qualification trial* (3.25) or both are achieved

Note 1 to entry: Requirements for PPT shall be as outlined in ISO 12736-2 or ISO 12736-3 and as *agreed* (3.1).

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

3.25
procedure qualification trial
PQT
series of tests designed to demonstrate that the *materials* (3.18), *system provider* (3.37), equipment and procedures can produce a *system* (3.35) in accordance with the *validation dossier* (3.44) and meet specific *project* (3.26) requirements

Note 1 to entry: Requirements for PQT shall be as outlined in ISO 12736-2 or ISO 12736-3 and as *agreed* (3.1).

3.26
project
scope of work *agreed* (3.1) upon contractually between *system purchaser* (3.38) and *system provider* (3.37)

3.27
R-lay
reel-lay
method of *pipeline* (3.22) installation in which long *stalks* (3.32) of pre-insulated pipes are pre-assembled by welding and application of *field joint* (3.8) *system* (3.35) onshore before being spooled onto large reels onboard the installation vessel, which then lays the pipes by unspooling the reel offshore

3.28
riser
vertical portion of a *pipeline* (3.22), including the bottom bend, arriving on or departing from an offshore surface installation

3.29
safety data sheet
SDS
DEPRACATED: material safety data sheet
document intended to provide workers and emergency personnel with procedures for handling and working with a *material* (3.18) utilized in the manufacture of the *system* (3.35) in a safe manner including physical data and first aid, etc.

Note 1 to entry: Physical data can include flash point and toxicity.

3.30
service life
specified period of use for a *system* (3.35) in service

3.31
solid/solid filled
insulation *material* (3.18) that systematically does not contain voids or hollow particles

3.32
stalk
continuous string of welded and *field joint* (3.8) coated pipe, which is prepared in readiness for pipe spooling onto a *R-lay* (3.27) barge

Note 1 to entry: A number of stalks will normally be required to make up a *pipeline* (3.22).

3.33
subsea equipment
components from a subsea production system, including subsea processing items and structures, meant to control hydrocarbons, not including *pipelines* (3.22)

EXAMPLE Valve, connector, manifold, christmas tree, flowline end termination.

3.34
substrate
surface to which a *material* (3.18) is applied or will be applied

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

3.35
system
all of the various *materials* (3.18) and the combination thereof, which can include layers of anti-corrosion, insulation, adhesive, and protective materials, as defined by cross-section to the underlying *substrate* (3.34) at a single point, which function together to act as a *wet thermal insulation* (3.45)

3.36
system maximum and minimum rated temperature
maximum and minimum temperature to which a particular *system* (3.35) can be continuously exposed, as per *system provider* (3.37) recommendation, during storage or in service

3.37
system provider
legal entity which is selling the applied *system* (3.35)

3.38
system purchaser
entity which is purchasing the applied *system* (3.35)

3.39
thermal conductivity
k-value
conductivity
heat flow through a unit length of *material* (3.18) under the influence of a thermal gradient

Note 1 to entry: Thermal conductivity is expressed in $W \cdot m^{-1} \cdot K^{-1}$.

3.40
thermoplastic
material (3.18), which is a polymeric compound that solidifies upon cooling and can flow and be reformed upon reheating

EXAMPLE Polypropylene.

3.41
tie-in field joint
connection of a *pipeline* (3.22) to a facility or *subsea equipment* (3.33), to other pipelines, or the connecting together of different sections of a single pipeline

3.42
U-value
overall heat transfer coefficient
rate of heat transfer from a reference surface under the influence of a thermal gradient

Note 1 to entry: U-value is expressed in $W \cdot m^{-2} \cdot K^{-1}$.

3.43
validation
demonstration of *material* (3.18) and *system* (3.35) performance during storage, handling and operation, within a specified envelope of use, as determined by the *system provider* (3.39)

3.44
validation dossier
collection of documentation and test reports, prepared in accordance with specific requirements, which provides detailed information on the proposed *system* (3.35), method of application, the *materials* (3.18) which form said *system* (3.35), and demonstration of *system* (3.35) performance

Note 1 to entry: Specific requirements are found in 7.6.

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

3.45
wet thermal insulation
system (3.35) that provides external corrosion protection and thermal insulation, and that is in direct contact with surrounding seawater

4 Symbols and abbreviated terms

4.1 Symbols

E_{kin}	impact energy (kinetic energy), expressed in joules
g	standard gravity, equivalent to 9,81 metres per seconds squared
H	pendulum height, expressed in metres
m_h	mass of hammer, expressed in kilograms
$Q_{ave,i}$	average value of heat flux transducers signals for sample *i*, where *i* = 1, 2, or 3, expressed in microvolts
Q_{lower}	lower plate heat flux transducer signal, expressed in microvolts
$Q_{Lower,Average}$	average lower plate heat flux transducer signal, expressed in microvolts
$Q_{Ref\ Mat\ ave}$	average value of heat flux transducers signals for reference material sample, expressed in watts per microvolts
$Q_{Ref\ Mat\ ave,i}$	average value of heat flux transducers signals for reference material sample *i*, where *i* = 1 or 2, and 1 is typically the thinner sample, expressed in watts per microvolts
Q_{upper}	upper plate heat flow, expressed in microvolts
$Q_{Upper,Average}$	average upper plate heat flow, expressed in microvolts
S_{Cal}	calibration factor, expressed in watts per microvolts
S_{Cal1}	single-thickness calibration factor, proportional factor between the electrical signal and heat flow, expressed in watts per microvolts
S_{Cal2}	two-thickness calibration factor, proportional factor between the electrical signal and heat flow, expressed in watts per microvolts
$S_{Cal,Lower}$	lower plate calibration factor, expressed in watts per microvolts
$S_{Cal,Upper}$	upper plate calibration factor, expressed in watts per microvolts
$\bar{R}_{ave}$	total average measured thermal resistance across all samples, expressed in metre square degrees kelvin per Watt
$R_{ave,i}$	average measured thermal resistance of sample *i*, where *i* = 1, 2, or 3, expressed in metre square degrees kelvin per Watt
R_{cal}	calibration contact resistance, expressed in metre square degrees kelvin per watt
$2R_{Cal,Lower}$	lower plate calibration contact resistance, expressed in metre square degrees kelvin per watt
$2R_{Cal,Upper}$	upper plate calibration contact resistance, expressed in metre square degrees kelvin per watt

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

$2R_{sample}$	contact resistance of the sample, expressed in metres square degrees kelvin per watt
ΔT	average temperature difference across the sample(s), expressed in degrees Celsius
T_{lower}	lower plate temperature, expressed in degrees Celsius
T_{upper}	upper plate temperature, expressed in degrees Celsius
$x_{ave,i}$	average measured thickness of sample *i*, where *i* = 1, 2, or 3, expressed in metres
$\bar{x}_{ave}$	total average measured thickness across all samples
$x_{Ref\ Mat\ ave}$	average thickness of the reference material sample, expressed in metres
$x_{Ref\ Mat\ ave,i}$	average thickness of reference material sample *i*, where *i* = 1 or 2, and 1 is typically the thinner sample, expressed in metres
$\lambda_{Ref\ Mat}$	thermal conductivity of the calibration reference material, expressed in watts per metre kelvin
$\lambda_{sampleA1}$	single thickness sample thermal conductivity, Test Type A1 specimen, expressed in watts per metre kelvin
$\lambda_{sampleA2}$	single thickness sample thermal conductivity, Test Type A2 specimen, expressed in watts per metre kelvin

4.2 Abbreviated terms

APS	application procedure specification
DMA	dynamic mechanical analysis
DSC	differential scanning calorimetry
ID	inner diameter
ITP	inspection and test plan
LVDT	linear variable differential transformer; linear variable displacement transformer; linear variable displacement transducer
OD	outer diameter
SI	International System of units
SST	simulated service test
QC	quality control
UV	ultraviolet

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

5 Conformance

5.1 Rounding

Unless otherwise stated in this document, observed or calculated values shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with ISO 80000-1.

NOTE For the purpose of this provision, the rounding method of ASTM E29 is equivalent to ISO 80000-1:2022, Annex B, Rule A.

5.2 Conformity to requirement

Systems for quality and environmental management, and the competence of testing and calibration laboratories, should be used.

NOTE The following documents can be used:

— ISO 29001 gives sector-specific requirements with guidance for the use of quality management systems;

— ISO 14001 gives requirements with guidance for the use of environmental management systems;

— ISO/IEC 17025 gives general requirements for the competence of testing and calibration laboratories.

The system provider shall be responsible for conforming with all the applicable requirements for the application of this document. The system purchaser shall be allowed to make any investigation necessary to ensure conformity by the system provider and to reject any material and/or system that does not conform with this document.

6 Material classes

The materials covered by this document are classified in Table 1. Each material used to make up the system shall be classified into the appropriate class by the system provider.

If other materials, not fitting the classes within Table 1, are used, the system provider shall identify the class that most closely represents the material and shall provide a gap analysis to the requirements for that class to be included in the validation dossier.

Table 1 — Material classes

	Solid/solid filled	Blown foam	Inorganic syntactic foam
Thermoplastics	1A	1B	1C
Liquid precursor non-elastomeric thermosets	2A	2B	2C
Liquid precursor elastomeric thermosets	3A	3B	3C
High molecular weight precursor thermosets	4A	4B	4C

7 Materials and system validation testing

7.1 General

This clause specifies the test requirements for validation of wet thermal insulation systems and for the materials used within such single or multi-layer systems.

The test data generated shall be considered when conducting a risk analysis in accordance with 7.5.

AVA Documents
Document Sharing Hub

© ISO 2023 – All rights reserved

Full document details: BS EN ISO 12736-1:2023

Material testing as described in 7.2 is based upon material maximum and minimum rated temperatures. System testing as described in 7.3 is based upon system maximum and minimum rated temperatures.

In the case of system testing (see 7.3), not all possible system variations regarding relative material layer thicknesses and build-up of multiple similar layers can be assessed during initial validation of a system. At least one representative system design, as proposed and justified by the system provider, shall be evaluated.

7.2 Material validation testing

7.2.1 General

Materials shall be tested as specified in Table 2, which specifies general properties to be tested for materials in an unexposed state, where applicable. Exposures to be performed on materials and testing to be performed post-exposure, where applicable, are described in 7.2.2. The method for sample preparation should be representative of the method used by the system supplier in manufacture of the system. If required, samples shall be machined from a larger section of material to ensure all test surfaces are representative of the through thickness of the material.

Material validation tests as specified in 7.2 are not required for materials with purely anti-corrosion and/or adhesive functionality. Validation of inter-layer adhesion performance is described in 7.3.3.2 and 7.3.4. Anti-corrosion materials are addressed in 7.7.

In the case of material types B (blown foam) and C (inorganic syntactic foam) per Table 1, both the minimum target density and the maximum target density, which can be the solid form, shall be tested for each individual material commercially offered in a range of target densities.

Table 2 — General properties and testing requirements for unexposed materials

Material property	Test specification	Applicable classes [a]												Test temperature [b]		
		Class 1			Class 2			Class 3			Class 4					
		A	B	C	A	B	C	A	B	C	A	B	C	23 °C ± 2 °C	Max	Min
Thermal conductivity	Annex B	√	√	√	√	√	√	√	√	√	√	√	√	√	√	
Specific heat capacity	ISO 11357-4	√	√	√	√	√	√	√	√	√	√	√	√	√	√	
Hydrostatic or triaxial compressive bulk modulus	Annex C	√	√	√	√	√	√	√	√	√	√	√	√	√	√	
Hydrostatic collapse pressure	Annex C			√			√			√			√	√	√	
Triaxial compression and creep performance	Annex C		√			√			√			√		selected temperatures and pressures as necessary to characterize the proposed operational window		
	Annex C at maximum rated pressure			√			√			√			√	√	√	
Density	ISO 1183 (all parts)	√	√	√	√	√	√	√	√	√	√	√	√	√		
Tensile properties	ISO 527 (all parts)	√	√	√	√	√	√							√	√	√
	ISO 37							√	√	√	√	√	√	√	√	√
Flexural properties [c]	ISO 178	√	√	√	√	√	√	√	√	√	√	√	√	√		
Tear strength	ISO 34-1 and ISO 34-2							√	√	√	√	√	√	√	√	
Notched Charpy impact strength	ISO 179-1	√	√	√	√	√	√	√	√	√				√		√
Hardness	ISO 868	√	√	√	√	√	√	√	√	√	√	√	√	√		
DSC	ISO 11357-1	√	√	√	√	√	√	√	√	√	√	√	√	Temperature range		
DMA	ISO 6721-1	√	√	√	√	√	√	√	√	√	√	√	√	Temperature range		
Compressive strength	ISO 844 or ISO 604	√	√	√	√	√	√							√	√	√
	ASTM D575							√	√	√	√	√	√	√	√	√

[a] As per Table 1.

[b] Test temperature is referenced to the material maximum and minimum rated temperatures.

[c] Required only if used for establishing the effects of wet or dry heat exposure per 7.2.2.3 and 7.2.2.4

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub

Full document details: BS EN ISO 12736-1:2023

Table 2 *(continued)*

Material property	Test specification	Applicable classes [a]												Test temperature [b]		
		Class 1			Class 2			Class 3			Class 4					
		A	B	C	A	B	C	A	B	C	A	B	C	23 °C ± 2 °C	Max	Min
Coefficient of linear thermal expansion	ISO 11359-2	√	√	√	√	√	√	√	√	√	√	√	√	Temperature range		

[a] As per Table 1.

[b] Test temperature is referenced to the material maximum and minimum rated temperatures.

[c] Required only if used for establishing the effects of wet or dry heat exposure per 7.2.2.3 and 7.2.2.4

7.2.2 Small-scale exposure testing for materials

7.2.2.1 General

The purpose of small-scale exposure testing is to provide material test data to be considered when assessing the potential risks involved with using the material under specific service conditions in accordance with 7.5.

The tests shall consider:

— water absorption and pressure effects;

— expected degradation phenomena (e.g. thermal, chemical, radiative);

— the dominant failure mechanism of the material in service.

For certain materials, physical changes can produce results in mechanical testing that are not indicative of chemical breakdown. In such cases, additional testing may be performed to understand and explain the extent and criticality of these physical changes. This may include the use of general and material specific analysis techniques that lie outside of this specification. The results of such investigative work shall be included in the validation dossier.

Four tests shall be performed:

a) determination of the potential for water absorption of each material in the insulation system (see 7.2.2.2);

b) determination of the change in the mechanical properties of each material due to water exposure (see 7.2.2.3);

c) determination of the change in the mechanical properties of each material due to dry heat exposure (see 7.2.2.4);

d) demonstration that the material of the outer-most layer of the system is resistant to UV exposure, if applicable (see 7.2.2.5).

7.2.2.2 Water absorption test

Water absorption at temperature and pressure shall be established by evaluating for changes in sample mass.

Sample preparation shall be fully described.

Exposure media shall match that utilized in 7.2.2.3. If natural seawater is used, the composition shall be analysed and the results shall be included in the test report. Exposure media shall be replaced at each sampling period.

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

The water absorption test shall be performed taking into account the following conditions:

a) at least four temperatures:

   1) 4 °C or 23 °C;

   2) material maximum rated temperature

   3) two additional temperatures not less than 30 °C below the material maximum rated temperature and not less than 10 °C apart, preferably:

      i. 15 °C below the material maximum rated temperature;

      ii. 30 °C below the material maximum rated temperature;

   4) if the validation envelope is to be extended by 15 °C or less, testing is only at the new material maximum rated temperature;

b) duration: 1 year;

c) pressure: sufficient to prevent boiling of exposure media for Class A materials and maximum rated pressure for Class B and C materials;

d) five samples per exposure temperature;

e) sample sizes for exposure: 50 mm × 50 mm, tested at a single thickness within a range of 2 mm to 8 mm, chosen at the discretion of the system provider;

f) minimum weighing intervals: before exposure, 1 week, 2 weeks, 1 month, 3 months, 6 months, and 12 months.

In order to ascertain the amount of water initially contained within the material under ambient conditions, an additional set of unexposed control samples may be weighed, dried in an oven maintained at 50 °C ± 5 °C for 24 hours, and re-weighed.

The exposure may utilize:

— several sets of parallel samples, one set for each sampling interval, in which case, after removal from water, the samples shall be dried with a clean dry cloth or filter paper and immediately weighed to the nearest 0,001 g within 24 hours; or

— a single set of samples, to be withdrawn for each sampling interval and, after removal from water, the samples shall be dried with a clean dry cloth or filter paper and immediately weighed to the nearest 0,001 g before being returned to the exposure medium to continue exposure within 24 hours.

7.2.2.3 Wet heat exposure

The effects of wet heat exposure shall be established by testing of tensile properties at 23 °C ± 2 °C. Flexural testing may be carried out in place of tensile testing for brittle materials.

Sample preparation shall be fully described.

Tensile and flexural testing shall be performed in accordance with the relevant International Standard as listed in Table 2. Exposure media shall be either deionized water or seawater. If artificial seawater is used, it shall be prepared in accordance with ISO 15711. If natural seawater is used, the composition shall be analysed and the results shall be included in the test report. Exposure media shall be replaced at each sampling period.

The wet heat exposure test shall be performed taking into account the following conditions:

a) at least three elevated temperatures, the same as utilized in 7.2.2.2, including the material maximum rated temperature;

© ISO 2023 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023

b) duration: 1 year;

c) pressure: greater than or equal to vapour pressure for Class A materials and maximum rated pressure for Class B and C materials;

d) five samples per exposure temperature and sampling interval;

e) minimum sampling intervals: 1 month, 3 months, 6 months, and 12 months.

Before the start of exposure, samples shall be weighed. A set of unexposed control specimens shall be tested in accordance with the relevant standard.

Before mechanical testing, samples shall be kept in water (identical to the water used for the exposure test) at 23 °C ± 2 °C for at least a period of 24 h and shall be tested immediately after being taken out of the water.

At sampling intervals, the surface of the samples shall be dried after removal from the water with a clean dry cloth or filter paper, weighed, and tested without any reconditioning (no drying of samples). Change in mass (water absorption) shall be reported along with mechanical test results.

7.2.2.4 Dry heat exposure

The effects of dry heat exposure shall be established by testing of tensile properties at 23 °C ± 2 °C. Flexural testing may be carried out in place of tensile testing for brittle materials.

Sample preparation shall be fully described.

Tensile and flexural testing shall be performed in accordance with the relevant International Standard as listed in Table 2. Exposure media shall be high purity nitrogen with a nitrogen content of ≥99,99 %. Exposure media shall be replaced at each sampling period.

The dry heat exposure test shall be performed taking into account the following conditions:

a) at least one temperature identical to the material maximum rated temperature used in 7.2.2.3;

b) duration: 1 year;

c) pressure: atmospheric;

d) five samples per exposure temperature and sampling interval;

e) minimum sampling intervals: 1 month, 3 months, 6 months, and 12 months;

f) use of a suitable exposure vessel, sealed to prevent nitrogen leakage during the exposure duration.

A set of unexposed control specimens shall be tested in accordance with the relevant standard.

Before mechanical testing, samples shall be cooled to 23 °C ± 2 °C in nitrogen for at least a period of 24 h and tested immediately after being removed from the nitrogen exposure vessel.

7.2.2.5 Weathering and UV resistance

Data shall be provided by the system provider to demonstrate that the material of the outer-most layer of the system can resist UV exposure. Alternatively, specific storage conditions or protection from atmospheric exposure shall be detailed by the system provider.

Weathering and UV resistance is a concern during storage of components or pipes and for parts exposed to atmospheric conditions. This effect is mainly superficial and concerns the outer-most layer of the system, hence underlying layers do not need to be tested.

© ISO 2023 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 12736-1:2023