

Paints and varnishes — Corrosion protection of steel structures by protective paint systems —

Part 5: Protective paint systems

The European Standard EN ISO 12944-5:1998 has the status of a British Standard

ICS 87.020; 91.080.10

National foreword

This British Standard is the English language version of EN ISO 12944-5:1998. It is identical with ISO 12944-5:1998. Together with the other seven parts of BS EN ISO 12944, it partially supersedes BS 5493:1977 which is declared obsolescent.

The UK participation in its preparation was entrusted to Technical Committee STI/27, Paint systems for metallic substrates, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

Attention is drawn to the fact that CEN and CENELEC Standards normally include an annex which lists normative references to international publications with their corresponding European publications. The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii to iv, pages 1 to 28, an inside back cover and a back cover.

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 November 1998

© BSI 1998

ISBN 0 580 30348 9

Amendments issued since publication

Amd. No.	Date	Text affected

ICS 87.020; 91.080.10

Descriptors: see ISO document

English version

Paints and varnishes - Corrosion protection of steel structures
by protective paint systems - Part 5: Protective paint systems
(ISO 12944-5:1998)

Peintures et vernis - Anticorrosion des structures en acier
par systèmes de peinture - Partie 5: Systèmes de peinture
(ISO 12944-5:1998)

Beschichtungsstoffe - Korrosionsschutz von Stahlbauten
durch Beschichtungssysteme - Teil 5:
Beschichtungssysteme (ISO 12944-5:1998)

This European Standard was approved by CEN on 13 November 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of the International Standard ISO 12944-5:1998 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1998, and conflicting national standards shall be withdrawn at the latest by November 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 12944-5:1998 was approved by CEN as a European Standard without any modification.

NOTE: Normative references to International Standards are listed in annex ZA (normative).

INTERNATIONAL STANDARD

ISO
12944-5

First edition
1998-05-15

Paints and varnishes — Corrosion protection of steel structures by protective paint systems —

Part 5: Protective paint systems

*Peintures et vernis — Anticorrosion des structures en acier par systèmes
de peinture —*

Partie 5: Systèmes de peinture



CONTENTS		Page
1	Scope	1
2	Normative references	1
3	Definitions	2
4	Types of paint.....	4
5	Paint systems	6
Annex A	Paint systems for corrosivity categories and categories for water and soil	12
Annex B	Prefabrication primers	24
Annex C	General properties of different generic types of paint.....	27
Annex ZA	Normative references to international publications with their corresponding European publications	28

Descriptors: paints, varnishes, steel construction, corrosion, corrosion prevention, protective coatings, paint coats, painting.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75% of the member bodies casting a vote.

International Standard ISO 12944-5 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 14, *Protective paint systems for steel structures*.

ISO 12944 consists of the following parts under the general title *Paints and varnishes - Corrosion protection of steel structures by protective paint systems*:

- Part 1: *General introduction*
- Part 2: *Classification of environments*
- Part 3: *Design considerations*
- Part 4: *Types of surface and surface preparation*
- Part 5: *Protective paint systems*
- Part 6: *Laboratory performance test methods*
- Part 7: *Execution and supervision of paint work*
- Part 8: *Development of specifications for new work and maintenance*

Annexes A to C of this part of ISO 12944 are for information only.

INTRODUCTION

Unprotected steel in the atmosphere, in water and in soil is subjected to corrosion that may lead to damage. Therefore, to avoid corrosion damage, steel structures are normally protected to withstand the corrosion stresses during the service life required of the structure.

There are different ways of protecting steel structures from corrosion. ISO 12944 deals with protection by paint systems and covers, in the various parts, all features that are important in achieving adequate corrosion protection. Additional or other measures are possible but require particular agreement between the interested parties.

In order to ensure effective corrosion protection of steel structures, it is necessary for owners of such structures, planners, consultants, companies carrying out corrosion protection work, inspectors of protective coatings and manufacturers of coating materials to have at their disposal state-of-the-art information in concise form on corrosion protection by paint systems. Such information has to be as complete as possible, unambiguous and easily understandable to avoid difficulties and misunderstandings between the parties concerned with the practical implementation of protection work.

This International Standard - ISO 12944 - is intended to give this information in the form of a series of instructions. It is written for those who have some technical knowledge. It is also assumed that the user of ISO 12944 is familiar with other relevant International Standards, in particular those dealing with surface preparation, as well as relevant national regulations.

Although ISO 12944 does not deal with financial and contractual questions, attention is drawn to the fact that, because of the considerable implications of inadequate corrosion protection, non-compliance with requirements and recommendations given in this standard may result in serious financial consequences.

ISO 12944-1 defines the overall scope of all parts of ISO 12944. It gives some basic terms and definitions and a general introduction to the other parts of ISO 12944. Furthermore, it includes a general statement on health, safety and environmental protection, and guidelines for using ISO 12944 for a given project.

This part of ISO 12944 gives some terms and definitions related to paint systems in combination with guidance for the selection of different types of protective paint system.

Paints and varnishes — Corrosion protection of steel structures by protective paint systems —

Part 5: Protective paint systems

1 SCOPE

This part of ISO 12944 describes the types of paint and paint system commonly used for corrosion protection of steel structures. It also provides guidance for the selection of paint systems available for different environments (see ISO 12944-2), surface preparation grades (see ISO 12944-4) and durabilities to be expected (see ISO 12944-1). The durability of paint systems is classified in terms of low, medium and high.

2 NORMATIVE REFERENCES

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 12944. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 12944 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 2808:1997	<i>Paints and varnishes - Determination of film thickness.</i>
ISO 3549:1995	<i>Zinc dust pigments for paints - Specifications and test methods.</i>
ISO 4628-1:1982	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 1: General principles and rating schemes.</i>
ISO 4628-2:1982	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 2: Designation of degree of blistering.</i>
ISO 4628-3:1982	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 3: Designation of degree of rusting.</i>
ISO 4628-4:1982	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 4: Designation of degree of cracking.</i>
ISO 4628-5:1982	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 5: Designation of degree of flaking.</i>
ISO 4628-6:1990	<i>Paints and varnishes - Evaluation of degradation of paint coatings - Designation of intensity, quantity and size of common types of defect - Part 6: Rating of degree of chalking by tape method.</i>

ISO 8501-1:1988	<i>Preparation of steel substrates before application of paints and related products - Visual assessment of surface cleanliness - Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings.</i>
ISO 8503-2:1988	<i>Preparation of steel substrates before application of paints and related products - Surface roughness characteristics of blast-cleaned steel substrates - Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel - Comparator procedure.</i>
ISO 12944-1:1998	<i>Paints and varnishes - Corrosion protection of steel structures by protective paint systems - Part 1: General introduction.</i>
ISO 12944-2:1998	<i>Paints and varnishes - Corrosion protection of steel structures by protective paints systems - Part 2: Classification of environments.</i>
ISO 12944-4:1998	<i>Paints and varnishes - Corrosion protection of steel structures by protective paint systems - Part 4: Types of surface and surface preparation.</i>
ISO 12944-6:1998	<i>Paints and varnishes - Corrosion protection of steel structures by protective paint systems - Part 6: Laboratory performance test methods.</i>

3 DEFINITIONS

This clause covers those expressions which are used in this part of ISO 12944 and not covered by ISO 12944-1.

3.1 High-build

The property of a coating material which permits the application of a coat of greater thickness than usually considered as normal for that type of coating. For the purposes of this part of ISO 12944, this means $\geq 80 \mu\text{m}$ dry film thickness.

3.2 High-solid

A term used to describe paint materials with a greater than normal volume of solids.

3.3 Compatibility

(I) of products in a paint system:

The ability of two or more products to be used in a paint system without causing undesirable effects.

(II) of a product with the substrate:

The ability of a product to be applied to a substrate without causing undesirable effects.

3.4 Priming coat(s)

The first coat(s) of a paint system, obtained by application of a primer.

Priming coats provide good adhesion to sufficiently roughened, cleaned metal and/or cleaned old coating, ensuring a sound base for and offering adhesion to the subsequent coats. They normally also provide corrosion protection during the overcoating interval and the whole service life of the paint system.

3.5 Intermediate coat(s)

Coat(s) between priming and top coat(s).

NOTE 1 In the English language, the term "undercoat" is sometimes used synonymously, normally for a coat applied directly before the top coat(s).

3.6 Top coat(s)

The last coat(s) of a paint system, designed to protect the coats beneath from the environment, to contribute to the overall corrosion protection offered by the system and to give the requisite colour.

3.7 Tie coat

A coat designed to improve intercoat adhesion and/or avoid certain defects during application.

3.8 Stripe coat

A supplementary coat applied to ensure adequate protection of critical areas like edges, welds etc.

3.9 Dry film thickness (DFT)

The thickness of a coating remaining on the surface when the coating has hardened.

3.10 Nominal dry film thickness (NDFT)

The dry film thickness specified for each coat or for the whole paint system to achieve the required durability.

3.11 Maximum dry film thickness

The highest acceptable dry film thickness above which the performance of the paint or the paint system may be impaired.

3.12 Primer

A paint that has been formulated for use as a priming coat on prepared surfaces, commonly under subsequent coats.

3.13 Pre-fabrication primer

A fast-drying paint that is applied to the blast-cleaned steel of a structure to protect the steel during fabrication while still allowing the steel to be welded.

NOTE 2 In many languages, the term pre-fabrication primer does not have the same meaning as in English.

3.14 Pot life

The maximum time during which a coating material supplied as separate components should be used after they have been mixed together.

3.15 Shelf life

The time during which a coating material will remain in good condition when stored in its original sealed containers under normal storage conditions.

NOTE 3 The expression "normal storage conditions" is usually understood to mean storage between +3 °C and +30 °C.

3.16 VOC (volatile organic compound)

Fundamentally, any organic liquid and/or solid that evaporates spontaneously at the prevailing temperature and pressure of the atmosphere with which it is in contact.

As to current usage of the term VOC in the field of coating materials see 3.17.

3.17 VOC content (volatile organic compound content/VOCC)

The mass of the volatile organic compounds present in a coating material, as determined under specified conditions.

NOTE 4 The exact interpretation of the word "volatile" will depend on the sphere of application of the coating material and the conditions at the place of application. For each sphere of application, the limiting values of the VOC content and the methods of determination or calculation are stipulated by regulations or by agreements.

4 TYPES OF PAINT

The following generic types of paint are widely used in paint systems for the protection of steel structures against corrosion. Typical binders for these paints are mentioned in the following sub-clauses. Many other modifications or combinations of them will also be possible.

NOTE 5 The information given hereafter concerns only the chemical and physical properties of paints and not the way they are used. The limits given for drying and curing temperatures are indicative only. Variations can be expected for each type of paint depending on its formulation.

4.1 Air drying paints

The film hardens by evaporation of organic solvents or water followed by reaction of the binder with oxygen in the air.

Typical binders are:

- alkyd;
- urethane alkyd;
- epoxy ester.

The drying time will depend, among other things, on the temperature. The reaction with oxygen can take place down to 0 °C, although at low temperatures it is much slower.

4.2 Physically drying paints

Formulations of these paints can be solvent-borne or water-borne.

4.2.1 Solvent-borne paints

The film dries by evaporation of the solvents. The process is reversible, i.e. the dry film remains soluble in its original solvents.

Typical binders are:

- chlorinated rubber;
- vinyl chloride copolymers (also known as PVC);
- acrylic resins;
- bitumen.

The drying time will depend, among other things, on air movement and temperature. Drying can take place down to 0 °C, although at low temperatures it is much slower.

4.2.2 Water-borne paints

In these paints the binder is dispersed in water.

The film hardens by evaporation of water and film-forming (coalescence) of the dispersed binder.

The process is not reversible, i.e. this type of coating is not redispersible in water after drying.