

BS EN ISO 1716:2010



BSI Standards Publication

Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value) (ISO 1716:2010)

bsi.

...making excellence a habit.
AVA Documents™
Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN ISO 1716:2010. It supersedes BS EN ISO 1716:2002 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee FSH/21/1, Reaction to fire tests - European fire test methods including ignitability tests.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2010

ISBN 978 0 580 60498 0

ICS 13.220.50; 91.100.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2010.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Reaction to fire tests for products - Determination of the gross heat of combustion (calorific value) (ISO 1716:2010)

Essais de réaction au feu de produits - Détermination du pouvoir calorifique supérieur (valeur calorifique) (ISO 1716:2010)

Prüfungen zum Brandverhalten von Bauprodukten - Bestimmung der Verbrennungswärme (des Brennwertes) (ISO 1716:2010)

This European Standard was approved by CEN on 26 May 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 1716:2010) has been prepared by Technical Committee ISO/TC 92 "Fire safety" in collaboration with Technical Committee CEN/TC 127 "Fire safety in buildings" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2010, and conflicting national standards shall be withdrawn at the latest by December 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1716:2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 1716:2010 has been approved by CEN as a EN ISO 1716:2010 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle.....	3
5 Test apparatus	3
5.1 General	3
5.2 Calorimetric bomb, constructed with the following characteristics	3
5.3 Calorimeter	3
6 Reagents and materials	4
7 Test specimens.....	5
7.1 General	5
7.2 Sampling.....	5
7.3 Determination of surface density	6
7.4 Grinding.....	6
7.5 Type of specimen	6
7.6 Conditioning	6
7.7 Number of test specimens.....	6
7.8 Determination of mass	6
7.9 Crucible method	7
7.10 "Cigarette" method	7
8 Test procedure.....	8
8.1 General	8
8.2 Calibration procedure	8
8.3 Standard test procedure	8
9 Expression of results	9
9.1 Corrections for manual apparatus.....	9
9.2 Corrections for isothermal calorimeter (see Annex C).....	10
9.3 Calculation of the gross heat of combustion of the specimen.....	10
9.4 Calculation of the gross heat of combustion of the product.....	11
10 Test report.....	12
11 Validity of test results	13
Annex A (normative) Calculation of net heat of combustion	18
Annex B (informative) Precision of test method.....	19
Annex C (informative) Calculation by graph of the corrective term, c, necessary because of the cooling of the calorimeter.....	22
Annex D (informative) Example of determination of the gross heat of combustion of a non-homogeneous product.....	23
Bibliography.....	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1716 was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Fire initiation and growth*.

This third edition cancels and replaces the second edition (ISO 1716:2002), which has been technically revised.

Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value)

WARNING — The attention of all persons concerned with managing and carrying out this test is drawn to the fact that fire testing may be hazardous and that there is a possibility that toxic and/or harmful gases may be evolved during the test. Operational hazards may also arise during the testing of specimens, such as the possibility of an explosion, and during the disposal of test residues.

WARNING — An assessment of all the potential hazards and risks to health should be made and safety precautions should be identified and provided. Written safety instructions should be issued. Appropriate training should be given to relevant personnel. Laboratory personnel should ensure that they follow written instructions at all times.

1 Scope

This International Standard specifies a method for the determination of the gross heat of combustion (Q_{PCS}) of products at constant volume in a bomb calorimeter.

Annex A describes the calculation of the net heat of combustion (Q_{PCI}) when required.

Information on the precision of the test method is given in Annex B.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 13943, *Fire safety — Vocabulary*

EN 13238, *Reaction to fire tests for building products — Conditioning procedures and general rules for selection of substrates*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943, and the following apply.

3.1

product

material, element or component about which information is required

3.2

material

single basic substance or uniformly dispersed mixture of substances

EXAMPLE Metal, stone, timber, concrete, mineral wool with a uniformly dispersed binder and polymers.

3.3

homogeneous product

product consisting of a single material having uniform density and composition throughout the product

3.4

non-homogeneous product

product that does not satisfy the requirements of a homogeneous product and which is composed of more than one component, substantial and/or non-substantial

3.5

substantial component

material that constitutes a significant part of a non-homogeneous product, and that has a mass/unit area $\geq 1,0 \text{ kg/m}^2$ or a thickness $\geq 1,0 \text{ mm}$

3.6

non-substantial component

material that does not constitute a significant part of a non-homogeneous product and that has a layer with a mass/unit area $< 1,0 \text{ kg/m}^2$ and a thickness $< 1,0 \text{ mm}$

3.7

internal non-substantial component

non-substantial component that is covered on both sides by at least one substantial component

3.8

external non-substantial component

non-substantial component that is not covered on one side by a substantial component

3.9

heat of combustion

calorific value (deprecated)

thermal energy produced by combustion of unit mass of a given substance

NOTE The heat of combustion is expressed in megajoules per kilogram.

[ISO 13943:2008]

3.10

gross heat of combustion

Q_{PCS}

heat of combustion of a substance when the combustion is complete and any produced water is entirely condensed under specified conditions

NOTE The gross heat of combustion is expressed in megajoules per kilogram.

3.11

net heat of combustion

Q_{PCI}

heat of combustion of a substance when the combustion is complete and any produced water is in the vapour state under specified conditions

NOTE 1 The net heat of combustion may be calculated from the gross heat of combustion.

NOTE 2 The net heat of combustion is expressed in megajoules per kilogram.

3.12

latent heat of vaporization of water

q

heat which is required to change water from a liquid to a gas

NOTE The latent heat of vaporization is expressed in megajoules per kilogram.

3.13

surface density

mass per unit area

NOTE The surface density is expressed in kilograms per square metre.

4 Principle

In this test, a test specimen of specified mass is burned under standardized conditions, at constant volume, in an atmosphere of oxygen, in a bomb calorimeter calibrated by combustion of certified benzoic acid. The heat of combustion determined under these conditions is calculated on the basis of the observed temperature rise, taking account of heat loss and the latent heat of vaporization of water.

This is a test method for determining an absolute value of the heat of combustion for a product and it does not take into account any inherent variability of the product.

5 Test apparatus

5.1 General

The test apparatus (bomb calorimeter) shall be as illustrated in Figure 1, and as detailed in 5.2 to 5.5. Additional equipment shall be in accordance with 5.6 to 5.11.

5.2 Calorimetric bomb, constructed with the following characteristics

The calorimetric bomb shall be constructed as follows:

- a) volume: (300 ± 50) ml;
- b) mass not greater than 3,25 kg;
- c) casing thickness at least 1/10 of the inner diameter of the body.

The lid is intended to receive the crucible and the electric firing device. The lid, including any seals, shall be capable of withstanding an internal pressure of 21 MPa.

NOTE These conditions define a bomb in which 1 g of coal under an initial oxygen pressure no greater than 3 MPa (pressure gauge method) is able to withstand, with a sufficient coefficient of safety, the maximum amount of pressure created under combustion, without a need for a calorimetric bomb of overlarge mass.

The inner surface of the bomb shall be resistant to attack by products of combustion and, even when “fuels” rich in sulfur are used, it shall resist pitting and inter-crystalline corrosion by acids produced during combustion.

5.3 Calorimeter

5.3.1 Jacket, consisting of a double-walled container, which is thermally insulated together with an insulated lid. The jacket is filled with water. The dimensions of the jacket shall be such that there is at least 10 mm space around the calorimetric vessel. The calorimetric vessel shall be supported on an as small as possible area of non-conducting material, preferably a 3-point support.

For an adiabatic calorimeter system, a heater and thermometer system shall be incorporated into the vessel such that the water temperature in the jacket is maintained at the same temperature as the water in the calorimetric vessel.

For an isothermal calorimeter system, the temperature of the water in the jacket shall be kept constant. For an isothermal calorimeter, the necessary corrections shall be made (see 9.2).

5.3.2 Calorimetric vessel, consisting of a polished metal container designed to accommodate the bomb. The dimensions shall be such that the bomb can be immersed in water (see 8.3.7).

5.3.3 Stirrer, driven by a constant-speed motor. To prevent the transfer of heat to and from the calorimeter, the driving shaft of the stirrer shall have a thermally insulated section in a gasket between the jacket lid and the jacket. A magnetic stirring device with a similar performance is an acceptable alternative.

5.4 Temperature measuring device, capable of giving a resolution of 0,005 K.

When using a mercury thermometer, this shall have at least 0,01 K graduations with a device, e.g. a lens, for taking readings to within 0,005 K. A mechanical vibrator shall also be used to gently tap the thermometer to ensure that the mercury column does not stick.

5.5 Crucible, made of metal, such as platinum, nickel, stainless steel or silica, with a flat base, 25 mm in diameter (maximum dimension if it is truncated) and 14 mm to 19 mm high.

NOTE 1 The following wall thickness is recommended:

- metal: 1,0 mm;
- silica: 1,5 mm.

NOTE 2 Several shapes of crucible have proved satisfactory.

5.6 Timing device, capable of recording the time elapsed to the nearest second and accurate to within 1 s in 1 h.

5.7 Electric power source, with the voltage to the firing circuit not exceeding 20 V for the firing. An ammeter shall be added to the circuit to indicate the breaking of the firing wire. A circuit breaker is a useful addition to the supply circuit.

5.8 Pressure gauge and needle-valve, attached to the oxygen-supply circuit to show the pressure in the bomb while it is being filled; this pressure shall be indicated with a resolution of 0,1 MPa.

5.9 Two balances, with the following characteristics:

- one is an analytical balance with an accuracy of 0,1 mg;
- the other is a balance with an accuracy of 0,1 g.

5.10 Device for making the “cigarette”, as shown in Figure 2.

The procedure for making the “cigarette” is as shown in Figure 2 and comprises a mould and a metallic mandrel (not aluminium).

5.11 Device for making the pellet.

If prefabricated pellets are not available, a suitable device for making the pellet shall be used.

6 Reagents and materials

6.1 Distilled or demineralized water.

6.2 Pressurized oxygen, free from any other combustible product (purity $\geq 99,5\%$).

WARNING — Oxygen prepared by electrolysis can contain a small percentage of hydrogen, which makes it unsuitable for this use.

6.3 Powder or pellet of benzoic acid, “reference standard for calorimetry”, whose gross heat of combustion is guaranteed.

6.4 Combustion aid, with a known heat of combustion, e.g. paraffin oil.

6.5 Cigarette-making paper, which is preglued and of minimum dimensions 55 mm × 50 mm with a known heat of combustion.

NOTE A commercially available cigarette-making paper of 55 mm × 100 mm has been found suitable when cut into two equal pieces.

6.6 Firing wire made of pure iron, 0,1 mm in diameter, e.g. piano wire. Other types of metal wire (e.g. platinum, nickel or chromium) may be used, provided that they break under their own tension when the switch is closed on the firing circuit and the exact heat of combustion for the wire is known. When using a metal crucible (5.5), there shall be no contact between the firing wire and the crucible. It is therefore advisable to wrap the metal wire with a cotton thread.

6.7 Thread, made of white cellulosic cotton (see 6.6).

7 Test specimens

7.1 General

In order to assess a product, each of its components shall be evaluated, taking into account the rules for non-substantial components. If a non-homogeneous product cannot be delaminated, its components shall be provided separately. A product can be delaminated when it is possible to separate one component from another without any part of the other component adhering to the component to be evaluated.

If two or more non-substantial layers are adjacent to each other, and when added together they comply with the definition for a substantial component, then each individual layer shall be tested separately and they shall be assessed together as substantial. The total calorific value of the adjacent layers, which are considered substantial, shall be calculated by adding together the relative percentage of the measured calorific value for each component (see Annex D).

If two or more non-substantial layers are adjacent to each other, and when added together they comply with the definition for a non-substantial component, then each individual layer shall be tested separately and they shall be assessed together as non-substantial. (see Annex D)

WARNING — Any aluminium or other metallic component of a product shall not be tested in the bomb calorimeter, with the risk of serious injury to the operator due to overheating and/or overpressure causing the bomb calorimeter to explode.

7.2 Sampling

7.2.1 General

From a representative amount of a homogeneous product, or a component of a non-homogeneous product, compose a sample from at least five randomly selected parts taken from across the thickness. A minimum mass of 50 g shall be taken from a homogeneous product and a substantial component of a non-homogeneous product. A minimum mass of 10 g shall be taken for a non-substantial component of a non-homogeneous product.

7.2.2 Loose-fill material

A sample shall be taken at random from the product of a minimum mass of 50 g.