



BSI Standards Publication

Resistance welding - Weldability

Part 3: Evaluation procedures for weldability in
spot weld bonding (ISO 18278-3:2017)

National foreword

This British Standard is the UK implementation of EN ISO 18278-3:2017. It is identical to ISO 18278-3:2017.

The UK participation in its preparation was entrusted to Technical Committee WEE/29, Resistance welding.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017
Published by BSI Standards Limited 2017

ISBN 978 0 580 93738 5

ICS 25.160.40

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Resistance welding - Weldability - Part 3: Evaluation
procedures for weldability in spot weld bonding (ISO
18278-3:2017)

Soudage par résistance - Soudabilité - Partie 3:
Méthodes d'évaluation de l'aptitude au soudocollage
par points (ISO 18278-3:2017)

Widerstandsschweißen - Schweißseignung - Teil 3:
Verfahren zum Bewerten der Eignung für das
Widerstandspunktschweißkleben (ISO 18278-3:2017)

This European Standard was approved by CEN on 4 June 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 18278-3:2017) has been prepared by Technical Committee ISO/TC 44 “Welding and allied processes” in collaboration with Technical Committee CEN/TC 121 “Welding and allied processes” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2018, and conflicting national standards shall be withdrawn at the latest by March 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 18278-3:2017 has been approved by CEN as EN ISO 18278-3:2017 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Weld bonding equipment	2
4.1 General	2
4.2 Adhesive dispensing equipment	2
4.3 Storage chamber	2
4.4 Electrodes	2
4.5 Welding current	2
4.6 Mechanical settings	2
4.7 Measurement of parameters	2
4.7.1 Temperature	2
4.7.2 Amount of adhesive applied	2
4.7.3 Welding current and electrode force	3
4.7.4 Electrode cooling water flow rate	3
4.8 Measurement of results	3
4.8.1 Weld diameter	3
4.8.2 Detection of expulsion	3
5 Assembly preparation	3
6 Preliminary adjustments	4
6.1 Electrode alignment	4
6.2 Electrode conditioning	4
7 Determination of the welding current range	5
7.1 Test specimens	5
7.2 Welding parameters	5
7.3 Test procedure	5
7.4 Current range criteria	5
7.5 Three sheet and multiple stack-ups	6
8 Estimation of electrode life	6
8.1 Test specimens	6
8.2 Welding parameters	6
8.3 Procedure	6
8.4 Test criteria, interpretation of results	7
9 Test report	7
9.1 General	7
9.2 Welding current range	8
9.3 Electrode life	8
Annex A (informative) Electrode alignment	9
Annex B (informative) Specimens with current shunt	11
Annex C (informative) Specific conditions for steel sheet customer qualification	13
Annex D (informative) Specimens for destructive testing	16
Annex E (informative) Example of a test report for welding current range	18
Annex F (informative) Example of a test report for electrode life test	19
Bibliography	20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 6, *Resistance welding and allied mechanical joining*.

A list of all parts in the ISO 18278 series can be found on the ISO website.

Requests for official interpretations of any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 6 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This document describes procedures for evaluating the weldability of weld bonding using the resistance spot welding process by determining the welding current range and electrode life.

These procedures can be used to evaluate the following:

- a) the effect of electrode material, shape, dimensions and electrode cooling;
- b) the effect of material types and thicknesses and coatings being welded;
- c) the effect of welding conditions;
- d) the effect of welding equipment;
- e) the effect of adhesive on welding.

Resistance welding — Weldability —

Part 3:

Evaluation procedures for weldability in spot weld bonding

1 Scope

This document specifies procedures for the determination of the acceptable welding current range and the electrode life for spot weld bonding using resistance spot welding with adhesive bonding.

This document is applicable for the evaluation of the weldability of prepared assemblies of uncoated and coated metal sheets with individual thicknesses from 0,4 mm to 6,0 mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 669, *Resistance welding — Resistance welding equipment — Mechanical and electrical requirements*

ISO 5182, *Resistance welding — Materials for electrodes and ancillary equipment*

ISO 5821, *Resistance welding — Spot welding electrode caps*

ISO 14373, *Resistance welding — Procedure for spot welding of uncoated and coated low carbon steels*

ISO 17677-1, *Resistance welding — Vocabulary — Part 1: Spot, projection and seam welding*

ISO 18278-1:2015, *Resistance welding — Weldability — Part 1: General requirements for the evaluation of weldability for resistance spot, seam and projection welding of metallic materials*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669, ISO 14373, ISO 17677-1 and ISO 18278-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

spot weld bonding

resistance spot welding through an adhesive or sealant

3.2

substrate

material upon the surface of which an adhesive is spread for weld bonding

3.3

prepared assembly

set of components (substrates and adhesives) positioned prior to welding

3.4

wearing sheet

sheet which is used to produce electrode wear through continuous spot welding

4 Weld bonding equipment

4.1 General

Methods to characterize resistance welding equipment can be found in ISO 669.

The mass and friction of the movable electrode assembly can be determined in accordance with ISO 18278-1.

4.2 Adhesive dispensing equipment

The adhesive dispensing equipment shall be defined by agreement between the contracting parties.

4.3 Storage chamber

The storage chamber shall have a temperature regulation system that is sufficient to maintain the properties of the adhesive or sealant, as required by the manufacturer of the adhesive or sealant.

4.4 Electrodes

The electrode materials shall be as defined in ISO 5182. Their geometry shall be defined according to ISO 5821.

4.5 Welding current

The type of welding current used (alternating current or direct current) shall be specified before testing and recorded. Constant current control settings shall be used.

When using AC resistance welding equipment, it shall be set so that welding current is not less than 30 % of R.M.S. value at full conduction angle.

4.6 Mechanical settings

The mechanical settings shall be chosen to limit the impact of the electrode meeting the sheet.

To limit the impact of the electrode an electrode approach speed of 0,15 m/s is recommended and/or the peak force should be less than 150 % of the nominal electrode force.

The machine squeeze time should be of sufficient duration to overcome electrode bounce effects and machine inertia so as to allow the electrode force to build up to the required value before the welding current is initiated.

4.7 Measurement of parameters

4.7.1 Temperature

The ambient temperature shall be measured.

4.7.2 Amount of adhesive applied

Measurement of the amount of adhesive applied shall be carried out as defined by the contracting parties.