BS EN ISO 20088-3:2019

BSI Standards Publication

Determination of the resistance to cryogenic spillage of insulation materials

Part 3: Jet release

Documents
Document Sharing Hub

Full document details: BS EN ISO 20088-3:2019

National foreword

This British Standard is the UK implementation of EN ISO 20088-3:2019. It is identical to ISO 20088-3:2018. It supersedes BS ISO 20088-3:2018, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PSE/17/-/9, Liquefied Natural Gas (LNG) installations and equipment.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 539 03470 7

ICS 75.200

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2018.

Amendments/corrigenda issued since publication

Date	Text affected
31 October 2019	This corrigendum renumbers BS ISO 20088-3:2018 as BS EN ISO 20088-3:2019

Documents
Document Sharing Hub

Full document details: BS EN ISO 20088-3:2019

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 20088-3

October 2019

ICS 75.200

English Version

Determination of the resistance to cryogenic spillage of insulation materials - Part 3: Jet release (ISO 20088-3:2018)

Détermination de la résistance des matériaux d'isolation thermique suite à un refroidissement cryogénique - Partie 3: Émission sous forme de jet (ISO 20088-3:2018)

Bestimmung der Beständigkeit von Isoliermaterialien bei kryogenem Auslaufen - Teil 3: Freisetzung von Hochdruckstrahlen (ISO 20088-3:2018)

This European Standard was approved by CEN on 5 August 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2019 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 20088-3:2019 E

Documents
Document Sharing Hub

Full document details: BS EN ISO 20088-3:2019

European foreword

The text of ISO 20088-3:2018 has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 20088-3:2019 by Technical Committee CEN/TC 282 "Installation and equipment for LNG" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2020, and conflicting national standards shall be withdrawn at the latest by April 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 20088-3:2018 has been approved by CEN as EN ISO 20088-3:2019 without any modification.

AVA Documents
Document Sharing Hub

Full document details: BS EN ISO 20088-3:2019

Contents

Page

Foreword ... **iv**
Introduction ... **v**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **2**
4 Test configurations ... **2**
4.1 General ... 2
5 Construction of the test apparatus and substrates ... **2**
5.1 General ... 2
5.2 Material ... 3
5.3 Release nozzle ... 3
5.3.1 Nozzle construction ... 3
5.3.2 Nozzle position ... 4
5.4 Specimen support ... 4
5.5 Recirculation chamber ... 6
6 Cryogenic spill protection materials ... **6**
6.1 General ... 6
6.2 Wet applied coating systems ... 10
6.3 Preformed system testing ... 10
7 Instrumentation for test specimens ... **10**
7.1 General ... 10
7.2 Thermocouple location ... 10
8 Test environment ... **10**
9 Test procedure ... **12**
10 Repeatability and reproducibility ... **13**
11 Uncertainty of measurement ... **13**
12 Test report ... **13**
13 Practical applications of test results ... **14**
13.1 General ... 14
13.2 Performance criteria ... 14
13.2.1 General ... 14
13.2.2 Coatings and spray-applied materials ... 15
13.2.3 Systems and assemblies ... 15
13.3 Factors affecting the validity of the test ... 15
13.3.1 General ... 15
13.3.2 Failure at nozzle ... 15
13.3.3 Failure of thermocouples ... 15
Annex A (normative) **Methods of fixing thermocouples** ... **17**
Annex B (normative) **Complete set-up** ... **18**
Annex C (informative) **Classification** ... **21**
Bibliography ... **23**

© ISO 2018 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 9, *Liquefied natural gas installations and equipment*.

A list of all parts in the ISO 20088 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2018 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019

Introduction

The test is intended to be, as far as practicable, representative of a potential accidental pressurized release of cryogenic liquid natural gas (LNG) manufactured in industrial plants. The test includes:

a) an initial enhanced cooling effect due to the momentum driven liquid contact with the substrate;

b) a localized force that may be expected in a cryogenic jet release.

This test is designed to give an indication of how cryogenic spill protection systems will perform when subjected to a sudden cryogenic jet release.

The dimensions of the test specimen might be smaller than typical items of structure and plant. The liquid cryogenic jet mass flow rates can be substantially less than that which might occur in a credible event. However, the thermal and mechanical loads imparted to the cryogenic spill protection systems from the cryogenic jet release, described in this document, are representative of a cryogenic LNG jet release with hole size 20 mm or less and release pressure less than or equal to 6 barg.

© ISO 2018 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019

Determination of the resistance to cryogenic spillage of insulation materials —

Part 3:
Jet release

CAUTION — The attention of all persons concerned with managing and carrying out cryogenic spill tests is drawn to the fact that liquid nitrogen testing can be hazardous and that there is a danger of condensing liquid oxygen (fire/explosion), receiving a 'cold burn' and/or the possibility that harmful gases (risk of anoxia) can be evolved during the test. Mechanical and operational hazards can also arise during the construction of the test elements or structures, their testing and disposal of test residues. An assessment of all potential hazards and risks to health shall be made and safety precautions identified and provided. Appropriate training and Personal Protection Equipment shall be given to relevant personnel. The test laboratory is responsible for conducting an appropriate risk assessment in order to consider the impact of liquid and gaseous nitrogen exposure to equipment, personnel and the environment.

1 Scope

This document describes a method for determining the resistance of a cryogenic spill protection (CSP) system to a cryogenic jet as a result of a pressurized release which does not result in immersion conditions. It is applicable where CSP systems are installed on carbon steel and will be in contact with cryogenic fluids.

A cryogenic jet can be formed upon release from process equipment operating at pressure (e.g. some liquefaction processes utilize 40 to 60 bar operating pressure). Due to high pressure discharge, the cryogenic spillage protection can be compromised by the large momentum combined with extreme cryogenic temperature.

Although the test uses liquid nitrogen as the cryogenic liquid, the test described in this document is representative of a release of LNG, through a 20 mm orifice or less, at a release pressure of 6 barg or less, based upon simulated parameters 1 m from the release point. Confidence in this test being representative is based upon a comparison of the expected dynamic pressure of the simulated release in comparison with dynamic pressure from releases in accordance with this document.

It is not practical in this test to cover the whole range of cryogenic process conditions found in real plant conditions; in particular the test does not cover high pressure cryogenic jet releases that might be found in refrigeration circuits and in LNG streams immediately post-liquefaction.

Liquid nitrogen is used as the cryogenic medium due to the ability to safely handle the material at the pressures described in this document. The test condition is run at nominally 8 barg pressure.

ISO 20088-1 covers cryogenic release scenarios which can lead to pooling conditions for steel work protected by cryogenic spill protection as a result of a jet release or low pressure release of LNG or liquid nitrogen. ISO 20088-2 covers vapour phase exposure conditions as a result of a jet release or low pressure release of LNG or liquid nitrogen.

2 Normative references

There are no normative references in this document.

© ISO 2018 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at http://www.electropedia.org/

3.1
cryogenic jet release
unintended exposure to cryogenic liquid as a result of a pressurized release

3.2
cryogenic spill protection
CSP
coating or cladding arrangement, or free-standing system which, in the event of a cryogenic jet release, will provide insulation to restrict the heat transfer rate from the substrate

3.3
limiting temperature
minimum temperature that the equipment, assembly or structure to be protected may be allowed to reach

3.4
nozzle
assembly from which the cryogenic liquid is released as a jet

3.5
sponsor
person or organization that requests a test

3.6
specimen owner
person or company that holds/produces a material to test

4 Test configurations

4.1 General

The configuration under which the test is conducted is where the specimen is placed horizontally at height on suitable supports. The test piece is impacted at the mid-point by a horizontal liquid nitrogen cryogenic jet release. Due to safety concerns, it is proposed that the test should only be performed outside, unless there are sufficient safeguards implemented to mitigate the confined space and liquid nitrogen safety risks.

5 Construction of the test apparatus and substrates

5.1 General

The key items required for the test are:

— a nozzle and cryogenic liquid feeder assembly where the temperature and pressure of the liquid can be measured at the point the liquid enters the reducing diameter pipe to the nozzle;

— liquid nitrogen of sufficient volume for the test duration supplied from a tanker capable of offload via a pump to generate the required stable pressure at the nozzle;

— a carbon steel specimen protected with CSP;

© ISO 2018 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019

— thermocouples to determine the temperature as a function of time in the steel specimen.

5.2 Material

The steel grade used for the test is to be recorded. Where welded plate girders are used, construction is to be representative of the as-built structure. All dimensions are in millimetres and, unless otherwise stated, the following tolerances shall be used:

— whole number ± 1,0 mm;

— decimal to point ,0 ± 0,4 mm;

— decimal to point ,00 ± 0,02 mm;

— angles ± 0’ 30”;

— radius ± 0,4 mm.

Test specimens shall include as a minimum a beam of designation 406 mm × 178 mm × 60 kg/m or tubular specimen of wall thickness 6,3 mm and outer diameter between 270 mm and 350 mm (including the cryogenic spill protection material). All test specimens are to be 2,5 m in length unless otherwise agreed by the sponsor.

5.3 Release nozzle

5.3.1 Nozzle construction

Liquid nitrogen is released towards the specimen from a nozzle as shown in Figure 1. The nozzle shall be of length (150 ± 1,0) mm, constructed from 10 mm nominal diameter stainless steel pipe with outside diameter of 20 mm to 30 mm, -0,5/+0,5 mm giving a wall thickness between 5 mm and 10 mm. The nozzle shall not be tapered and the end shall be clean cut with no chamfering of pipe walls. The nozzle is fed with liquid nitrogen from a 52,5 mm diameter schedule 40 stainless steel pipe gradually reducing in internal diameter to 10 mm over a length of 200 mm to 250 mm.

© ISO 2018 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 20088-3:2019