BS EN ISO 22674:2016

BSI Standards Publication

Dentistry — Metallic materials for fixed and removable restorations and appliances (ISO 22674:2016)

bsi.

...making excellence a habit.™

Document Sharing Hub

National foreword

This British Standard is the UK implementation of EN ISO 22674:2016. It supersedes BS EN ISO 22674:2006 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CH/106/2, Prosthodontic materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 78981 6

ICS 11.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

Amendments issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS EN ISO 22674:2016

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 22674

February 2016

ICS 11.060.10

Supersedes EN ISO 22674:2006

English Version

Dentistry - Metallic materials for fixed and removable restorations and appliances (ISO 22674:2016)

Médecine bucco-dentaire - Matériaux métalliques pour les restaurations fixes et amovibles et les appareillages (ISO 22674:2016)

Zahnheilkunde - Metallische Werkstoffe für festsitzenden und herausnehmbaren Zahnersatz und Applikationen (ISO 22674:2016)

This European Standard was approved by CEN on 24 October 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2016 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 22674:2016 E

Documents
Document Sharing Hub

Full document details: BS EN ISO 22674:2016

European foreword

This document (EN ISO 22674:2016) has been prepared by Technical Committee ISO/TC 106 "Dentistry" in collaboration with Technical Committee CEN/TC 55 “Dentistry” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

This document supersedes EN ISO 22674:2006.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 22674:2016 has been approved by CEN as EN ISO 22674:2016 without any modification.

Documents
Document Sharing Hub

Full document details: BS EN ISO 22674:2016

Contents

Page

Foreword ... **v**
Introduction ... **vi**
1 Scope ... **1**
2 Normative references ... **1**
3 Terms and definitions ... **1**
4 Classification ... **3**
5 Requirements ... **4**
5.1 Chemical composition ... 4
5.1.1 Reported composition ... 4
5.1.2 Permitted deviation from the reported composition for elements ... 4
5.2 Hazardous elements ... 4
5.2.1 Hazardous elements ... 4
5.2.2 Limits for the hazardous elements cadmium and beryllium ... 4
5.2.3 Limit for lead ... 4
5.2.4 Nickel ... 5
5.3 Biocompatibility ... 5
5.4 Mechanical properties ... 5
5.4.1 General ... 5
5.4.2 Proof stress of 0,2 % non-proportional extension ... 6
5.4.3 Elongation after fracture ... 6
5.5 Elastic modulus ... 7
5.5.1 Precision of measurement method ... 7
5.5.2 Determination of compliance with the requirements for Type 5 materials ... 7
5.5.3 Mean value ... 8
5.6 Density ... 8
5.7 Corrosion resistance for material integrity ... 8
5.8 Tarnish resistance ... 8
5.9 Solidus and liquidus temperatures (alloy) or melting point (commercially pure metal) ... 8
5.10 Thermal expansion coefficient ... 8
5.11 Information, instructions and marking ... 9
6 Sampling ... **9**
7 Preparation of test specimens ... **9**
7.1 General ... 9
7.2 Heat treatment ... 9
7.2.1 General conditions ... 9
7.2.2 Metallic materials for which a heat treatment is recommended in the manufacturer's instructions for use ... 9
7.2.3 Metallic material for metal-ceramic restorations ... 9
7.2.4 Metallic materials for which no heat-treatment is recommended in the manufacturer's instructions for use ... 9
7.3 Proof stress of 0,2 % non-proportional extension and the elongation after fracture: Metallic materials for which production of conventional specimens is possible ... 10
7.4 Type 0 metallic materials for which the production of conventional specimens is not possible ... 11
7.5 Elastic moduli ... 11
7.5.1 General ... 11
7.5.2 Tensile strain method ... 11
7.5.3 Flexure method (three or four point bending) ... 11
7.5.4 Acoustic resonance method ... 12
7.6 Density measurement ... 13
7.7 Corrosion resistance ... 13
7.8 Tarnish resistance and colour ... 13

AVA Documents
Document Sharing Hub

© ISO 2016 – All rights reserved

Full document details: BS EN ISO 22674:2016

7.9 Linear thermal expansion ... 13

8 Test methods ... 13
8.1 Information, instructions and marking ... 13
8.2 Chemical composition ... 14
8.3 Mechanical testing ... 14
8.3.1 Apparatus ... 14
8.3.2 Test procedure ... 14
8.4 Proof stress of 0,2 % non-proportional extension ... 15
8.4.1 Calculation ... 15
8.4.2 Mean value ... 15
8.5 Percentage elongation after fracture ... 15
8.5.1 Calculation ... 15
8.5.2 Mean value ... 15
8.6 Elastic modulus measurement ... 15
8.6.1 Tensile strain method ... 15
8.6.2 Flexure method in three- or four-point bending mode ... 16
8.6.3 Acoustic resonance method ... 18
8.7 Calculation of elasticity parameters from acoustic measurement ... 19
8.7.1 General ... 19
8.7.2 Elastic modulus ... 20
8.7.3 Shear modulus ... 20
8.7.4 Poisson ratio ... 21
8.8 Density ... 21
8.8.1 Preparation of test specimens ... 21
8.8.2 Reagents ... 21
8.8.3 Apparatus ... 21
8.8.4 Procedure ... 21
8.9 Corrosion resistance by the static immersion procedure of ISO 10271:2011 ... 21
8.9.1 Preparation of test specimens ... 21
8.9.2 Reagents ... 21
8.9.3 Apparatus ... 21
8.9.4 Test solution ... 22
8.9.5 Test procedure ... 22
8.9.6 Analysis ... 22
8.9.7 Treatment of data ... 22
8.10 Sulfide tarnish test (cyclic immersion) ... 22
8.11 Sulfide tarnish test (static immersion) ... 22
8.12 Solidus and liquidus temperatures (dental casting alloys) or melting point (commercially pure metals) ... 22
8.12.1 Cooling curve method ... 22
8.12.2 Thermal analysis method ... 23
8.13 Linear thermal expansion ... 24

9 Information and instructions for use ... 24
9.1 Information ... 24
9.2 Processing instructions ... 25
10 Marking and labelling ... 25
10.1 Marking ... 25
10.2 Labelling of the package ... 25

Annex A (informative) **Tensile testing of a non-cast Type 0 metallic material that is intended for use in a thickness between 0,1 mm and 0,5 mm ... 27**

Annex B (normative) **Calculation of uncertainty for elasticity measurement ... 30**

Annex C (informative) **Measurement of Poisson ratio ... 34**

Bibliography ... 36

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 106, *Dentistry*, Subcommittee SC 2, *Prosthodontic materials*.

This second edition cancels and replaces the first edition (ISO 22674:2006), which has been technically revised with the following changes:

— Corrosion resistance measurement was referred to the recent standard ISO 10271:2011.

— A second tarnish test was included, referring to provisions in ISO 10271:2011.

— Clarification of the term "free of" was added to the requirements of composition and labelling;

— Lead was added as a hazardous element.

— Measurement of elasticity was revised. Beside the method of calculation of elastic modulus using an extensometer, other alternative methods were added, namely, the flexure method in three- and four-point bending and the acoustic resonance method.

— Informative Annex A was added, dealing with tensile testing of non-cast Type 0 metallic materials intended for use in a thickness between 0,1 and 0,5 mm.

— Normative Annex B was added, giving information on calculation of uncertainty for elastic measurement.

— Informative Annex C was added, giving information for measurement of Poisson ratio.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

Introduction

Specific qualitative and quantitative requirements for freedom from biological hazard are not included in this International Standard, but it is recommended that, in assessing possible biological hazards, reference has to be made to ISO 10993-1 and ISO 7405.

Requirements for the performance of metals and alloys used for the metallic component of a metal-ceramic restoration contained in this International Standard supersede such requirements formerly contained in ISO 9693. The requirements for the performance of ceramic material and the metal-ceramic bond in metal-ceramic restorative systems continue to be specified in ISO 9693-1.

Requirements for the proof stress and minimum elongation after fracture for Type 0 metallic materials are not included in this International Standard, but it is recommended to adopt the test procedure given in Annex A when measuring these properties. Requirements will be included in a revision of this International Standard when information becomes available to Technical Committee ISO/TC 106/SC 2.

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

INTERNATIONAL STANDARD ISO 22674:2016(E)

Dentistry — Metallic materials for fixed and removable restorations and appliances

1 Scope

This International Standard classifies metallic materials that are suitable for the fabrication of dental restorations and appliances, including metallic materials recommended for use either with or without a ceramic veneer, or recommended for both uses, and specifies their requirements. Furthermore, it specifies requirements with respect to packaging and marking the products and to the instructions to be supplied for the use of these materials, including products delivered for sale to a third party.

This International Standard does not apply to alloys for dental amalgam (ISO 24234), dental brazing materials (ISO 9333), or metallic materials for orthodontic appliances (ISO 15841) (e.g. wires, brackets, bands and screws).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1942, *Dentistry — Vocabulary*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 5832-2, *Implants for surgery — Metallic materials — Part 2: Unalloyed titanium*

ISO 5832-3[1)], *Implants for surgery — Metallic materials — Part 3: Wrought titanium 6-aluminium 4-vanadium alloy*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 6892-1[2)], *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

ISO 9693-1, *Dentistry — Compatibility testing — Part 1: Metal-ceramic systems*

ISO 10271:2011, *Dentistry — Corrosion test methods for metallic materials*

ISO 15223-1:2012, *Medical devices — Symbols to be used with medical device labels, labelling and information to be supplied — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions of ISO 1942 and the following apply.

3.1
base metal
any metallic element with the exception of noble metals (i. e. gold and metals of the platinum group) and silver

1) To be published.

2) To be published.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

3.2
noble metal
gold and metals of the platinum group

[SOURCE: ISO 1942:2009, 2.187]

3.3
hazardous element
element that is known for its potential to produce an adverse biological effect

Note 1 to entry: The presence of such an element (as an alloying addition or as an impurity) in a dental alloy does not imply that the alloy, in itself, is hazardous.

3.4
metallic material
material having the properties that are associated with an alloy, noble metal or base metal

Note 1 to entry: This may be a pure element, commercially pure metal or an alloy.

3.5
casting alloy
metallic material designed for casting into an investment mould

3.6
ceramic veneer
thin ceramic surface layer present on a metallic material restoration to provide an aesthetic effect

3.7
metal-ceramic restoration
dental restoration in which a ceramic veneer is bonded to a metallic material substructure by firing

Note 1 to entry: This can apply also to the metallic material used for such a restoration. In this context, metal-ceramic alloy is a synonym.

Note 2 to entry: If recommended, such a metallic material may be used without a ceramic veneer.

3.8
metallic base
metal with highest concentration by mass fraction in the alloy

Note 1 to entry: The name of this element shall precede the words "-based metallic material for dental restoration" or "-based dental casting alloy" or "-based dental metal-ceramic material", as is appropriate.

3.9
base-metal alloy
alloy having a base metal as the principal element

3.10
as-cast condition
metallurgical condition of the metallic material in its solid state when removed from the casting machine

Note 1 to entry: This condition is dependent upon the manufacturer's recommended cooling procedure (e.g. bench cooling).

3.11
bench-cooling
process whereby a casting is retained in its investment with exposed metal uppermost and placed on a flat, insulating surface at ambient temperature in freely circulating air until its temperature falls to ambient

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

3.12
hardening
heat-treatment of a metallic material producing a condition which provides a higher 0,2 % proof stress than the "as-cast" state

Note 1 to entry: If recommended by the manufacturer, explicit instructions shall be given in the instructions for use.

3.13
softening
heat-treatment of a metallic material producing a condition which provides a lower 0,2 % proof stress than the "as-cast" state

Note 1 to entry: If recommended by the manufacturer, explicit instructions shall be given in the instructions for use.

3.14
one-surface inlay
an inlay restoration that is exposed to the oral environment on one and no more of the surfaces that are used to define the tooth for the purposes of charting

3.15
elastic modulus
E
the ratio of elastic stress to elastic strain, also termed tensile elastic modulus or Young's modulus, symbol *E*

4 Classification

For the purposes of this International Standard, a metallic material is classified according to its mechanical properties by a Type number, of which there are six.

Examples of the applications for which these Types are intended are as follows:

— **Type 0:** intended for low stress bearing single-tooth fixed prostheses, e.g. small veneered one-surface inlays, veneered crowns;

NOTE Metallic materials for metal-ceramic crowns produced by electroforming or sintering belong to Type 0.

— **Type 1:** for low stress bearing single-tooth fixed prostheses, e.g. veneered or unveneered one-surface inlays, veneered crowns;

— **Type 2:** for single tooth fixed prostheses, e.g. crowns or inlays without restriction on the number of surfaces;

— **Type 3:** for multiple unit fixed prostheses;

— **Type 4:** for appliances with thin sections that are subject to very high forces, e.g. removable partial dentures, clasps, thin veneered single crowns, full arch fixed dental prostheses or those with small cross-sections, bars, attachments, implant retained superstructures;

— **Type 5:** for appliances in which parts require the combination of high stiffness and proof stress, e.g. thin removable partial dentures, parts with thin cross-sections, clasps.

NOTE 1 The higher application type can include lower application types.

NOTE 2 Multiple-unit and full-arch, fixed dental prostheses are also referred to as bridges.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

5 Requirements

5.1 Chemical composition

5.1.1 Reported composition

For all elements that are present in excess of 1,0 % (mass fraction), each constituent element shall be declared by the manufacturer and shall be reported [see 9.1 a)] to a precision of 0,1 % (mass fraction).

Any element that is present in excess of 0,1 % (mass fraction), but not of 1,0 % (mass fraction), shall be identified in [see 9.1 a)] either by name or symbol.

EXAMPLE If a constituent element is present with 0,6 % (mass fraction), it shall be identified [9.1 a)] either by name or symbol. If a constituent element is present with 22,06 % (mass fraction), it shall be reported [9.1 a)] as 22,1 % [precision of 0,1 % (mass fraction)].

If the metallic material contains less than 0,1 % (mass fraction) of a specified element (other than one named in 5.2), it may be named as "free of" this specified element [see 9.1 p) and 10.2 h)].

5.1.2 Permitted deviation from the reported composition for elements

The permitted deviation of the reported composition for elements from the value stated on the package or label or insert [see 9.1 a)] is given in Table 1.

Table 1 — Permitted deviation from the reported composition for elements

Alloy	Elemental content	
	1,0 % < mass fraction ≤ 20 %	mass fraction > 20 %
Base-metal alloy	max. 1,0 %	max. 2,0 %
Silver-based and noble metal alloy	max. 0,5 %	max. 0,5 %

5.2 Hazardous elements

5.2.1 Hazardous elements

For the purposes of this International Standard, the elements nickel, cadmium, beryllium and lead are designated to be hazardous elements.

5.2.2 Limits for the hazardous elements cadmium and beryllium

The metallic material shall not contain more than 0,02 % (mass fraction) cadmium or beryllium.

Cadmium and beryllium are neither alloying elements nor elements inherent to the manufacturing process of titanium metallic materials. For titanium metallic materials that comply with the requirements of chemical composition of ISO 5832-2 and ISO 5832-3, cadmium and beryllium do not need to be analysed.

5.2.3 Limit for lead

The metallic material shall not contain more than 0,02 % (mass fraction) lead.

Lead is neither an alloying elements nor an element inherent to the manufacturing process of titanium metallic materials. For titanium metallic materials that comply with the requirements of chemical composition of ISO 5832-2 and ISO 5832-3, lead does not need to be analysed.

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

5.2.4 Nickel

5.2.4.1 Manufacturer's reported nickel content and permitted deviation

If the metallic material contains more than 0,1 % (mass fraction) nickel, this content shall be given to an accuracy of 0,1 % (mass fraction) in the literature which accompanies the package [see 9.1 n)] and on the package, label or insert [see 10.2 f)].

The mass fraction shall not exceed the value stated in 9.1 n) and 10.2 f).

5.2.4.2 Nickel-free products

For the purposes of this International Standard, alloys with a maximum of 0,1 % (mass fraction) nickel can be labelled "nickel free" [see 9.1 o) and 10.2 g)].

If nickel is not declared, it must be limited to a maximum of 0,1 %. This limit has to be adhered to when nickel is a natural impurity in a component of the alloy.

5.3 Biocompatibility

For guidance on biocompatibility, see Introduction.

5.4 Mechanical properties

5.4.1 General

This requirement (see Table 2) shall be met by the metallic material after the recommended processing techniques (e.g. casting, bench-cooling, machining) and after the ceramic firing schedule (if appropriate) have been applied. A metallic material recommended for use either with or without a ceramic veneer shall meet this requirement in both metallurgical conditions.

If a heat-treatment is recommended by the manufacturer [see 9.2 c)] this requirement shall be met by the material in the heat-treated condition, applied in accordance with the manufacturer's instructions for use.

For a metallic material, the Type can be classified differently (according to Table 2) if it is recommended for use in more than one metallurgical condition (produced by alternative processing schedules). The highest applicable Type shall be specified for each condition.

Table 2 — Mechanical properties

Type	Proof stress of 0,2 % non-proportional extension $R_{p0,2}$ MPa minimum	Elongation after fracture % minimum	Elastic modulus GPa minimum
0	—	—	—
1	80	18	—
2	180	10	—
3	270	5	—
4	360	2	—
5	500	2	150

Testing shall be done according to 8.3.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

5.4.2 Proof stress of 0,2 % non-proportional extension

5.4.2.1 Determination of compliance

Refer to the classification Type stated in 9.1 b).

If four, five or six of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material complies with the requirement.

If two or fewer of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material fails to comply with the requirement.

NOTE 1 Two lots of six specimens are produced (see Clause 7). One of these lots is tested in the first test series. If required, replacement specimens are drawn from the second lot and used in the first test series. The remaining specimens in the second lot form the second test series.

NOTE 2 In this context, the number six is reached to complete the set in the first test series when the number of specimens tested less those rejected after post fracture examination (8.3.2) is six, (i.e. replacement specimens are included in the total).

If three or four specimens in the first lot of six specimens are rejected on the basis of 8.3.2 and replaced with specimens from the second lot, all 12 specimens shall be tested. If at least eight results meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material complies with the requirement.

If three of the results for the set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension, all remaining specimens shall be tested in a second test series. If five or six of the results for the specimens in the second test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material complies with the requirement.

Under this compliance criterion, if one specimen from the first lot has been rejected on the basis of inspection after fracture (8.3.2) during the first test series and a specimen from the second lot of six used as its replacement, then all five remaining specimens in the second series shall meet the requirement. Only one replacement is possible for a borderline metallic material.

If three of the results for the first set of six specimens in the first test series meet the requirement for proof stress of 0,2 % non-proportional extension and four or fewer of the results from the specimens in the second test series meet the requirement for proof stress of 0,2 % non-proportional extension, the metallic material fails to comply with the requirement.

Testing shall be done according to 8.3.2.

5.4.2.2 Mean value

The mean value for the proof stress of 0,2 % non-proportional extension, calculated according to 8.4.2 shall not differ by more than 10 % from the value given in the literature accompanying the package [see 9.1 c)].

5.4.3 Elongation after fracture

5.4.3.1 Determination of compliance with the requirement

Refer to the classification Type stated in 9.1 b).

If the four, five or six of the results for the set of six specimens in the first test series that meet the requirement for proof stress of 0,2 % non-proportional extension also meet the requirement for elongation after fracture, the metallic material complies with the requirement for elongation after fracture.

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016

If two or fewer of the results for the set of six specimens in the first test series meet the requirement for elongation after fracture, the metallic material fails to comply with the requirement for elongation after fracture.

NOTE 1 Two lots of six specimens are produced (see Clause 7). One of these lots is tested in the first test series. If required, replacement specimens are drawn from the second lot and used in the first test series. The remaining specimens in the second lot form the second test series.

NOTE 2 In this context, the number six is reached to complete the set in the first test series when the number of specimens tested less those rejected after post fracture examination (8.3.2) is six, (i.e. replacement specimens are included in the total).

If three or four specimens in the first lot of six specimens are rejected on the basis of 8.3.2 and replaced with specimens from the second lot, all 12 specimens shall be tested. If at least eight results of the specimens that meet the requirement for proof stress of 0,2 % non-proportional extension also meet the requirement for elongation after fracture, the metallic material complies with the requirement.

If three of the results for the first set of six specimens in the first test series that meet the requirement for proof stress of 0,2 % non-proportional extension also have an elongation after fracture that meets the requirement for elongation after fracture, all remaining specimens shall be tested in a second test series. If five or six of the results for the specimens in the second test series have both an elongation after fracture and a proof stress of 0,2 % non-proportional extension that meet both requirements, the metallic material complies with the requirement for the percentage elongation after fracture. If the results for the five or six specimens in the second series meet the requirement for elongation after fracture, but not the requirement for proof stress of 0,2 % non-proportional extension, the metallic material fails to comply with requirement for elongation after fracture.

Under this compliance criterion, if one specimen in the first lot has been rejected on the basis of inspection after fracture (8.3.2) during the first test series and a specimen from the second lot of six used as its replacement, then all five remaining specimens in the second series must meet the requirement. Only one replacement is possible for a borderline metallic material.

If three of the results for the first set of six specimens in the first test series meet the requirement for the percentage elongation after fracture and four or fewer of the results from specimens in the second test series meet the requirement for elongation after fracture, the metallic material fails to comply with the requirement for elongation after fracture.

5.4.3.2 Mean value

The mean value of percentage elongation after fracture calculated according to 8.5.2 must exceed 70 % of the value stated in the literature accompanying the package and not be less than the minimum value for the type [see 9.1 d)].

5.5 Elastic modulus

5.5.1 Precision of measurement method

The measurement of elastic modulus shall be performed by a method (see 8.6) capable of a precision that gives a combined standard uncertainty less than 10 % of the measured value.

NOTE For guidance on the determination of combined standard uncertainty, see ISO/IEC Guide 98-3.

5.5.2 Determination of compliance with the requirements for Type 5 materials

Refer to classification Type stated in 9.1 b).

Where compliance with Type 5 is claimed, the mean value of the elastic modulus as determined according to 8.6 shall be at least 150 GPa.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS EN ISO 22674:2016