



BSI Standards Publication

Sintered metal material — Specifications

National foreword

This British Standard is the UK implementation of EN ISO 5755:2022. It is identical to ISO 5755:2022. It supersedes BS EN ISO 5755:2012, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee W/-, Consumer Products and Services Sector Policy and Strategy Committee.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 539 16210 3

ICS 77.160

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2022.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Sintered metal material - Specifications (ISO 5755:2022)

Matériaux métalliques frittés - Spécifications (ISO
5755:2022)

Sintermetallwerkstoffe - Anforderungen (ISO
5755:2022)

This European Standard was approved by CEN on 8 May 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 5755:2022) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy" in collaboration with CCMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2023, and conflicting national standards shall be withdrawn at the latest by April 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 5755:2012.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 5755:2022 has been approved by CEN as EN ISO 5755:2022 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling	3
5 Test methods for normative properties	3
5.1 General	3
5.2 Chemical analysis	3
5.3 Open porosity	3
5.4 Mechanical properties	3
5.4.1 General	3
5.4.2 Tensile properties	4
5.4.3 Radial crushing strength	4
6 Test methods for informative properties	5
6.1 General	5
6.2 Density	5
6.3 Tensile strength	5
6.4 Tensile yield strength	5
6.5 Elongation	5
6.6 Young's modulus	5
6.7 Poisson's ratio	5
6.8 Impact energy	6
6.9 Compressive yield strength	6
6.10 Transverse rupture strength	6
6.11 Fatigue strength	6
6.11.1 General	6
6.11.2 Rotating bending fatigue strength	6
6.11.3 Plane-bending fatigue strength	6
6.11.4 Axial fatigue strength	7
6.12 Apparent hardness	7
6.13 Coefficient of linear expansion	7
7 Specifications	7
8 Designations	7
Annex A (normative) Designation system	35
Annex B (informative) Microstructures	38
Annex C (informative) Equivalence of standards of powder metallurgy materials	53
Bibliography	68

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 5, *Specifications for powder metallurgical materials (excluding hardmetals)*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/SS M11, *Powder metallurgy*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 5755:2012), which has been technically revised.

The main changes are as follows:

- [Annex B](#) has been updated to include information on metallography of sintered materials;
- a new [Annex C](#) has been added to include tables of equivalences of the materials of the standard with the materials of other international standards of habitual use.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Sintered metal material — Specifications

1 Scope

This document specifies the requirements for the chemical composition and the mechanical and physical properties of sintered metal materials used for bearings and structural parts.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1099, *Metallic materials — Fatigue testing — Axial force-controlled method*

ISO 2738, *Sintered metal materials, excluding hardmetals — Permeable sintered metal materials — Determination of density, oil content and open porosity*

ISO 2739, *Sintered metal bushings — Determination of radial crushing strength*

ISO 2740, *Sintered metal materials, excluding hardmetals — Tensile test pieces*

ISO 2795, *Plain bearings — Sintered bushes — Dimensions and tolerances*

ISO 3325, *Sintered metal materials, excluding hardmetals — Determination of transverse rupture strength*

ISO 3954, *Powders for powder metallurgical purposes — Sampling*

ISO 4498, *Sintered metal materials, excluding hardmetals — Determination of apparent hardness and microhardness*

ISO 5754, *Sintered metal materials, excluding hardmetals — Unnotched impact test piece*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7625, *Sintered metal materials, excluding hardmetals — Preparation of samples for chemical analysis for determination of carbon content*

ISO 14317, *Sintered metal materials excluding hardmetals — Determination of compressive yield strength*

ASTM E228, *Standard Test Method for Linear Thermal Expansion of Solid Materials with a Push-Rod Dilatometer*

ASTM E1875, *Standard Test Method for Dynamic Young's Modulus, Shear Modulus, and Poisson's Ratio by Sonic Resonance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 tensile strength

R_m
ability of a test specimen to resist fracture when a pulling force is applied in a direction parallel to its longitudinal axis

Note 1 to entry: It is equal to the maximum load divided by the original cross-sectional area.

Note 2 to entry: It is expressed in MPa.

3.2 tensile yield strength

$R_{p0,2}$
load at which the material exhibits a 0,2 % offset from proportionality on a stress-strain curve in tension, divided by the original cross-sectional area

Note 1 to entry: It is expressed in MPa.

3.3 Young's modulus

E
ratio of normal stress to corresponding strain for tensile or compressive stresses below the proportional limit of the material

Note 1 to entry: It is expressed in GPa.

3.4 Poisson's ratio

ν
absolute value of the ratio of transverse strain to the corresponding axial strain, resulting from uniformly distributed axial stress below the proportional limit of the material

3.5 impact energy

measurement of the energy absorbed when fracturing a specimen with a single blow

Note 1 to entry: It is expressed in Joules (J).

3.6 compressive yield strength

stress at which a material exhibits a specified permanent set

Note 1 to entry: It is expressed in MPa.

3.7 transverse rupture strength

stress, calculated from the bending strength formula, required to break a specimen of a given dimension

Note 1 to entry: It is expressed in MPa.

3.8 fatigue strength

maximum alternating stress that can be sustained for a specific number of cycles without failure, the stress being reversed with each cycle unless otherwise stated

Note 1 to entry: It is expressed in MPa.

3.9 radial crushing strength

radial stress required to fracture a hollow cylindrical part of specified dimensions

Note 1 to entry: It is expressed in MPa.

3.10**density**

mass per unit volume of the material

Note 1 to entry: It is expressed in g/cm^3 .

3.11**apparent hardness**

resistance of a powder metallurgical (PM) material to indentation, tested under specified conditions

Note 1 to entry: For PM materials, it is a function of the density of the material.

3.12**open porosity**

oil content after full impregnation, divided by the volume of the test piece, and multiplied by 100

Note 1 to entry: It is expressed as a volume percentage.

3.13**coefficient of linear expansion**

change in length per unit length per degree change in temperature

Note 1 to entry: It is expressed in 10^{-6} K^{-1} .

4 Sampling

Sampling of powders to produce standard test pieces shall be carried out in accordance with ISO 3954.

5 Test methods for normative properties**5.1 General**

The following test methods shall be used to determine the normative properties given in [Tables 1 to 18](#).

5.2 Chemical analysis

The chemical composition table for each material lists the principal elements by minimum and maximum mass percentage before any additional process, such as oil impregnation, resin impregnation or steam treatment, has taken place. "Other elements" may include minor amounts of elements added for specific purposes and is reported as a maximum percentage.

Whenever possible, and always in cases of dispute, the methods of chemical analysis shall be those specified in the relevant International Standards. If no International Standard is available, the method may be agreed upon and specified at the time of enquiry and order.

Samples for the determination of total carbon content shall be prepared in accordance with ISO 7625. Determination of the total carbon content can be in accordance with ISO 437.

5.3 Open porosity

The open porosity shall be determined in accordance with ISO 2738.

5.4 Mechanical properties**5.4.1 General**

The as-sintered mechanical properties given in [Tables 1 to 18](#) were determined on pressed and sintered test pieces with a mean chemical composition. The heat-treated mechanical properties given in [Tables 1](#)

to 18 were determined on test bars which were either pressed and sintered or machined from pressed and sintered blanks. They are intended as a guide to the initial selection of materials. When selecting powder metallurgical (PM) materials, it should be taken into account that the properties depend not only on the chemical composition and density, but also on the production methods. The properties of sintered materials giving satisfactory service in particular applications may not necessarily be the same as those of wrought or cast materials that might otherwise be used. Therefore, liaison with prospective suppliers is recommended. They may also be used as a basis for specifying any special tests that may be indicated on the drawing.

The mechanical properties shall neither be calculated from hardness values nor be determined on tensile test pieces taken from a component and used for verifying the values given in [Tables 1 to 18](#). If the customer requires that a specified level of mechanical properties be obtained by tests on the component, these shall be agreed with the supplier and shall be stated on the drawing and/or any technical documentation of the customer referred to on the drawing.

5.4.2 Tensile properties

The ultimate tensile strength and the yield strength shall be determined in accordance with ISO 2740 and ISO 6892-1. For heat-treated materials, tensile strength and yield strength are approximately equal and, in this case, tensile strength is specified.

The normative yield strengths (as-sintered condition) and ultimate tensile strengths (heat-treated condition) are shown as minimum values. These strengths may be used in designing PM part applications. To select a material which is optimum in both properties and cost-effectiveness, it is essential that the part application be discussed with the PM parts manufacturer.

The minimum values were developed from tensile specimens prepared specifically for evaluating PM materials.

Tensile specimens machined from commercial parts may differ from those obtained from prepared tensile specimens. To evaluate the part strength, it is recommended that static or dynamic proof-testing be agreed between the purchaser and the manufacturer and carried out on the first production lot of parts. The results of testing to failure can be used statistically to determine a minimum breaking force for future production lots.

Acceptable strength can also be demonstrated by processing tensile specimens prepared specifically for evaluating PM materials manufactured from the same batch of powder as the production parts and processed with them.

As indicated above, the testing of test bars machined from the PM component is the least desirable method for demonstrating minimum properties.

For heat-treated properties, the test bars were quench-hardened and tempered to increase the strength, hardness and wear resistance. Tempering is essential to develop the properties given in this document. Heat-treat equipment that utilizes a gas atmosphere or vacuum is recommended. The use of liquid salts is not recommended due to entrapment of the salts in the porosity causing "salt bleed-out" and "internal corrosion". Some materials may be heat-treated directly after the sintering process by controlling the cooling rate within the sintering furnace. This process is usually known as "sinter hardening". Materials processed by this route also require tempering to develop their optimum strengths.

5.4.3 Radial crushing strength

The radial crushing strength shall be determined in accordance with ISO 2739. The wall thicknesses of test pieces to be used shall be in the range covered by ISO 2795. For test pieces outside this range, the specified radial crushing strength values are different and shall be agreed between the customer and the supplier.

6 Test methods for informative properties

6.1 General

Typical values are given for each material; these include tensile and yield strengths. These typical values are given for general guidance only. They should not be used as minimum values.

These typical properties should be achievable through normal manufacturing processing. Again, any specific tests on components should be discussed and agreed between the purchaser and the manufacturer.

6.2 Density

The density shall be determined in accordance with ISO 2738. Density is normally determined after the removal of any oils or non-metallic materials from the porosity and is known as the “dry density”. The “wet density” is sometimes reported on production bearings or parts, this is the mass per unit volume, including any oil or non-metallic material that has impregnated the component.

6.3 Tensile strength

The tensile strength shall be determined in accordance with ISO 2740 and ISO 6892-1.

6.4 Tensile yield strength

The tensile yield strength shall be determined in accordance with ISO 2740 and ISO 6892-1.

6.5 Elongation

Elongation (plastic) shall be determined in accordance with ISO 6892-1. It is expressed as a percentage of the original gauge length (usually 25 mm), and is determined by measuring the increase in gauge length after the fracture, providing the fracture takes place within the gauge length. Elongation can also be measured with a break-away extensometer on a tensile specimen. The recorded stress/strain curve displays total elongation (elastic and plastic). The elastic strain shall be subtracted from the total elongation to give the plastic elongation (this can sometimes be provided with the test machine's software).

6.6 Young's modulus

Young's modulus shall be determined in accordance with ASTM E1875. Data for the elastic constants in this document were generated from resonant frequency testing. [Formula \(1\)](#) relates the three elastic constants:

$$\nu = (E / 2G) - 1 \quad (1)$$

where

ν is Poisson's ratio;

E is Young's modulus;

G is the shear modulus.

6.7 Poisson's ratio

Poisson's ratio shall be determined in accordance with ASTM E1875.

6.8 Impact energy

The impact energy shall be determined in accordance with ISO 5754. The data in this document were obtained using an unnotched Charpy specimen.

6.9 Compressive yield strength

The compressive yield strength shall be determined in accordance with ISO 14317. For certain heat-treated materials listed in the tables, the hardenability is not sufficient to completely through-harden the 9,00 mm diameter test specimen. Due to variation in hardenability among the heat-treated steels listed in the tables, the compressive yield strength data are appropriate only for 9,00 mm sections. Typically, smaller cross-sections have higher compressive yield strengths and larger sections have somewhat lower strengths due to the hardenability response. Since the cross-section of the tensile yield test specimen is smaller than the compressive yield specimen, a direct correspondence between tensile and compressive yield strength data are not possible.

6.10 Transverse rupture strength

The transverse rupture strength shall be determined in accordance with ISO 3325.

The strength formula in ISO 3325 is strictly valid only for non-ductile materials; nevertheless, it is widely used for materials that bend at fracture and is useful for establishing comparative strengths. Data for such materials are included as typical properties in ISO 3325.

6.11 Fatigue strength

6.11.1 General

The number of cycles survived should be stated with each strength listed.

For PM ferrous materials, like wrought ferrous materials, fatigue strengths of 10^7 cycles in duration using unnotched specimens are considered to be sustainable indefinitely and are therefore considered to be fatigue limits (also termed endurance limits). By contrast, non-ferrous PM materials do not have 10^7 cycle maximum fatigue strengths sustainable for indefinite times and these stress limits therefore simply remain as the fatigue strength at 10^7 cycles.

The fatigue limits in this document were generated through statistical analysis of the test data. Due to the limited number of data points available for the analysis, these fatigue strengths were determined as the 90 % survival stress, i.e. the fatigue stress at which 90 % of the test specimens survived 10^7 cycles.

There are three methods of stressing the test specimens and each gives different fatigue strengths. These are described in [6.11.2](#) to [6.11.4](#).

6.11.2 Rotating bending fatigue strength

This test method uses a machined, round, smooth test specimen (in accordance with ISO 3928), with an R. R. Moore testing machine. Testing shall be in accordance with ISO 1143. The specimen is held at one end and rotated while it is stressed at the other end. The surface of the test bar is the most highly stressed area and the centre line has a neutral stress. This test method gives the highest fatigue strength.

6.11.3 Plane-bending fatigue strength

This method used for plane-bending fatigue uses a standard sintered fatigue test bar (in accordance with ISO 3928) that is subjected to an alternating stress. This test method gives a slightly lower fatigue strength than the rotating bending fatigue test, as more of the cross-sectional area is subjected to the stress. Evaluation of fatigue strength is done according to the staircase method described in MPIF Standard 56.

6.11.4 Axial fatigue strength

This method uses either a machined, round or standard sintered fatigue test bar (in accordance with ISO 3928) that is tested in a test machine by clamping both ends and subjecting the test bar to alternating stresses where $R = -1$. Testing shall be conducted in accordance with ISO 1099. As the whole of the cross-section is stressed, this test method gives the lowest fatigue strength.

6.12 Apparent hardness

The apparent hardness shall be determined in accordance with ISO 4498. The hardness value of a PM part when using a conventional indentation hardness tester is referred to as “apparent hardness” because it represents a combination of matrix hardness plus the effect of porosity. Apparent hardness measures the resistance to indentation.

Because of possible density variations in a finished PM part, the location of critical apparent hardness measurements should be specified on the engineering drawing of the part. As surface pore closure can affect the apparent hardness, the surface condition should also be specified.

6.13 Coefficient of linear expansion

The coefficient of linear expansion shall be determined in accordance with ASTM E228.

7 Specifications

The chemical composition and mechanical properties are given in [Tables 1 to 18](#).

The liquid lubricant content of materials for bearings, impregnated with liquid lubricant, shall be not less than 90 % of the measured open porosity.

8 Designations

Designations shall be in accordance with [Annex A](#).

Table 1 — Non-ferrous materials for bearings: bronze and bronze with graphite

	Grade ^a	Normative values				Informative values			
		Chemical composition			Open porosity min. <i>p</i> %	Radial crush- ing strength min. <i>K</i> MPa	Density (dry) <i>ρ</i> g/cm ³	Coefficient of linear expansion 10 ⁻⁶ K ⁻¹	
Graphite	Sn	Cu	Total other elements max. %						
		%	%	%					
Bronze	C-T10-K110	—	8,5 to 11,0	Balance	2	27	110	6,1	18
	C-T10-K140	—	8,5 to 11,0	Balance	2	22	140	6,6	18
	C-T10-K180	—	8,5 to 11,0	Balance	2	15	180	7,0	18
Bronze with graphite	C-T10G-K90	0,5 to 2,0	8,5 to 11,0	Balance	2	27	90	5,9	18
	C-T10G-K110 ^b	0,5 to 2,0	8,5 to 11,0	Balance	2	25	110	6,0	18
	C-T10G-K120	0,5 to 2,0	8,5 to 11,0	Balance	2	22	120	6,4	18
	C-T10G-K170 ^b	0,5 to 2,0	8,5 to 11,0	Balance	2	19	170	6,5	18
	C-T10G-K160	0,5 to 2,0	8,5 to 11,0	Balance	2	17	160	6,8	18
	C-T10G-K115	3 to 5	8,5 to 11,0	Balance	2	11	115	6,8	19
^a All materials can be oil-impregnated.									
^b These materials have a higher strength than is expected from the porosity listed, which can require different sintering parameters.									

Table 2 — Ferrous materials for bearings: iron, iron-copper, iron-bronze and iron-carbon graphite

	Grade ^a	Normative values						Informative values			
		Chemical composition						Open porosity min.	Radial crushing strength K MPa	Density (dry) ρ g/cm ³	Coefficient of linear expansion 10 ⁻⁶ K ⁻¹
	C combined ^b	Cu	Sn	Graphite	Fe	Total other elements max.					
Iron	F-00-K170	< 0,3	—	—	—	Balance	2	22	> 170	5,8	12
	F-00-K220	< 0,3	—	—	—	Balance	2	17	> 220	6,2	12
	F-00C2-K200	< 0,3	1 to 4	—	—	Balance	2	22	> 200	5,8	12
	F-00C2-K250	< 0,3	1 to 4	—	—	Balance	2	17	> 250	6,2	12
Iron copper	F-03C22-K150	< 0,5	18 to 25	—	—	Balance	2	18	> 150	6,4	13
	F-03C22G-K150	< 0,5	18 to 25	—	0,3 to 1,0	Balance	2	18	> 150	6,4	13
	F-03C22G-K200 ^d	< 0,5	18 to 25	—	1,0 to 3,0	Balance	2	18	> 200	6,4	13
	F-03C25T-K120	< 0,5	20 to 30	1,0 to 3,0	—	Balance	2	17	120 to 250	6,4	13
Iron bronze ^c	F-03C36T-K90	< 0,5	34 to 38	3,5 to 4,5	0,3 to 1,0	Balance	2	24	90 to 265	5,8	14
	F-03C36T-K120	< 0,5	34 to 38	3,5 to 4,5	0,3 to 1,0	Balance	2	19	120 to 345	6,2	14
	F-03C45T-K70	< 0,5	43 to 47	4,5 to 5,5	< 1,0	Balance	2	24	70 to 245	5,6	14
	F-03C45T-K100	< 0,5	43 to 47	4,5 to 5,5	< 1,0	Balance	2	19	100 to 310	6,0	14
Iron-carbon graphite ^c	F-03G3-K70	< 0,5	—	—	2,0 to 3,5	Balance	2	20	70 to 175	5,6	12
	F-03G3-K80	< 0,5	—	—	2,0 to 3,5	Balance	2	13	80 to 210	6,0	12

^a All materials can be oil-impregnated.

^b On the basis of iron phase only.

^c The range of values given for radial crushing strength (K) indicates the necessity to maintain a balance between combined carbon and free graphite.

^d This material has a higher strength than expected from the porosity listed, which can require different sintering parameters.

^a All materials can be oil-impregnated.^b On the basis of iron phase only.^c The range of values given for radial crushing strength (K) indicates the necessity to maintain a balance between combined carbon and free graphite.^d This material has a higher strength than expected from the porosity listed, which can require different sintering parameters.

Table 3 — Ferrous materials for structural parts: iron and carbon steel — As-sintered

	Grade	Normative values				Informative values													
		Chemical composition				Tensile yield strength min.	Density	Tensile strength	Tensile yield strength	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength	Rotating fatigue limit 90 % survival	Apparent hardness		
		C combined	Cu	Fe	Total other elements max.														
		%	%	%	%	R _{p0.2} MPa	ρ g/cm ³	R _m MPa	R _{p0.2} MPa	A ₂₅ %	GPa		J	(0,1 %) MPa	MPa	MPa	MPa	HV5	Rockwell
Iron	F-00-100	< 0,3	—	Balance	2	100	6,7	170	120	3	120	0,25	8	120	340	65	60	60 HRF	
	F-00-120	< 0,3	—	Balance	2	120	7,0	210	150	4	140	0,27	24	125	500	80	75	70 HRF	
	F-00-140	< 0,3	—	Balance	2	140	7,3	260	170	7	160	0,28	47	130	660	100	85	80 HRF	
Carbon steel	F-05-100	0,3 to 0,6	—	Balance	2	100	6,1	170	120	< 1	105	0,25	4	125	330	60	70	25 HRB	
	F-05-140	0,3 to 0,6	—	Balance	2	140	6,6	220	160	1	115	0,25	5	160	440	80	90	40 HRB	
	F-05-170	0,3 to 0,6	—	Balance	2	170	7,0	275	200	2	140	0,27	8	200	550	105	120	60 HRB	
Carbon steel	F-08-170	0,6 to 0,9	—	Balance	2	170	6,2	240	210	< 1	110	0,25	4	210	420	100	110	50 HRB	
	F-08-210	0,6 to 0,9	—	Balance	2	210	6,6	290	240	1	115	0,25	5	210	510	120	120	60 HRB	
	F-08-240	0,6 to 0,9	—	Balance	2	240	7,0	390	260	1	140	0,27	7	250	690	170	140	70 HRB	
These materials may be supplied with additives to improve machinability.																			
Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.																			
Machined test pieces according to ISO 3928.																			

Table 4 — Ferrous materials for structural parts: carbon steel — Heat-treated

Grade	Normative values				Informative values											
	Chemical composition				Ultimate tensile strength min.	Density	Tensile strength ^c	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength (0,1 %) MPa	Transverse rupture strength MPa	Rotating fatigue limit 90 % survival ^d MPa	Apparent hardness	
	C combined	Cu	Fe	Total other elements max.											R_m MPa	ρ g/cm ³
F-05-340H ^a	0,3 to 0,6	—	Balance	2	340	6,6	410	<1	115	0,25	4	300	720	160	280	20 HRC
F-05-410H ^a	0,3 to 0,6	—	Balance	2	410	6,8	480	<1	130	0,27	5	360	830	190	290	22 HRC
F-05-480H ^a	0,3 to 0,6	—	Balance	2	480	7,0	550	<1	140	0,27	5	420	970	220	300	25 HRC
F-08-450H ^b	0,6 to 0,9	—	Balance	2	450	6,6	520	<1	115	0,25	5	550	790	210	320	28 HRC
F-08-500H ^b	0,6 to 0,9	—	Balance	2	500	6,8	570	<1	130	0,27	6	600	860	230	345	31 HRC
F-08-550H ^b	0,6 to 0,9	—	Balance	2	550	7,0	620	<1	140	0,27	7	655	950	260	360	33 HRC
Heat-treated tensile properties were derived from machined test bars according to ISO 2740.																
^a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil-quenched and tempered at 180 °C for 1 h.																
^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil-quenched and tempered at 180 °C for 1 h.																
^c Tensile yield and ultimate tensile strength are approximately the same for heat-treated materials.																
^d Machined test pieces according to ISO 3928.																

Table 5 — Ferrous materials for structural parts: copper steel and copper-carbon steel — As-sintered

Grade		Normative values				Informative values													
Chemical composition				Tensile yield strength min.	Density ρ g/cm ³	Tensile strength		Tensile yield strength	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength	Rotating fatigue limit 90 % survival ^a	Bending fatigue limit 90 % survival ^b	Axial fatigue limit 90 % survival ^c	Apparent hardness	
C combined	Cu	Fe	Total other elements max.	R _{p0.2} MPa		R _m MPa	R _{p0.2} MPa	A ₂₅ %	GPa	(0,1 %) MPa	MPa	J	(0,1 %) MPa	MPa	MPa	MPa	MPa	HV5	Rockwell
Copper steel	< 0,3	1,3 to 3,0	Balance	2	110	6,2	180	150	1,5	110	0,25	6	130	340	70	—	—	60	16 HRB
	< 0,3	1,3 to 3,0	Balance	2	140	6,6	210	180	2	115	0,25	7	160	390	80	—	—	70	26 HRB
	< 0,3	1,3 to 3,0	Balance	2	175	7,0	235	205	3	140	0,27	8	185	445	89	—	—	90	39 HRB
Copper-carbon steels	0,3 to 0,6	1,3 to 3,0	Balance	2	230	6,2	270	270	< 1	110	0,25	3	270	480	95	—	—	110	44 HRB
	0,3 to 0,6	1,3 to 3,0	Balance	2	270	6,6	325	300	< 1	115	0,25	7	305	620	130	—	—	115	57 HRB
	0,3 to 0,6	1,3 to 3,0	Balance	2	300	7,0	390	330	< 1	140	0,27	10	330	760	190	—	150	150	68 HRB
	0,6 to 0,9	1,3 to 3,0	Balance	2	270	6,2	320	300	< 1	110	0,25	3	300	580	110	—	90	115	58 HRB
	0,6 to 0,9	1,3 to 3,0	Balance	2	350	6,6	390	360	< 1	115	0,25	7	330	800	150	—	120	140	70 HRB
	0,6 to 0,9	1,3 to 3,0	Balance	2	390	7,0	480	420	< 1	140	0,27	8	360	980	200	—	170	165	78 HRB
	0,6 to 0,9	1,3 to 3,0	Balance	2	410	7,2	520	450	< 1	155	0,28	9	380	1 070	230	—	190	185	84 HRB
These materials may be supplied with additives to improve machinability.																			
Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.																			
^a	Machined test pieces according to ISO 3928.																		
^b	As-sintered test pieces (sintered surfaces) according to ISO 3928.																		
^c	Machined test pieces according to ISO 3928.																		

These materials may be supplied with additives to improve machinability.

Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.

^a Machined test pieces according to ISO 3928.

^b As-sintered test pieces (sintered surfaces) according to ISO 3928.

^c Machined test pieces according to ISO 3928.

Table 6 — Ferrous materials for structural parts: copper-carbon steel — Heat-treated

Grade	Normative values					Informative values										
	Chemical composition				Ultimate tensile strength min.	Density	Tensile strength ^c	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength	Rotating fatigue limit ^d 90 % survival	Apparent hardness	
	C combined	Cu	Fe	Total other elements max.	R_m MPa	g/cm ³	R_m MPa	A ₂₅ %	GPa		J	(0,1 %) MPa	MPa	MPa	HV10	Rockwell
F-05C2-410H ^a	0,3 to 0,6	1,3 to 3,0	Balance	2	410	6,2	480	< 1	110	0,25	3	390	660	190	270	19 HRC
F-05C2-500H ^a	0,3 to 0,6	1,3 to 3,0	Balance	2	500	6,6	580	< 1	115	0,25	5	520	800	220	310	27 HRC
F-05C2-620H ^a	0,3 to 0,6	1,3 to 3,0	Balance	2	620	7,0	690	< 1	140	0,27	7	660	930	260	390	36 HRC
F-08C2-360H ^b	0,6 to 0,9	1,3 to 3,0	Balance	2	360	6,2	470	< 1	110	0,25	4	430	690	180	290	22 HRC
F-08C2-500H ^b	0,6 to 0,9	1,3 to 3,0	Balance	2	500	6,6	570	< 1	115	0,25	6	560	830	230	360	33 HRC
F-08C2-620H ^b	0,6 to 0,9	1,3 to 3,0	Balance	2	620	7,0	690	< 1	140	0,27	6	690	1 000	270	430	40 HRC
F-08C2-670H ^b	0,6 to 0,9	1,3 to 3,0	Balance	2	670	7,2	750	< 1	155	0,28	7	750	1 070	290	470	44 HRC

Heat-treated tensile properties were derived from machined test bars according to ISO 2740.

^a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil-quenched and tempered at 180 °C for 1 h.

^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil-quenched and tempered at 180 °C for 1 h.

^c Tensile yield and ultimate tensile strength are approximately the same for heat-treated materials.

^d Machined test pieces according to ISO 3928.

Table 7 — Ferrous materials for structural parts: phosphorus steels — As-sintered

Grade		Normative values					Informative values											
		Chemical composition					Tensile yield strength min.	Density	Tensile strength	Tensile yield strength	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Transverse rupture strength	Bending fatigue limit 90 % survival ^b	Apparent hardness	
		C combined	P	Cu	Fe	Total other elements max.	$R_{p0,2}$ MPa	ρ g/cm ³	R_m MPa	$R_{p0,2}$ MPa	A_{25} %	GPa		J	MPa	MPa	HV5	Rockwell
		%	%	%	%	%												
Phosphorus steel ^a	F-00P05-180	< 0,1	0,40 to 0,50	—	Balance	2	180	6,6	300	210	4	115	0,25	18	600	95	70	40 HRB
	F-00P05-210	< 0,1	0,40 to 0,50	—	Balance	2	210	7,0	400	240	9	140	0,27	30	900	125	120	60 HRB
Phosphorus-carbon steel	F-05P05-270	0,3 to 0,6	0,40 to 0,50	—	Balance	2	270	6,6	400	305	3	115	0,25	9	700	125	130	65 HRB
	F-05P05-320	0,3 to 0,6	0,40 to 0,50	—	Balance	2	320	7,0	480	365	5	140	0,27	15	1 000	160	150	72 HRB
Copper-phosphorus steel	F-00C2P-260	< 0,3	0,40 to 0,50	1,5 to 2,5	Balance	2	260	6,6	400	300	3	115	0,25	—	—	115	120	60 HRB
	F-00C2P-300	< 0,3	0,40 to 0,50	1,5 to 2,5	Balance	2	300	7,0	500	340	6	140	0,27	—	—	145	140	69 HRB
Copper-phosphorus-carbon steel	F-05C2P-320	0,3 to 0,6	0,40 to 0,50	1,5 to 2,5	Balance	2	320	6,6	450	360	2	115	0,25	—	820	135	140	69 HRB
	F-05C2P-380	0,3 to 0,6	0,40 to 0,50	1,5 to 2,5	Balance	2	380	7,0	550	400	3	140	0,27	—	1 120	165	160	74 HRB
Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.																		
^a Consultation with the supplier is recommended before these materials are used in magnetic applications. Some soft magnetic PM materials are standardized in IEC 60404-8-9.																		
^b As-sintered test pieces (sintered surfaces) according to ISO 3928.																		

Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.

^a Consultation with the supplier is recommended before these materials are used in magnetic applications. Some soft magnetic PM materials are standardized in IEC 60404-8-9.^b As-sintered test pieces (sintered surfaces) according to ISO 3928.

Table 8 — Ferrous materials for structural parts: nickel steels — As-sintered

Grade	Normative values					Informative values										Apparent hardness		
	Chemical composition					Tensile yield strength min.	Density	Tensile strength	Tensile yield strength	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength			Rotating fatigue limit ^a 90 % survival ^a
	C combined	Ni	Cu	Fe	Total other elements max.													
F-05N2-140	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	140	6,6	280	170	1,5	115	0,25	8	170	450	100	80	44 HRB
F-05N2-180	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	180	7,0	360	220	2,5	140	0,27	20	210	740	130	130	62 HRB
F-05N2-210	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	210	7,2	410	240	4,0	155	0,28	28	240	860	150	145	69 HRB
F-05N2-240	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	240	7,4	480	280	5,5	170	0,28	46	280	1030	180	170	78 HRB
F-08N2-220	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	220	6,8	350	260	1,5	130	0,27	9	260	660	120	145	68 HRB
F-08N2-260	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	260	7,0	430	300	1,5	140	0,27	13	300	800	150	160	74 HRB
F-08N2-300	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	300	7,2	515	325	2,2	155	0,28	18	325	985	180	175	80 HRB
F-05N4-180	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	180	6,6	285	220	1,0	115	0,25	8	240	500	110	105	53 HRB
F-05N4-240	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	240	7,0	410	280	3,0	140	0,27	20	280	830	150	145	71 HRB
F-05N4-310	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	310	7,4	620	340	4,5	170	0,28	45	310	1 210	220	185	84 HRB
F-08N4-300	0,6 to 0,9	3,5 to 4,5	0,0 to 2,0	Balance	2	300	6,8	420	320	1,0	130	0,27	9	320	720	150	160	75 HRB
F-08N4-330	0,6 to 0,9	3,5 to 4,5	0,0 to 2,0	Balance	2	330	7,0	480	360	1,0	140	0,27	11	360	850	170	175	80 HRB
F-08N4-380	0,6 to 0,9	3,5 to 4,5	0,0 to 2,0	Balance	2	380	7,2	550	410	1,0	155	0,28	15	410	1 030	190	205	87 HRB

Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.
Machined test pieces according to ISO 3928.

Properties were derived from pressed and sintered test pieces (not machined) according to ISO 2740.

^a Machined test pieces according to ISO 3928.

Table 9 — Ferrous materials for structural parts: nickel steels — Heat-treated

Grade	Normative values					Informative values												
	Chemical composition					Ultimate tensile strength min.	Density	Tensile strength ^c	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength	Rotating fatigue limit ^d 90 % survival	Apparent hardness		
	C combined	NI	Cu	Fe	Total other elements max.													
	%	%	%	%	%	R _m MPa	ρ g/cm ³	R _m MPa	A ₂₅ %	GPa		J	(0,1 %) MPa	MPa	MPa	MPa	HV10	Rockwell
F-05N2-550H ^a	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	550	6,6	620	< 1	115	0,25	5	410	830	180	290	23 HRC	
F-05N2-800H ^a	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	800	7,0	900	< 1	140	0,27	7	600	1 200	260	350	31 HRC	
F-05N2-1070H ^a	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	1 070	7,2	1 100	< 1	155	0,28	9	830	1 480	320	390	36 HRC	
F-05N2-1240H ^a	0,3 to 0,6	1,5 to 2,5	0,0 to 2,5	Balance	2	1 240	7,4	1 280	< 1	170	0,28	13	970	1 720	370	430	40 HRC	
F-08N2-600H ^b	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	600	6,7	620	< 1	120	0,25	5	680	830	200	310	26 HRC	
F-08N2-900H ^b	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	900	7,0	1 000	< 1	140	0,27	7	940	1 280	320	380	35 HRC	
F-08N2-1070H ^b	0,6 to 0,9	1,5 to 2,5	0,0 to 2,5	Balance	2	1 070	7,2	1 170	< 1	155	0,28	9	1 120	1 520	370	420	39 HRC	
F-05N4-600H ^a	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	600	6,6	640	< 1	115	0,25	6	510	860	190	270	21 HRC	
F-05N4-900H ^a	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	900	7,0	930	< 1	140	0,27	9	710	1 380	290	350	31 HRC	
F-05N4-1240H ^a	0,3 to 0,6	3,5 to 4,5	0,0 to 2,0	Balance	2	1 240	7,4	1 280	< 1	170	0,28	18	910	1 930	390	430	40 HRC	
Heat-treated tensile properties were derived from machined test bars according to ISO 2740.																		
^a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil-quenched and tempered at 260 °C for 1 h.																		
^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil-quenched and tempered at 260 °C for 1 h.																		
^c Tensile yield and ultimate tensile strength are approximately the same for heat-treated materials.																		
^d Machined test pieces according to ISO 3928.																		

Table 10 — Ferrous materials for structural parts: diffusion-alloyed nickel-copper-molybdenum steels — As-sintered

Grade ^a	Normative values						Informative values													
	Chemical composition						Tensile yield strength min.	Density	Tensile strength	Tensile yield strength	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength	Transverse rupture strength	Rotating fatigue limit 90 % survival ^b	Bending fatigue limit 90 % survival ^c	Apparent hardness	
	C.combined	Ni	Cu	Mo	Fe	Total other elements max.														
	%	%	%	%	%	%	$R_{p0,2}$ MPa	ρ g/cm ³	R_m MPa	$R_{p0,2}$ MPa	A ₂₅ %	GPa		J	(0,1 %) MPa	MPa	MPa	MPa	HV5	Rockwell
FFD-05N2C-360	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	360	6,9	540	390	2	135	0,27	14	350	1 040	190	170	155	74 HRB
FFD-05N2C-400	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	400	7,1	590	420	3	150	0,27	22	380	1 200	220	195	180	81 HRB
FFD-05N2C-440	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	440	7,4	680	460	4	170	0,28	38	430	1 450	260	220	210	86 HRB
FFD-08N2C-350	0,6 to 0,9	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	350	6,8	500	410	< 1	130	0,27	10	410	980	195	190	175	80 HRB
FFD-08N2C-390	0,6 to 0,9	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	390	7,0	580	450	1	140	0,27	14	450	1 160	240	210	190	84 HRB
FFD-08N2C-430	0,6 to 0,9	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	430	7,2	680	490	1	155	0,28	20	490	1 300	300	230	215	87 HRB
FFD-05N4C-400	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	400	6,9	650	445	1	135	0,27	21	410	1 220	—	205	170	79 HRB
FFD-05N4C-420	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	420	7,1	750	465	2	150	0,27	28	440	1 380	—	215	200	85 HRB
FFD-05N4C-450	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	450	7,4	875	485	3	170	0,28	39	510	1 630	290	235	230	89 HRB
FFD-08N4C-360	0,6 to 0,9	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	360	6,8	540	410	1	130	0,27	14	450	1 000	—	240	205	86 HRB
FFD-08N4C-390	0,6 to 0,9	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	390	7,0	650	440	1	140	0,27	19	480	1 190	—	255	220	88 HRB
FFD-08N4C-410	0,6 to 0,9	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	410	7,2	760	460	1,5	155	0,28	24	500	1 380	—	270	235	90 HRB

These materials are produced from diffusion-alloyed powders with the addition of elemental graphite.

Machined test pieces according to ISO 3928.

As-sintered test pieces (sintered surfaces) according to ISO 3928.

Table 11 — Ferrous materials for structural parts: diffusion-alloyed nickel-copper-molybdenum steels — Heat-treated

Grade ^a	Normative values						Informative values											
	Chemical composition						Ultimate tensile strength min.	Density	Tensile strength ^c	Elongation	Young's modulus	Poisson's ratio	Unnotched Charpy impact	Compressive yield strength (0,1 %) MPa	Transverse rupture strength	Rotating fatigue limit ^d 90 % survival ^d	Apparent hardness	
	C combined	Ni	Cu	Mo	Fe	Total other elements max.												
	%	%	%	%	%	%	R_m MPa	ρ g/cm ³	R_m MPa	A ₂₅ %	GPa	J			MPa	MPa	HV10	Rockwell
FD-05N2C-700H ^b	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	700	6,8	770	<1	130	8	950	1 150	310	340	30 HRC	
FD-05N2C-950H ^b	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	950	7,1	1 020	<1	150	11	1 170	1 420	430	400	37 HRC	
FD-05N2C-1100H ^b	0,3 to 0,6	1,5 to 2,0	1,3 to 1,7	0,4 to 0,6	Balance	2	1 100	7,4	1 170	<1	170	15	1 380	1 650	520	480	45 HRC	
FD-05N4C-725H ^b	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	725	6,8	780	<1	130	8	890	1 130	—	320	31 HRC	
FD-05N4C-930H ^b	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	930	7,1	1 000	<1	150	10	1 060	1 420	—	390	36 HRC	
FD-05N4C-1100H ^b	0,3 to 0,6	3,6 to 4,4	1,3 to 1,7	0,4 to 0,6	Balance	2	1 100	7,4	1 170	<1	170	15	1 240	1 650	—	460	43 HRC	
Heat-treated tensile properties were derived from machined test bars according to ISO 2740.																		
^a These materials are produced from diffusion-alloyed powders with the addition of elemental graphite.																		
^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil-quenched and tempered at 180 °C for 1 h.																		
^c Tensile yield and ultimate tensile strength are approximately the same for heat-treated materials.																		
^d Machined test pieces according to ISO 3928.																		