



BSI Standards Publication

Paints and varnishes - Determination of hiding power

Part 1: Kubelka-Munk method for white and light-coloured paints

National foreword

This British Standard is the UK implementation of EN ISO 6504-1:2019. It is identical to ISO 6504-1:2019. It supersedes BS EN ISO 6504-1:2006 (dual numbered as BS 3900-D7:1983), which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/10, Test methods for paints.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 97801 2

ICS 87.040

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

English Version

Paints and varnishes - Determination of hiding power -
Part 1: Kubelka-Munk method for white and light-coloured
paints (ISO 6504-1:2019)

Peintures et vernis - Détermination du pouvoir
masquant - Partie 1: Méthode de Kubelka-Munk pour
les peintures blanches et les peintures claires (ISO
6504-1:2019)

Beschichtungsstoffe - Bestimmung des Deckvermögens
- Teil 1: Verfahren nach Kubelka-Munk für weiße und
helle Beschichtungen (ISO 6504-1:2019)

This European Standard was approved by CEN on 13 May 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, North Macedonia, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 6504-1:2019) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6504-1:2006.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6504-1:2019 has been approved by CEN as EN ISO 6504-1:2019 without any modification.

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Kubelka-Munk equations.....	2
6 Apparatus and materials.....	3
6.1 Substrates.....	3
6.1.1 Determination of R_B	3
6.1.2 Determination of R_∞	4
6.2 Film applicators.....	4
6.3 Reflectometer.....	4
6.4 Template.....	4
7 Limitations.....	4
8 Sampling.....	4
9 Procedure.....	4
9.1 Determination of R_∞	4
9.2 Determination of R_B	5
9.2.1 Preparation of test films.....	5
9.2.2 Measurement of reflectance R_B	5
9.3 Determination of film thickness.....	6
9.3.1 General.....	6
9.3.2 Method using polyester film.....	6
9.3.3 Method using black glass plates.....	6
10 Expression of results.....	6
10.1 Calculation of wet film thickness.....	6
10.2 Calculation of hiding power.....	7
11 Precision.....	7
11.1 Repeatability (r).....	7
11.2 Reproducibility (R).....	7
12 Test report.....	7
Annex A (informative) Graphs for determination of St from R_B and R_∞ for $R_g = 0,80$.....	8
Annex B (informative) Table of values of reflectivity R_∞ and factor α for $R_g = 0,80$.....	33
Annex C (informative) Examples of the calculation of hiding power from measurements of R_B and R_∞.....	34
Bibliography.....	36

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test method for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 6504-1:1983), which has been technically revised. The main changes compared to the previous edition are as follows:

- a) the normative references in [Clause 2](#) have been updated;
- b) [Clause 3](#) for terms and definitions has been added;
- c) [Clause 7](#) for limitations has been added;
- d) the term "contrast ratio" has been changed to "hiding power" throughout the text;
- e) it has been clarified that the reflectance R_g needs to be measured and that the graphs in [Annex A](#) and values in [Table B.1](#) are only examples for $R_g = 0,80$.

A list of all parts in the ISO 6504 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

ISO 6504-3^[1] specifies a method for determining the hiding power of paints at a fixed spreading rate, by applying paint films to black and white charts and to polyester film respectively. It depends on the observation that there is a linear relationship between hiding power and reciprocal film thickness, at least over a limited range of film thickness.

Hiding power of paints is generally defined as the spreading rate required to give a hiding power of 98 %. To determine this by the method specified in ISO 6504-3^[1] would be time-consuming and require considerable extrapolation which often exceeds the limit of linearity of the relationship between hiding power and spreading rate. Therefore, this method for the determination of hiding power, involving the Kubelka-Munk (K-M) equations which relate scattering and absorption coefficients to optical properties, has also been standardized.

Paints and varnishes — Determination of hiding power —

Part 1:

Kubelka-Munk method for white and light-coloured paints

1 Scope

This document specifies a method for determining the hiding power (spreading rate necessary to give a hiding power of 98 %) of white or light-coloured paints. It is applicable to paint films having the tristimulus value of $Y \geq 70$ and hiding power > 80 %. It is not applicable to fluorescent or metallic paints.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pycnometer method*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

light-coloured paint

coating with tristimulus values Y and Y_{10} greater than 25, measured with a spectrophotometer on a black and white substrate

4 Principle

The method is based on the Kubelka and Munk equations relating the scattering and absorption coefficients of pigmented films to their colour and opacity.

For the determination of hiding power, both the reflectance (R_B) of a paint film of thickness t on a black background and the reflectivity (R_∞) are required for introduction into the Kubelka-Munk equations (Clause 5).

5 Kubelka-Munk equations

The Kubelka-Munk (K-M) equations required are

$$a = \frac{1}{2} \left(R_{\infty} + \frac{1}{R_{\infty}} \right) \quad (1)$$

$$b = a - R_{\infty} \quad (2)$$

$$R_B = \frac{1}{a + b \coth bSt} \quad (3)$$

$$R = \frac{1 - R_g (a - b \coth bSt)}{a + b \coth bSt - R_g} \quad (4)$$

where

R_{∞} is the reflectivity, i.e. the reflectance of a paint film of such thickness that further increase in thickness gives no further change in reflectance;

R_B is the reflectance of a paint film of thickness t applied over a black background;

R is the reflectance of a paint film of thickness t applied over a white background of determined reflectance R_g ;

S is the scattering coefficient per micrometre (μm^{-1});

t is the thickness, in micrometres, of the paint film.

When using [Formulae \(1\) to \(4\)](#) with this method, the measured CIE tristimulus values Y divided by 100 are inserted for R , R_B and R_{∞} , respectively.

The hiding power $V_{0,98}$ is the spreading rate necessary to give a hiding power (R_B/R) of 0,98, and is determined via the equivalent film thickness $t_{0,98}$ according to the formula

$$V = \frac{1\,000}{t}$$

where

V is the hiding power, in square metres per litre;

t is the thickness, in micrometres, of the wet paint film.

From [Formulae \(3\)](#) and [\(4\)](#), when the hiding power (R_B/R) is equal to 0,98

$$\frac{a - 0,8 + b \coth bSt_{0,98}}{[a + b \coth bSt_{0,98}] \{1 - 0,8[a - b \coth bSt_{0,98}]\}} = 0,98$$

or after, rearrangement

$$t_{0,98} = \frac{1}{bS} \operatorname{arccoth} \left(\frac{0,02 + \sqrt{D}}{1,568 b} \right) \quad (5)$$

where

$$D = 3,136 a [1 - 0,98(1 - 0,8a)] - 2,508 4$$

and

$$V = \frac{1\,000}{t} = \frac{1\,000 bS}{\operatorname{arccoth} \left(\frac{0,02 + \sqrt{D}}{1,568 b} \right)} =_{\infty} S \quad (6)$$

NOTE 1 If $y = \coth x$, $x = \operatorname{arccoth} y$.

NOTE 2 It can be seen that for constant values of R_g and hiding power ($V_{0,98}$), factor α is a function of R_{∞} .

The scattering coefficient S is determined from a rearrangement of [Formula \(3\)](#), the values of a and b being known by calculation from [Formulae \(1\)](#) and [\(2\)](#) respectively, as follows:

$$St = \frac{1}{b} \operatorname{arccoth} \left(\frac{1 - aR_B}{bR_B} \right) \quad (7)$$

To simplify the calculations, graphs are available for the determination of the product St from measured values of R_g and R_{∞} .

The scattering coefficient S is calculated by dividing St by the film thickness t , and $V_{0,98}$ is obtained from [Formulae \(5\)](#) and [\(6\)](#). A table of values of α for various values of R_{∞} (see [Table B.1](#)) simplifies the calculation.

NOTE 3 Suitable tables and graphs are for example referred to in ASTM D2805. [Table B.1](#) is taken, with modifications, from ASTM D2805-80[2] and the graphs in [Annex A](#) are from Reference [3].

6 Apparatus and materials

6.1 Substrates

6.1.1 Determination of R_B

6.1.1.1 Glass plates, black, plane, polished, not less than 6 mm thick and of dimensions at least 200 mm × 200 mm, or

6.1.1.2 Polyester film, clear, untreated, transparent, of uniform thickness between 30 µm and 100 µm, and of dimensions at least 100 mm × 150 mm, together with a glass plate as specified in [6.1.1.1](#).

NOTE Commercially available polyester sheet has been found to be satisfactory.

6.1.2 Determination of R_{∞}

6.1.2.1 Smooth surfaced paper charts, readily wetted by, but impervious to, solvent and water thinned paints, and similar in reflectance to the paint to be tested.

Suitable chart colours are grey for paints of low reflectivity and white for paints of high reflectivity. Alternatively, ceramic tiles or glass may be used.

6.2 Film applicators

A series of film applicators giving films of uniform thickness within the range 40 μm to 150 μm is required. For application to glass, bar applicators are suitable. For application to polyester film or paper charts, wirewound applicators are more suitable.

The film laid down shall be at least 150 mm wide (using glass) or 70 mm wide (using polyester film) to cover areas, at a uniform thickness, of at least 100 mm $\times$ 125 mm or 60 mm $\times$ 60 mm respectively. The application of uniform films is facilitated by the use of automatic applicators, which are recommended.

6.3 Reflectometer

A photoelectric instrument is required, giving an indicated reading proportional to the intensity of light reflected from the surface under test to an accuracy of 0,1 % of full scale deflection, and having a spectral response approximating to the product of the relative spectral energy distribution of CIE standard illuminant D 65 and the colour matching function $\bar{y}(\lambda)$ of the CIE standard observer.

It is recognized that the relative geometrical arrangement of the illuminating beam and the light detector can affect the measurement of reflectance, but it is considered that variations arising from this factor in commercial reflectometers should be considerably less than the figures for reproducibility stated in [11.2](#). In the event of dispute, 8°/diffuse geometry, without gloss trap, should be used.

For other than reference purposes, CIE illuminant C may be used.

6.4 Template

A rectangular metal template with minimum dimensions of 100 mm $\times$ 125 mm is required for films applied to black glass. For films on polyester film, a metal template or die stamp with minimum dimensions of 60 mm $\times$ 60 mm is required.

7 Limitations

Temperature and humidity are important parameters affecting test results. Deviations from the requirements specified can lead to results that are not comparable. However, the interested parties may agree upon alternative parameters and these parameters shall be reported.

8 Sampling

Take a representative sample of the product to be tested as described in ISO 15528.

Examine and prepare the sample for testing as described in ISO 1513.

9 Procedure

9.1 Determination of R_{∞}

Measure the reflectance R_g of the uncoated paper substrate. Apply a few millilitres of the paint sample in a line across one end of a paper substrate and spread it immediately by drawing down a suitable

applicator at a steady rate so as to give a uniform film thickness. Repeat the operation so as to provide uniform films having dry film thicknesses of about 75 µm, 100 µm, 125 µm and 150 µm. Dry the paint as described in 9.2.1.4. Measure the reflectance of each paint film at four positions on each coated paper. Record the value of reflectance which is independent of the film thickness as the reflectivity R_{∞} .

If the reflectance is still increasing when the film thickness reaches 150 µm, further coats should be applied until a constant reflectance is obtained.

9.2 Determination of R_B

9.2.1 Preparation of test films

9.2.1.1 General

Apply a film thickness that will give a dry film having a reflectance at least 0,02 lower than the reflectivity R_{∞} of the paint sample.

9.2.1.2 Method using polyester film

Prepare the polyester film (6.1.1.2) for coating by either

- a) spreading it on a black glass plate (6.1.1.1) which has first been moistened with just sufficient white spirit (a few drops), to hold the film in position by surface tension. Ensure that none of the liquid wets the upper surface of the film and that no air bubbles are trapped under it;

or, if wirewound applicators are to be used

- b) by fixing the polyester film at one end and laying it over a flat rubber block.

Apply a few millilitres of the paint sample, according to the film thickness required, in a line across one end of the polyester film and spread it immediately by drawing down a suitable applicator at a steady rate to give a uniform film thickness. Prepare a total of four test films in this way.

9.2.1.3 Method using black glass plates

Apply a few millilitres of the paint sample in a line across one end of a black glass plate (6.1.1.1) and spread it immediately by drawing down a suitable applicator at a steady rate to give a uniform film thickness. Repeat the application with different black glass plates (6.1.1.1) until four uniform films of approximately the same thickness have been prepared.

9.2.1.4 Drying and conditioning

With the coated substrates in a horizontal position, dry the paint by the appropriate procedure for the type of paint or as agreed between the parties. Maintain the dried test films at a temperature of $(23 \pm 2) ^\circ\text{C}$ in a dust free atmosphere having a relative humidity of $(50 \pm 5) \%$ for at least 24 h, but not more than 168 h, before carrying out the reflectance measurements.

9.2.2 Measurement of reflectance R_B

9.2.2.1 General

Variation in readings is likely to be the result of non-uniform application of the paint film and is dependent on the techniques used. If the precision (Clause 11) is not obtained, the technique should be re-examined.

9.2.2.2 Method using polyester film

Fix the coated polyester films over a black glass plate, introducing a few drops of white spirit between the underside of the film and the glass to ensure optical contact. Measure the reflectance of the test films at a minimum of four positions and calculate the mean reflectance R_B of each coated plate.

9.2.2.3 Method using black glass plates

Measure the reflectance R_B directly by means of the reflectometer (6.3), taking readings at a minimum of four positions on each coated plate, avoiding its edges, and calculate the mean reflectance R_B of each coated plate.

9.3 Determination of film thickness

9.3.1 General

The method using polyester film (see 9.3.2) is preferred. Other methods for measuring wet film thickness, based on those specified in ISO 2808, may also be found to be suitable.

9.3.2 Method using polyester film

By means of the metal template and a sharp knife or precision die stamp, cut equal areas of dimensions at least 60 mm × 60 mm from the centres of the coated polyester films.

Weigh the detached pieces to the nearest 0,1 mg. Remove the paint film by the use of a solvent which has been found to have no effect on the dry mass of the polyester film, and, after thorough drying, reweigh the film. Record the mass m of the paint film, i.e. the difference in mass between the coated and uncoated polyester film and repeat the procedure with the other three films tested.

If difficulty is experienced in removing the paint film with solvent, an approximation to the dry film mass may be obtained from the difference in mass between coated and uncoated polyester films of the same area.

9.3.3 Method using black glass plates

Cover the area of the film previously used for the measurement of reflectance R_B with the metal template (6.4), ensuring that the template is not within 20 mm of any edge of the film. Scrape away and discard the excess film around the template using a fresh razor blade in a holder. Remove the template and scrape the remaining film from the substrate on to a tared weighing dish. Manipulate the razor blade at all times so that the blade is almost flat on the glass and cannot nick or scratch the glass substrate. Record the mass m , to the nearest 0,1 mg, and repeat the procedure with the other three films tested.

10 Expression of results

10.1 Calculation of wet film thickness

Calculate the wet film thickness of each of the four films, from the formula

$$t = \frac{m}{A \times \rho \times NV} \times 10^8$$

where

t is the wet film thickness, in micrometres;

m is the mass, in grams, of the paint film;

A is the area, in square millimetres, of the template;

ρ is the density, in grams per millilitre, of the paint, determined by the method specified in ISO 2811-1;

NV is the non-volatile matter content, expressed as a percentage by mass, of the paint, determined by the method specified in ISO 3251.

10.2 Calculation of hiding power

Calculate the hiding power, $V_{0,98}$, using the formulae given in [Clause 5](#), from the measured values of R_B and t for each film, and from the mean value of R_∞ .

Examples of the calculations, using both the table and graphs and directly from the formulae, are given in [Annex C](#).

11 Precision

11.1 Repeatability (r)

The value below which the absolute difference between two single test results on identical material, obtained by one operator in one laboratory using the same equipment within a short interval of time using the standardized test method, may be expected to lie with a 95 % probability, is 2 %.

11.2 Reproducibility (R)

The value below which the absolute difference between two single test results on identical material, obtained by operators in different laboratories, using the standardized test method, may be expected to lie with a 95 % probability, is 6 %.

12 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the paint tested;
- b) a reference to this document (i.e. ISO 6504-1);
- c) the result of the test;
- d) the paint density and the non-volatile matter content, expressed as a percentage by mass, used in the calculation of the test result;
- e) the drying time (and/or stoving conditions);
- f) whether black glass plates or polyester film were used as the substrate;
- g) any deviation, by agreement or otherwise, from the procedure specified;
- h) any unusual features (anomalies) observed during the test;
- i) the date of the test.