

CONFIRMED
DECEMBER 2007

Adhesives — Guide to the selection of standard laboratory ageing conditions for testing bonded joints

The European Standard EN ISO 9142:2003 has the status of a
British Standard

ICS 83.180

National foreword

This British Standard is the official English language version of EN ISO 9142:2003. It is identical with ISO 9142:2003. It supersedes BS EN 29142:1993 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/52, Adhesives, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii to iv, pages 1 to 24, the Annex ZA page and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments
15070 Corrigendum No. 1	6 April 2004	Corrected EN ISO foreword page and incorporation of Annex ZA

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 8 January 2004

© BSI 6 April 2004

English version

Adhesives - Guide to the selection of standard laboratory ageing conditions for testing bonded joints (ISO 9142:2003)

Adhésifs - Guide pour la sélection de conditions normales d'essai de vieillissement en laboratoire des assemblages collés (ISO 9142:2003)

Klebstoffe - Auswahlrichtlinien für Labor-Alterungsbedingungen zur Prüfung von Klebverbindungen (ISO 9142:2003)

This European Standard was approved by CEN on 8 December 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

CORRECTED 2004-03-03

Foreword

This document (EN ISO 9142:2003) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 193 "Adhesives", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

This document supersedes EN 29142:1993.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 9142:2003 has been approved by CEN as EN ISO 9142:2003 without any modifications.

NOTE Normative references to International Standards are listed in Annex ZA (normative).

INTERNATIONAL STANDARD

**ISO
9142**

Second edition
2003-12-15

Adhesives — Guide to the selection of standard laboratory ageing conditions for testing bonded joints

*Adhésifs — Guide pour la sélection de conditions normales d'essai de
vieillessement en laboratoire des assemblages collés*



Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Materials	2
4 Apparatus	2
5 Specimens	2
6 Procedure	2
7 Expression of results	3
8 Test report	4
Annex A (normative) General conditions of ageing	5
Annex B (normative) Atmospheric conditions for single-variable ageing	6
Annex C (normative) Atmospheric conditions for multi-variable ageing	7
Annex D (normative) Atmospheric conditions for cyclic ageing	8
Annex E (normative) Special procedures	23
Annex F (normative) Exposure to chemical attack	24

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9142 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 9142:1990), of which it constitutes a minor revision.

Adhesives — Guide to the selection of standard laboratory ageing conditions for testing bonded joints

1 Scope

This International Standard describes laboratory ageing conditions under which adhesive joints may be exposed to various environmental influences — climatic or chemical — for the purpose of assessing the effects of such influences on certain properties.

The ageing conditions are applicable to bonded assemblies and may be used to constitute a set of tests for the evaluation of an adhesive.

The results obtained using the procedures described in this International Standard are not necessarily applicable to the determination of the service life of a bonded assembly because there is no direct relation between the test results and the behaviour of a bonded assembly over a period of time under service conditions. However, for certain specific applications, experience with the procedures may enable a correlation to be established.

NOTE The ageing conditions should preferably be related to the specific application of the adhesive.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 175:1999, *Plastics — Methods of test for the determination of the effects of immersion in liquid chemicals*

ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing*

ISO 483:1988, *Plastics — Small enclosures for conditioning and testing using aqueous solutions to maintain relative humidity at constant value*

ISO 3205:1976, *Preferred test temperatures*

ISO 4587:2003, *Adhesives — Determination of tensile lap-shear strength of rigid-to-rigid bonded assemblies*

ISO 4588:1995, *Adhesives — Guidelines for the surface preparation of metals*

ISO 4892 (all parts), *Plastics — Methods of exposure to laboratory light sources*

ISO 6238:2001, *Adhesives — Wood-to-wood adhesive bonds — Determination of shear strength by compression loading*

ISO 9227:1990, *Corrosion tests in artificial atmospheres — Salt spray tests*

3 Materials

3.1 De-ionized or distilled water, having a conductivity less than 200 $\mu\text{S/m}$.

3.2 Materials for ageing tests under special environmental conditions (see appropriate annex).

4 Apparatus

4.1 Conditioning chamber, meeting the requirements of ISO 483, capable of being maintained at a temperature of $(23 \pm 2)^\circ\text{C}$ and a relative humidity of $(50 \pm 5)\%$.

4.2 Dry-heat chamber, ventilated and adjustable to a temperature between 20°C and 200°C .

4.3 Humid chamber, meeting the requirements of ISO 483, adjustable to a relative humidity between 25 % and 100 %. The chamber shall be equipped with

- a) a device to enable the temperature to be measured to within 1°C ;
- b) a device to enable the relative humidity to be measured to within 3 % R.H.

4.4 Cold chamber, adjustable to temperatures of $(-20 \pm 3)^\circ\text{C}$ and $(-40 \pm 3)^\circ\text{C}$.

4.5 Controlled-pressure chamber, capable of operating at a pressure of 0,6 MPa¹⁾ and at an underpressure of 0,092 MPa.

5 Specimens

5.1 Number and type

The number of test specimens, and the type used, will depend on the properties to be measured and the required ageing conditions. The test specimens shall be prepared in accordance with the requirements of the appropriate ISO standard test method. Prepare a sufficient number of specimens to provide homogeneous sets of samples for testing and to provide control samples. The following International Standards, which do not constitute an exhaustive list, are applicable: ISO 4587, ISO 4588, ISO 6238.

5.2 Conditioning

Specimens shall be conditioned in the conditioning chamber (4.1) for a minimum duration of 24 h before being subjected to ageing. The conditioning shall be carried out after the adhesive has been cured in accordance with the materials specification or the methods specified by the manufacturer of the adhesive.

6 Procedure

6.1 Tests before ageing

Determine the properties required for the sample under test by the appropriate test method, using specimens conditioned in accordance with 5.2.

1) 1 MPa = 10 bar

6.2 Ageing

Expose conditioned specimens to the environmental conditions as defined in Annex A to Annex F, as required.

6.3 Tests after ageing

Determine the properties after ageing in accordance with the procedure(s) of the appropriate standard(s). Unless there are indications to the contrary in the Annexes, condition test specimens in the conditioning chamber (4.1)

- for (3 ± 1) h in the case of specimens exposed at a relative humidity higher than 50 %,
- for at least 24 h for all other specimens,

before determining the properties.

In addition to the test results, all changes visible during the ageing and testing periods, including mode of failure, shall be noted.

6.4 Controls

For control purposes, a representative group of specimens shall be kept in the conditioning chamber (4.1) for the period of time covered by the ageing conditions selected.

7 Expression of results

For properties that can be measured, the results obtained are expressed as either

- absolute values or
- a relative variation with respect to the initial value.

For properties that cannot be measured, the nature of the effects observed shall be noted, e.g. rupture between the substrate and adhesive, failure of cohesion of the adhesive joint due to partial or total corrosion of the substrate beneath the adhesive, etc.

NOTE It may be worth verifying that the variation in a measured property is caused only by the ageing process from the following three values:

- A* the value of the property measured before accelerated ageing;
- B* the value of the same property measured on the control specimen which has undergone only intrinsic ageing at $(23 \pm 2) ^\circ\text{C}$ and $(50 \pm 5) \% \text{ R.H.}$ (see 6.4);
- C* the value of the property measured after ageing.

This can be done by calculating the following ratios:

- a) $[(A - B)/A] \times 100$ (this ratio represents the intrinsic ageing during the period concerned);
- b) $[(A - C)/A] \times 100$ (this ratio represents the overall ageing due to intrinsic ageing and the accelerated ageing under the conditions specified in this International Standard);
- c) $[(B - C)/A] \times 100$ (this ratio represents the degree of ageing due to ageing under the conditions specified in this International Standard).