



BSI Standards Publication

Paper and board — Determination of CIE whiteness, $C/2^\circ$ (indoor illumination conditions)

National foreword

This British Standard is the UK implementation of ISO 11476:2016. It supersedes BS ISO 11476:2010 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 83773 9

ICS 85.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2016.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

BS ISO 11476:2016

ISO
11476

Third edition
2016-08-15

Paper and board — Determination of CIE whiteness, C/2° (indoor illumination conditions)

*Papier et carton — Détermination du degré de blanc CIE C/2°
(éclairage intérieur)*



Reference number
ISO 11476:2016(E)
Documents
Document Sharing Hub
© ISO 2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus and equipment	3
6 Calibration	4
7 Sampling and conditioning	5
8 Preparation of test pieces	5
9 Procedure	5
10 Calculation and expression of results	6
11 Precision	7
12 Test report	7
Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values	8
Annex B (normative) UV-calibration service	14
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 11476:2010), which has been technically revised. The major change is to allow for calculations using ASTM E308 for instruments that have bandpass correction and still maintain the non-bandpass-correction procedure.

It is based on the CIE whiteness formula, published in CIE Publication 15:2004, *Colorimetry*.

Paper and board — Determination of CIE whiteness, $C/2^\circ$ (indoor illumination conditions)

1 Scope

This International Standard specifies the procedure to be used for determining the CIE whiteness of papers and boards, in order to obtain values which correspond to the visual appearance of white papers and boards, with or without fluorescent whitening agents, when they are viewed indoors. It is based on radiance factor data obtained over the full visible spectral range (VIS) in contrast to the measurement of ISO brightness, which is limited to the blue region of VIS. This International Standard also specifies the procedures for the determination of CIE tint values and the fluorescent component of CIE whiteness.

In addition, it specifies a method for adjustment of the UV-content to correspond to that of CIE illuminant C,^{[10][12]} since the results obtained when fluorescent whitening agents are present are dependent upon the UV-content of the radiation falling upon the sample. The CIE illuminant C is taken to be representative of indoor illumination conditions because it contains a suitable proportion of UV radiation.^[7] This method is not applicable to coloured papers containing fluorescent dyes. It is specific to the situation where the fluorescence occurs in the blue region of the visible spectral range.

This International Standard is read in conjunction with ISO 2469.

NOTE 1 It is recognized that the CIE whiteness formula was developed in the context of the CIE standard illuminant D65,^[5] but the similarity between the relative spectral power curves for the C and D65 illuminants within the visible region and the closeness of their correlated colour temperatures (6 770 K and 6 500 K respectively) are taken as a justification for the use of the analogous whiteness formula with the CIE illuminant C.

NOTE 2 A related International Standard, ISO 11475, specifies the procedure for obtaining values corresponding to the appearance of papers viewed under the CIE standard illuminant D65.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE The symbols used here are selected to maintain consistency, wherever possible, with the CIE International Lighting Vocabulary ILV. While the definitions used here are based upon the CIE ILV, they have been adapted for this International Standard.

3.1 reflectance factor

R

ratio of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions

Note 1 to entry: The reflectance factor is usually expressed as a percentage.

3.2 intrinsic reflectance factor

R_{∞}

reflectance factor (3.1) of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

3.3 diffuse radiance factor

β

ratio of the diffusely reflected radiance of a body in a given direction to that of the perfect reflecting diffuser under specified conditions of irradiation

Note 1 to entry: For fluorescent (luminescent) materials, the specified conditions of irradiation in this International Standard are for CIE Illuminant C and the diffuse radiance factor is strictly the total radiance factor, β , which contains two components, the reflected radiance factor, β_R , and the luminescent radiance factor, β_L , so that

$$\beta = \beta_R + \beta_L$$

Note 2 to entry: For non-fluorescent materials, the diffuse radiance factor, β , is simply the *reflectance factor*, R (3.1).

3.4 intrinsic diffuse radiance factor

β_{∞}

diffuse radiance factor (3.3) of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

Note 1 to entry: For fluorescent (luminescent) materials, the intrinsic total radiance factor, β_{∞} , is the sum of two portions, the intrinsic reflected radiance factor, $\beta_{\infty,R}$, and the intrinsic luminescent radiance factor, $\beta_{\infty,L}$, so that

$$\beta_{\infty} = \beta_{\infty,R} + \beta_{\infty,L}$$

Note 2 to entry: For non-fluorescent materials, the intrinsic diffuse radiance factor, β_{∞} , is simply the *intrinsic reflectance factor*, R_{∞} (3.2).

3.5 CIE whiteness

W

measure of CIE whiteness derived from the CIE tristimulus values determined under the conditions specified in this International Standard

Note 1 to entry: The CIE whiteness is expressed in CIE whiteness units.