BS ISO 1304:2016

BSI Standards Publication

Rubber compounding ingredients — Carbon black — Determination of iodine adsorption number

Documents
Document Sharing Hub

Full document details: BS ISO 1304:2016

National foreword

This British Standard is the UK implementation of ISO 1304:2016. It supersedes BS ISO 1304:2006 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Raw materials (including latex) for use in the rubber industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 89099 4

ICS 83.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2016.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS ISO 1304:2016

INTERNATIONAL STANDARD

ISO 1304

Fifth edition
2016-10-15

Rubber compounding ingredients — Carbon black — Determination of iodine adsorption number

Ingrédients de mélange du caoutchouc — Noir de carbone — Détermination de l'indice d'adsorption d'iode

Reference number
ISO 1304:2016(E)

Documents
Document Sharing Hub

© ISO 2016

Full document details: BS ISO 1304:2016

COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub

Full document details: BS ISO 1304:2016

Contents

Page

Foreword ..... **iv**
1 Scope **1**
2 Normative references **1**
3 Principle **1**
4 Apparatus **2**
5 Reagents **3**
6 Preparation of solutions **3**
7 Standardization of the solutions **6**
7.1 General 6
7.2 Sodium thiosulfate solution 6
7.3 Iodine solution 7
8 Procedure **8**
8.1 Conditions of test 8
8.2 Sample preparation 8
8.3 Iodine number determination 8
9 Expression of results **9**
10 Verification using standard reference blacks **10**
11 Test report **10**
Annex A (informative) **Precision** **11**
Annex B (informative) **CAS numbers of reagents** **13**
Bibliography **14**

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS ISO 1304:2016

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fifth edition cancels and replaces the fourth edition (ISO 1304:2006), which has been technically revised with the following changes:

— Clause 2 "Normative references" has been updated;

— the preferred method is stated in the scope and in 7.2.5;

— 4.1 (analytical balance) and 4.12 (desiccator) have been updated;

— the tolerance of the weighting in 6.1.5 has been modified to 0,01 g;

— the precision data have been moved to an informative annex.

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS ISO 1304:2016

INTERNATIONAL STANDARD ISO 1304:2016(E)

Rubber compounding ingredients — Carbon black — Determination of iodine adsorption number

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies methods for the determination of iodine adsorption number of carbon blacks for use in the rubber industry. Two titration methods are described:

— method A: titration using a burette and starch as indicator;

— method B: potentiometric titration with an automatic titrator.

The iodine adsorption number is related to the surface area of a carbon black and is generally in agreement with the nitrogen surface area. However, it is significantly depressed in the presence of a high content of volatile or solvent-extractable materials; the iodine adsorption number therefore does not always provide a measure of the specific surface area of a carbon black. Ageing of carbon black can also influence the iodine number.

In case of dispute, the preferred method is method B (potentiometric titration).

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1126, *Rubber compounding ingredients — Carbon black — Determination of loss on heating*

3 Principle

A test portion of carbon black is dried, weighed and mixed vigorously with a measured volume of standard iodine solution. The mixture is then centrifuged. A measured volume of the clear iodine solution is titrated with a standard solution of sodium thiosulfate. From this titration value and the mass of the test portion, the iodine adsorption number of the carbon black is calculated.

© ISO 2016 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS ISO 1304:2016

4 Apparatus

Ordinary laboratory equipment (beakers, funnels, porcelain spoon, weighing bottles, etc.), plus the following:

4.1 Analytical balance, with sensitivities:

a) 0,01 g (for 6.1.5 and 7.3.5);

b) 0,1 mg (for other paragraphs).

4.2 Oven, preferably of the gravity-convection type, capable of temperature regulation to within ±1 °C at 125 °C and temperature uniformity to within ±5 °C.

4.3 Stoppered one-mark volumetric flasks, preferably class A in accordance with ISO 1042, of capacities:

a) 2 000 cm^3, with a tolerance of ±0,60 cm^3;

b) 1 000 cm^3, with a tolerance of ±0,40 cm^3.

4.4 Repetitive dispenser, 25 cm^3 capacity, calibrated to within ±0,03 cm^3 accuracy, or **one-mark pipettes**, high precision, of capacities:

a) 20 cm^3, with a tolerance of ±0,03 cm^3;

b) 25 cm^3, with a tolerance of ±0,03 cm^3.

If class A pipettes in accordance with ISO 648 are used, no calibration is necessary. In other cases, pipettes shall be calibrated to the nearest 0,01 cm^3 with distilled water, a temperature correction being made if necessary to show the true delivery at any volume used to within 0,01 cm^3. The true delivered volume is the read volume plus (or minus) the calibration correction at that volume. For high-precision volume determination (see 7.2.2, 7.3.2, 8.3.3, 8.3.6 and 8.3.8), it is recommended that the 20 cm^3 and 25 cm^3 pipettes have calibration corrections of the same magnitude and in the same sense.

4.5 Digital burettes, with 0,01 cm^3 increment counter and zero-reset control, calibrated to within ±0,05 cm^3 accuracy, or **burettes** (for method A only), high precision, side-arm filling, graduated in 0,05 cm^3 and with automatic zero, of capacities:

a) 25 cm^3, with a tolerance of ±0,05 cm^3;

b) 50 cm^3, with a tolerance of ±0,05 cm^3.

If class A burettes in accordance with ISO 385 are used, no calibration is necessary. In other cases, burettes shall be calibrated to the nearest 0,01 cm^3 with distilled water, a temperature correction being made if necessary to show the true delivery at any volume used to within 0,01 cm^3. The true delivered volume is the read volume plus (or minus) the calibration correction at that volume.

4.6 Stoppered bottles, with ground-glass stoppers, of capacities 250 cm^3 and 500 cm^3.

4.7 Glass bottle, with ground-glass stopper, of capacity 2 000 cm^3.

4.8 Amber-glass bottles, with ground-glass stoppers, of capacities 1 000 cm^3 and 2 000 cm^3.

© ISO 2016 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS ISO 1304:2016