

BS ISO 14531-3:2010



BSI Standards Publication

Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications

Part 3: Fittings for mechanical jointing
(including PE-X/metal transitions)

bsi.

...making excellence a habit.
AVA Document Sharing Hub

National foreword

This British Standard is the UK implementation of ISO 14531-3:2010. It supersedes BS ISO 14531-3:2006 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/88/2, Plastics piping for pressure applications.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 72194 6

ICS 23.040.20; 23.040.45; 75.200; 83.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2011.

Amendments issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
14531-3

Second edition
2010-12-01

Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications —

Part 3: Fittings for mechanical jointing (including PE-X/metal transitions)

Tubes et raccords en matières plastiques — Systèmes de tubes en polyéthylène réticulé (PE-X) pour le transport de combustibles gazeux — Série métrique — Spécifications —

Partie 3: Raccords pour assemblage mécanique (y compris transitions PE-X/métal)



Reference number
ISO 14531-3:2010(E)



Documents

Document Sharing Hub
© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	3
4 Materials	3
4.1 General	3
4.2 Strength	4
4.3 Chemical resistance	4
4.4 Lubricants	5
4.5 Reprocessable (re-work) material.....	5
5 Fittings.....	5
5.1 Design.....	5
5.2 Appearance	6
5.3 Dimensions	7
5.4 Mechanical performance	7
5.5 Validation of fitting design and design pressure DP_F	7
5.6 Performance requirements for fittings in conformity with ISO 10838	9
6 Elastomeric seals	9
7 Marking.....	9
7.1 Legibility.....	9
7.2 Damage.....	9
7.3 Minimum marking requirements.....	10
7.4 Labels	10
Annex A (normative) Resistance to gas constituents	11
Annex B (normative) Method of test of the integrity of a fitting after an external blow	12
Annex C (normative) Constant-strain thermal-cycling test.....	14
Annex D (informative) Validation of fitting design pressure DP_F at 20 °C (plastic bodied fittings)	16
Annex E (normative) Validation of fitting design pressure DP_F at 20 °C (metal bodied fittings)	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14531-3 was prepared by Technical Committee ISO/TC 138, *Plastic pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastic pipes and fittings for the supply of gaseous fuels*.

This second edition cancels and replaces the first edition (ISO 14531-3:2006), of which it constitutes a minor revision.

ISO 14531 consists of the following parts, under the general title *Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications*:

- *Part 1: Pipes*
- *Part 2: Fittings for heat-fusion jointing*
- *Part 3: Fittings for mechanical jointing (including PE-X/metal transitions)*
- *Part 4: System design and installation guidelines*

Introduction

Further to the publication of International Standards for crosslinked polyethylene (PE-X) hot-water pipes, it has become evident that the properties of PE-X, in particular its high fracture resistance and a recently established socket and saddle fusion-jointing capability, render it suitable for use in high-performance gas-distribution systems. The philosophy of ISO 14531 is to provide the basis for the introduction of PE-X gas pipe systems by the specification of a performance envelope beyond that covered by existing PE standards in order to take its application into regimes of higher operating pressures and extremes of operating temperature.

This part of ISO 14531 is therefore one part of a four-part system standard covering pipes, fittings for heat-fusion jointing, fittings for mechanical jointing and design and installation guidelines. The content is suitable for use by procurement authorities and distribution engineers responsible for the design, installation and operation of pipeline systems.

This part of ISO 14531 is structured to ensure the supply of mechanical fittings with an end-load resistance greater than that exhibited by the pipe(s) to which the fittings are connected.

Plastics pipes and fittings — Crosslinked polyethylene (PE-X) pipe systems for the conveyance of gaseous fuels — Metric series — Specifications —

Part 3: Fittings for mechanical jointing (including PE-X/metal transitions)

1 Scope

This part of ISO 14531 specifies the physical properties and mechanical-performance requirements for full-end-load-resistant mechanical fittings for use in the connection of crosslinked polyethylene (PE-X) pipes conforming to ISO 14531-1 and in the construction of transition assemblies for joining PE-X pipes to metal pipes having plain spigot, screw thread, compression socket and flange terminations. In addition, it lays down dimensional requirements and specifies some general material properties (including chemical resistance) together with a classification scheme for PE-X fitting materials produced in the form of pipe.

This part of ISO 14531, when used in conjunction with the other parts of ISO 14531, provides the basis for the design, manufacture and installation of PE-X piping systems (PE-X pipes, PE-X fusion fittings and mechanical fittings) for the supply of category D and category E hydrocarbon-based fuels (see ISO 13623) at

- a) maximum operating pressures (MOPs) up to and including 16 bar¹⁾ and
- b) a maximum operating temperature of +60 °C and
- c) a minimum operating temperature of
 - 1) –50 °C;
 - 2) –35 °C;
 - 3) –20 °C.

Conformity to this part of ISO 14531-3 of mechanical fittings produced in accordance with ISO 10838-1, ISO 10838-2 or ISO 10838-3 may be claimed subject to the satisfactory conclusion of the tests listed in 5.6 and an end-use restriction on operating temperatures to the temperature range –20 °C to +40 °C.

NOTE It is recognized that mechanical fittings conforming to ISO 10838-1, ISO 10838-2 or ISO 10838-3 are limited to a maximum operating temperature of 40 °C. Provision is made in ISO 14531-4 for the use on a restricted-temperature basis of ISO 10838 fittings conforming to 5.6 in conjunction with PE-X pipes conforming to ISO 14531-1. The fitting manufacturer's technical file should also be consulted for relevant supporting information.

For installation purposes, this part of ISO 14531 provides for the jointing of mechanical fittings to PE-X pipes within the temperature range –5 °C to +40 °C.

1) 1 bar = 10⁵ N/m² = 100 kPa.