



BSI Standards Publication

Plastics — Marine biodegradation testing — Preparation of optimized intertidal seawater and sediment

National foreword

This British Standard is the UK implementation of ISO 16623:2024.

The UK participation in its preparation was entrusted to Technical Committee PRI/89, Plastics - Environmental Aspects.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2024
Published by BSI Standards Limited 2024

ISBN 978 0 539 22709 3

ICS 13.020.40; 83.080.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 December 2024.

Amendments/corrigenda issued since publication

Date	Text affected



**International
Standard**

ISO 16623

**Plastics — Marine biodegradation
testing — Preparation of optimized
intertidal seawater and sediment**

*Plastiques — Essais de biodégradation en milieu marin —
Préparation d'eau de mer et de sédiments intertidaux optimisés*

**First edition
2024-12**

Reference number
ISO 16623:2024(en)

Full document details: BS ISO 16623:2024

© ISO 2024  **Documents**
Document Sharing Hub



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus	4
6 Procedure	4
6.1 General	4
6.2 Collection of sediment with less than 2 mm particle size and preparation of rinsed seawater	5
6.3 Preparation of refined sediment	5
6.4 Purification of seawater for biodegradation test from suspended seawater	5
7 Validity of preparation	6
7.1 Sediment for disintegration testing	6
7.2 Refined sediment for biodegradation testing	6
8 Preparation report of seawater and sediments	6
Annex A (informative) Diagram of seawater and sediment preparation — Seawater and sediment preparation by wet filtration and flotation	8
Annex B (informative) Preparation of seawater and sediments from seafloor sediments: Wet filtration and flotation of sediments	9
Annex C (informative) Evolved carbon dioxide of seawater and sediment prepared from seafloor sediments	11
Annex D (informative) Test validity of ISO 19679 — Validity of biodegradation test based on carbon dioxide evolved	13
Annex E (informative) Example of biodegradation of reference material by ISO 19679	15
Annex F (informative) Example of biodegradation of plastic films by ISO 19679 — Biodegradation of plastic films using rinsed seawater and sand gravel sediments	16
Annex G (informative) Example of live and total cell count in sediment and seawater: Live and total cell count in sediment and seawater by fluorescence method	17
Annex H (informative) Example of biodegradation of plastic films by ISO 19679	19
Annex I (informative) Interlaboratory test ISO 19679 and ISO 18830 final report	20
Bibliography	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The assessment of the degree of biodegradation of plastics in marine habitats is one effective measure to understand and evaluate the impact of reuse, recycling and environmental pollution of plastics. The biodegradation of plastics is the process, in which plastics are decomposed by heterotrophic microorganisms, such as bacteria and fungi, through enzymatic hydrolysis and subsequent metabolization. Marine biodegradation proceeds mainly in microbial consortia that form at the interface between seawater and plastics. This is because marine microorganisms live aerobically within biofilms at the interface between the liquid phase of seawater and solid phases such as gravel and shells.

The diversity of microbial consortia in the marine environment is high, depending on their natural environmental conditions. The species and number of microorganisms vary depending on the climate, ocean currents, tides, and topography. Considering the diverse habitats of these microorganisms, three types of biodegradation assessment methods have been developed:

- one-phase systems consisting of seawater or sediment and
- two-phase systems consisting of seawater and seafloor sediments.

However, due to the diversity of microorganisms even a biodegradable material such as cellulose, which is used as a reference material, gave biodegradation results that ranged from 0 to 100 percent in ring tests of these test methods. From the perspective of biodegradable plastic specification, it is thus necessary to optimize the preparation of natural inoculum for the biodegradation tests to avoid those fluctuations in experimental outcomes.

In order to reduce the impact of seasonal and regional variation in the marine inoculum composition, this document describes a method for preparing seawater and seafloor sediments. The prepared seawater and sediment can be used for the test methods defined in ISO 19679, ISO 18830, ISO 22404, ISO 23977-1, ISO 23977-2 and ISO 23832.

Prepared seawater for biodegradation tests is obtained by rinsing seafloor sediments with seawater. Sand and gravel mixtures with particle sizes from 250 µm to 2 mm are used as sediments to provide pore water flow, oxygen supply, seawater filtration and biofilm growth. Through the preparation of defined compositions of seawater and sediments in marine tests, the number of microorganisms and aerobic conditions are stabilized, and reproducibility and comparability of biodegradation experiments (including curves, lag time, etc.) are improved.

This document specifies methods for preparing seawater and sediments in the intertidal zone for estimating the aerobic biodegradation of plastics in pelagic to coastal marine environments.

Plastics — Marine biodegradation testing — Preparation of optimized intertidal seawater and sediment

1 Scope

This document specifies procedures for preparing seawater and sediments used in test methods to assess the biodegradation of plastic materials in the marine environment. The screened sediment and sediment-rinsed seawater are prepared to sustain aerobic testing at laboratory scale. The described method is designed to separate sediment-rinsed seawater and sand-gravel sediments from intertidal sediments by wet filtration and seawater flotation. This document does not include steps to enhance the biodegradation of plastic materials by concentrating the natural seawater, adding nutrients to the seawater, and pre-culturing the inoculum.

The methods described in this document are intended to be used in addition to issued ISO standard test methods for evaluating the biodegradation and disintegration of plastic materials. The applicable evaluation test methods are ISO 18830, ISO 19679, ISO 22404, ISO 23977-1, ISO 23977-2 and ISO 23832.

NOTE The conditions described in this document do not always correspond to the optimum conditions for maximum biodegradation. This is a method of preparing test sediments from coastal seafloor sediments, not a method of preparing sediments from deep-sea seafloors.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 18830, *Plastics — Determination of aerobic biodegradation of non-floating plastic materials in a seawater/sandy sediment interface — Method by measuring the oxygen demand in closed respirometer*

ISO 19679, *Plastics — Determination of aerobic biodegradation of non-floating plastic materials in a seawater/sediment interface — Method by analysis of evolved carbon dioxide*

ISO 22404, *Plastics — Determination of the aerobic biodegradation of non-floating materials exposed to marine sediment — Method by analysis of evolved carbon dioxide*

ISO 23977-1, *Plastics — Determination of the aerobic biodegradation of plastic materials exposed to seawater — Part 1: Method by analysis of evolved carbon dioxide*

ISO 23977-2, *Plastics — Determination of the aerobic biodegradation of plastic materials exposed to seawater — Part 2: Method by measuring the oxygen demand in closed respirometer*

ISO 23832, *Plastics — Test methods for determination of degradation rate and disintegration degree of plastic materials exposed to marine environmental matrices under laboratory conditions*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>