

Founding — Ausferritic spheroidal graphite cast irons — Classification

ICS 77.080.10

National foreword

This British Standard reproduces verbatim ISO 17804:2005 and implements it as the UK national standard.

The UK participation in its preparation was entrusted to Technical Committee ISE/35, Cast iron, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the ISO title page, pages ii to vi, pages 1 to 30, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 25 January 2006

© BSI 25 January 2006

ISBN 0 580 47497 6

Amendments issued since publication

Amd. No.	Date	Comments

INTERNATIONAL STANDARD

**ISO
17804**

First edition
2005-11-01

Founding — Ausferritic spheroidal graphite cast irons — Classification

Fonderie — Fonte ausferritique à graphite sphéroïdal — Classification



Reference number
ISO 17804:2005(E)

AVA Documents
Document Sharing Hub

Contents

Page

Foreword.....	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Designation	2
5 Order information	2
6 Manufacture.....	3
7 Requirements	3
7.1 General.....	3
7.2 Test pieces machined from separately cast and cast-on samples	3
7.3 Test pieces machined from samples cut from a casting.....	3
7.4 Hardness.....	5
7.5 Graphite structure.....	5
7.6 Matrix structure.....	5
8 Sampling.....	5
8.1 General.....	5
8.2 Separately cast samples	5
8.3 Cast-on samples	6
8.4 Samples cut from a casting	7
9 Test methods.....	8
9.1 Tensile test	8
9.2 Impact test, Charpy V	8
9.3 Hardness test	8
10 Retests	8
10.1 Need for retesting	8
10.2 Test validity	9
10.3 Non-conforming test results.....	9
10.4 Heat treatment of samples and castings.....	9
11 Additional information.....	9
Annex A (normative) Abrasion-resistant grades of ausferritic spheroidal graphite cast iron.....	16
Annex B (normative) Minimum elongation values for a test piece with original gauge length $L_0 = 4 \times d$	18
Annex C (informative) Guidance values for Brinell hardness	19
Annex D (informative) Procedure for the determination of the hardness range	20
Annex E (informative) Guidance values for tensile strength and elongation for test pieces machined from samples cut from a casting [1]	21
Annex F (informative) Unnotched impact test.....	22
Annex G (informative) Additional information on mechanical and physical properties.....	24
Annex H (informative) Nodularity (or spheroidal graphite rate)	26
Annex I (informative) Machinability of ausferritic spheroidal graphite cast irons	27

Annex J (informative) Cross-references of similar grades of ausferritic spheroidal graphite cast iron..... 29

Bibliography 30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17804 was prepared by Technical Committee ISO/TC 25, *Cast irons and pig irons*, Subcommittee SC 2, *Spheroidal graphite cast irons*.

Introduction

Ausferritic spheroidal graphite cast iron is a cast alloy, iron and carbon based, carbon being present mainly in the form of spheroidal graphite particles.

Compared with the spheroidal graphite cast-iron grades (see ISO 1083:2004), this material combines higher strength and toughness properties as a result of the austempering heat treatment.

This International Standard deals with the classification of ausferritic spheroidal graphite cast irons in accordance with the mechanical properties of the material.

The mechanical properties of these ausferritic spheroidal graphite cast irons depend on their structure, e.g. the form of the graphite and the structure of the matrix.

The required structure is developed by selecting the appropriate composition and subsequent processing.

The mechanical properties of the material can be evaluated on machined test pieces prepared from:

- separately cast samples with an appropriate gating system, able to provide metallurgical conditions similar to those of the castings they represent;
- samples cast onto either the casting or the running system, hereafter referred to as cast-on samples;
- samples cut from a casting (only by agreement between the manufacturer and the purchaser, the agreement specifying, in particular, the conditions of sampling and the values to be obtained).

Two grades of ausferritic spheroidal graphite cast iron are specified in Annex A, in accordance with their hardness. These cast irons are used in applications (e.g. mining, earth moving and manufacturing industries) where high abrasion resistance is required.

Five grades of ausferritic spheroidal graphite cast iron are specified by the mechanical properties. When, for these grades, hardness is a requirement for the application, Annex D provides means for determining appropriate hardness ranges.

Founding — Ausferritic spheroidal graphite cast irons — Classification

1 Scope

This International Standard defines the grades and the corresponding requirements for ausferritic spheroidal graphite cast irons.

This International Standard specifies five grades of ausferritic spheroidal graphite cast iron by a classification based on mechanical properties measured on machined test pieces prepared from:

- separately cast samples or cast-on samples;
- samples cut from a casting.

This International Standard also specifies two grades by a classification as a function of hardness.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

ISO 148-2, *Metallic materials — Charpy pendulum impact test — Part 2: Verification of test machines*

ISO 148-3, *Metallic materials — Charpy pendulum impact test — Part 3: Preparation and characterization of Charpy V reference test pieces for verification of test machines*

ISO 945, *Cast iron — Designation of microstructure of graphite*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6892, *Metallic materials — Tensile testing at ambient temperature*

ISO/TR 15931, *Designation system for cast irons and pig irons*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

ausferritic spheroidal graphite cast iron

cast material, iron and carbon based, carbon being present mainly in the form of spheroidal graphite particles, subjected to an austemper heat treatment in order to produce an ausferritic matrix

NOTE Ausferritic spheroidal graphite cast iron is also known as austempered ductile iron (ADI).

3.2

graphite spheroidising treatment

process which brings the liquid iron into contact with a substance to produce graphite in spheroidal form during solidification

3.3

austemper heat treatment of spheroidal graphite cast iron

process, consisting of heating the castings above the A_{C1} temperature (at which austenite starts to form during heating), cooling at a rate sufficient to avoid the formation of pearlite, and transforming the matrix structure for a time and a temperature (above the martensite start temperature) sufficient to produce the desired properties

NOTE This process produces a microstructure that consists predominantly of ferrite and austenite. This microstructure is called ausferrite.

3.4

relevant wall thickness

section of the casting, agreed between the manufacturer and the purchaser, to which the determined mechanical properties apply

NOTE Relevant wall thickness may be associated with a range of casting sections and/or with a sample type and size according to Table 3. The association is made by considering the cooling conditions during solidification and heat treatment.

4 Designation

The material shall be designated in accordance with ISO/TR 15931.

Annex J gives a selection of approximate cross-references of grade designations in this International Standard to standard grades from EN, ASTM, JIS and SAE standards.

5 Order information

The following information shall be supplied by the purchaser:

- a) the complete designation of the material;
- b) any special requirements.

All agreements shall be made between the manufacturer and the purchaser by the time of acceptance of the order.

6 Manufacture

The method of producing ausferritic spheroidal graphite cast iron, its chemical composition and heat treatment, shall be left to the discretion of the manufacturer, who shall ensure that the casting process and heat treatment process are carried out with the same process parameters as the approved first samples.

7 Requirements

7.1 General

The property values for these materials apply to castings cast in sand moulds or moulds of comparable thermal behaviour. Subject to amendments to be agreed upon in the order, they can apply to castings obtained by alternative methods.

The material designation is based on the minimum mechanical properties obtained in separately cast or cast-on samples, cast in a sand mould or a mould of comparable thermal behaviour, corresponding to a relevant wall thickness $12,5 \text{ mm} < t \leq 30 \text{ mm}$, as given in Table 1.

NOTE Mechanical properties for test pieces cut from a casting are affected not only by material properties (a subject of this International Standard), but also by the local casting soundness (not a subject of this International Standard). Tensile testing requires sound test bars in order to guarantee pure uniaxial stress during the test.

7.2 Test pieces machined from separately cast and cast-on samples

7.2.1 General

The mechanical properties of ausferritic spheroidal graphite cast iron shall be as specified in Table 1 and, if applicable, in accordance with the requirements given in 7.2.2.

7.2.2 Impact test

The impact-resistance values given in Table 2 at room temperature, if applicable, shall only be determined if specified by the purchaser by the time of acceptance of the order.

7.3 Test pieces machined from samples cut from a casting

If applicable, the manufacturer and the purchaser shall agree on:

- the location(s) on a casting where the sample(s) shall be taken;
- the mechanical properties that shall be measured;
- the minimum values (or allowable range of values) for these mechanical properties (for information, see Annex E).

NOTE 1 The properties of castings are not uniform, depending on the complexity of the castings and variation in their section thickness.

NOTE 2 Tables 1 and 2 may be used for guidance on the likely mechanical properties of the castings. These properties may be equal to or lower than those given in these tables.

Table 1 — Mechanical properties measured on test pieces machined from separately cast samples or cast-on samples [1]

Material designation	Relevant wall thickness of the casting t mm	Tensile strength R_m N/mm ² min.	0,2 % proof strength $R_{p0,2}$ N/mm ² min.	Elongation A % min.
ISO 17804/JS/800-10 ISO 17804/JS/800-10RT	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 100$	800 750 720	500	10 6 5
ISO 17804/JS/900-8	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 100$	900 850 820	600	8 5 4
ISO 17804/JS/1050-6	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 100$	1 050 1 000 970	700	6 4 3
ISO 17804/JS/1200-3	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 100$	1 200 1 170 1 140	850	3 2 1
ISO 17804/JS/1400-1	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 100$	1 400 1 170 1 140	1 100	1
			To be agreed between the manufacturer and the purchaser	

NOTE 1 The properties of castings are not uniform because of the complexity and variation in section thickness.

NOTE 2 With the appropriate heat treatment, the specified minimum 0,2 % proof strength values according to this table can be maintained. However, with increasing casting wall thickness, the tensile strength and elongation values will decrease.

NOTE 3 1 N/mm² = 1 MPa.

NOTE 4 If the type of sample is to be specified, a "J" is added to the designation, followed by a letter indicating the type of sample:
— S for a separately cast sample;
— U for a cast-on sample.

Table 2 — Minimum impact-resistance values measured on V-notched test pieces machined from separately cast samples or cast-on samples [1]

Material designation	Relevant wall thickness of the casting t mm	Minimum impact-resistance value at room temperature (23 ± 5 °C)	
		Mean value of 3 tests J	Individual value J
ISO 17804/JS/800-10RT	$t \leq 30$	10	9
	$30 < t \leq 60$	9	8
	$60 < t \leq 100$	8	7

NOTE If the type of sample is to be specified, a "J" is added to the designation, followed by a letter indicating the type of sample:
— S for a separately cast sample;
— U for a cast-on sample.