BS ISO 18747-2:2019

BSI Standards Publication

Determination of particle density by sedimentation methods

Part 2: Multi-velocity approach

Documents
Document Sharing Hub

Full document details: BS ISO 18747-2:2019

National foreword

This British Standard is the UK implementation of ISO 18747-2:2019.

The UK participation in its preparation was entrusted to Technical Committee LBI/37, Particle characterization including sieving.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 89336 0

ICS 19.120

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2019.

Amendments/corrigenda issued since publication

Date	Text affected

Documents
Document Sharing Hub

Full document details: BS ISO 18747-2:2019

INTERNATIONAL STANDARD

ISO 18747-2

First edition
2019-06

Determination of particle density by sedimentation methods —

Part 2: Multi-velocity approach

Détermination de la densité de particules par méthodes de sédimentation —

Partie 2: Approche à multi vitesses

Reference number
ISO 18747-2:2019(E)

Documents
Document Sharing Hub

© ISO 2019

Full document details: BS ISO 18747-2:2019

COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2019 – All rights reserved

Documents
Document Sharing Hub

Full document details: BS ISO 18747-2:2019

Contents

Page

Foreword ..... **iv**
Introduction ..... **v**
1 Scope **1**
2 Normative references **1**
3 Terms and definitions **1**
4 Symbols **2**
5 Basic principle of the method **2**
6 Measuring techniques to determine sedimentation and creaming/flotation velocity of dispersed particles **4**
7 Preparation of samples **5**
7.1 Continuous phase liquids 5
7.2 Dispersing procedure 6
8 Measurements and data analysis **6**
9 Reference materials and measurement uncertainty **7**
9.1 Reference materials 7
9.2 Measurement uncertainty 8
Annex A (informative) **Isopycnic density gradient (buoyant density) centrifugation** **10**
Annex B (informative) **Examples of measurements and data analysis to determine particle density by multi-velocity approach** **11**
Annex C (informative) **Uncertainty derivation of particle density based on uncertainty propagation rules** **15**
Bibliography **18**

© ISO 2019 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS ISO 18747-2:2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 24, *Particle characterization including sieving*, Subcommittee SC 4, *Particle characterization*.

A list of all parts in the ISO 18747 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

© ISO 2019 – All rights reserved
Documents
Document Sharing Hub
Full document details: BS ISO 18747-2:2019

Introduction

Dispersions are widely used in industry and everyday life. There is a need to understand the density of dispersed particles or droplets, e.g. for physico-chemical calculations such as kinematic viscosity of dispersions[1], determination of particle size distribution by sedimentation[2][3] or acoustic techniques[4], particle characterization by field-flow approaches[5], optimization of dispersion long-term stability by density matching[6] as well as, more generally, characterization of particles (e.g. composition, internal phase content of double emulsions or homogeneity of hollow capsules) in manifold academic and industrial areas. Nowadays there is an increasing interest in using particle density to estimate the mass transfer of nanoparticles atop cell layers by sedimentation (dosage calculation for in vitro nanotoxicity assessment[7][8][9]).

The density of a body is defined as its mass divided by its volume. This calculation is straightforward for a large uniform body or particle. However, determination of the volume of a macroscopic body is difficult. The geometrical volume (defined by length, width and thickness) and the volume relevant for the determination of density may differ due to surface irregularities, fractures, fissures and pores or the measuring techniques employed.

Density determination of micro-particles, especially nanoparticles dispersed in a liquid, is difficult not only due to the determination of mass and volume for small particles, but also due to the fuzzy boundary between the liquid and the particle, which is often described in terms of a corona[10]. Liquid and solute molecules in the continuous phase are partially immobilized at the surface. Physico-chemical properties (e.g. viscosity, ion composition, solute concentration) in the fuzzy coat differ from the bulk. This effect is especially important for small microparticles and nanoparticles that are dispersed in a polymer or biological media[11]. The so-called corona may be interpreted as an integral part of the particle and increases the effective/apparent volume compared to the space occupied by the dry particle. The thickness of this layer ranges between a few to tens of nanometres. The effective/apparent volume deviates increasingly from the “geometrical” volume of dry particles as the particles become smaller. Correspondingly, density determination by traditional methods is affected. These concerns hold also for particle size, which may refer to different geometrical and physical properties. In the context of this document, the Stokes diameter and diameter of the enveloping sphere/hull are particularly relevant.

© ISO 2019 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS ISO 18747-2:2019

Documents
Document Sharing Hub

Determination of particle density by sedimentation methods —

Part 2:
Multi-velocity approach

1 Scope

This document specifies an in situ method for the determination of the density of solid particles or liquid droplets (herein referred to as "particle") dispersed in liquid continuous phase. The method is based on direct experimental determination of particle velocity in these liquids or media in gravitational or centrifugal fields based on Stokes law. The particle density is calculated from experimentally determined particle velocities in different liquids or media, taking into account their dynamic viscosities and densities, respectively. The approach does not require the knowledge of particle size distribution but assumes that sedimentation relevant characteristics (e.g. volume, shape, agglomeration state) do not change. This document does not consider polydispersity with regard to particle density, i.e. all particles are assumed to be of the same material composition.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14887, *Sample preparation — Dispersing procedures for powders in liquids*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at http://www.electropedia.org/

— ISO Online browsing platform: available at https://www.iso.org/obp

3.1
buoyant density
ratio of particle mass to particle volume including filled or closed pores as well as adjacent layers of liquid or other coating materials

3.2
dynamic viscosity
measure of the resistance of a fluid which is being deformed by shear stress

Note 1 to entry: Dynamic viscosity is calculated by shear stress divided by shear rate and determines the dynamics of an incompressible Newtonian fluid.

© ISO 2019 – All rights reserved

Documents
Document Sharing Hub
Full document details: BS ISO 18747-2:2019