



BSI Standards Publication

Determination of the specific surface area of porous and particulate systems by small-angle X-ray scattering (SAXS)

National foreword

This British Standard is the UK implementation of ISO 20804:2022.

The UK participation in its preparation was entrusted to Technical Committee LBI/37, Particle characterization including sieving.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 580 99796 9

ICS 19.120

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2022.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
20804

First edition
2022-03-29

Determination of the specific surface area of porous and particulate systems by small-angle X-ray scattering (SAXS)

*Détermination de la surface spécifique pour des systèmes poreux et
particulaires par diffusion des rayons X aux petits angles (SAXS)*



Reference number
ISO 20804:2022(E)
Documents
Document Sharing Hub
© ISO 2022



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	3
5 Principle of the method	4
5.1 General	4
5.2 Ideal two-phase model	5
5.3 Porod law - Specific surface area	6
6 Apparatus	8
6.1 Optics - Focusing - Collimation – Resolution	8
6.2 Additional requirements for the absolute-scale method	10
7 Preliminary procedures and instrument set-up	10
8 Sample preparation	11
8.1 General	11
8.2 Degassing	11
9 Determination of the specific surface area	11
9.1 K/Q ('Invariant') method	11
9.2 Absolute-scale method	13
10 Documentation and test report	15
10.1 Test report	15
10.2 Technical records	16
Annex A (informative) Example of a typical experimental protocol	17
Bibliography	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 24 *Particle characterization including sieving*, Subcommittee SC 4, *Particle characterization*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Small-angle X-ray scattering (SAXS) can be used to determine the specific surface area of nanoporous (presence of nanopores) and nanoparticulate systems which include mesoporous and partly macroporous materials. SAXS is a well-established method to obtain structural information on inhomogeneities in materials at the nanoscale, typically between 1 nm and 100 nm, and is thus perfectly suited for nanoporous, i.e. materials comprising nanopores and nanoparticulate systems which include mesoporous (presence of mesopores) and partly macroporous (presence of macropores) materials. With special instrumentation, and/or by using absolute-scale techniques, the limits can be significantly extended. User-friendly commercial instruments are available worldwide from a number of manufacturers for both routine and more sophisticated analyses, and state-of-the-art research instruments are available at synchrotron radiation facilities.

As in all measurement techniques for surface area, care is required in all aspects of the use of the instrument, collection of data, and further interpretation. Therefore, there is a need for an International Standard that allows users to obtain good inter-laboratory agreement on the accuracy and reproducibility of the technique.

SAXS can be applied to any hetero-phase system, in which the two or more phases have a different electron density. A 'phase' is in this context understood as a homogeneous electron density domain in the typical size range for SAXS between about 1 nm and 100 nm. State-of-the-art SAXS instruments and synchrotron SAXS beamlines allow significantly extending the limit of 100 nm to several hundred nanometres. Special instrumentation for ultra-small angle X-ray scattering (USAXS) pushes the upper size limit even up to the μm range. This document describes two different evaluation approaches for determining the specific surface area: The Invariant (K/Q) method has an upper size limit for the structure of up to several hundred nanometres, whereas for the absolute-scale method the size of the structure can even be in the μm range.

Because SAXS is sensitive to the squared electron density difference, it does not matter whether the scattering system is composed of pores or particles within a matrix, respectively.

Small-angle neutron scattering is not described in this document but can be used without restriction because the theory and application are similar.

This page deliberately left blank

Determination of the specific surface area of porous and particulate systems by small-angle X-ray scattering (SAXS)

1 Scope

This document specifies the application of small-angle X-ray scattering (SAXS) for the determination of specific surface area. Both the mass specific surface area in the order of $1 \text{ m}^2\text{g}^{-1}$ to $2\,000 \text{ m}^2\text{g}^{-1}$ and the volume specific surface areas in the range from $0,01 \text{ m}^2\text{cm}^{-3}$ to $1\,000 \text{ m}^2\text{cm}^{-3}$ can be obtained.

The method described is applicable to dilute and concentrated systems.

NOTE In ISO 17867:2020, the determination of the particle size by SAXS is limited to dilute systems.

The determination of surfaces with SAXS is straightforward for two-phase systems only. Surface determination in systems with more than two phases is beyond the scope of this document.

The term 'surface' refers to any interface between domains of different density (more precisely: electron density) and is not restricted to the external surface of particles. As any interfaces between areas with different electron density, not only to air or vacuum, can be probed, the method can be applied to any heterogeneous system.

SAXS measures not only the specific surface area of open pores but also of inaccessible, closed pores or inclusions.

NOTE This is in contrast to gas sorption methods which are described in ISO 9277:2010.

In addition to porous systems, there can be contributions of internal interfaces to the measured specific surface area of any heterogeneous compact solid system, such as between crystalline and amorphous phases, provided there is an electron density contrast. Although materials comprising micropores (pore width $< 2 \text{ nm}$) can also be analysed with respect to their specific surface area with SAXS, this document does not cover these materials.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

nanopore

pore with width of 100 nm or less

[SOURCE: ISO 15901-2:2021, 3.10]

3.2

macropore

pore with width greater than 50 nm

[SOURCE: ISO 15901-1:2016, 3.7]

3.3

mesopore

pore of internal width between 2 nm and 50 nm

[SOURCE: ISO 15901-1:2016, 3.8]

3.4

micropore

pore of internal width less than 2 nm

[SOURCE: ISO 15901-1:2016, 3.9]

3.5

surface area

extent of accessible surface area as determined by a given method under stated conditions

[SOURCE: ISO 15901-1:2016, 3.30]

3.6

mass specific surface area

surface area of the sample divided by sample mass

3.7

volume specific surface area

surface area of the sample divided by sample volume

3.8

external (outer) surface

envelope surface of particles in the micrometre and sub-micrometre range

3.9

internal (inner) surface

surface of pores, cavities, or any other heterogeneity within particles or bulk materials

3.10

closed pore

pore totally enclosed by its walls and hence not interconnecting with other pores and not accessible to fluids

[SOURCE: ISO 15901-1:2016, 3.10]

3.11

open pore

pore not totally enclosed by its walls and open to the surface either directly or by interconnecting with other pores and therefore accessible to fluid

[SOURCE: ISO 15901-1:2016, 3.11]

3.12

powder

porous or nonporous solid composed of discrete particles with maximum dimension less than about 1 mm, powders with a particle size below about 1 µm are often referred to as fine powders

[SOURCE: ISO 15901-1:2016, 3.4]