



BSI Standards Publication

Ships and marine technology — Bioassay methods for screening anti-fouling paints

Part 3: Mussels

National foreword

This British Standard is the UK implementation of [ISO 21716-3:2020](#).

The UK participation in its preparation was entrusted to Technical Committee SME/32, Ships and marine technology - Steering committee.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2023
Published by BSI Standards Limited 2023

ISBN 978 0 539 06209 0

ICS 13.020.99; 47.020.99

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2023.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

ISO
21716-3

First edition
2020-11-27

Ships and marine technology — Bioassay methods for screening anti- fouling paints —

Part 3: Mussels



Reference number
ISO 21716-3:2020(E)

AVA Documents
Document Sharing Hub
© ISO 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Material and apparatus	3
6 Preparation of the test organism and the test seawater	4
6.1 General	4
6.2 Preparation of the test organism	4
6.3 Preparation of test seawater	4
7 Preparation of the test panels and control panels	4
7.1 General	4
7.2 Preparation of the test panels	4
7.3 Affixing of mussels to the test panels and control panels	4
8 Operation of the test	5
9 Validation of the test	6
10 Byssus threads formation	6
10.1 General	6
10.2 Calculation of the average number of byssus threads formed	7
10.3 Data treatment and interpretation of the results	7
11 Test report	8
Annex A (informative) Statistical analysis — Examples	10
Annex B (informative) General information of mussel, <i>Mytilus galloprovincialis</i>	14
Annex C (informative) Identification of <i>Mytilus galloprovincialis</i>	17
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 8, *Ships and marine technology*, Subcommittee SC 2, *Marine environment protection*, in collaboration with Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

A list of all parts in the ISO 21716 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Anti-fouling paints that contain biocides are widely used to prevent fouling of ship hulls by marine organisms. Effective anti-fouling technologies are critical for maintaining fuel consumption efficiency of ships and also for minimizing possible translocation of aquatic species through maritime trade. The evaluation of anti-fouling paints is generally undertaken by adopting a tiered approach whereby paint manufacturers use a battery of laboratory, raft, patch tests and full vessel trials. Raft, patch tests and full vessel trials are generally conducted over extended periods of time and are predominantly relied upon for the prediction of coating performance when used commercially on in-service ships.

The results of raft, patch test and full vessel trials (field testing) can be used as part of the regulatory process for pesticidal or biocidal products in certain countries in order to demonstrate the efficacy of an anti-fouling paint. Laboratory testing alone is recognized as being unable to predict in-service performance or efficacy. For example, guidance published by the European Chemicals Agency (ECHA) on the assessment and evaluation of efficacy for anti-fouling products states clearly that laboratory testing of individual anti-fouling paints is not undertaken as it is not considered to be a realistic evaluation of the product; field testing, which permits anti-fouling products to be tested under similar operating conditions and stresses as those encountered when the antifouling products are in service is routinely undertaken instead (see Reference [35]).

Whilst laboratory tests are unable to reliably predict in-service coating performance, they have merit in the screening of experimental coatings for further evaluation during the research and development process.

Reproducible objective data obtained by following standardized screening methods, independent of the test location or the season, can be a useful tool to support the selection of anti-fouling paints for higher tier testing, e.g., raft or ship tests. [ISO 21716](#) provides a compilation and description of *in vitro* bioassay methods intended to aid the process of screening anti-fouling paints prior to higher tier raft or ship tests. Toxicological screening methods included in each part of [ISO 21716](#) can be used for such purposes as early decision-making in research and product development, rapid feedback on potential toxicological concerns, or for the preliminary assessment of anti-fouling paints. For instance, [ISO 21716](#) provides information on methods that can be used to screen anti-fouling paints in order to determine whether to continue development of an experimental paint and/or a product that contains a particular ingredient, or to determine whether to take on the cost of performing the remaining tiers within a complete tiered-testing strategy.

[ISO 21716](#) provides screening bioassays related to certain common genera of fouling organisms, namely barnacles, mussels and algae. These screening tests are relatively simple and rapid laboratory tests that can be performed to provide an indication of the toxicity of a painted surface towards selected test organisms. The screening tests described in each part of [ISO 21716](#) can be used as part of a tiered approach to predict the ability of an anti-fouling paint to prevent fouling on ships. Alternatively, to prevent the translocation of invasive marine species by progressively involving subsequent semi-field (e.g. raft panels) and field testing (e.g. ship trials). On their own, the screening tests described in each part of [ISO 21716](#) do not reliably predict the ability of an anti-fouling paint to prevent fouling on ships or the translocation of invasive marine species.

[ISO 21716](#) is not intended to provide a list of validated tests for testing the efficacy of anti-fouling paints; this can be covered in regulations. It is not intended to provide a list of validated tests for this purpose, nor for predicting the ability of a fouling control paint to prevent fouling on ships or to prevent the translocation of invasive marine species.

Mussels are typical marine sessile organisms regarded as harmful fouling organisms because of the impact on fuel consumption and the potential for translocation of non-indigenous species if they become attached to ship hulls.

This test method utilizes young mussels to assess settling behaviour in the presence of treated panels. Young mussels are used because they have higher byssus threads production activity as compared to the adults. More information is provided in [Annex B](#).

Ships and marine technology — Bioassay methods for screening anti-fouling paints —

Part 3: Mussels

1 Scope

This document specifies a laboratory test method for screening anti-fouling paints in a flow-through system using mussels as the test organism. It is intended to be used in conjunction with [ISO 21716-1](#), which specifies the general requirements. The purpose of the test is to determine if there is a difference in mussel settlement on painted test panels compared with mussel settlement on inert non-toxic control panels under the conditions of the test. Examples of statistical analysis to determine if the difference in mussel settlement is statistically significant are given in [Annex A](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[ISO 21716-1:2020](#), *Ships and marine technology — Bioassay methods for screening anti-fouling paints — Part 1: General requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in [ISO 21716-1](#) and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>;
- IEC Electropedia: available at <http://www.electropedia.org/>.

3.1

byssus

attachment organ secreted by a mussel, consisting of stem, byssus threads and adhesive discs

Note 1 to entry: See [Figure 1](#).