

Surface chemical analysis — Auger electron spectroscopy — Repeatability and constancy of intensity scale

ICS 71.040.40

National foreword

This British Standard reproduces verbatim ISO 24236:2005 and implements it as the UK national standard.

The UK participation in its preparation was entrusted to Technical Committee CII/60, Surface chemical analysis, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the ISO title page, pages ii to v, a blank page, pages 1 to 14, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 12 May 2005

© BSI 12 May 2005

ISBN 0 580 45967 5

INTERNATIONAL STANDARD

ISO
24236

First edition
2005-04-15

Surface chemical analysis — Auger electron spectroscopy — Repeatability and constancy of intensity scale

*Analyse chimique des surfaces — Spectroscopie d'électrons Auger —
Répétabilité et constance de l'échelle d'énergie*



Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Symbols	1
3 Outline of method	2
4 Method for evaluating the repeatability and constancy of the intensity scale	2
4.1 Obtaining the reference sample	2
4.2 Mounting the sample	3
4.3 Cleaning the sample	3
4.4 Choosing the spectrometer settings for which intensity stability is to be determined	4
4.5 Operating the instrument	5
4.6 Options for initial or subsequent evaluation measurements	5
4.7 Measurements for the intensity and repeatability	5
4.8 Calculating the peak intensities, intensity ratios and uncertainties	7
4.9 Procedure for the regular evaluation of the constancy of the intensity scale	8
4.10 Next evaluation	9
Annex A (informative) Example of calculations and measurements of the intensity repeatability for a commercial Auger electron spectrometer	10
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 24236 was prepared by Technical Committee ISO/TC 201, *Surface chemical analysis*, Subcommittee SC 7, *X-ray photoelectron spectroscopy*.

Introduction

Auger electron spectroscopy (AES) is used extensively for the surface analysis of materials. Elements in the sample (with the exception of hydrogen and helium) are identified from comparisons of the measured kinetic energies of emitted Auger electrons with tabulations of those energies for the different elements. Information on the quantities of such elements can be derived from the measured Auger electron intensities. Calculation of the quantities present may then be made using formulae and relative sensitivity factors provided by the spectrometer manufacturer. It is important that the sensitivity factors are appropriate for the instrument and this will generally be the case directly after installation of the equipment or calibration of the instrument intensity/energy response function by an appropriate organization. There are two important instrumental contributions to the uncertainty of AES intensity measurements that are addressed in this International Standard: (i) the repeatability of intensity measurements and (ii) the drift of the intensities with time.

Repeatability is important for analysing the trends and differences between samples that are similar. The instrumental issues that limit the measurement repeatability include the stability of the electron beam source, the settings of the detector, the sensitivity of the instrument to the sample placement, the data acquisition parameters and the data-processing procedure. The drift of the instrument intensity scale will limit the overall accuracy of any quantitative interpretation and arises from such effects as the ageing of components of the structure of the spectrometer, of its electronic supplies and of the detector. In AES instruments, it has been found that, in service, the instrument intensity/energy response function may change as the instrument ages.

This International Standard describes a simple method for determining the repeatability and constancy of the intensity scale of the instrument so that remedial action, such as improving the operating procedure, resetting of the instrument parameters or recalibration of the intensity/energy response function, may be made. This method should, therefore, be conducted at regular intervals and is most useful if the data include a period in which the instrument has been checked to be working correctly by the manufacturer or other appropriate body. This method uses a sample of pure copper (Cu) and is applicable to Auger electron spectrometers with an electron gun with a beam energy of 2 keV or greater.

This method does not address all of the possible defects of instruments since the required tests would be very time-consuming and need both specialist knowledge and equipment. This method is, however, designed to address the basic common problem of repeatability and of drift of the intensity scales of AES instruments. This method may be conducted at the same time as the spectrometer energy calibration using ISO 17973^[1] or ISO 17974^[2].

