

Iron ores — Experimental methods for checking the precision of sampling, sample preparation and measurement

ICS 73.060.10

National foreword

This British Standard is the UK implementation of ISO 3085:2002. It supersedes BS ISO 3085:1996 and BS 5662-2:1987 which are withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/58, Iron ores.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard, having been prepared under the direction of the Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 25 April 2002

© BSI 2010

ISBN 978 0 580 69921 4

Amendments/corrigenda issued since publication

Date	Comments
28 February 2010	Supersession text amended

**Iron ores — Experimental methods for
checking the precision of sampling, sample
preparation and measurement**

*Minerais de fer — Méthodes expérimentales de contrôle de la fidélité de
l'échantillonnage, de préparation des échantillons et de mesurage*



Reference number
ISO 3085:2002(E)

Contents		Page
Foreword.....		iv
1	Scope	1
2	Normative references	1
3	Definitions	1
4	Principle.....	1
5	General conditions	2
6	Method of experiment	3
7	Analysis of experimental data	7
8	Interpretation of results and action	12
9	Test report	12
Annex A (informative) Example of experiment on periodic systematic sampling by method 1		14
Annex B (informative) Alternative method for analysis of experimental data		20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3085 was prepared by Technical Committee ISO/TC 102, *Iron ore and direct reduced iron*, Subcommittee SC 1, *Sampling*.

This fourth edition cancels and replaces the third which has been technically revised.

Annexes A and B of this International Standard are for information only.

Iron ores — Experimental methods for checking the precision of sampling, sample preparation and measurement

1 Scope

This International Standard specifies experimental methods for checking the precision of sampling, sample preparation and measurement of iron ores being carried out in accordance with the methods specified in ISO 3082 and the relevant ISO standards for measurement.

NOTE This International Standard may also be applied for the purpose of checking the precision of sampling, sample preparation and measurement separately.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 3082:2000, *Iron ores — Sampling and sample preparation procedures*

ISO 3084:1998, *Iron ores — Experimental methods for evaluation of quality variation*

ISO 11323:—¹⁾, *Iron ore and direct reduced iron — Vocabulary*

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 11323 apply.

NOTE The precision of sampling is defined mathematically in annex A of ISO 3082:2000.

4 Principle

Sampling from twenty lots or more, preferably taking twice as many increments as specified in ISO 3082 and placing the increments alternately into two gross samples. If this is impracticable or the precision testing is carried out in conjunction with routine sampling, the normal number of increments specified in ISO 3082 may be used.

Preparation of separate test samples from each gross sample and determination of relevant quality characteristics.

Analysis of the experimental data obtained and calculation of the estimated value of the precision of sampling, sample preparation and measurement for each selected quality characteristic.

¹⁾ To be published. (Revision of ISO 11323:1996)

Comparison of the estimated precision with that specified in Table 1 of ISO 3082:2000 and necessary action if the estimated precision does not attain these specified values.

5 General conditions

5.1 Sampling

5.1.1 General

The sampling procedure to be followed shall be selected from the two methods of sampling, viz. periodic systematic sampling or stratified sampling, depending on the method of taking increments from the lot in accordance with ISO 3082.

5.1.2 Number of lots

To reach a reliable conclusion, it is recommended that the experiment be carried out on more than 20 lots of the same type of iron ore. However, if this is impracticable, at least 10 lots should be covered. If the number of lots for the experiment is not sufficient, each lot may be divided into several parts to produce more than 20 parts in total for the experiment, and the experiment should be carried out on each part, considering each part as a separate lot in accordance with ISO 3082.

5.1.3 Number of increments and number of gross samples

The number of increments required for the experiment shall preferably be twice the number specified in ISO 3082. Hence, if the number of increments required for routine sampling is n_1 and one gross sample is made up from these increments, the number of increments required for the experiment shall be $2n_1$ and two gross samples shall be constituted.

Alternatively, if the experiment is carried out as part of routine sampling, n_1 increments may be taken and two gross samples constituted, each comprising $n_1/2$ increments. In this case the sampling precision obtained will be for $n_1/2$ increments. The precision thus obtained must be divided by $\sqrt{2}$ to obtain the precision for gross samples comprising n_1 increments (see clause 7).

When the experiment is carried out with n_1 increments and n_1 is an odd number, an additional increment shall be taken in order to make the number of increments even.

5.2 Sample preparation and measurement

Sample preparation shall be carried out in accordance with ISO 3082. The measurement shall be carried out in accordance with the relevant ISO standards for chemical analysis, moisture content and size analysis of iron ores.

NOTE 1 For chemical analysis it is preferable to carry out a series of determinations on test samples for a lot over a period of several days, in order to maintain the independence of test results.

NOTE 2 The method of determination of any quality characteristic should remain the same throughout the experiment.

5.3 Replication of experiment

Even when a series of experiments has been conducted prior to regular sampling operations, the experiments should be carried out periodically to check for possible changes in quality variation and, at the same time, to control the precision of sampling, sample preparation and measurement. Because of the amount of work involved, it should be carried out as part of routine sampling, sample preparation and measurement.

5.4 Record of the experiment

For future reference and to avoid errors and omissions, it is recommended that detailed records of experiments be kept in a standardized format (see clause 9 and annex A).

6 Method of experiment

6.1 Sampling

6.1.1 Periodic systematic sampling

6.1.1.1 The number of increments, n_1 , shall be determined in accordance with ISO 3082.

6.1.1.2 When $2n_1$ increments are taken, the sampling intervals, Δm , in tonnes, shall be calculated by dividing the mass, m_L , of the lot by $2n_1$, i.e. giving intervals equal to one-half of the sampling interval for routine sampling.

$$\Delta m = \frac{m_L}{2n_1}$$

Alternatively, when the experiment is carried out as part of routine sampling and n_1 increments are taken, the sampling interval, Δm , shall be calculated by dividing the mass, m_L , of the lot by n_1 .

$$\Delta m = \frac{m_L}{n_1}$$

The sampling intervals thus calculated may be rounded down to the nearest 10 t.

6.1.1.3 The increments shall be taken at the sampling interval determined in 6.1.1.2, with a random start.

6.1.1.4 The increments shall be placed alternately in two containers. Thus, two gross samples, A and B, will be constituted.

EXAMPLE 1 See Figure 1.

Suppose that a lot of 19 000 t is transferred by belt conveyors and the number of increments determined in accordance with ISO 3082 for routine sampling, n_1 , is 60.

When $2n_1$ increments are taken, the sampling interval for the experiment, Δm , is given by the equation

$$\Delta m = \frac{m_L}{2n_1} = \frac{19\,000}{60 \times 2} = 158 \rightarrow 150$$

Thus, increments are taken at 150 t intervals. The point for taking the first increment from the first sampling interval of 150 t is determined by a random selection method. If the point for taking the first increments is determined as 20 t from the beginning of handling the lot, subsequent increments should be taken at the point $20 + i\Delta m$, where $i = 1, 2, \dots, 2n_1$ (170 t, 320 t and so on). Since the whole lot size is 19 000 t, 126 increments shall be taken.

The increments are placed alternately in two containers, and two gross samples, A and B, are constituted, each composed of 63 increments.