

BS ISO 5433:2013



BSI Standards Publication

Leather — Bovine wet blue — Specification

bsi.

...making excellence a habit.
AVA Documents™
Document Sharing Hub

National foreword

This British Standard is the UK implementation of ISO 5433:2013. It supersedes BS ISO 5433:1999 which is withdrawn.

It is considered the view of the UK committee that the application of this standard to bovine wet blue can be limiting on three counts:

1. The requirement for a water extract pH value of greater than 3.5 is considered restrictive as tanners are producing high quality bovine wet blue with water extract values of less than 3.5, such as a pH value 3.2.
2. It states that a 3.5 % chrome content is required to achieve a 100 °C shrinkage temperature. However, this shrinkage temperature is being commercially achieved at a chrome content of 3 %.
3. At the request of their customers, tanners are not placing trade names or names and addresses of the manufacturer on their packaging. The labelling requirements of the standard do not reflect the commercial realities that tanners operate within and would require the tanner and customer to disclose this information without any perceived benefit.

It is acknowledged by the UK committee that this standard can be applied for UK commercial transactions and aspects can be used in case of dispute between parties but all parties should be aware of the limitations detailed above for bovine wet blue production.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.
Published by BSI Standards Limited 2013

ISBN 978 0 580 80571 4

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2013.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL STANDARD

BS ISO 5433:2013

ISO
5433

Second edition
2013-08-15

Leather — Bovine wet blue — Specification

Cuir — Peaux de bovins à l'état "bleu humide" — Spécifications



Reference number
ISO 5433:2013(E)
Documents
Document Sharing Hub
© ISO 2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
4.1 Raw material	2
4.2 Form and trimming	2
4.3 Tanning	2
4.4 Fungicidal additives	2
4.5 Presentation	3
4.6 Shrinkage temperature	3
4.7 Chemical requirements	3
5 Sampling	3
5.1 Sampling for routine testing	3
5.2 Sampling in case of dispute	3
5.3 Preparation of samples	4
6 Method of test	4
6.1 Visual tests	4
6.2 Shrinkage temperature	4
6.3 Volatile matter	4
6.4 pH of the water extract	4
6.5 Effectiveness of the fungicide	4
7 Packaging and marking	4
7.1 Packaging	4
7.2 Marking	4