

Process Specification and Operator Qualification for Laser Hybrid Welding



Documents

Document Sharing Hub

AWS C7.6/C7.6M:2017
An American National Standard

Approved by the
American National Standards Institute
February 16th, 2017

Process Specification and Operator Qualification for Laser Hybrid Welding

1st Edition

Prepared by the
American Welding Society (AWS) C7 Committee on High Energy Beam Welding and Cutting

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors



American Welding Society®



Documents
Document Sharing Hub

ISBN: 978-0-87171-908-9
© 2017 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by new editions. This standard may also be corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex G). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS C7 Committee on High Energy Beam Welding and Cutting. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS C7 Committee on High Energy Beam Welding and Cutting and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS C7 Committee on High Energy Beam Welding and Cutting to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the *Rules of Operation of the Technical Activities Committee*. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS C7 Committee on High Energy Beam Welding and Cutting

T. A. Palmer, Chair	<i>Penn State University</i>
K. W. Lachenberg, Vice Chair	<i>Sciaky Corporation</i>
D. D. Kautz., 2nd Vice Chair	<i>Los Alamos National Laboratory</i>
P. Portela, Secretary	<i>American Welding Society</i>
P. E. Denney	<i>The Lincoln Electric Company</i>
J. W. Elmer	<i>Lawrence Livermore National Laboratory</i>
P. W. Hochandel	<i>Los Alamos National Laboratory</i>
F. Kong	<i>ESAB Welding & Cutting Products</i>
G. R. LaFlamme	<i>PTR-Precision Technologies, Incorporated</i>
E. D. Levert	<i>Lockheed Martin Missiles & Fire Control</i>
E. M. Lord	<i>Bechtel Marine Propulsion Corporation</i>
R. P. Martukanitz	<i>Penn State University</i>
B. D. Ribic	<i>Rolls-Royce Corporation</i>

Advisors to the AWS C7 Committee on High Energy Beam Welding and Cutting

P. Blomquist	<i>Edison Welding Institute</i>
P. W. Fuerschbach	<i>SmartWeld Solutions</i>
J. O. Milewski	<i>Los Alamos National Laboratory</i>
T. M. Mustaleski	<i>Welding Engineer</i>
D. E. Powers	<i>PTR-Precision Technologies, Incorporated</i>
D. A. Zoller	<i>ESAB Welding & Cutting Products</i>

AWS C7D Subcommittee on Laser Hybrid Welding

B. D. Ribic, Chair	<i>Rolls-Royce Corporation</i>
F. Kong, Vice Chair	<i>ESAB Welding & Cutting Products</i>
P. E. Denney, 2nd Vice Chair	<i>The Lincoln Electric Company</i>
P. Portela, Secretary	<i>American Welding Society</i>
K. Eglund	<i>Caterpillar, Incorporated</i>
P. W. Hochandel	<i>Los Alamos National Laboratory</i>
W. M. Penn	<i>Alabama Laser</i>

Advisors to the AWS C7D Subcommittee on Laser Hybrid Welding

L. Blais	<i>Novika Solutions</i>
E. D. Levert	<i>Lockheed Martin Missiles & Fire Control</i>
J. Milewski	<i>Los Alamos National Laboratory</i>

This page is intentionally blank.

Foreword

This foreword is not part of this standard but is included for informational purposes only.

Combining lasers with other welding techniques to achieve a *hybrid process* has been around almost as long as laser welding. While there are many advantages associated with the high power density properties of lasers, it was determined that gap, base material metallurgy, and weldment performance may be difficult to address with the laser beam alone. One approach was to utilize the advantages of the laser while addressing its shortcomings with the addition of a process that added material to the weld joint. While material could be added in a number of methods (blown powder, preplaced inserts, sacrificial features, etc.), one simple method was to combine the laser with techniques already used for conventional arc welding. This included combining the laser with a Gas Metal Arc Welding (GMAW) process or with a resistant heated wire as is used in Gas Tungsten Arc Welding (GTAW) to form a *Hybrid Process*.

The hybrid laser process has already been accepted for many applications. It has been utilized in the welding of ship structures, structural components, and automotive parts. While the materials processing applications of hybrid laser processing are diverse and may be required to meet other performance criteria, this document focuses on the process specification and operator qualification.

The data contained in this *Process Specification and Operator Qualification for Laser Hybrid Welding* has been compiled and reviewed by the C7D Laser Hybrid Welding Subcommittee of the American Welding Society, which includes representatives from manufacturers and users of laser beam welding and those involved in hybrid laser processes and equipment.

This page is intentionally blank.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	ix
1. General Requirements	1
1.1 Scope.....	1
1.2 Units of Measurement	1
1.3 Safety	1
2. Normative References	2
3. Terms and Definitions	2
4. Safety	4
4.1 Electric Shock.....	4
4.2 Fumes and Gases	4
4.3 Laser Radiation Hazards.....	4
4.4 Radiation Hazards	4
4.5 Mechanical Systems	4
5. Requirements	4
5.1 Equipment	5
5.2 Materials.....	6
5.3 Joint/Surface Design.....	6
5.4 Procedures	6
5.5 Essential Variables and Limits	9
5.6 Operator Qualification Test Record	12
5.7 Production Welding/Cladding Records	13
5.8 Inspection Procedures.....	13
6. Fabrication	13
7. Quality Examination	13
7.1 Nondestructive Examination (NDE).....	13
7.2 Discontinuity Limits	13
7.3 Destructive Evaluation	13
7.4 Traceability.....	14
7.5 Archive of Records	14
8. System Calibration	14
9. Quality Assurance	15
9.1 Sampling Plans	15
9.2 Lot Definition	15
9.3 Preproduction Sampling.....	15
9.4 Part Acceptance	15
9.5 Part Repair or Rework	15
9.6 Traceability.....	15
9.7 Archive of Records	15

10. Approval for Work	15
10.1 Preproduction Development Approval.....	15
10.2 Deviations to WPS	15
10.3 Reports	15
10.4 Traceability	15
10.5 Archive of Reports	15
<i>Annex A (Informative)—Sample Equipment Qualification Record.....</i>	<i>17</i>
<i>Annex B (Informative)—Sample Welding Procedure Qualification Record (PQR)</i>	<i>21</i>
<i>Annex C (Informative)—Sample Welding Procedure Specification (WPS).....</i>	<i>29</i>
<i>Annex D (Informative)—Laser Weld Discontinuity Limits</i>	<i>33</i>
<i>Annex E (Informative)—Acronyms</i>	<i>35</i>
<i>Annex F (Informative)—Sample Operator Process Qualification Test Record (OPQTR)</i>	<i>37</i>
<i>Annex G (Informative)—Requesting an Official Interpretation on an AWS Standard.....</i>	<i>39</i>
<i>List of AWS Documents on High Energy Beam Welding & Cutting</i>	<i>41</i>

List of Tables

Table	Page No.
5.5.1 Laser Beam Generator.....	9
5.5.2 Laser Beam Delivery Hardware	9
5.5.3.1 Auxiliary Power Supply	10
5.5.3.2 Wire Feed	10
5.5.3.3 Wire.....	10
5.5.4 Motion Control, Weld Direction, and Filler Metal Delivery.....	11
5.5.5 Shielding Gas	11
5.5.6 Materials	12
5.5.7 Weld or Cladding Surface Design and Tooling.....	12
7.1 Nondestructive Examination	14

Process Specification and Operator Qualification for Laser Hybrid Welding

1. General Requirements

1.1 Scope. This specification covers processing and quality control requirements for Laser Hybrid Processing. Equipment includes any laser source (examples include, but are not exclusive to CO₂, Nd: YAG, Diode, Ruby, Yb Fiber (Fibre), Yb Disk (Disc), Nd: Glass) in combination with an arc welding system (power supply, wire feeder, torch, etc.) as defined by AWS A3.0M/A3.0, *Standard Welding Terms and Definitions Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying*.

Specifically, this specification covers both (1) Laser Hybrid Arc Welding that uses both a laser to create a keyhole and GMAW (Gas Metal Arc Welding) to add filler material (resulting in a weld bead that is deeper compared to a traditional arc weld and wider than an autogenous laser weld) and (2) Laser Hot Wire Processing that uses a laser to create a conduction mode or keyhole mode molten puddle and an auxiliary power supply that adds heat to the filler wire that enters the puddle (resulting in a lower heat input weldment that could be used to weld joints or to add a hardfacing overlay).

Tutorial information regarding techniques of welding or details of machine setup or operation of laser hybrid processing and laser hybrid processing systems is beyond the scope of this specification. For more information on this subject, refer to AWS C7.2, *Recommended Practices for Laser Welding, Cutting, and Related Processes*.

1.1.1 Materials. This specification covers all major engineering alloys including the following:

- (1) Ferrous Alloys (e.g., steels and stainless steels)
- (2) Non-Ferrous Alloys (e.g., Al alloys, Ni alloys, Ti alloys, Superalloys)
- (3) Heat-Resisting Alloys (e.g., Mo alloys, Ta alloys, W alloys)
- (4) Other Metals (e.g., Be and Cu alloys, precious metals)

1.2 Units of Measurement. This standard makes use of both U.S. Customary Units and the International System of Units (SI). The latter are shown within brackets [] or in appropriate columns in tables and figures. The measurements may not be exact equivalents; therefore, each system must be used independently.

1.3 Safety. Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein.

Safety and health information is available in the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable Regulatory Agencies

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous, and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply.

American National Standards Institute (ANSI) standards:

ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*;

ANSI Z87.1, *Practices for Occupational and Educational Eye and Face Protection*; and

ANSI Z136.1, *Practices for the Safe Use of Lasers*.

American Welding Society (AWS) standards:

AWS A3.0M/A3.0, *Standard Welding Terms and Definition, Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying*;

AWS B2.1, *Specification for Welding Procedure and Performance Qualification*; and

AWS B4.0, *Standard Methods for Mechanical Testing of Welds*;

Other documents:

SDSs, *Safety Data Sheets*.

3. Terms and Definitions

AWS A3.0M/A3.0, *Standard Welding Terms and Definitions* provides the basis for terms and definitions used herein. The terms and definitions used in this text are generally specific to laser hybrid processing. Terms that are not part of common welding vocabulary are defined, and the definitions of some standard welding terms are changed slightly to more accurately describe those terms as they apply to laser hybrid welding processes. A list of acronyms used within the document can be found in Annex E. However, the following terms and definitions are included to accommodate usage specific to this document.

auxiliary power supply. A secondary energy source used in the laser hybrid welding process, besides the laser beam, which contributes sufficient energy such that the additional absorbed energy augments the resulting molten pool geometry. Examples of an auxiliary power supply are GMAW or hot wire.

cavity. See **resonator**.

CNC. An acronym for computer numerical control, a device that controls a machine tool by reading numerical data and transforming it into machine axis movements.

continuous power. See **continuous wave**.

continuous wave (CW). A laser beam which is produced continuously rather than as a series of pulses.

dilution ratio. The ratio of the substrate area melted to the total area melted and can be measured geometrically by the formula $\frac{a}{(a+b)^2}$, where a is the cross sectional area of the substrate that was melted by the cladding process, and b is the cross sectional area of the cladding bead above the substrate, or determined by other techniques.

diode laser. A type of laser in which the active medium is a semiconductor with polished end facets forming mirror surfaces. Also called semiconductor laser. Diode lasers used for alignment emit in the visible; other diode lasers emitting in the infrared are used for material processing. Typical wavelengths for this type of laser range from 0.63 to 0.99 micrometers depending upon the laser active medium chemical composition.

fiber laser. A solid-state laser design in which the active medium is a doped optical fiber. Typical wavelengths for this type of laser are 1.06, 1.55, or 1.8 micrometers depending upon the active medium dopant.

focal length. In a lens or lens system, the distance from the principal plane, the surface at which the projections of an entering and exiting ray intersect, to the focal point. In a thick lens or system of lenses, the principal plane is often inside the lens itself; for setup purposes, operators often use the back focal length, which is the distance from the front surface of a focusing lens or mirror system to the focal point.

infrared (IR). Electromagnetic radiation possessing wavelengths between those of visible light and microwaves.

keyhole. A laser melting mode characterized by high power densities and vaporization of material that is pushed out, creating a weld that has a high depth to width aspect ratio.

laser. A device that produces a concentrated coherent light beam by stimulated electronic or molecular transitions to lower energy levels. Laser is an acronym for light amplification by stimulated emission of radiation.

laser beam. The output radiation of a laser that can be steered and focused by mirrors, lenses, or both, to do useful work.

laser beam to wire distance. Distance from the center of the laser beam diameter at the workpiece and the projection of the wire tip onto the workpiece surface measured parallel to the weld axis.

laser generator. See **laser**.

laser system. A machine or fabrication tool consisting of a laser, a workpiece holder, and a means of delivering the beam to the workpiece and deflecting it over the workpiece in a controlled manner. The most common type of controller is a computer numerical controller, or CNC, but a robot controller is also used.

lens. A transparent optical element with curved surfaces, used to converge or diverge light rays via refraction.

mirror. An optical element that reflects nearly 100% of the laser beam.

Nd:Glass. Neodymium-doped glass that is utilized as the lasing material in some solid-state lasers. The neodymium atoms form the active medium. A typical wavelength for this type of laser is 1.06 micrometers.

Nd:YAG. Neodymium-doped yttrium aluminum garnet (YAG) crystal that is utilized as the lasing material in a common type of solid-state laser. The neodymium atoms form the active medium. See **YAG**. A typical wavelength for this type of laser is 1.06 micrometers.

nozzle. A device projecting from the focusing head with an outlet to direct gas into the laser beam processing area.

plume. The vapor cloud that forms above the laser/material interaction zone. It can consist of excited and partially ionized assist gases (plasma) and atoms of the material vaporized by the intense laser beam and can have a temperature equivalent to tens of thousands of degrees Kelvin. Under certain conditions, the plume can absorb or scatter the incoming laser beam, reducing transmission of the beam, the energy absorbed by the workpiece, and weld penetration.

polarizer. An optic that transmits light of only a single polarization, or otherwise alters the polarization of radiation.

power. With respect to lasers, power is the rate of energy flow from the radiation source. Power is usually measured in watts, an energy flow of a joule per second, or kilowatts (kW). With respect to the auxiliary power supply, power is the mathematical product of electric current and voltage. In laser hybrid processing, power is referred to as the sum of the laser power and the power of GMAW or hot wire power supplies.

Procedure Qualification Record (PQR). A written record of welding variables used to produce an acceptable test weldment and the results of tests conducted on that weldment to qualify a Welding Procedure Specification (see **Welding Procedure Specification (WPS)**).

process orientation. The relationship between the laser beam, travel direction, and auxiliary process (GMAW or hot wire). The laser hybrid welding process can be divided into two categories: torch leading or laser leading. The auxiliary

power device can be positioned in front of the laser spot in the travel direction, which is referred to as torch leading; otherwise, it is referred to as laser leading.

pulsed laser. A laser that emits light as a pulse or a series of pulses rather than continuously.

pulse duration. The duration measured between the half-peak-power points at the front and trailing edges of a pulse.

pulse length. See **pulse duration**.

Welding Procedure Specification (WPS). A document that delineates or references all required welding variables to provide direction for welding.

YAG (Yttrium Aluminum Garnet). A synthetic crystal used as a laser rod host material in Nd:YAG laser.

Yb Disk Laser. A diode pumped, solid-state laser design in which the active medium is a doped, very thin disk. A typical wavelength for this type of laser is 1.06 micrometers.

Yb:YAG. An active laser medium lasing at 1030 nm.

4. Safety

The following potential hazards are associated with laser hybrid processing: electric shock, invisible light radiation, visible light radiation, fumes, gases, and molten particles.

4.1 Electric Shock. Voltages and currents in the laser and auxiliary power supplies are sufficient to be lethal and should be handled accordingly.

4.2 Fumes and Gases. Ozone, nitrogen oxides, metal vapors, and other noxious/hazardous fumes may be generated by laser beam welding (LBW) or GMAW.

4.2.1 Efficient exhaust venting shall be provided with the laser hybrid processing system to remove noxious fumes to acceptable levels in personnel-occupied areas and to protect the cover lens of the laser head from pollution of GMAW induced fume or spatters. A thermal sensor might be installed to monitor the temperature of the cover lens regarding the safety issues of the laser head and the associated fiber-optic cable. Various types of ventilation systems, including general supply and exhaust and local exhaust, for control of welding fumes and reference to information on air contaminants found in the welding fumes, principles of systems design and selection, and drawings that illustrate ventilation techniques can be found in AWS F3.2M/F3.2.

4.2.2 Safety Data Sheets (SDSs) shall be read to determine hazards in working with all materials associated with the welding/cladding processes. These include the SDS for materials contained in the workpieces, fixturing, and cleaning materials.

4.3 Laser Radiation Hazards. Direct, Diffuse, and Specular Reflection of laser energy is produced by laser hybrid welding/cladding equipment during operation. Proper guarding and/or barriers shall be employed to protect personnel who are in the Nominal Hazard Zone (NHZ) of the laser. See ANSI Z136.1 to calculate the NHZ.

4.4 Radiation Hazards. Direct viewing of the weld area during welding can expose personnel to hazardous visible and invisible Infrared (IR), or Ultraviolet (UV) light radiation with possible long-term eye and skin damage. Appropriate optical filters shall be used as per ANSI Z87.1 to shield personnel from possible exposure to both hazardous visible and invisible (IR and UV) radiation.

4.5 Mechanical Systems. Follow appropriate lock-out and tag-out procedures when servicing laser system equipment to avoid possible pinch points.

5. Requirements

This clause discusses requirements a laser hybrid weldment must meet before it is deemed to meet the welding qualifications in this Standard. The documents generated from following these requirements (WPS's and PQR's) are not intended as public documents but for the users to develop and maintain their procedures to an industrial standard.

5.1 Equipment. The major subsystems of a laser system may be grouped as described below. Because of the integrated nature of a typical system, a vital consideration for establishing qualified welding procedures is the calibration, monitoring, and maintenance of the system. Based on this need, it is suggested that a welding equipment qualification procedure be added during the establishment of the Procedure Qualification Record (PQR), Welding Procedure Specification (WPS), and welder operator qualification. To ensure that the system is properly calibrated and maintained, the suggested equipment qualification procedure should be conducted prior to developing the PQR and WPS.

The suggested welding equipment qualification procedure subsystems are detailed in Clause 5.1 and suggested operational limits are detailed in Clause 5.5. Clause 8 details the measurements and calibration of the subsystems and the laser system as a whole. The actual measurements made should be reported in an Equipment Qualification Record (EQR), and a sample of such a record is shown in Annex A. As part of this procedure, it is suggested that an equipment journal indicating all maintenance requirements and activities for the system, subsystem, and individual components is maintained.

5.1.1 Laser Beam Generator. The laser generator shall meet the essential variables and possible limits as outlined in 5.5.1 of this specification.

5.1.1.1 At appropriate intervals, to be noted in the welding EQR, the laser system (see Clause 5.5 for essential process variables) shall be qualified to determine that equipment is in proper working order and capable of weld process requirements.

5.1.1.2 Any modification to the Laser Beam Generator shall require an equipment requalification.

5.1.2 Beam Delivery Optics and Optical Hardware. The beam delivery optics and optical hardware shall safely and consistently deliver the laser beam from the laser generator to the workpiece.

5.1.2.1 The beam delivery hardware consists of all optical components from the Laser Beam Generator up to laser beam/material interaction point. These optical components may consist of polarizers, reflective mirrors, transmissive optics, fiber-optic cables, focus optics, optical scanning devices, and beam cover tubes. Suggested essential variable and possible limits for laser beam delivery hardware are outlined in 5.5.2 of this specification.

5.1.2.2 Any modification to the beam delivery hardware shall require an equipment requalification.

5.1.3 Auxiliary Power Supply. The method for adding heat other than that coming from the laser to the process is an essential variable, and the possible limits are outlined in 5.5.3 of this specification.

5.1.3.1 Auxiliary power includes all of the components related to the heating of the filler material. This includes the auxiliary power supply, the type of feeding system (i.e., push, push-pull, push-push, etc.), the control of the power to the wire, and changes in the current path (changes in the resistance of the system).

5.1.3.2 At appropriate intervals, to be noted in the welding EQR, the auxiliary power supply shall be evaluated to determine that equipment is in proper working order and capable of weld process requirements.

5.1.3.3 Any modification to the wire delivery hardware shall require an equipment requalification.

5.1.4 Motion System and Control System Control. The motion control system shall safely and consistently control the speed and path of the workpiece, the piece part assembly or laser beam, relative to each other.

5.1.4.1 The motion control system includes all devices that manipulate the piece part, piece part assembly or laser beam and may include machine tool or robotic axes, motion controller, and support structure.

5.1.4.2 Any component repair or replacement of the motion control system will require an equipment re-qualification.

5.1.4.3 Suggested essential variables and possible limits for the motion control system are outlined in 5.5.4 of this specification.

5.1.5 Tooling and Weld Fixtures. The fixturing shall safely and consistently position and locate the workpiece. Fixturing shall consist of all components that hold the position and locate the workpiece including gas delivery devices for plasma suppression, auxiliary gas shields, and spatter and reflection protection. Fixturing shall be made from materials that will not affect the composition of the weldment or base metal through mechanical contact and provide consistent heat sink for the cladding/weld surface.

5.1.5.1 All tooling shall be cleaned to a level insuring no contamination is introduced into the weldment by surface contaminants.

5.1.5.2 Tolerances and calibration of tooling shall be inspected at intervals noted in the WPS so that proper part setups and part movements are maintained. Results of this inspection will be reported in the EQR and PQR.

5.1.5.3 Any modification to the tooling or weld fixtures that may affect the heat sinking conditions of the material or the ability to hold the part securely during welding shall require an equipment requalification.

5.1.6 Shielding Gas. The shielding gas and shielding gas delivery system shall safely and consistently maintain a sufficient concentration of shielding gas during processing such that absorption and interaction of undesired ambient environment gases with the workpiece are minimized or negligible.

5.1.6.1 The shielding gas delivery system includes all devices that control shielding gas flow vectors, shielding gas composition, the orientation of shielding gas streams relative to the workpiece surface, laser beam generator, or auxiliary power source, and the mixing or entrainment of undesired ambient gases with the shielding gas. Suggested essential variables and possible limits for shielding gas and the delivery of shielding gas are outlined in 5.5.5 of this specification.

5.1.6.2 Shielding gas composition shall be in accordance with the mixture tolerances and minimum requirements on purities and moisture contents of gases and gas mixtures outlined in AWS A5.32M/A5.32. Any modification to the shielding gas composition beyond the tolerances and requirements outlined in A5.32M/A5.32 or the shielding gas delivery system shall require an equipment requalification.

5.2 Materials. This subclause addresses the materials being joined by laser hybrid welding.

5.2.1 Base materials shall be specified on the applicable component drawing. Material type, alloying composition, heat treat condition, part surface condition, and thickness shall be included as required in a qualified WPS.

5.2.2 Hazardous materials shall be welded only after adequate safety precautions are taken. Appropriate SDSs referenced on the applicable component drawing shall be consulted before welding/cladding to determine whether the base or the filler materials are hazardous at the elevated temperatures encountered during welding/cladding.

5.2.3 Filler materials. Reference to wire shall be specified on the applicable drawing, in the qualified WPS, or both. The filler material will be specified by the variables chemical composition, type (solid, metal cored, etc.), diameter, and feed rate.

5.2.4 Cleaning of the surfaces to be joined shall be performed to remove residues, lubricants, and other contaminants left from machining and other part handling.

5.2.5 Suggested essential variables and possible limits for the welding materials are outlined in 5.5.5.

5.3 Joint/Surface Design. This subclause discusses process geometries and design.

5.3.1 For claddings, total build up (i.e., total number of passes, and/or cladding thickness) and dilution shall be specified in the WPS and recorded in the PQR. For weld joints, fit-up tolerances and part mismatch allowance shall be specified in the WPS and recorded in the PQR.

5.3.2 Joint geometries and the tolerances shall be prepared so that they meet the component drawing and WPS requirements.

5.3.3 Suggested essential variables and possible limits for the weld joint or cladding surface design are outlined in 5.5.6.

5.4 Procedures. All weldments/depositions shall be fabricated in accordance to the WPS, and qualified and accepted for each category of weld employed. Required records and documents include the PQR and WPS, and qualified procedures covering deviations from the aforementioned specifications such as weld repair procedure specifications.

5.4.1 Welding Procedure Development. This subclause covers the procedures required to make and repair claddings/welds covered under this specification. Three categories of qualified cladding/welding procedures are referred to in this subclause. They are as follows:

5.4.1.1 Standard Qualified Weldments. Procedures for standard weldments shall be performed according to 5.4.4. In some circumstances where 5.4.4 is not considered complete, additional guidelines may be found in AWS B2.1/B2.1M.